DOI: 10.1002/ ((please add manuscript number))

Article type: Full Paper

Manipulating Active Layer Morphology of Small Molecule Donor/Polymer Acceptor based Organic Solar Cells through Ternary Blends

Zijian Zhang, Zicheng Ding, Zhaozhao Bi, Xiangjian Wan, Xiaojing Long, Chuandong Dou, Wei Ma,* David J. Jones, Wallace W. H. Wong, Yongsheng Chen,* Jun Liu,* and Lixiang Wang*

Z. Zhang, Dr. Z. Ding, X. Long, Dr. C. Dou, Prof. J. Liu, Prof. L. Wang
State Key Laboratory of Polymer Physics and Chemistry, Changchun Institute of Applied Chemistry, Chinese Academy of Sciences, Changchun, 130022, P. R. China

E-mail: dean132@ciac.ac.cn, liujun@ciac.ac.cn

Z. Bi, Prof. W. Ma

State Key Laboratory for Mechanical Behavior of Materials, Xi'an Jiaotong University, Xi'an 710049, P. R. China

Email: msewma@xjtu.edu.cn

Z. Zhang, X. Long

University of the Chinese Academy of Sciences, No.19A Yuquan Road, Beijing 100049, P. R. China

Dr. D. J. Jones, Dr. W. W. H. Wong

School of Chemistry, Bio21 Institute, The University of Melbourne, 30 Flemington Road, Parkville, Victoria 3010, Australia.

Prof. X. Wan, Prof. Y. Chen

Key Laboratory for Functional Polymer Materials and Centre for Nanoscale Science and Technology, Institute of Polymer Chemistry, College of Chemistry, Nankai University, Tianjin 300071, China

Email: yschen99@nankai.edu.cn

Keywords: organic solar cells, small molecule donor, polymer acceptor, blend morphology, ternary blend

Abstract

The development of small molecule donor/polymer acceptor blend (S_D/P_A) type organic solar cells (OSCs) lags far behind those of other types of OSCs. This is due to the large-size phase separation morphology of S_D/P_A blend films, which results from the high crystallinity of small molecule donors. In this manuscript, to suppress crystallinity of small molecule donors, we use ternary blends to develop OSCs with one polymer acceptor (P-BNBP-fBT) and two small molecule donors (DR3TBDDT and BTR) of similar chemical structures. The ternary OSCs exhibits power conversion efficiency of 4.85%, which is higher than those of the binary OSCs (PCE=3.60% or 3.86%). To our best knowledge, this is the first report of ternary S_D/P_A -type OSCs and this PCE is the among the highest for S_D/P_A -type OSCs reported so far. Compared with the binary blends, the ternary blend exhibits decreased crystalline size and improved face-on orientation of the two small molecule donors. As the result, the ternary blend exhibits improved and balanced charge mobility, suppressed charge recombination and increased donor/acceptor interfacial areas, which leads to the high J_{SC} and high FF. These results suggest that ternary blend is an effective strategy to manipulate active layer morphology and enhance photovoltaic performance of S_D/P_A -type OSCs.

1. Introduction

Bulk-heterojunction organic solar cells (OSCs) use blends of electron donor and electron acceptor as the active layer^[1, 2]. OSCs are a promising photovoltaic technology with the advantages of low cost, light weight and mechanical flexibility. Recently, non-fullerene electron acceptors and the corresponding OSC devices have draw particular attention and have lead to breakthrough of power conversion efficiency (PCE)^[3, 4]. Based on the types of electron donor and electron acceptor, OSCs may be classified into four types, including polymer donor/polymer acceptor blend (P_D/P_A), polymer donor/small molecule donor blend (P_D/S_A), small molecule donor/polymer acceptor blend (S_D/P_A), and small molecule donor/small molecule acceptor blend (S_D/S_A). Among them, the development of S_D/P_A type OSCs (PCE<5%) lags far behind those of the other three types of OSCs (PCE>9%)^[5-9]. The key reason for the relatively low PCE of S_D/P_A -type OSCs is the large-size phase separation morphology of S_D/P_A blend films. Small molecule donors are always highly crystalline for high hole mobility. However, they tend to form large crystalline domains in the S_D/P_A blend films, which prevents efficient exciton diffusion/dissociation and results in low short-circuit current densities (J_{SC}) and low fill factor (FF). It is a great challenge to control crystalline domain size of small molecule donors in S_D/P_A blend to enhance device performance of S_D/P_A -type OSC devices.

Ternary blend is an effective approach to enhance photovoltaic performance of OSCs. Although ternary blend has been widely used in P_D/S_A -type OSCs and traditional fullerene-based OSCs, ternary blend has never been reported in S_D/P_A -type OSCs. In this manuscript, to suppress crystallinity of small molecule donors and manipulate S_D/P_A blend morphology, we develop ternary OSCs based on one polymer acceptor and two small molecule donors with similar chemical structure. Compared with the binary blend using one small molecule donor, the ternary blend film shows not only decreased crystalline size, but also improved face-on orientation of the two small molecule donors. As the result, PCE of the OSC devices increases

Commented [WW1]: Instead of small molecule, I think it is better to use molecular donor.
Most of the 'small molecule donors' are not really small molecules in the traditional organic chemistry definition of a small molecule. They are actually quite large and closer to oligomers than small molecules.

from 3.85% to 4.85%. [To our best knowledge, it is the first report of ternary blends in S_D/P_A-type OSCs and this PCE is among the highest value for S_D/P_A-type OSCs reported so far. The effect of ternary blend on the active layer morphology and the physical process are comprehensively investigated.

2. Results and discussion

2.1. Optical and electrochemical properties

Scheme 1 shows the OSC device structure and chemical structures of the two small molecule donors, (5Z,5'Z)-5,5'-((5'',5'''-(4,8-bis(4-(2-ethylhexyl)thiophen-2-yl) benzo[1,2-b:4,5-b']dithiophene-2,6-diyl)bis(3,3''-dioctyl-[2,2':5',2''-terthiophene]-5'',5'-diyl))bis(methanylylidene))bis(3-ethyl-2-thioxothiazolidin-4-one) (DR3TBDTT)^[10], (5Z,5'Z)-5,5'-((5'',5'''-(4,8-bis(4-(2-ethylhexyl)-5-hexylthiophen-2-yl)benzo[1,2-b:4,5-b']dithiophene-2,6-diyl)bis(3',3''-dihexyl-[2,2':5',2''-terthiophene]-5'',5'-diyl))bis(methanylylidene))bis(3-hexyl-2-thioxothiazolidin-4-one) (BTR)^[11] and the polymer acceptor, poly[7-(3,3'-difluoro-[2,2'-bithiophen]-5-yl)-4,4,9,9-tetrafluoro-5,10-bis(2-octyldodecyl)-4,5,9,10-tetrahydro-3a,5,8a,10-tetraaza-4,9-diborapyrene-3a,8a-dium-5,11-diide] (P-BNBP-fBT)^[12]. DR3TBDTT and BTR have the same π -conjugated backbone but different side chains.^[10, 11] As previously reported by our authors, both the two molecules exhibit excellent OSC device performance in fullerene acceptor-type OSCs. Compared with DR3TBDTT, BTR shows better solubility in the common organic solvents because of more alkyl side chains. Scheme 1c shows the UV-vis absorption spectra of each material and the ternary blend in thin film. DR3TBDTT itself shows an absorption peak at 592 nm and a vibronic shoulder at 640 nm, while BTR itself exhibits slightly blueshifted absorption spectrum with an absorption peak at 578 nm and a vibronic shoulder at 621 nm. For the ternary blend with the optimal ratio, the absorption peaks of the two small molecule donors blueshift and the relative intensity of the vibronic shoulder decreases. The vibronic shoulder of the small molecule donors in the ternary blend is also weaker than that in the DR3TBDTT:P-BNBP-fBT and BTR:P-BNBP-fBT binary blends (Figure S1). It indicates

Commented [WW2]: What is the best S_D/P_A-type OSCs?
Probably need some references here.

that the π - π packing of the two small molecule donors are seriously disturbed in the ternary blend film. The energy-level diagram for the two small molecule donors and polymer acceptor is shown in Scheme 1d. The LUMO and HOMO energy levels are -3.55, -3.52 and -3.62 eV, and -5.30, -5.34 and -5.87 eV for DR3TBDTT, BTR and P-BNBP-fBT, respectively.^[12] The small LUMO energy level offsets between the two donors and the acceptor is adequate for charge separation to give photovoltaic response. Although the offsets are smaller than that (ca. 0.3 eV) empirically required for fullerene-based OSCs, as can be seen later, the OSC devices can still give good photovoltaic performance. The large difference between the HOMO energy levels of the two donors and the LUMO energy level of P-BNBP-fBT acceptor is expected to result in high open-circuit voltage (V_{OC}) of the OSC devices.

Scheme 1. (a) Device structure of the OSCs. (b) Chemical structures of DR3TBDTT, BTR and P-BNBP-fBT. (c) Optical absorption spectra of the films from DR3TBDTT, BTR and P-BNBP-fBT, DR3TBDTT:BTR:P-BNBP-fBT ternary blend with optimal ratio of 1.6:2.4:1. (d) Energy-level diagram for of DR3TBDTT, BTR and P-BNBP-fBT.

2.2. Device performance

Commented [WW3]: There are errors on both BTR and DR3TBDTT structures. The regiochemistry of the alkyl sidechains on the thiophenes of the BDT cores is incorrect.

The binary or ternary OSC devices were fabricated with the normal configuration of ITO/PEDOT:PSS/Active layer/Ca/Al. The donor:acceptor weight ratio was optimized to be 4:1. Figure 1a shows the current density-voltage (J - V) plots of the OSC devices based on the DR3TBDTT:P-BNBP-fBT and BTR:P-BNBP-fBT binary blend and the DR3TBDTT:BTR:P-BNBP-fBT ternary blend under 100 mW cm⁻² AM 1.5G illumination. The device characteristics are shown in Table 1. The DR3TBDTT:P-BNBP-fBT binary device shows a open-circuit voltage (V_{OC}) of 1.17 V, a J_{SC} of 5.95 mA cm⁻² and a FF of 51.63%, corresponding to a PCE of 3.60%. The BTR:P-BNBP-fBT binary device shows a V_{OC} of 1.23 V, a J_{SC} of 5.47 mA cm⁻² and a FF of 57.28%, corresponding to a PCE of 3.86%. Compared with the binary devices, the DR3TBDTT:BTR:P-BNBP-fBT ternary devices at different compositional ratios show variable V_{OC} and FF, but higher J_{SC} (Figure S2 and Table S1). It indicates that DR3TBDTT:BTR:P-BNBP-fBT ternary devices adopt a parallel-linkage model.^[13, 14] At the weight ratio of 2:3 for DR3TBDTT:BTR, the ternary device give the best PCE of 4.85% with a V_{OC} of 1.18 V, a J_{SC} of 7.39 mAcm⁻², a FF of 55.62%. The high V_{OC} is consistent with the large offset between the HOMO energy levels of DR3TBDTT/BTR and the high-lying LUMO energy level of P-BNBP-fBT (Scheme 1d). The differences in the J_{SC} values for the binary and ternary devices are also consistent with the EQE curves. As shown in Figure 1b, the external quantum efficiency of the ternary device is much higher than those of the two binary devices in the whole photoresponse range from 300 to 800 nm. The maximum EQE value of the ternary device is 41.6% at 630 nm, while the maximum EQE value is 34.2% at 620 nm for the DR3TBDTT:P-BNBP-fBT blend and 34.2% at 550 nm for the BTR:P-BNBP-fBT blend. The J_{SC} integrated from the EQE curves are consistent with the J_{SC} measured from the J - V plots.

Figure 1. (a) J - V plots and (b) EQE curves of the OSC devices based on DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT ternary blend.

Table 1. Characteristics of OSC devices based on DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT ternary blend.

Blend	V_{OC} (V)	J_{SC} (mA cm ⁻²)	FF (%)	PCE _{max} (PCE ^a) (%)	E_{loss} (eV)
DR3TBDTT:P-BNBP-fBT	1.17	5.95	51.63	3.60 (3.54)	0.55
BTR:P-BNBP-fBT	1.23	5.47	57.28	3.86 (3.81)	0.59
DR3TBDTT: BTR:P-BNBP-fBT	1.18	7.39	55.62	4.85 (4.82)	0.54

^a) average PCE of 12 devices

We also find that a small photon energy loss (E_{loss}) can be obtained in these S_D/P_A-types OSCs. E_{loss} is defined as the difference between the lowest optical bandgap (E_g) of donor/acceptor materials and the eV_{OC} of OSC devices ($E_{loss}=E_g-eV_{OC}$) [15]. For OSCs, the E_{loss} is always in the range of 0.7–1.0 eV and seldom below 0.6 eV [16, 17]. The E_{loss} of the DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT devices

are as small as 0.55 eV, 0.59 eV and 0.54 eV, respectively. The small E_{loss} in these S_D/P_A type OSCs is attributed to the polymer acceptor P-BNBP-fBT, which always exhibits small E_{loss} of ca. 0.5 eV.^[12, 18, 19]

2.3. Blend morphology of the active layers

To investigate the effect of active layer morphology on the OSC device performance, we conducted two-dimensional grazing-incident wide-angle X-ray scattering (2D-GIWAXS), resonant soft X-ray scattering (R-SoXS), atomic force microscopy (AFM) and transmission electron microscopy (TEM) measurement on the binary and ternary blend films. 2D-GIWAXS was used to investigate the molecular packing behaviors in the thin films. The 2D-GIWAXS patterns are shown in Figure 2a-c and the in-plane/out-of-plane line cuts are shown in Figure 2d. The relative GIWAXS characterization data are shown in Table 2. Both the two binary blend films show multiple higher order ($h00$) reflections in the out-of-plane direction and strong (010) reflection of π - π stacking in the in-plane direction. It indicates that both DR3TBDTT and BTR adopt edge-on orientation in the binary blend films^[11, 20]. In contrast, for the ternary blend, the multiple higher order reflection of ($h00$) appears in the in-plane direction, and the π - π stacking reflection in the out-of-plane direction become stronger than that in the in-plane direction of the ternary blend. These results suggest that the small molecule donors adopt face-on orientation in the ternary blend. The face-on orientation is favorable for charge transporting in the OSC devices. The intensity of ($h00$) reflections of the small molecules are much weaker in the ternary blend film than that in the binary blend films, indicating that the crystallinity of the small molecules are effectively suppressed in the ternary blend. We further quantify the coherence lengths from the full width at half-maximum of the (010) diffraction peaks (assigned to π - π stacking) with Scherrer equation. As listed in Table 2, the π - π stacking correlation length is smaller for the ternary blend than that for the two binary blends, confirming the suppressed crystallinity in the ternary blend.

Figure 2. 2D-GIWAXS images of the films from (a) DR3TBDTT:P-BNBP-fBT, (b) BTR:P-BNBP-fBT, (c) DR3TBDTT:BTR:P-BNBP-fBT ternary blend, (d) Linecuts of GIWAXS images in the in-plane and out-of-plane of the binary and ternary blend films.

Table 2. GIWAXS characterization data of the binary and ternary blend films.

System	100				010			
	Location (Å ⁻¹)	d-spacing (Å)	FWHM (Å ⁻¹)	CL (Å)	Location (Å ⁻¹)	d-spacing (Å)	FWHM (Å ⁻¹)	CL (Å)
DR3TBDTT:P-BNBP-fBT	0.32	19.94	0.034	163.92	1.73	3.63	0.10	59.33
BTR:P-BNBP-fBT	0.32	19.80	0.019	295.79	1.70	3.69	0.10	55.87
Ternary blend	0.31	20.35	0.030	190.12	1.71	3.68	0.11	49.68

Figure 3 shows the R-SoXS data acquired at 285.2 eV for DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT blend films. All the three blends all show a broader domain size distribution. The peaks corresponding to ca. 74 and 48 nm domains is observed for DR3TBDTT:P-BNBP-fBT and BTR:P-BNBP-fBT blend. The composition variation was calculated by integrate the area of $I \cdot q^2$ versus q plot to define the

phase purity in the blend films. The relative domain purity of DR3TBDTT:P-BNBP-fBT and BTR:P-BNBP-fBT blend films is 1 and 0.56. The larger domain size and higher domain purity for DR3TBDTT:P-BNBP-fBT binary blend compared with BTR:P-BNBP-fBT binary blend are attributed to the poorer solubility of DR3TBDTT. The R-SoXS scattering profile of the ternary blend film is similar to that of the DR3TBDTT:P-BNBP-fBT binary blend, indicating that DR3TBDTT dominates the crystallization in the ternary blend film. The domain size of the ternary blend decreases to 65 nm and maintain a high domain purity of 0.88. On the one hand, the reduced domain size and high phase purity benefit charge transporting and reduce charge recombination, thus leading to improved OSC device performance of the ternary blend. On the other hand, the phase separation size of the ternary blend is still much larger than the exciton diffusion length (ca. 10 nm), which limits further J_{SC} enhancement.

Figure 3. R-SoXS scattering profiles of DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT ternary blend.

The reduced domain size in the ternary blend can also be observed in the AFM and TEM images. As shown in Figure 4a-c, the large aggregates in the AFM height images are attributed to the crystalline domain of the small molecules. While DR3TBDTT:P-BNBP-fBT and BTR:P-BNBP-fBT films show the domain size of 60-100 nm and 80-130 nm, respectively, the ternary blend film exhibits the domain size of 40-70 nm. The root-mean-square (RMS) roughness value decrease from 3.06 nm for DR3TBDTT:P-BNBP-fBT and 3.37 nm for BTR:P-BNBP-fBT to 2.51 nm for the ternary blend. The TEM images in Figure 4d-f indicate the formation of fibrous networks in the blend films. Large dark areas appear in the TEM images of the DR3TBDTT:P-BNBP-fBT and BTR:P-BNBP-fBT films. In comparison, in the TEM images of the ternary blend, small dark areas can be seen and the fibers are uniformly distributed. These results indicate that large size phase separation takes place in the binary blend and that the phase separation is effectively suppressed in the ternary blend. The reduced domain size in the ternary blend increases the donor/acceptor interfacial area and thus improves the exciton dissociation. Therefore, the increased J_{SC} and FF in the ternary OSC devices are attributed to the small phase separation domain size and face-on orientation of the two small molecule donors.

Figure 4. AFM height images of the blend films: (a) DR3TBDTT:P-BNBP-fBT, (b) BTR:P-BNBP-fBT, (c) DR3TBDTT:BTR:P-BNBP-fBT ternary blend. TEM images of the blend

films: (d) DR3TBDTT:P-BNBP-fBT, (e) BTR:P-BNBP-fBT, (f) DR3TBDTT:BTR:P-BNBP-fBT ternary blend.

2.4. Charge transporting and recombination

To investigate the charge transporting properties in the binary and ternary blend films, we measure the electron and hole mobilities using space-charge-limited current (SCLC) method. The J - V plots and SCLC fittings of the hole-only devices (device structure: ITO/PEDOT/active layer/MoO₃/Ag) and electron-only devices (device structure: ITO/PEIE/active layer/Ca/Al) are shown in Figure 5. Table 3 summarizes the estimated hole and electron mobilities. The hole mobility (μ_h) of DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT films is 1.95×10^{-4} , 3.93×10^{-4} and 6.23×10^{-4} cm²V⁻¹s⁻¹, respectively. The enhanced μ_h of the ternary blend may be due to the preferred face-on orientation of the small molecule donors. The electron mobility (μ_e) of DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT films is 3.90×10^{-5} , 1.23×10^{-4} and 2.50×10^{-4} cm²V⁻¹s⁻¹, respectively. The enhanced μ_e of the ternary blend may be attributed to the fibrous network of polymer acceptor, which can be seen in the TEM images. The suppressed crystallinity of the small molecule donors in the ternary blend may help the formation of P-BNBP-fBT fibers in the phase separation process. As listed in Table 3, the μ_h/μ_e ratio of the ternary blend is 2.49, which is smaller than those of the two binary blends. The enhanced and balanced charge carrier mobilities of the ternary blend result in improved charge transport/collection and lead to high J_{SC} and FF.

Figure 5. Space-charge-limited J – V characteristics in dark for (a) hole-only and (b) electron-only devices of the two binary blends and the ternary blend.

Table 3. Hole and electron mobilities of DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT ternary blend.

Active layer	μ_h (cm ² V ^{−1} s ^{−1})	μ_e (cm ² V ^{−1} s ^{−1})	μ_h / μ_e
DR3TBDTT:P-BNBP-fBT	1.95×10^{-4}	3.90×10^{-5}	5.00
BTR:P-BNBP-fBT	3.93×10^{-4}	1.23×10^{-4}	3.20
Ternary blend	6.23×10^{-4}	2.50×10^{-4}	2.49

We further investigate the charge recombination of the three OSC devices via the light intensity dependent J – V characteristics and the charge-transfer state (CTS) dissociation probability. The relationship between J_{SC} and the light intensity (I) can be described as $J_{SC} \propto I^\alpha$, where α is the calculated power-law exponent^[21]. As shown in Figure 6a, the α value is 0.94, 0.96 and 0.96 for the devices of DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and the ternary blend, respectively. These high α values indicate that bimolecular recombination is not

significant in all the three devices. The V_{OC} varies logarithmically with light intensity ($\ln(I)$) ($V_{OC} \propto nkT/q \ln(I)$, where n is a constant, k is Boltzmann's constant, T is temperature, q is the elementary charge)^[22]. Trap-assisted recombination and germinate recombination are dominant when the slope value is equal to $2kT/q$, while the slope value would be kT/q when only bimolecular recombination takes place. As shown in Figure 6b, the slope value is $1.42kT/q$, $1.06kT/q$ and $1.03kT/q$ for the DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and the ternary blend devices. These results indicate that the trap-assisted recombination and germinate recombination is effectively suppressed in the ternary blend compared with the two binary blends. This may be due to the reduced crystalline domain size and the face-on-orientation of the two small molecule donors in the ternary blend. The suppressed charge recombination is consistent with the improved device performance of the ternary blend. The CTS dissociation probability was measured from the plots of photogenerated current density ($J_{ph} = J_L - J_D$, where J_L is the current density under illumination and J_D is the current density in the dark) versus effective voltage ($V_{eff} = V_0 - V_a$, where V_0 is the voltage when J_{ph} is zero and V_a is the applied voltage)^[23]. The CTS dissociation probability value can be obtained from $J_{ph, sc}/J_{ph, sat}$, where $J_{ph, sc}$ is the photocurrent density under short-circuit conditions and $J_{ph, sat}$ is the saturation photocurrent density. As shown in Figure 6c, DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT blends show similar CTS dissociation probabilities of 0.72, 0.71 and 0.74, respectively, but different $J_{ph, sat}$ of 8.24 mA cm^{-2} , 7.28 mA cm^{-2} and 9.89 mA cm^{-2} , respectively. The higher $J_{ph, sat}$ for the ternary blend than for the binary blends is due to the increased donor/acceptor interfacial areas with small size-phase separation in the ternary blend. The improved and balanced charge mobility, suppressed charge recombination and increased donor/acceptor interfacial areas account for the high J_{SC} and high FF of the ternary blend device.

Figure 6. Light intensity dependence of (a) J_{sc} and (b) V_{oc} (solid lines are fits), (c) J_{ph} versus V_{eff} plots of the OSC devices based on DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT ternary blend.

3. Conclusions

In summary, we studied the first ternary S_D/P_A-type OSC with one polymer acceptor (P-BNBP-fBT) and two small molecule donors (DR3TBDTT and BTR) of similar chemical

structures. Compared with the DR3TBDTT:P-BNBP-fBT and BTR:P-BNBP-fBT binary blends, the DR3TBDTT: BTR:P-BNBP-fBT ternary blend exhibits decreased crystalline size and improved face-on orientation of the small molecule donors. As the result, the ternary blend shows improved and balanced charge mobility, suppressed charge recombination and increased donor/acceptor interfacial areas. The ternary OSCs exhibits PCE of 4.85%, which is higher than that of the two binary OSCs (PCE=3.60% or 3.85%). These results suggest that ternary blend is an effective strategy to manipulate active layer morphology and enhance photovoltaic performance of S_D/P_A -type OSCs.

4. Experimental section

Materials: DRR3TBDTT, BTR and P-BNBP-fBT ($M_n = 116.0$ kDa, PDI = 2.6) were obtained according to the previous reported methods.^[10-12]

Absorption spectra of thin films: The pure DR3TBDTT, BTR, P-BNBP-T films and the ternary blend film with different ratios were spin-coated on quartz substrates from their chlorobenzene solutions. The films were measured with a PerkinElmer Lambda 35 UV/VIS Spectrometer.

OSC device fabrication and measurement: ITO glass substrates were ultrasonicated for 10 min sequentially with detergent, de-ionized water, acetone and *iso*-propanol, respectively. The ITO glass substrates were dried at 120 °C for 2 h and treated with UV-ozone for 25 min. PEDOT:PSS (Clevios PVP Al4083 from H. C. Starck Inc.) was spin-coated on the pre-cleaned ITO substrates and then baked at 120 °C for 30 min. All the substrates were transferred to a nitrogen-filled glove box. The binary blend of DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and the ternary blend of DR3TBDTT:BTR:P-BNBP-fBT (D:A=4:1, w/w and the polymer concentration is 2.5 mg ml⁻¹) was dissolved in chlorobenzene (CB). The solution was stirred at 80 °C for 3 hours to ensure the complete dissolution in the glove box. Before spin coating, both the solution and ITO/PEDOT:PSS substrates were preheated on a hot plate at 80 °C. The active layers with a thickness of ca. 80 nm were gained by spin coating the warm solution

Commented [WW4]: Dr David Jones wondered if you have tried other solvents (such as chloroform) to control film morphology of the blends.

onto the preheated substrate. After that, a solvent mixture of 1, 8-diiodooctane (DIO) and hexane (0.5:99.5, v/v) was spin-coated on the top of the active layer with a speed of 3000 rpm for 1 min.^[24] The active layers were then transferred into a vacuum chamber. Finally, Ca (20 nm) and Al (100 nm) were sequentially deposited on the top of the active layer at a pressure of 2×10^{-4} Pa. The active area of the devices was 8 mm². The current-voltage (*J*-*V*) plots of the device were measured using a Keithley 2400 source meter under 100 mW cm⁻² AM 1.5G simulated solar light illumination provided by a XES-40S2-CE Class Solar Simulator (Japan, SAN-EI Electric Co., Ltd.). The EQE spectrum was measured using a Solar Cell Spectral Response Measurement System QE-R3011 (Enlitech Co., Ltd.) under the short-circuit condition at a chopping frequency of 165 Hz.

GIWAXS Characterization: GIWAXS measurements were performed at beamline 7.3.3 at the Advanced Light Source. The pure films and DR3TBDTT:BTR blend (2:3, w/w) film were prepared from their CB solutions. The DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and the ternary blend films were prepared using identical blend solutions as those used in devices on Si substrate. The 10 keV X-ray beam was incident at a grazing angle of 0.12°–0.16°, which maximized the scattering intensity from the samples. The scattered X-rays were detected using a Dectris Pilatus 1M photon counting detector.

R-SoXS characterization: R-SoXS transmission measurements were performed at beamline 11.0.1.2 at the Advanced Light Source (ALS). A 285.2 eV beamline energy was chosen to enhance the contrast. Samples for R-SoXS measurements were prepared on a PEDOT:PSS modified Si substrate under the same conditions as those used for device fabrication, and then transferred by floating in water to a 1.5 mm×1.5 mm, 100 nm thick Si₃N₄ membrane supported by a 5 mm×5 mm, 200 μm thick Si frame (Norcada Inc.). 2-D scattering patterns were collected on an in-vacuum CCD camera (Princeton Instrument PI-MTE). The sample detector distance was calibrated from diffraction peaks of a triblock copolymer poly(isoprene-*b*-styrene-*b*-2-vinyl pyridine), which has a known spacing of 391 Å. The beam size at the

sample is approximately 100 μm by 200 μm .

AFM and TEM characterizations: AFM characterization was performed on a SPA 300HV with a SPI 3800N controller (Seiko Instruments, Inc., Japan) in tapping mode. A silicon micro cantilever (spring constant 2 N m^{-1} and resonance frequency ca. 300 kHz, Olympus Co., Japan) with an etched conical tip was used for the scan. The samples for AFM measurement were prepared by spin-coating the blend solution onto the ITO/PEDOT:PSS substrates and processed with the same procedures as the device conditions. TEM images were obtained with a JEM-1011 (JEOL Co., Japan) operated at an accelerating voltage of 100 kV. TEM samples were made by floating the blend films onto the water surface and picked up the films onto a copper mesh.

Hole- and electron-only devices fabrication and mobility measurement: The hole and electron mobilities of the blend film with different processing conditions were measured by the space-charge-limited current (SCLC) method. The hole-only device structure is ITO/PEDOT:PSS (40 nm)/active layer/ MoO_3 (7 nm)/Ag (100 nm) and the electron-only device structure is ITO/PEIE (10 nm)/active layer/Ca (20 nm)/Al (100 nm), respectively. J - V plots in the range of 0–10 V were measured using a Keithley 2400 source meter, and the mobility was obtained by fitting the J - V plots near quadratic region according to the modified Mott–Gurney equation:

$$J = \frac{9}{8} \epsilon_r \epsilon_0 \mu \frac{V^2}{L^3} \exp\left(0.89\beta \frac{\sqrt{V}}{\sqrt{L}}\right)$$

Where J is the current density, ϵ_0 is permittivity of free space, ϵ_r is the relative permittivity (assumed to be 3), μ is the zero-field mobility, V is the potential across the device ($V = V_{\text{applied}} - V_{\text{bi}} - V_{\text{series}}$), L is the thickness of active layer, and β is the field-activation factor. The series and contact resistance (V_{series}) of the device (10–20 Ω) were measured using blank device of ITO/PEDOT:PSS/ MoO_3 /Ag or ITO/PEIE/Ca/Al.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

The authors are grateful for the financial support from the National Key Basic Research and Development Program of China (973 Program, Grant no. 2014CB643504, 2015CB655001) funded by MOST, the National Natural Science Foundation of China (no. 51373165, 51403200, 21625403), the Strategic Priority Research Program of the Chinese Academy of Sciences (no. XDB12010200). The collaborative work in this project between Australia and China was made possible by funding from the Australian Renewable Energy Agency, the Australian Centre for Advanced Photovoltaics and the International Research & Research Training Fund of the University of Melbourne. Responsibility for the views, information or advice expressed herein is not accepted by the Australian Government. WWHW is supported by an ARC Future Fellowship (FT130100500) and by the ARC Centre of Excellence in Exciton Science (CE170100026).

Received: ((will be filled in by the editorial staff))

Revised: ((will be filled in by the editorial staff))

Published online: ((will be filled in by the editorial staff))

References

- [1] G. Yu, J. Gao, J. C. Hummelen, F. Wudl, A. J. Heeger, *Science* **1995**, 270, 1789.
- [2] S. Gunes, H. Neugebauer, N. S. Sariciftci, *Chem. Rev.* **2007**, 107, 1324.
- [3] C. B. Nielsen, S. Holliday, H.-Y. Chen, S. J. Cryer, I. McCulloch, *Accounts Chem Res* **2015**, 48, 2803.
- [4] H. Kang, W. Lee, J. Oh, T. Kim, C. Lee, B. J. Kim, *Accounts Chem Res* **2016**, 49, 2424.
- [5] W. Zhao, S. Li, H. Yao, S. Zhang, Y. Zhang, B. Yang, J. Hou, *J Am Chem Soc* **2017**, 139, 7148.
- [6] B. Fan, L. Ying, Z. Wang, B. He, X. Jiang, F. Huang, Y. Cao, *Energy Environ. Sci.* **2017**, 10, 1243.
- [7] H. Bin, Y. Yang, Z.-G. Zhang, L. Ye, M. Ghasemi, S. Chen, Y. Zhang, C. Zhang, C. Sun, L. Xue, C. Yang, H. Ade, Y. Li, *J Am Chem Soc* **2017**, 139, 5085.
- [8] L. Yang, S. Zhang, C. He, J. Zhang, H. Yao, Y. Yang, Y. Zhang, W. Zhao, J. Hou, *J Am Chem Soc* **2017**, 139, 1958.
- [9] J. W. Jung, T. P. Russell, W. H. Jo, *Chem Mater* **2015**, 27, 4865.
- [10] J. Y. Zhou, Y. Zuo, X. J. Wan, G. K. Long, Q. Zhang, W. Ni, Y. S. Liu, Z. Li, G. R. He, C. X. Li, B. Kan, M. M. Li, Y. S. Chen, *J Am Chem Soc* **2013**, 135, 8484.
- [11] K. Sun, Z. Xiao, S. Lu, W. Zajaczkowski, W. Pisula, E. Hanssen, J. M. White, R. M. Williamson, J. Subbiah, J. Ouyang, A. B. Holmes, W. W. H. Wong, D. J. Jones, *Nat. Commun.* **2015**, 6, 6013.
- [12] X. Long, Z. Ding, C. Dou, J. Zhang, J. Liu, L. Wang, *Adv. Mater.* **2016**, 28, 6504.
- [13] T. Ameri, P. Khoram, J. Min, C. J. Brabec, *Adv. Mater.* **2013**, 25, 4245.

- [14] L. Y. Lu, M. A. Kelly, W. You, L. P. Yu, *Nat. Photonics* **2015**, 9, 491.
- [15] R. A. J. Janssen, J. Nelson, *Adv. Mater.* **2013**, 25, 1847.
- [16] D. Veldman, S. C. J. Meskers, R. A. J. Janssen, *Adv. Funct. Mater.* **2009**, 19, 1939.
- [17] A. Polman, M. Knight, E. C. Garnett, B. Ehrler, W. C. Sinke, *Science* **2016**, 352, aad4424.
- [18] Z. Ding, X. Long, C. Dou, J. Liu, L. Wang, *Chem. Sci.* **2016**, 7, 6197.
- [19] C. Dou, J. Liu, L. Wang, *Sci. China Chem.* **2017**, 60, 450.
- [20] M. M. Li, F. Liu, X. J. Wan, W. Ni, B. Kan, H. R. Feng, Q. Zhang, X. Yang, Y. C. Wang, Y. M. Zhang, Y. Shen, T. P. Russell, Y. S. Chen, *Adv. Mater.* **2015**, 27, 6296.
- [21] L. J. A. Koster, V. D. Mihailetschi, H. Xie, P. W. M. Blom, *Appl Phys Lett* **2005**, 87, 203502.
- [22] L. J. A. Koster, V. D. Mihailetschi, R. Ramaker, P. W. M. Blom, *Appl Phys Lett* **2005**, 86, 123509.
- [23] V. D. Mihailetschi, L. J. A. Koster, P. W. M. Blom, C. Melzer, B. de Boer, J. K. J. van Duren, R. A. J. Janssen, *Adv. Funct. Mater.* **2005**, 15, 795.
- [24] J. Kong, I.-W. Hwang, K. Lee, *Adv. Mater.* **2014**, 24, 6275.

Supporting Information

Manipulating Active Layer Morphology of Small Molecule Donor/Polymer Acceptor based Organic Solar Cells through Ternary Blends

Zijian Zhang, Zicheng Ding, Zhaozhao Bi, Xiangjian Wan, Xiaojing Long, Chuandong Dou, Wei Ma,* David J. Jones, Wallace W. H. Wong, Yongsheng Chen,* Jun Liu,* and Lixiang Wang*

Z. Zhang, Dr. Z. Ding, X. Long, Dr. C. Dou, Prof. J. Liu, Prof. L. Wang
State Key Laboratory of Polymer Physics and Chemistry, Changchun Institute of Applied Chemistry, Chinese Academy of Sciences, Changchun, 130022, P. R. China
E-mail: dean132@ciac.ac.cn, liujun@ciac.ac.cn

Z. Bi, Prof. W. Ma
State Key Laboratory for Mechanical Behavior of Materials, Xi'an Jiaotong University, Xi'an 710049, P. R. China
Email: msewma@xjtu.edu.cn

Z. Zhang, X. Long
University of the Chinese Academy of Sciences, No.19A Yuquan Road, Beijing 100049, P. R. China

Dr. D. J. Jones, Dr. W. W. H. Wong
School of Chemistry, Bio21 Institute, The University of Melbourne, 30 Flemington Road, Parkville, Victoria 3010, Australia.

Prof. X. Wan, Prof. Y. Chen
Key Laboratory for Functional Polymer Materials and Centre for Nanoscale Science and Technology, Institute of Polymer Chemistry, College of Chemistry, Nankai University, Tianjin 300071, China
Email: yschen99@nankai.edu.cn

Figure S1. UV-vis absorption spectra of the DR3TBDTT:BTR:P-BNBP-fBT ternary blend films with different ratios.

Figure S2. (a) J - V plots and (b) EQE curves of the OSC devices based on DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT ternary blend with different ratios.

Figure S3. 2D-GIWAXS images of the films from (a) pure DR3TBDTT, (b) pure BTR, (c) pure P-BNBP-fBT, and DR3TBDTT:BTR blend (2:3, w/w). (e) Linecut of GIWAXS images in the in-plane and out-of-plane of the pure and blend films.

Figure S4. Optical contrast plots of different systems. The energy 285.2 eV was used to obtain the data.

Figure S5. AFM phase images of the blend films from (a) DR3TBDTT:P-BNBP-fBT, (b) BTR:P-BNBP-fBT, (c) DR3TBDTT:BTR:P-BNBP-fBT ternary blend.

Table S1. Characteristics of OSC devices based on DR3TBDTT:P-BNBP-fBT, BTR:P-BNBP-fBT and DR3TBDTT:BTR:P-BNBP-fBT ternary blend with different ratios.

DR3TBDTT:BTR:P-BNBP-fBT	V_{oc} (V)	J_{sc} (mAcm ⁻²)	FF (%)	PCE (%)
4:0:1	1.17	5.95	51.63	3.60
3.2:0.8:1	1.18	6.17	52.44	3.86
2.4:1.6:1	1.18	6.54	53.91	4.16
2:2:1	1.18	7.04	54.32	4.51
1.6:2.4:1	1.18	7.39	55.62	4.85
1.2:2.8:1	1.19	7.10	55.32	4.68
0.8:3.2:1	1.19	6.73	56.15	4.50
0:4:1	1.23	5.47	57.28	3.86

Table S2. GIWAXS characterization data of the pure and binary blend films.

System	100				010			
	Location (Å ⁻¹)	d-spacing (Å)	FWHM	CL (Å)	Location (Å ⁻¹)	d-spacing (Å)	FWHM	CL (Å)
DR3TBDTT	0.32	19.92	0.022	255.42	1.72	3.65	0.08	68.25
BTR	0.33	19.30	0.015	369.48	1.66	3.78	0.08	71.13
DR3TBDTT:BTR	0.31	20.04	0.016	364.56	1.69	3.71	0.10	58.19