[Click here to view linked References](#)

Plastic Hinge Analysis for Lightly Reinforced and Unconfined Concrete Structural Walls

Ryan D. Hoult^{1,4}, Helen M. Goldsworthy^{2,4}, Elisa Lumantarna^{3,4}

1. Corresponding Author. PhD Candidate, Department of Infrastructure Engineering, University of Melbourne, Parkville, 3010, Australia. Email: ryan.hoult@unimelb.edu.au. Ph: +61401955374
2. Associate Professor, Department of Infrastructure Engineering, University of Melbourne, Parkville, 3010, Australia. Email: helenmg@unimelb.edu.au
3. Lecturer, Department of Infrastructure Engineering, University of Melbourne, Parkville, 3010, Australia. Email: elu@unimelb.edu.au
4. Bushfire and Natural Hazards Cooperative Research Centre, Melbourne, Australia

Abstract

Poor performance of lightly reinforced and unconfined concrete structural walls have been observed in recent earthquake events. This research investigates the displacement capacity of such walls by comparing the results of a series of state-of-the-art finite element analyses for a range of different structural walls to that estimated using plastic hinge analyses. The common expressions used in estimating the yield curvature, yield displacement and plastic displacement are scrutinised for these types of walls. Some recommendations are given to improve the prediction of the displacement capacity of lightly reinforced and unconfined rectangular and C-shaped walls for flexural actions using a plastic hinge analysis. Importantly, a parameter has been recommended to be used in a “modified” approach for estimating the nominal yield displacement of lightly reinforced concrete walls. Different expressions are also recommended depending on the amount of longitudinal reinforcement used in the wall in comparison to that required to initiate secondary cracking. This is important for providing better estimations of the displacement capacity of RC structural wall buildings in low-to-moderate seismic regions such that vulnerability studies can be conducted.

1. Introduction

The moment magnitude (M_w) 6.2 aftershock event in Christchurch on February 22nd, 2011, the most damaging event in the Canterbury earthquake sequence, highlighted the poor behaviour that can be exhibited by lightly reinforced and unconfined reinforced concrete (RC) walls. For example, some of the walls in the Gallery Apartments building had a single, primary crack form at their base (Figure 1) rather than the well distributed cracks (over a plastic hinge zone) that were expected to form. As

33 shown in Figure 1b, it was common to find fracturing of the reinforcing bars that crossed this crack
34 due to the concentration of tensile strains in the vicinity of the crack (Henry, 2013; Sritharan *et al.*,
35 2014). ‘The building’s [Gallery Apartments] overall damage state may be described as being at near
36 collapse. A potentially catastrophic failure might have been observed for a slightly longer duration of
37 severe ground shaking’ (Morris *et al.*, 2015). This type of performance in RC walls was also
38 observed during the Chilean Earthquake of 1985 in the El Faro building (Wood *et al.*, 1991; Wood,
39 1989). The investigation by Wood *et al.* (1991) on the El Faro building provided a ‘rare, documented
40 failure of a structural wall-system’, with failure and ultimately collapse of the building occurring after
41 the longitudinal reinforcement fractured in a first-story wall. To the authors’ knowledge, this was the
42 first documented case of a single-crack-failure in a RC wall from an earthquake event, where this
43 single-crack phenomenon can be attributed to the low amount of longitudinal reinforcement used in
44 the wall (CERC, 2012; Hoult *et al.*, 2017).

45 **Figure 1 Single-crack failure observed in the Gallery Apartments building, Christchurch (a) concrete**
46 **removal and (b) fractured bar (Sritharan *et al.*, 2014)**

47 The collapse of the Pyne Gould building was another example of poor building performance observed
48 from the Christchurch earthquake. The building was reliant on RC walls for its lateral load resisting

49 system, which formed a core surrounding stairs and lifts. The core walls were lightly reinforced and
50 unconfined, having a single layer of deformed 16 mm bars spaced at 381 mm for both the horizontal
51 and longitudinal reinforcement (Beca, 2011). The failure, according to Beca (2011), occurred
52 between levels one and two due to the vertical reinforcement in the west wall of the core yielding in
53 vertical tension and subsequently fracturing due to the concentration of strains at a suspected single,
54 primary crack. Furthermore, the core, continuing to deform to the east, reaching its unconfined
55 compression capacity in the east wall of the core. This poor behaviour of the core walls resulted in
56 large deformations of the gravity system (frames) and eventually led to a “pancake”-type collapse of
57 the building. It is important to note that the Christchurch earthquake sequence had similar
58 mechanisms to that associated with intraplate earthquake events in Australia, i.e. it was a reverse
59 faulting mechanism which was shallow and had a high stress-drop (Bradley *et al.*, 2014; Brown &
60 Gibson, 2004; Goldsworthy, 2012). Buildings in Australia and other low-to-moderate seismic regions
61 commonly use RC structural walls as their lateral load resisting system. The low standard of detailing
62 required in the current (and previous) concrete structures standards in Australia (AS 3600), coupled
63 with the low return period earthquake typically used in design, has resulted in the great majority of
64 these walls being lightly reinforced and unconfined. The failures observed in Christchurch are a
65 forewarning of the catastrophic structural damage that would potentially occur in Australia due to the
66 poor behaviour of RC structural wall buildings if a similar magnitude event were to occur near a
67 densely-populated area.

68 Until recently, experimental seismic testing typically focused on RC walls that were rectangular in
69 cross-section, well confined in the boundary regions and highly reinforced (Cardenas & Magura,
70 1972; Oesterle *et al.*, 1979; Oesterle *et al.*, 1976; Wight *et al.*, 1984). Furthermore, while rectangular
71 walls are commonly utilised on the perimeters of buildings (e.g. “peripheral walls”), many RC walls
72 (or cores) are non-rectangular due to architectural requirements (Belletti *et al.*, 2013; Smyrou *et al.*,
73 2013). For example, C-shaped walls are commonly found enclosing a service core, elevators, stairs,
74 or toilets in buildings (Beyer *et al.*, 2008a). There have been several experimental programs to assess
75 the seismic performance of C-shaped (or “U-shaped”) RC walls detailed to regions of high seismicity

76 in the past decade or so (Beyer *et al.*, 2008b; Constantin & Beyer, 2016; Ile & Reynouard, 2005;
77 Lowes *et al.*, 2013; Pegon *et al.*, 2000; Sittipunt & Wood, 1993). However, despite being popular in
78 construction, there have been relatively few studies conducted on the seismic performance of C-
79 shaped walls with the type of detailing that would commonly be found in Australia and other low-to-
80 moderate seismic regions, and there is a lack of experimental data for these types of walls. Moreover,
81 the plentiful of plastic hinge analysis expressions used for estimating the displacement capacity of
82 cantilever walls have been primarily calibrated to well-detailed RC elements. Thus, it is possible that
83 these same expressions cannot accurately estimate the displacement capacity of lightly reinforced and
84 unconfined walls found in low-to-moderate seismic regions.

85 The aim of this research is to assess the validity of using plastic hinge analyses (PHA) to estimate the
86 displacement capacity of lightly reinforced and unconfined walls. Two different wall shapes are used
87 for this assessment; rectangular and C-shaped. An extensive number of finite element modelling
88 results, previously used for analysing the equivalent plastic hinge length (Hoult *et al.*, 2017, 2018),
89 will be used to examine the displacement capacity and for comparison to the estimate produced with
90 the crude method of PHA. Expressions are ultimately recommended to be used in PHA for lightly
91 reinforced concrete walls, which are also dependent on the amount of longitudinal reinforcement ratio
92 used in the wall (compared to the minimum required to cause secondary cracking).

93 The results from this study will provide vital information for the vulnerability studies of RC buildings
94 that are being carried out by the authors within the earthquake mitigation component of the Australian
95 CRC (Cooperative Research Centre) for Bushfires and Natural Hazards.

96 **2. Plastic Hinge Analysis**

97 For the purposes of seismic design and assessment, it is common to use a bilinear approximation of
98 the force-displacement response of RC walls (Priestley *et al.*, 1996), as illustrated in Figure 2. A PHA
99 is one of the most widely used and simplest methods for calculating the force-displacement capacities
100 of RC members (Almeida *et al.*, 2016). The PHA acknowledges that the top displacement of a
101 cantilever wall structure is the summation of the deformation components primarily due to flexure,

shear and slipping. These deformation components can be used to calculate the yield displacement (Δ_y) and plastic displacement (Δ_p), as illustrated in Figure 2. The ultimate displacement (Δ_u) of the cantilever RC wall is the summation of Δ_y and Δ_p . The ultimate capacity (or failure) of RC walls in some research has been taken at the point at which the maximum strength is reduced by 20% (Krolicki *et al.*, 2011; Park, 1989). However, as illustrated in Figure 2, the non-ductile failure that is typically expected in unconfined walls with the details commonly found in low-to-moderate seismic regions is likely to correspond to a more abrupt reduction in strength. Therefore, “failure” here is deemed to correspond to material strain limits in the reinforcing steel and concrete for the “collapse prevention” performance level for unconfined RC walls. This corresponds to strains limits of -0.003 and 0.05 in the concrete (ϵ_c) and steel (ϵ_s), respectively, which were subsequently used as the failure strain limits in the studies conducted by Hoult *et al.* (2017) and Hoult *et al.* (2018) for rectangular and C-shaped RC walls respectively. In short, this concrete strain limit for unconfined RC walls represent the concrete reaching close to its ultimate capacity. Furthermore, the steel strains are limited to prevent collapse due to low cycle fatigue (due to inelastic cycles in main event plus aftershocks) and out-of-plane buckling on reversal of load. This has been calculated as $0.6\epsilon_{su}$ as per the recommendations in Priestley *et al.* (2007), where the uniform elongation strain (ϵ_{su}) has been taken as an approximate mean value given in Menegon *et al.* (2015) for D500N bars. It should be noted that these values have been chosen for assessment, where more conservative values could be warranted for the reinforcing steel in design, such as 0.03, which corresponds to 0.6 of the nominal uniform elongation strain for N-type reinforcing steel (Standards Australia/New Zealand, 2001). An even more stringent tension strain limit for the design of RC walls could also warranted to mitigate against out-of-plane buckling of the wall.

Figure 2 Idealised Force-displacement response

In this section, a review is undertaken for some of the equations that have been recommended in the literature for determining the displacement capacity of RC walls using the PHA method. These PHA equations will ultimately be scrutinised as to their applicability for lightly reinforced and unconfined rectangular and C-shaped walls. It should be noted that the research conducted here is primarily focused on improving the displacement capacity estimates for these types of walls due to flexure. The authors acknowledge the potential for other contributions to the overall displacement capacity of a RC wall, such as shear and slip, or other modes of failure, such as out-of-plane buckling due to poor confinement. However, due to both lack of experimental evidence and limitations of the PHA method, the primary focus of this research is to investigate the displacement capacity of these types of walls assuming the performance is governed by flexure.

2.1 Yield Displacement

The displacement of the wall at first yield (Δ'_y) is defined as when the outermost reinforcing bar in the extreme tension fibre region of the RC section first reaches the strain at yield. The line that extends from this point to the nominal yield (Δ_y) point (Figure 2) is calculated using Equation 1.

$$\Delta_y = \frac{\Delta'_y F_u}{F_y}$$

For moderate to slender rectangular RC walls with high aspect ratios ($A_r > 2$) the contribution of shear deformations and displacements due to slip are commonly ignored due to the negligible amount they contribute to the overall displacement capacity (Wibowo *et al.*, 2013). However, the shear deformations can make an important contribution to the overall displacement of non-rectangular RC sections, such as C-shaped walls, even if the A_r is greater than 2 (Beyer *et al.*, 2008b; Constantin & Beyer, 2016; Zhang & Li, 2014). A commonly used expression for estimating Δ_y is given in Priestley *et al.* (2007) with Equation 2. Importantly, this expression has been derived assuming the curvature profile up the height of the wall is a ‘straight line from the yield value at the base to zero at the top of the wall’ (Priestley *et al.*, 2007).

$$\Delta_y = \frac{\Phi_y H_e^2}{2} \left(1 - \frac{H_e}{3H_n} \right) \quad 2$$

where Φ_y is the nominal yield curvature, H_e is the effective height of the cantilever wall and H_n is the height of the cantilever wall at roof level.

However, Beyer (2007) recognised that the assumption of the linear curvature profile ‘tends to overestimate the flexural displacements in the upper part of the wall’. It is also probable that the linear curvature assumption is vastly different to the realistic curvature profiles obtained from lightly reinforced concrete walls when pushed to their ultimate limit state. This is particularly true for lightly reinforced walls that exhibit a single, primary crack, where the strains (at yield) will be concentrated over a small height at the base of the wall. To overcome this, a new approach was proposed in Beyer (2007) to calculate the yield displacement based on the flexural, strain penetration and shear deformation components. A factor (defined here as k_{cr}) was also introduced by Beyer (2007), and later revised by Constantin (2016), to account for the actual height of the wall that is estimated to be cracked, which is illustrated in Figure 3. Thus, the yield displacement expression for a RC wall as proposed by Beyer (2007) is in the form of Equation 3, which includes the contributions due to shear deformations using the shear-to-flexure deformation ratio (Δ_s / Δ_f).

Figure 3 Factors proposed by Beyer (2007) and Constantin (2016) for calculating the yield displacement

$$\Delta_y = \Phi_y \left(\frac{k_{cr}}{3} H_n^2 + L_{yp} H_n \right) \left(1 + \frac{\Delta_s}{\Delta_f} \right) \quad 3$$

where L_{yp} is the yield strain penetration length (a parameter discussed further in Section 2.2). The expression for k_{cr} is given in Constantin (2016) in the form of Equation 4.

$$k_{cr} = \alpha + 0.5(1 - \alpha) \left(\frac{3H_{cr}}{H_n} - \frac{H_{cr}^2}{H_n^2} \right) \quad 4$$

where α is the ratio of cracked to uncracked flexural wall stiffness ($E_c I_{cr} / E_c I_g$) and H_{cr} is the height of the cracked wall, which can be estimated using Equation 5. It should be noted that the stiffness of the cracked section ($E_c I_{cr}$) can be estimated using the ratio of the moment to curvature at first yield (M'_y / Φ'_y).

$$H_{cr} = \max \left(L_w, \left(1 - \frac{M_{cr}}{M'_y} \right) H_n \right) \quad 5$$

where M_{cr} is the cracking moment (Equation 6).

$$M_{cr} = \frac{\left(f'_{ct.f} + \frac{P}{A_g} \right) I_g}{y} \quad 6$$

where P is the axial load, A_g is the gross section area, I_g is the gross second moment of inertia of the wall cross-section, y is the distance from the neutral axis to the extreme tension fibre region and $f_{ct,fl}$ is the mean value of the flexure tensile strength of the concrete.

It should be noted that in some RC wall cases, when a very low amount of longitudinal reinforcing steel has been used, the M_{cr} could be greater than M'_y . Therefore, H_{cr} (Equation 5) is taken as L_w for these types of walls. Although this value of H_{cr} (of L_w) is unrealistic, given that these types of walls are more likely to produce a single, primary crack at the base, the proposed modification factor (discussed later in Sections 4.1.2 and 4.2.2) rectifies this problem.

The curvature at first yield (Φ'_y) can be calculated from a sectional analysis (or “moment-curvature analysis”), where Equation 7 corresponds to the curvature at which the outer-most longitudinal reinforcing bar in the extreme tension fibre region reaching the yield strain (ϵ_y). The yield strain can be determined from the yield stress (f_y) and the Young’s modulus (E_s) of the reinforcing steel ($\epsilon_y = f_y/E_s$). The nominal yield curvature (Φ_y) can thus be calculated using Equation 8. Moreover, the expression shown in Equation 9, which was first suggested by Priestley and Kowalsky (1998), can be used to estimate the Φ_y of a RC wall, where the ‘proportionality factor’ (K_I) is said to be largely depend on the longitudinal reinforcement layout and the shape of the cross section of the wall.

$$\Phi'_y = \frac{M_y}{E_c I_{eff}} \quad 7$$

$$\Phi_y = \Phi'_y \left(\frac{M_u}{M_y} \right) \quad 8$$

where M_u is the ultimate moment capacity of the RC section.

$$\Phi_y = \frac{K_I \epsilon_{sy}}{L_w} \quad 9$$

Several researchers have given recommendations on the value of K_I that should be used to estimate Φ_y (Equation 9) for a range of wall shapes. For example, a commonly used value of K_I for RC rectangular walls is 2.0, which has been derived from analytical and experimental studies (Paulay, 2002; Priestley & Kowalski, 1998). The K_I value of 2.0 for RC rectangular walls has subsequently

been used in the PHA method outlined in Priestley *et al.* (2007). However, as discussed in Priestley and Kowalski (1998), the relationship for yield curvature with a K_I factor 2.0 ‘should not be extrapolated beyond the range $300 \leq f_y \leq 500$ MPa nor beyond the limits of longitudinal steel ratio’, which were between $1.00\% \leq \rho_{wy} \leq 4.00\%$. Given that the lower characteristic value of the yield stress (f_y) of D500N reinforcing bars commonly used in Australia is 500 MPa (Standards Australia/New Zealand, 2001), the actual value of f_y will typically be higher than 500 MPa. Moreover, the majority of RC walls found in this region will have longitudinal reinforcement ratios lower than 1.00% (Albidah *et al.*, 2013; Wibowo *et al.*, 2013). Adebar and Lorzadeh (2012) also discuss that it is rare for RC walls to have a ρ_{wy} higher than 1.00%. Hence the equation for estimating the nominal yield curvature for rectangular walls in Australia needs further investigation.

Beyer (2007) recognised that K_I factors had not been derived explicitly for U-shaped (or C-shaped) RC sections. However, Beyer (2007) realised it was possible that the K_I factors for I-shaped and T-shaped walls could ‘serve as approximates’ for C-shaped walls and bending about the major and minor axes, respectively. Following the research by Beyer (2007), some values have been proposed by Sullivan *et al.* (2012) for C-shaped walls, given in Table 1. It should be noted that ‘Major’ corresponds to bending of the C-shaped wall in the direction parallel to the web (about the major axis), whereas WiC and WiT correspond to the wall bending in the direction parallel to the flanges (about the minor axis) with web in compression and web in tension, respectively. These different modes of bending for a C-shaped wall are illustrated in Figure 4, where the shaded regions of the wall are the idealised compression zones. Testing of the seismic performance of C-shaped walls designed to regions of high seismicity from Constantin (2016) found that these proposed values corresponded well to experimental observations.

Table 1 K_I values proposed for C-shaped walls

	Major	WiC	WiT
Sullivan <i>et al.</i> (2012)	1.40	1.40	1.80

Figure 4 Different modes of bending for (a) rectangular walls and (b-d) C-shaped wall, with idealised neutral axis for high levels of loading

2.2 Plastic Displacement

To estimate the plastic deformation (Δ_p), the strains and corresponding curvatures need to be determined, and these will vary considerably up the height of a cantilevered wall. However, it is common practice to simply assume that the inelastic curvature is uniform for a height above the base that is equivalent to the plastic hinge length (L_p) (Fenwick & Dhakal, 2007). This is a reasonable approximation and is utilised in the equations proposed by Priestley *et al.* (2007) for the displacement profile of a cantilevered wall in Equation 10. It should be noted that the shear-to-flexure ratio has been included in Equation 10, which was also used by Constantin (2016) for the plastic displacement of C-shaped walls; for rectangular walls with A_r greater than 2, it is assumed that the Δ_s / Δ_f is equivalent to zero (negligible).

$$\Delta_p = L_p (\Phi_u - \Phi_y) H_e \left(1 + \frac{\Delta_s}{\Delta_f} \right) \quad 10$$

where Φ_u is the ultimate curvature.

Many empirical equations are available for calculation of the equivalent plastic hinge length (L_p). For example, Equation 11 is recommended from Priestley *et al.* (2007) for RC cantilever walls.

$$L_p = k H_e + 0.1 L_w + L_{yp} \quad 11$$

where k is a constant reflecting the distribution of plasticity dependent on the ratio of the ultimate strength to yield strength of the reinforcing steel ($k = 0.2(f_u/f_y - 1) \leq 0.08$) and L_{yp} is the strain penetration length defined in Priestley *et al.* (2007) with Equation 12.

$$L_{yp} = 0.022f_{ye}d_{bl} \quad 12$$

236 where f_{ye} is the expected yield stress of the steel ($1.1f_y$).

237 More recently, Equation 13 was specifically derived from analytical and experimental results of RC
238 C-shaped walls from (Constantin, 2016).

$$L_p = \left[0.05H_e + 0.05L_w \left(\frac{\tau}{0.17\sqrt{f'_c}} \right) \right] (1 + 4ALR) \quad 13$$

239 where ALR is the axial load ratio and τ is the average shear stress parameter, which can be calculated
240 from a sectional analysis (“moment-curvature” analysis) or can be estimated by dividing the base
241 shear (V_b) of the wall by the effective area (A_{eff}) of the section. The ALR is calculated as $P/f_{cmi}A_g$,
242 where P is the axial force on the wall, f_{cmi} is the mean compressive strength of concrete.

243 However, Equations 11 and 13, as well as many other expressions for estimating L_p (Bohl & Adebar,
244 2011; Kazaz, 2013; Paulay, 1986; Priestley & Park, 1984; Thomsen & Wallace, 2004; Wallace &
245 Moehle, 1992), have been derived primarily from analytical and experimental results for RC elements
246 that are not representative of lightly reinforced and unconfined concrete walls in regions of low-to-
247 moderate seismicity. It was shown in Hoult *et al.* (2017) and Hoult *et al.* (2018) that these commonly
248 used expressions provide a large scatter of results in comparison to the L_p derived from numerical
249 analyses for lightly reinforced rectangular and C-shaped walls respectively. Subsequently, an
250 expression was derived to predict the L_p for lightly reinforced and unconfined rectangular walls with
251 Equation 14. Importantly, this expression was only recommended to be used for RC walls that had a
252 sufficient amount of longitudinal reinforcement to allow secondary cracking. Thus, if a wall has a
253 longitudinal reinforcement ratio less than the minimum required to initiate secondary cracking ($\rho_{wv} <$
254 $\rho_{wv.min}$), a L_p of 100 mm was recommended for design purposes; a slightly less conservative L_p of 150
255 mm will be used here for assessment purposes. It should be noted that the L_p of 150 mm,
256 corresponding to the strain penetration length (L_{yp}), is close to the value of that calculated with
257 Equation 12 (assuming the d_{bl} is 12 mm). Furthermore, the value of 150 mm is approximate to the
258 mean of the L_p values determined from the results of all of the rectangular and C-shaped walls with a
259 ρ_{wv} less than $\rho_{wv.min}$ analysed in VecTor3 using the Equivalent Plastic Hinge Length method (Hoult *et*

al., 2018). The $\rho_{wv.min}$ can be calculated using the expression given in Hoult *et al.* (2017) (Equation 15). More information about the derivation and limitations of the L_p expression for lightly reinforced rectangular concrete walls can be found in Hoult *et al.* (2017).

$$L_p = (0.1L_w + 0.075H_e)(1 - 6ALR) \leq 0.5L_w \quad 14$$

$$\rho_{wv.min} = \frac{(t_w - n_t d_{bt}) f_{ct.fl}}{f_u t} \quad 15$$

where t_w is the thickness of the wall, n_t is the number of grids of transverse reinforcing bars, d_{bt} is the diameter of the transverse reinforcing bars and f_u is the ultimate tensile strength of the reinforcing steel. The $f_{ct.fl}$ can be approximated using the expressions given in fib (2012).

Expressions for predicting the L_p of lightly reinforced and unconfined C-shaped walls were also derived for the 3 different modes of bending (about the major axis [$L_{p.major}$] and about the minor axis with web in compression [$L_{p.minor.WiC}$] and web in tension [$L_{p.minor.WiT}$]), given in Equations 16, 17 and 18 respectively. It should be noted that these expressions (Equations 16 to 18) should only be used for walls that have a sufficient amount of longitudinal reinforcement for secondary cracking; if a C-shaped wall has a ρ_{wv} less than $\rho_{wv.min}$ (Equation 15), then a L_p of 150 mm is used here for assessment purposes (as discussed above). More information about the derivation and limitations of the L_p expressions for lightly reinforced C-shaped concrete walls can be found in Hoult *et al.* (2018).

$$L_{p.major} = (0.1L_{web} - 0.013H_e)(1 - 13ALR)(7e^{-0.8v}) \leq 0.5L_{web} \quad 16$$

where L_{web} is the length of the web of the C-shaped wall (Figure 4) and v is the average normalised shear stress. The v parameter is calculated as $\tau/0.17\sqrt{f_{cmi}}$, where the $0.17\sqrt{f_{cmi}}$ term is taken from ACI-11 (ACI, 2011) for the shear stress capacity at diagonal cracking, which is also used in AS 3600:2009 (Standards Australia, 2009) for the calculation of the minimum shear strength of a wall (without consideration of the shear reinforcement).

$$L_{p.minor.WiC} = (0.5L_{flange} - 0.015H_e)(1 - 3ALR)(1.6e^{-0.1v}) \leq L_{flange} \quad 17$$

where L_{flange} is the length of the flange of the C-shaped wall (Figure 4).

$$L_{p.minor.WiT} = (1.0L_{flange} - 0.073H_e)(1 - 8ALR)(2.5e^{-2.1\nu}) \leq 0.5L_{flange} \quad 18$$

2.3 Shear Displacement

As previously mentioned in Section 2.1, a common assumption in a plastic hinge analyses for rectangular RC wall sections with large A_r is to neglect the shear and slip displacements (Almeida *et al.*, 2016). For example, this assumption appeared to be valid for the three experimental lightly reinforced rectangular concrete walls tested by Albidah (2016) and Altheeb (2016). However, for non-rectangular wall sections (e.g. C-shaped), shear deformations can represent a larger portion of the total displacement capacity of the wall in comparison to that for rectangular walls. For instance, Beyer (2007) found that the shear-to-flexure (Δ_s / Δ_f) ratios of the two experimentally tested C-shaped walls ranged from approximately 8% to 38%, depending on the direction of loading. Moreover, recent experimental testing on two other C-shaped walls from Constantin (2016) found similar values for the same directions of loading, with Δ_s / Δ_f values ranging from 16% to 33%. Given the potential for shear deformations to make a large contribution to the overall displacement capacity of RC C-shaped walls, it is important to incorporate a shear deformation model into the PHA for these types of walls.

Over the past decade or so, several models have been recommended for use in predicting the shear displacement of RC walls, and these can be incorporated into a PHA (Beyer *et al.*, 2011; Hannewald, 2013; Hines *et al.*, 2004; Priestley *et al.*, 2007). The simplified method for incorporating the shear deformations (Δ_s) in a PHA for RC walls is to compare the shear contribution to the overall flexural deformation (Δ_f). This is because the shear-to-flexure ratio (Δ_s / Δ_f) has previously been found to be relatively constant throughout the inelastic range (Beyer *et al.*, 2011; Hines *et al.*, 2004).

The Δ_s / Δ_f deformation model proposed by Beyer *et al.* (2011) is expressed in the form of Equation 19. This expression (Equation 19) assumes that the shear-to-flexure ratio is constant throughout the inelastic range and that the shear deformations only occur in the equivalent plastic hinge region.

$$\frac{\Delta_s}{\Delta_f} = 1.5 \left(\frac{\varepsilon_m}{\Phi_u \tan \theta_c} \right) \left(\frac{1}{H_e} \right) \quad 19$$

where ε_m is the mean axial strain of the RC section (which can be estimated from a moment-curvature analysis) and θ_c is the crack angle.

The crack angle (θ_c) has traditionally been taken as 45° (Krolicki *et al.*, 2011), a value which is also used for design purposes (Beyer *et al.*, 2011). However, recent research has indicated that there is some variability in the cracking angle, which can range from 25° to 65° (Krolicki *et al.*, 2011). Moreover, Priestley *et al.* (1996) recommended an average cracking angle of 30° to be used for the assessment of existing structures.

3. Finite element modelling results

An extensive number of finite element modelling analyses were originally conducted in Hoult *et al.* (2017) and Hoult *et al.* (2018) for lightly reinforced and unconfined rectangular and C-shaped walls respectively. The strain distribution results from the numerical analyses were initially used to calculate the equivalent plastic hinge length for a range of walls and different parameters with values that would be prevalent in the low-to-moderate seismic region of Australia. The force-displacement relationships from these same numerical analyses are used in this research to investigate that displacement capacity, with comparisons being made to the estimates from PHA. The next section briefly discusses how the finite element modelling programs were validated, which is followed by sections that summarise the different wall parameters that were used in the numerical analyses. For the sake of brevity, the reader is referred to Hoult *et al.* (2017) and Hoult *et al.* (2018) for more information with regards to the finite element modelling programs used, model and mesh setup, as well as the subsequent material models used (and validation of such models).

3.1 Validation of VecTor

VecTor2 (Wong *et al.*, 2013) and VecTor3 (ElMohandes & Vecchio, 2013) are state-of-the-art nonlinear finite element modelling programs used for RC 2-dimensional and 3-dimensional solids (respectively) that use the Disturbed Stress Field Model (DSFM) (Vecchio *et al.*, 2000). Information about the program and some improvements of the predictions for the behaviour of RC elements can be found in Wong *et al.* (2013) and ElMohandes (2013). VecTor2 has been used in a variety of past

research for modelling RC walls (Beyer, 2007; Bohl & Adebar, 2011; Dai, 2011; Ghorbani-Renani *et al.*, 2009; Lu *et al.*, 2014; Luu *et al.*, 2013; Sritharan *et al.*, 2014). To the authors' knowledge VecTor3 has only been used for comparison with one past experimental study on RC walls (Peña, 2001). The results from Peña (2001) on a H-shaped wall using VecTor3 compared well to the results given by VecTor2, as the wall was symmetrical and could be analysed by both programs.

A range of material models have been incorporated in VecTor2 and VecTor3 to represent modelling of the concrete and steel materials. These models were used for the finite element modelling analyses conducted in Hoult *et al.* (2017) and Hoult *et al.* (2018) for lightly reinforced and unconfined rectangular and C-shaped walls respectively. These models are summarised in Table 2, where the reader is directed to Hoult *et al.* (2017) and ElMohandes and Vecchio (2013) for more information on the selected models.

Table 2 Material models used in VecTor2 and VecTor3

Constitutive Behavior	Model
Compression Pre-Peak	Popovics NSC ¹ /Popovics HSC ²
Compression Post-Peak	Popovics NSC ¹ /Popovics HSC ²
Compression Softening	Vecchio 1992-B (e1/e0-Form)
Tension Stiffening	Modified Bentz 2003
Tension Softening	Bilinear
FRC Tension	Not Considered
Confined Strength	Kupfer/Richter
Dilation	Variable - Kupfer
Cracking Criterion	CEB-FIP Model (Kupfer <i>et al.</i> , 1973)
Crack Stress Calc	Basic (DSFM/MCFT)
Crack Width Check	Aggregate 2.5mm Max Crack Width (Default)
Crack Slip Calc	Walraven (Monotonic)
Creep and Relaxation	Not Available
Hysteretic Response	Palermo 2002 (with Decay)

¹Normal Strength Concrete (NSC) < 45MPa

²High Strength Concrete (HSC) ≥ 45MPa

VecTor2 was shown in Hoult *et al.* (2017) to provide reasonably good results in comparison to the relevant experimental data from rectangular wall specimens R1 from Oesterle *et al.* (1976) and C1 from Lu *et al.* (2015), including the force-displacement relationship (monotonic and reverse cyclic),

cracking distribution and strain/curvature distribution up the height of the wall. Furthermore, the experimental results from specimens Wall1 and Wall2 from Altheeb (2016) were also used in Hoult (2017) to determine the applicability of the material models (Table 2) for VecTor2. Importantly, Wall1 and Wall2 were both lightly reinforced and unconfined rectangular walls detailed to current Australian practice (Altheeb, 2016), with Wall1 forming a single-crack at the base of the wall during testing. The force-displacement results from VecTor2 for Wall1 and Wall2 (and for monotonic loading) is given in Figure 5.

Figure 5 VecTor2 results for (a) Wall1 and (b) Wall2 from Altheeb (2016)

VecTor3 was shown to provide reasonably good results in Hoult *et al.* (2018) in comparison to the relevant experimental data for C-shaped wall specimens TUA from Beyer *et al.* (2008b) and S02 from Menegon *et al.* (2017), including the force-displacement relationship (monotonic and reverse cyclic), cracking distribution and strain/curvature distribution up the height of the wall. Importantly, wall specimen S02 from Menegon *et al.* (2017) was an unconfined C-shaped core wall (box-shaped building core with door opening) that was ‘designed to best represent current building practices in Australia’. The force-displacement relationship determined from VecTor3 for wall specimen S02 (and for both reverse cyclic and monotonic loading) is shown in Figure 6, where the experimental relationship from Menegon *et al.* (2017) is superimposed in the figure. It should be noted that the VecTor3 monotonic analysis for the modelled S02 wall specimen (results shown in Figure 6) was

pushed past what the authors of this research have defined as failure, which corresponds to the limiting strain values for “Collapse Prevention” (discussed in Section 2). The circle symbol in Figure 6 indicates when the unconfined concrete strain of -0.003 was reached in the VecTor3 monotonic analysis. This ultimate displacement corresponds to an average drift of 1.57%, which is similar to the 1.5% average drift reached experimentally in Menegon *et al.* (2017) before ‘lateral load failure’ occurs. The experimental specimen S02 was found to fail with degradation of the concrete ‘due to a combination of tensile fracturing, unzipping of the lap splice and bond failure between the concrete and reinforcement in the previous reversed load cycle’ (Menegon *et al.*, 2017). The VecTor3 model of S02 is unable to capture this degradation, as the lap splice and discontinuity of longitudinal reinforcement up the height of the wall were not modelled in VecTor3 (Hoult *et al.*, 2018) and smeared longitudinal (and transverse) reinforcement were used to model the bars (where bond degradation cannot be modelled). However, it is shown that an unconfined compression strain of -0.003 does a reasonable job of estimating failure (or onset of failure) for this wall specimen.

Figure 6 Force-displacement results from VecTor3 for wall specimen S02

3.2 Rectangular walls

VecTor2 (Wong *et al.*, 2013) was used in Hoult *et al.* (2017) to analyse a total of 378 lightly reinforced and unconfined rectangular concrete walls with varying parameters. The range of different parameters are discussed below and summarised in Table 3.

The effective height (H_e) is estimated to be $0.7H_n$ as recommended by Priestley *et al.* (2007) and all of the walls' aspect ratios (A_r) are equal to or greater than 2 (governed by flexure). The $ALRs$ have been chosen to represent the majority of the building stock in low-to-moderate seismic regions, where $ALRs$ of less than 5% are common in walls with low vertical reinforcement (Henry, 2013). Moreover, the RC walls investigated by Albidah *et al.* (2013) for low-to-moderate seismic regions indicated that most of the walls had $ALRs$ less than 5%, and the highest ALR did not exceed 10%. The minimum transverse reinforcement ratio of 0.25% from AS 3600:2009 (Standards Australia, 2009) is used for all of the walls. The minimum longitudinal reinforcement ratio (ρ_{lv}) required by AS 3600:2009 (Standards Australia, 2009) is 0.15%, while RC walls with ρ_{lv} less than 2.00% are said to 'represent the great majority of building stock in low-to-moderate seismic regions such as Australia' (Wibowo *et al.*, 2013). As previously discussed in Section 2.1, Adebar and Lorzadeh (2012) believe it is rare for RC walls to have a ρ_{lv} higher than 1.00%. Therefore, the ρ_{lv} values used were 0.15%, 0.30%, 0.45%, 0.60%, 0.75%, 0.90% and 1.00%. The longitudinal reinforcement is distributed evenly throughout the wall, which is commonly practice in low-to-moderate seismic regions (Hoult *et al.*, 2017). The two f_{cmi} values of the walls considered in this study were 40 MPa and 60 MPa, which are realistic values for walls designed originally with a characteristic compressive strength (f'_c) of 32 MPa and 40 MPa, given that the target strength would have been higher than this and that the concrete strength will increase with time. The f_{cmi} values adopted correspond to increased strength factor ($\kappa = f_{cmi} / f'_c$) values of 1.25 and 1.50 respectively; these are values representative of concrete that has aged over several years as indicated in Moehle (2015). Mean values of the material properties for the reinforcing steel were adopted from Menegon *et al.* (2015) for D500N bars which conform to AS/NZS 4671 (Standards Australia/New Zealand, 2001). The f_y used was 551 MPa with a Young's Modulus (E) of 200,000 MPa and ultimate-to-yield stress ratio (f_u/f_y) of 1.20. The ultimate strain for the purpose of the wall assessments was taken as 60% of the mean value of the uniform elongation strain, i.e. $0.6\epsilon_{su}$ ($0.6 \times 94.6 \text{ mm/m} = 57 \text{ mm/m}$), based on the recommendations from Priestley *et al.* (2007) as discussed previously in Section 2.

Table 3 Walls used in VecTor2 with varying parameters

L_w (m)	t (m)	A_r	H_e (m)	ALR (%)	f_{cmi} (MPa)	ρ_{lv} (%)	ρ_{wh} (%)
-----------	---------	-------	-----------	-----------	-----------------	-----------------	-----------------

3	0.2	2.5, 4.1, 5.7	7.35, 12.25, 17.15	1.5, 5, 10	40, 60	0.15 - 1.00	0.25
6	0.2	2.0, 3.3, 4.1	12.25, 19.60, 24.50	1.5, 5, 10	40, 60	0.15 - 1.00	0.25
9	0.25	2.7, 3.8, 4.9	24.50, 34.30, 44.10	1.5, 5, 10	40, 60	0.15 - 1.00	0.25

3.3 C-shaped walls

VecTor3 (ElMohandes & Vecchio, 2013) was used in Hoult *et al.* (2018) to analyse a total of 144 lightly reinforced and unconfined *C-shaped* concrete walls with varying parameters. The range of different parameters are discussed below and are summarised in Table 4.

Similar to Section 3.2 for the rectangular walls, the $ALRs$, ρ_{wh} and ρ_{wv} values have been chosen to represent common values found in Australia and other low-to-moderate seismic regions. It should also be noted that the longitudinal reinforcement is distributed evenly throughout the C-shaped walls. Furthermore, the same f_{cmi} values used in Section 3.2 for the rectangular walls are used here; the two f_{cmi} values considered in this study were 40 MPa and 60 MPa. Mean values of the material properties for the reinforcing steel were taken from Menegon *et al.* (2015) for D500N bars (provided in Section 3.2), which conform to AS/NZS 4671:2001 (Standards Australia/New Zealand, 2001). The ultimate strain of the reinforcing steel was taken as $0.6\epsilon_{su}$ based on the recommendations from Priestley *et al.* (2007) and as discussed previously in Section 3.2.

Table 4 Walls used in VecTor2 with varying parameters

Wall	ALR (%)	f_{cmi} (MPa)	ρ_{wv} (%)	ρ_{wh} (%)
LR	1.5, 5	40, 60	0.15, 0.45, 0.70, 1.0	0.25
MR	1.5, 5	40, 60	0.15, 0.45, 0.70, 1.0	0.25
HR	1.5, 5	40, 60	0.15, 0.45, 0.70, 1.0	0.25

Three different wall sizes have been chosen to represent C-shaped RC cores enclosing elevators for a low-rise (LR), mid-rise (MR) and high-rise (HR) building. The number of storeys of the LR, MR and HR C-shaped walls was chosen to be 3, 6 and 12 respectively, which are within the range given in FEMA (2010) and Maqsood *et al.* (2014). Using an inter-storey height of 3500 mm, the effective height ($H_e \approx 0.7H_n$) is approximately 7.35 m, 14.70 m and 29.40 m for the LR, MR and HR wall respectively. The number of elevator cars required for the different rise of building determines the

size of the walls based on the recommendations given in RLB (2014). The LR C-shaped wall was assumed to enclose two elevator cars (2x500kg, 6 person), while the MR C-shaped wall was assumed to enclose three cars (3x900kg, 12 person) and the HR C-shaped wall was assumed to enclose four cars (4x1150kg, 16 person). The internal dimensions (width x depth, in mm) of the 500kg, 900kg and 1150kg elevator cars are 1000 x 1300, 1400 x 1500 and 1500 x 1800 respectively. Therefore, the resulting lengths of the web (L_{web}) and flange (L_{flange}) that were required for the three different walls are given in Table 5. After some discussions with P. McBean (personal communication, February 26, 2016), a consulting engineer and Joint Managing Director of Wallbridge & Gilbert, 200mm thick walls and a length of 600 mm (approximately 2 ft) for the returns (L_{return}) were taken as values that reflect current and past practice in Australia. The thickness (t_w) of the HR C-shaped wall was increased to 250 mm, as shown in Table 5. The A_r values of the C-shaped walls, which are all greater than 2.0, are different depending on the direction of loading; for bending about the major axis, the A_r is taken as H_e/L_{web} , whereas for bending about the minor axis the A_r is taken as H_e/L_{flange} . These two different A_r values for each of the walls are given in Table 5.

Table 5 Dimensions of the C-shaped walls

Wall	t_w (mm)	L_{web} (mm)	L_{flange} (mm)	L_{return} (mm)	A_r	H_e (m)
LR	200	3600	2000	600	2.1 ^a , 3.7 ^b	7.35
MR	200	6200	2200	600	2.4 ^a , 6.7 ^b	14.70
HR	250	8500	2500	600	3.4 ^a , 11.7 ^b	29.30

^aFor bending about the major axis

^bFor bending about the minor axes

4. Displacement capacity results

The following sections discuss the finite element modelling results, in terms of the displacement capacities achieved, from the rectangular and C-shaped wall analyses. The curvature and displacement estimates from the numerical results are compared to the estimates made with PHA. Recommendations are ultimately given to improve the PHA accuracy for these types of walls.

4.1 Displacement capacity of rectangular walls

4.1.1 Yield Curvature

As discussed previously in Section 2.1, a value of 2.0 is commonly used for K_I when estimating Φ_y for rectangular RC walls using Equation 9. A K_I value of 2.0 was found to overpredict the yield curvature in comparison to experimental observations of six rectangular structural RC walls tested on a shaker table by Lestuzzi and Bachmann (2007). Lestuzzi and Bachmann (2007) found that the poor correlation is the result of the properties of reinforcing steel that is outside the limitations of the equation proposed by Priestley and Kowalski (1998), as discussed in Section 2.1. Interestingly, the reinforcing steel used in these experimental RC wall specimens had mechanical properties similar to the D500N bars used for this research investigation.

Using the minimum of the sum of the squares for the results of the 378 rectangular walls analysed in VecTor2, it was found that a K_I value of 1.7 correlated well to the VecTor2 results for the nominal yield curvature (Φ_y) when using Equation 9. The resulting value of 1.7 was within the values (of K_I) adopted by Lestuzzi and Bachmann (2007) of 1.75 and 1.56, depending on whether the experimental rectangular wall specimens that were tested had light or heavy amounts of longitudinal reinforcement concentrated (lumped) at the ends of the wall. The yield curvature estimates using K_I values of 1.7 and 2.0 are illustrated in Figure 7; although the same R^2 value is achieved using either of the K_I values, it can be observed that the K_I value of 2.0 (Figure 7b) primarily overestimates Φ_y in comparison to the VecTor2 data.

Figure 7 Yield curvature results from VecTor2 compared to estimates using Equation 9 with K_I values of (a) 1.7 and (b) 2.0

4.1.2 Yield Displacement

The nominal yield displacement (Δ_y) was found from the VecTor2 results for the lightly reinforced and unconfined rectangular walls. These values were calculated using Equation 1, where the displacement at first yield (Δ'_y) corresponded to the yield strain being reached in the extreme tension fibre region. The results from the numerical analyses showed that Δ_y increased as a function of the ρ_{wy} of the walls. For example, the nominal yield displacement values are given as function of the longitudinal reinforcement ratio in Figure 8 for the six-metre rectangular walls (with f_{cm} of 40 MPa) and three different ALRs. An increasing yield displacement with increasing amounts of the longitudinal reinforcement content is expected, given that a higher ρ_{wy} would induce a larger extent of cracking in the yielding region of the wall; if more cracks form at the base of the wall, the strain is more evenly distributed up the wall height, allowing higher displacement capacities to be achieved. Little variance can be observed in Figure 8 for the Δ_y achieved by the walls with the different ALRs, particularly for the walls with a higher ρ_{wy} (or once secondary cracking is achieved). Based on the work in Hoult *et al.* (2017) and Equation 15, the minimum longitudinal reinforcement ratio ($\rho_{wy,min}$) required to initiate secondary cracking is approximately 0.50% and 0.65% for the 40 MPa and 60 MPa RC walls. These estimated values of $\rho_{wy,min}$ were shown to correspond well to the cracking and strain distributions investigated using the same numerical results in Hoult *et al.* (2017). As reflected in Figure 8, a higher Δ_y is achieved when secondary cracking occurs in comparison to the walls with insufficient longitudinal reinforcement. In the latter case, the wall exhibits a single, primary crack, where the yield and plastic strains are concentrated over a small height of the wall, and hence a lower nominal yield displacement capacity is achieved for these walls.

Figure 8 Nominal yield displacement as a function of longitudinal reinforcement for the 6 metre (40 MPa) rectangular walls

Interestingly, the PHA approach recommended by Priestley *et al.* (2007) for calculating Δ_y (Equation 2) is independent on the flexural strength of the wall and is therefore constant throughout the range of ρ_{wy} used for a given cross-section of wall. This is shown in Figure 9, where the Δ_y estimates using Equation 2 from Priestley *et al.* (2007) are superimposed with the Δ_y results from VecTor2 for the 6 metre (40 MPa, 5% ALR) rectangular walls of varying aspect ratio (A_r). It should be noted that the nominal yield curvature (Φ_y) in Equation 2 has been calculated using Equation 9, where a value of 1.7 was used for K_I , due to the findings in Section 4.1.1, and a value of 0.0027 for ϵ_{sy} . The estimated Δ_y , using the expression from Priestley *et al.* (2007), overpredicts the Δ_y in comparison to the numerical results throughout the ρ_{wy} range, even with the reduced value of 1.7 [from 2.0 recommended in Priestley *et al.* (2007)] for K_I for lightly reinforced walls. This conforms with the supposition from Beyer (2007) discussed in Section 2.1, where it was suggested that the linear curvature profile approach [from Priestley *et al.* (2007)] will overestimate the nominal yield displacement capacity. To illustrate this further, Figure 10 gives the curvature profile at yield for the 6 metre walls (40 MPa, ALR of 5% and an A_r of 3.27) with varying ρ_{wy} . Superimposed on this figure is the linear curvature profile, which is one of the assumptions used to derive Equation 2 from Priestley *et al.* (2007). It should be noted that the height of the wall in Figure 10 has been normalised to the height of the cantilever wall at roof level (H_n) of 28 m. Although it appears that some yielding (and thus, some cracking) has occurred in the majority of the walls (with a sufficient longitudinal reinforcement ratio

515 to allow secondary cracking) and in the lower 20-40% of the wall height (from the base), the actual
 516 curvature profiles are far different from the approximate linear curvature profile. Moreover, the
 517 curvature distribution becomes more linear as the longitudinal reinforcement ratio increases, which
 518 explains the trend illustrated in Figure 8 and Figure 9.

519

520 **Figure 9 Nominal yield displacement estimates using the expression by Priestley *et al.* (2007)**

521

522 **Figure 10 Yield curvature profiles for the 6 metre walls compared to the linear curvature profile**

523 In contrast to the PHA approach from Priestley *et al.* (2007), the method proposed by Beyer (2007)
 524 (Equation 3) attempts to determine the height of the wall that is cracked and uncracked. Importantly,
 525 Equation 3 is dependent on the ratio of cracked to uncracked flexural wall stiffness (α), which can be

determined for each RC wall case with the M'_y and Φ'_y values, and the height of the cracked wall H_{cr} (Equation 5), which is determined from the ratio of M_{cr} to M'_y (Equation 6). Figure 11 gives the Δ_y results as a function of the ρ_{wy} used from VecTor2 for the 6 metre (40 MPa, 5% ALR) rectangular walls of varying aspect ratio (A_r), where the Δ_y estimates using Equation 3 are superimposed. It should be noted that Φ_y in Equation 3 has been estimated using a K_I value of 1.7 and a value of 0.0027 for ε_{sy} . The majority of the estimated values of Δ_y in Figure 11, using the expression from Beyer (2007) and revised curvature profile from Constantin (2016) (Figure 3), overestimate the displacement in comparison to the values obtained from numerical analyses. There is, however, a noticeable trend that is similar to the results from VecTor2, where the Δ_y increases as a function of the ρ_{wy} used in the wall.

Figure 11 Nominal yield displacement estimates using the expression from Beyer (2007) and Constantin (2016)

In order to accurately estimate the Δ_y for lightly reinforced ($\rho_{wy} \leq 1.00\%$) RC rectangular walls, a parameter (K_A) is introduced here (Equation 20) to modify Equation 3 from Beyer (2007) (termed here as the “modified Beyer” approach). The resulting expression (Equation 21) simply includes the K_A factor to decrease the estimated Δ_y depending on the ρ_{wy} of the wall; as has been observed, the Δ_y increases as a function of ρ_{wy} for lightly reinforced walls. Using the Δ_y values obtained from the VecTor2 analyses for all of the rectangular walls, the minimum of the sum of the squares determined the constants in Equation 20 that resulted in the closest correlation of Δ_y using Equation 21.

$$K_{\Delta} = 45\rho_{wv} + 0.22 \quad 20$$

$$\Delta_y = K_{\Delta}\Phi_y\left(\frac{k_{cr}}{3}H_n^2 + L_{yp}H_n\right) \quad 21$$

Figure 12 give the Δ_y results from VecTor2 for the 6 metre (40 MPa, 5% ALR) rectangular walls of varying aspect ratio (A_r) and estimates using Equation 21 (modified Beyer approach). It should be noted, as previous, that Φ_y in Equation 21 has been estimated using a K_I value of 1.7 and a value of 0.0027 for ε_{sy} . The modified Beyer approach provides good estimates in comparison to the numerical results for this rectangular wall of varying A_r and ρ_{wv} . Importantly, the great majority of the estimates in Figure 12 from the modified Beyer approach have given slightly conservative results, rather than an overestimation.

Figure 12 Nominal yield displacement estimates using the modified expression from Beyer (2007) and Constantin (2016)

The estimated Δ_y values, using Equation 21 (modified Beyer approach), in comparison to all of the VecTor2 results are shown to correlate well in Figure 13(c). This is compared to the nominal yield displacement estimates using the expressions from Priestley *et al.* (2007) and Beyer (2007) in Figure 13(a) and Figure 13(b) respectively, without the K_{Δ} factor, which over predict the nominal yield displacement compared to the results of all of the rectangular walls analysed in VecTor2. Clearly a better estimate of the Δ_y can be achieved, illustrated with the different R^2 correlations in Figure 13, by including a factor (K_{Δ}) for lightly reinforced and rectangular concrete walls.

Figure 13 Nominal yield displacement estimates compared to VecTor2 results using expressions from (a) Priestley *et al.* (2007) (b) Beyer (2007) and (c) modified Beyer approach

4.1.3 Plastic curvature of single-crack rectangular walls

As discussed in Section 1, observations from the Christchurch earthquake indicated that some lightly reinforced walls may fail in a non-ductile fashion with a single crack in the plastic hinge zone. In this case, the curvature is concentrated over a small height at the base of the wall. Furthermore, a typical moment-curvature analysis may not be able to predict the ultimate curvature achieved by these types of walls as the performance is governed by strain penetration deformation rather than flexural deformation, where the assumptions inherently built in to a moment-curvature analyses no longer apply. Research by Wibowo *et al.* (2016) has led to a simplified alternative for the moment and curvature calculations when conducting a sectional analyses for lightly reinforced concrete columns.

However, the expressions recommended by Wibowo *et al.* (2016) may not be applicable to RC walls since there is typically a greater axial load ratio (ALR) and longitudinal reinforcement ratio (ρ_{lv}) in lightly reinforced columns in comparison to lightly reinforced walls. However, it is worth noting that the simplified alternative from Wibowo *et al.* (2016) increases both the yield (or strain) penetration moment and curvature achieved by the column in comparison to the flexural moment and curvature obtained from a sectional analysis.

Instead, the proposed plastic curvature estimation here is derived from treating the plastic behaviour due to yield penetration and bond slip at the base as a plastic rotation due to an estimated curvature multiplied by a plastic hinge length. This estimate of the plastic curvature (Φ_p) of the walls with a single-crack failure is illustrated in Figure 14. The Φ_p can be calculated using Equation 22, which conservatively assumes that no compression region exists over the length of the wall. An ultimate strain value equal to 0.6 of the uniform elongation strain (ϵ_{su}) for the reinforcing steel is used due to the recommendations by Priestley *et al.* (2007) for low-cycle fatigue. The yield strain (ϵ_{sy}) value is subtracted from the ultimate strain ($0.6\epsilon_{su}$).

$$\Phi_p = \frac{0.6\epsilon_{su} - \epsilon_{sy}}{L_w} \quad 22$$

In contrast, for walls that achieve secondary cracking, and hence well distributed cracks within the plastic hinge zone, a typical moment-curvature analysis can be used to obtain an estimate of the ultimate curvature (Φ_u), as it is assumed that the walls' performance will be governed by flexural behaviour. In this case Φ_p can then be calculated by subtracting the estimated nominal yield curvature (e.g. $\Phi_p = \Phi_u - \Phi_y$)

Figure 14 Idealised strain reached at the ultimate state for a single-crack-failure wall

Equation 22 is used to calculate the plastic curvature (Φ_p) for the RC rectangular walls analysed in VecTor2 that were found to form a single, primary crack at the base (correlating with walls having a ρ_{wv} less than $\rho_{wv.min}$). The Φ_p values for these walls estimated using Equation 22 are compared to the Φ_p values determined in VecTor3 in Figure 15, where a good fit is achieved.

Figure 15 Plastic curvature comparisons for the rectangular walls

4.1.4 Plastic displacement

Rearranging Equation 10, the L_p can be found (using Equation 23) for all of the RC rectangular walls using the Δ_p and plastic curvature ($\Phi_p = \Phi_u - \Phi_y$) from the VecTor2 analyses, where the ratio of Δ_s / Δ_f is assumed to be zero.

$$L_p = \frac{\Delta_p}{\Phi_p H_e}$$

23

605 These results are compared to the estimated L_p from Hoult *et al.* (2017) (Equation 14) and Priestley *et al.* (2007) (Equation 11) in Figure 16. The L_p estimates from Hoult *et al.* (2017), specifically derived
606 for lightly reinforced and rectangular concrete walls, achieves a higher correlation and better fit to the
607 VecTor2 data in comparison to the estimates from Priestley *et al.* (2007), which gives a large scatter
608 of results. It is noted that Equation 11 from Priestley *et al.* (2007) can produce good estimates for
609 some walls (shown in Figure 16b), which primarily corresponds to the RC walls that have formed
610 secondary cracking (e.g. where $\rho_{wv} \geq \rho_{wv.min}$). Importantly, all of the estimated L_p values using the
611 expression from Hoult *et al.* (2017) (Figure 16a) resulted in conservative values in comparison to the
612 VecTor2 data. The good correlation of L_p estimates from Hoult *et al.* (2017) to the VecTor2 data is
613 not all that surprising, given that the same VecTor2 data that is used for comparisons here was used to
614 derive the expression (Equation 14). However, it should be noted that the Equivalent Plastic Hinge
615 Length method was used in Hoult *et al.* (2017) to derive the L_p values, which required analysis of the
616 strain distribution up the wall height, rather than the crude estimates made here with Equation 23.
617 Furthermore, the L_p estimates using Equation 14 were found to correlate better to the experimental
618 observations of a series of tests conducted on lightly reinforced rectangular concrete wall specimens
619 (Hoult *et al.*, 2017).
620

621 **Figure 16** Equivalent plastic hinge length results from VecTor2 compared to estimates from (a) Hoult *et*
622 *al.* (2017) and (b) (Priestley *et al.*, 2007)

Furthermore, Figure 17 compares the plastic displacement (Δ_p) from VecTor2 for all of rectangular walls analysed to the estimates using Equation 10 and the corresponding L_p equations discussed above. Not surprisingly, the Δ_p estimates from Priestley *et al.* (2007) provide results with a large range of scatter and primarily overestimation (Figure 17b), which is due to the L_p expression used (Equation 11). Once again, it should be noted that the Δ_p estimates from Priestley *et al.* (2007) can produce reasonably good estimates for some of the walls, typically corresponding to the RC walls that have formed secondary cracking (e.g. where $\rho_{wv} \geq \rho_{wv,min}$). In contrast, the Δ_p estimates using the L_p expression from Hoult *et al.* (2017) correlate well to the VecTor2 data (Figure 17a).

Figure 17 Plastic displacement results from VecTor2 compared to estimates from (a) Hoult *et al.* (2017) and (b) (Priestley *et al.*, 2007)

4.2 Displacement capacity of C-shaped walls

The following sections investigate the yield curvature, yield displacement, plastic curvature (for single-crack C-shaped walls) and plastic displacement with respect to the different directions of bending.

4.2.1 Yield Curvature

4.2.1.1 Major Axis

As discussed previously in Section 2.1, a value of 1.4 is recommended to be used for K_I when estimating Φ_y for C-shaped RC walls (for bending about the major axis) using Equation 9. The minimum of the sum of the squares was used with the yield curvature results from the 48 C-shaped

walls analysed in VecTor3 such that bending about the major axis occurred. A value of 1.6 was calculated to provide the highest correlation for the K_I parameter when using Equation 9 and comparing the estimate to the VecTor3 data. Figure 18 gives the correlation between the VecTor3 results and Equation 9 using K_I values of 1.6 and 1.4. A slightly better correlation can be observed to be achieved by using a K_I value of 1.6 for the type of C-shaped walls analysed here (e.g. lightly reinforced and unconfined) and for bending about the major axis. It should be noted that two of the walls that were analysed (discussed in Section 3.3), and for bending about the major axis, were subtracted from the dataset used here, as the Collapse Prevention limit strain in the concrete ($\epsilon_c = 0.003$) was reached before yielding of the steel reinforcement.

Figure 18 Nominal yield curvature correlations with a K_I value of (a) 1.6 and (b) 1.4

4.2.1.2 Minor Axis (WiC)

Similar to the procedure used in Section 4.2.1.1, the minimum of the sum of the squares was used to find that a K_I value of 1.45 correlated best to the VecTor3 results for the C-shaped walls bending about the minor axis (WiC) and using the yield curvature expression from Equation 9. This is close to the value of 1.40 recommended by Sullivan *et al.* (2012) for T-shaped and C-shaped walls for this direction of bending (discussed in Section 2.1). Therefore, a K_I value of 1.4 is adopted for the C-shaped walls which are bending about the minor axis (WiC). The estimated values of Φ_y obtained using Equation 9 with a K_I value of 1.4 are compared with the VecTor3 data in Figure 19.

Figure 19 Nominal yield curvature correlations with a K_I value of 1.4

4.2.1.3 Minor Axis (WiT)

The same process used in deriving the nominal yield curvature (Φ_y) in Section 4.2.1.1 and 4.2.1.2 was used here. Using the minimum of the sum of the squares, a K_I value of 1.59 was found to correlate best to the VecTor3 results for the C-shaped walls bending about the minor axis (WiT) and using the yield curvature expression from Equation 9. Therefore, a rounded K_I value of 1.6 was used for bending about the minor axis (WiC). Importantly, only the C-shaped walls (and bending about the minor axis with WiT) that reached or exceeded yield were used in the dataset to find the best value of K_I . This value is lower than the K_I value of 1.8 proposed by Paulay (2002) and Sullivan *et al.* (2012) for T-shaped and C-shaped walls for this direction of bending (discussed in Section 2.1). A comparison is made in Figure 20 between the Φ_y values obtained using K_I values of 1.6 and 1.8 to the VecTor3 results. Although the R^2 value is the same using either of the K_I values, there is clearly a more observable fit using a K_I value of 1.6 shown in Figure 20(a).

Figure 20 Nominal yield curvature correlations with a K_I value of (a) 1.6 and (b) 1.8

4.2.2 Yield Displacement

The nominal yield displacement (Δ_y) values were calculated from VecTor3 for all of the C-shaped walls using Equation 1, by extracting the values for Δ'_y , F_u and F_y from the finite element results for each increment of ρ_{wv} . Similar to the observations for the rectangular walls analysed in Section 4.1, the resulting values of Δ_y for the C-shaped walls analysed in VecTor3 were found to increase as a function of the longitudinal reinforcement ratio (ρ_{wv}) of the wall. Therefore, a factor (K_Δ) is proposed in Equation 24, similar to that in Section 4.1 for rectangular walls, which can be used in conjunction with the yield displacement equation proposed by Beyer (2007) (the “modified Beyer” approach).

$$K_\Delta = \theta \rho_{wv} + \beta \quad 24$$

The minimum of the sum of the squares was used to find the values for θ and β (in Equation 24) that gave the highest correlating values of Δ_y to the VecTor3 data when using Equation 25. These values of θ and β were derived for the three different directions of loading and are given in Table 6. Therefore, using Equation 25 (“modified Beyer” approach), the nominal yield displacement for lightly reinforced and unconfined C-shaped walls can be estimated. It should be noted that the deformations due to shear (Δ_s / Δ_f) have been included in Equation 25.

$$\Delta_y = K_{\Delta} \Phi_y \left(\frac{k_{cr}}{3} H_n^2 + L_{yp} H_n \right) \left(1 + \frac{\Delta_s}{\Delta_f} \right)$$

25

Table 6 Values for calculation of K_{Δ}

	Major	Minor (WiC)	Minor (WiT)
θ	80	50	100
β	0.0	0.3	1.0

Figure 21 illustrate the different correlations of Δ_y from the C-shaped wall results analysed in VecTor3 to the estimated values of Δ_y using the expressions proposed by Priestley *et al.* (2007) (Equation 2), Beyer (2007) (Equation 3) and the modified Beyer approach (Equation 25). It should be noted that the same values of Φ_y for each of the different walls were used in all of the expressions, which were determined using Equation 9 and the K_{Δ} values derived from Section 4.2.1 (corresponding to the different directions of loading). Furthermore, to determine the deformations due to shear (Δ_s / Δ_f), a conservative cracking angle of 30° has been assumed, which was a value recommended in Priestley *et al.* (1996) to be used for assessment purposes. Similar to the findings for the rectangular walls, it is clear that by including the K_{Δ} parameter proposed here for lightly reinforced and unconfined C-shaped walls, the estimate of Δ_y can be significantly improved.

Figure 21 Yield Displacement using expression proposed from (a) Priestley *et al.* (2007) (b) Beyer (2007) and (c) modified Beyer

4.2.3 Plastic curvature of single-crack C-shaped walls

It was discussed in Section 4.1.2 that a typical moment-curvature analysis may not be able to predict the ultimate curvature achieved by single-crack failure walls. Therefore, Equation 22 (in Section 4.1.2) should also be used to calculate the plastic curvature (Φ_p) for the C-shaped walls with, (i) insufficient longitudinal reinforcement to allow secondary cracking ($\rho_{vv} < \rho_{vv.min}$) and (ii) governed by tension strains (in the steel). It should be noted that L_w in Equation 22 corresponds to the wall length parallel to the direction of loading for the C-shaped walls. The estimated Φ_p values using Equation 22 are compared to the Φ_p values determined from VecTor3 in Figure 22 for the C-shaped walls that conform to the criteria above, where a good fit is achieved.

Figure 22 Plastic curvature comparisons for the C-shaped walls

4.2.4 Plastic Displacement

Similar to Section 4.1.3, the L_p was estimated from the VecTor3 results for the C-shaped walls by rearranging Equation 10. These results are compared to the estimated L_p from Hoult *et al.* (2018) (Equation 16 - 18) and Constantin (2016) (Equation 13) in Figure 23. The L_p estimates from Hoult *et al.* (2018), specifically derived for lightly reinforced and unconfined C-shaped walls, achieve a higher correlation and better fit to the VecTor3 data in comparison to the estimates from Constantin (2016), which in contrast give a large scatter of results. Importantly, the great majority of the estimated L_p values using the expression from Hoult *et al.* (2018) resulted in conservative values in comparison to the VecTor3 data. The higher correlation of the estimated L_p values using the expressions from Hoult *et al.* (2018) to the VecTor3 data, in comparison to the expressions from Constantin (2016), is not all that surprising; the same VecTor3 data that is used for comparisons here was also used to derive the expressions from Hoult *et al.* (2018) (Equation 16 to 18), while the expression from Constantin (2016) was derived from numerical and experimental results of highly reinforced and well confined C-shaped wall specimens.

Figure 23 Equivalent plastic hinge length results from VecTor3 compared to estimates from (a) Hoult *et al.* (2017) and (b) (Priestley *et al.*, 2007)

The plastic displacement (Δ_p) of all of the C-shaped walls analysed in VecTor3 were found by subtracting the nominal yield displacement (Δ_y) found in Section 4.2.2 from the ultimate displacement capacity of the wall (Δ_u). The values of Δ_p obtained from the numerical analyses can be compared to the values of Δ_p calculated from PHA (Equation 10). The values of Φ_u used in Equation 10 were calculated directly from the VecTor3 results (i.e. from the respective compression and tension strains in the extreme fibre regions at the base of the wall), while the L_p was estimated using the expressions from Hoult *et al.* (2018) and Constantin (2016) given in Section 2.2. The shear-to-flexure ratio (Δ_s / Δ_f) was calculated using a conservative cracking angle of 30°. In general, the calculated plastic displacement, using the L_p expressions from Hoult *et al.* (2018), correlated well to the Δ_p found from VecTor3 for all of the walls and directions of loading, as illustrated in Figure 24(a). In some cases, and in particular for the HR walls, the calculated value of Δ_p was found to be conservative. The cause of this underestimation was likely to be due to the low L_p estimate (of 150 mm) for “single-crack” walls, when in fact some HR walls were found to form several primary cracks and thus increase the plastic deformation of the walls. Not surprisingly, the Δ_p estimates using the L_p expression from Constantin (2016) in Figure 24(b) provide results with a large range of scatter and primarily overestimation.

Figure 24 Plastic displacement results from VecTor3 compared to estimates from (a) Hoult *et al.* (2018) and (b) Constantin (2016)

4.2.5 Elastic Displacement

For some of the C-shaped walls analysed in VecTor3 (and for bending about the minor axis with WiT), the longitudinal steel in the extreme tension fibre region did not reach (or exceed) the yield strain prior to failure; the failure was caused by the ultimate unconfined compression strain being reached at the boundary ends of the flanges (extreme compression fibre region of the wall). Therefore, the proposed expressions for estimating the displacement corresponding to the “Serviceability” performance level (Δ_s) for these types of walls and for this direction of loading is given in Equation 26, i.e. it is assumed that a plastic hinge does not form. It should be noted that the Serviceability performance level for unconfined concrete walls has been taken here as when ε_c reaches -0.001, where the concrete stress-strain curve is close to linear.

$$\Delta_s = \frac{PH_e^3}{3E_c I_{eff}} = \frac{MH_e^2}{3E_c I_{eff}} \quad 26$$

where M is the moment corresponding to a performance level, E_c is the Young’s modulus of the concrete and I_{eff} is the effective moment of inertia.

For the purposes of this study, the I_{eff} is taken as 0.8 of the gross cross-sectional moment of inertia ($0.8I_g$), which has been adopted from ASCE (2007) for uncracked concrete sections. A factor of 0.8 of the I_g was found to correspond well to the displacement of these walls at the Serviceability

performance level (Δ_s), as shown in Figure 25(a). It should be noted that the E_c is taken as $5000\sqrt{f'_c}$, taken from AS 3600:2009 (Standards Australia, 2009), where f_{cmi} is used as substitute for the f'_c value. The displacement for the Damage Control and Collapse Prevention performance levels (Δ_{dc} and Δ_{cp}) can be found by using a factor (Ω) to increase the calculated Δ_s . The minimum of the sum of squares is used to determine the best value of Ω for each performance level using the VecTor3 data for all of the walls that remained “elastic” and for bending about the minor axis (WiT). Table 7 gives the resulting values of Ω corresponding to the different performance levels. It should be noted that the Damage Control performance level for unconfined concrete walls has been taken here as when ε_c reaches -0.002, where the concrete is now expected to be in the non-linear range but there is a low expectation (small margin) of spalling.

Table 7 Different values of Ω for the performance levels

Ω	Performance Level	
	Damage Control	Collapse Prevention
	1.5	1.8

Figure 25(a) shows the goodness of the fit from using Equation 26 for Δ_s . Moreover, the goodness of the fit is shown for Δ_{dc} and Δ_{cp} in Figure 25(b) and Figure 25(c) respectively by using the different values of Ω in Table 7. It should be noted that the corresponding force (P) used in Equation 26 to calculate these values was taken from VecTor3. Alternatively, the moment (M) could be used in Equation 26 to determine the Serviceability displacement capacity, which can be found from a moment-curvature (or sectional) analysis. Moreover, three examples of the resulting force-displacement relationship are given in Figure 26 by using Equation 26 and the Ω values in Table 7. These resulting force-displacement plots have been compared to the LR, MR and HR C-shaped walls that have been analysed in VecTor3 (and have remained essentially “elastic” up until failure). These walls were chosen for the purpose of illustration; they all have an f_{cmi} of 40 MPa and an ALR of 5%, while the ρ_{wy} of the LR and MR walls is 0.70% and the ρ_{wy} of the HR wall is 1.00%. It is shown that the displacement estimates using Equation 26 and the Ω values proposed here for the different

performance levels result in a similar force-displacement plot to that obtained using finite element modelling analyses in VecTor3.

Figure 25 VecTor3 displacements compared to the displacements predicted for (a) Serviceability (b) Damage Control and (c) Collapse Prevention

Figure 26 Force-displacement relationship for (a) LR (b) MR and (c) HR C-shaped wall that remained elastic

5. Summary of recommended expressions

In summary, the following equations are recommended to be used (for assessment) in calculating the displacement capacity of lightly reinforced and unconfined rectangular and C-shaped walls using plastic hinge analysis. Different equations for the plastic displacement are recommended depending on the ratio of the longitudinal reinforcement ratio (ρ_{vv}) to the minimum longitudinal reinforcement ratio ($\rho_{vv,min}$) required to allow secondary cracking:

800 Yield Curvature

801 $\Phi_y = \frac{K_1 \varepsilon_{sy}}{L_w}$

	C-Shaped			
	Rectangular	Major	Minor (WiC)	Minor (WiT)
K_l	1.7	1.6	1.4	1.6

802

803 Shear Displacement

804 $\frac{\Delta_s}{\Delta_f} = 1.5 \left(\frac{\varepsilon_m}{\Phi_u \tan \theta_c} \right) \left(\frac{1}{H_e} \right)$, or $\frac{\Delta_s}{\Delta_f} = 0$ for rectangular walls with $A_r > 2$

805 Yield Displacement

806 $K_\Delta = \theta \rho_{wv} + \beta$

	C-Shaped			
	Rectangular	Major	Minor (WiC)	Minor (WiT)
θ	45	80	50	100
β	0.22	0.00	0.30	1.00

807

808 $\alpha = \frac{M'_y / \Phi'_y}{E_c I_g}$

809 $H_{cr} = \max \left(L_w, \left(1 - \frac{M_{cr}}{M'_y} \right) H_n \right)$

810 $k_{cr} = \alpha + 0.5(1 - \alpha) \left(\frac{3H_{cr}}{H_n} - \frac{H_{cr}^2}{H_n^2} \right)$

811 $\Delta_y = K_\Delta \Phi_y \left(\frac{k_{cr}}{3} H_n^2 + L_{yp} H_n \right) \left(1 + \frac{\Delta_s}{\Delta_f} \right)$

812 Plastic Displacement

813 $\rho_{wv.min} = \frac{(t_w - n_t d_{bt}) f_{ct.fl}}{f_u t}$

$$814 \quad \text{If } \frac{\rho_{wv}}{\rho_{wv.min}} \leq 1$$

$$815 \quad \Phi_p = \frac{0.6\varepsilon_{su} - \varepsilon_{sy}}{L_w} \text{ and } L_p = 150\text{mm}$$

$$816 \quad \text{If } \frac{\rho_{wv}}{\rho_{wv.min}} > 1$$

817 Φ_p to be determined from moment-curvature analysis

$$818 \quad L_{p.rectangular} = (0.1L_w + 0.075H_e)(1 - 6ALR) \leq 0.5L_w$$

$$819 \quad L_{p.major} = (0.1L_{web} - 0.013H_e)(1 - 13ALR)(7e^{-0.8v}) \leq 0.5L_{web}$$

$$820 \quad L_{p.minor.WiC} = (0.5L_{flange} - 0.015H_e)(1 - 3ALR)(1.6e^{-0.1v}) \leq L_{flange}$$

$$821 \quad L_{p.minor.WiT} = (1.0L_{flange} - 0.073H_e)(1 - 8ALR)(2.5e^{-2.1v}) \leq 0.5L_{flange}$$

$$822 \quad \Delta_p = L_p(\Phi_u - \Phi_y)H_e\left(1 + \frac{\Delta_s}{\Delta_f}\right)$$

823 Ultimate Displacement

$$824 \quad \Delta_u = \Delta_y + \Delta_p$$

825 **6. Conclusions**

826 The current expressions that exist in the literature for determining the displacement of reinforced
827 concrete walls using a plastic hinge analysis cannot be used to accurately estimate the capacity of
828 lightly reinforced members that are commonly found in low-to-moderate seismic regions. This was
829 shown in this research investigation by comparing the displacement capacity results of 378
830 rectangular and 144 C-shaped lightly reinforced and unconfined concrete walls analysed in finite
831 element modelling to the commonly used plastic hinge analysis expressions. Importantly, the
832 assumption of a linear curvature profile up the wall height at first yield was vastly different to the
833 actual yield curvature profile obtained from all of the finite element modelling results. Thus, a
834 parameter was derived (K_d) to be included in the expression that is recommended by Beyer (2007) to
835 modify the estimated yield displacement for lightly reinforced walls (“the modified Beyer” approach).

The value of K_d is dependent on the longitudinal reinforcement ratio (ρ_{wv}) of the wall, as the results of the lightly reinforced concrete walls from finite element modelling showed that the Δ_y increased as a function of the ρ_{wv} . A higher correlation of the values for the nominal yield displacement was achieved between the finite element modelling results and the plastic hinge analysis expression from Beyer (2007) with the inclusion of the K_d term. Other recommendations from this research include an expression for the estimation of the plastic curvature for when a single, primary crack is expected to occur; the onset of secondary cracking can be predicted by comparing the ρ_{wv} of the wall to the minimum longitudinal reinforcement ratio ($\rho_{wv,min}$) required to initiate secondary cracking. This is important, as it is expected that a moment-curvature analysis will provide a poor estimate of the strain penetration moment and curvature due to the moment-curvature (or sectional) analysis inherently assuming a flexurally dominant performance of the wall.

The expressions recommended in this research for lightly reinforced and unconfined rectangular and C-shaped walls will provide better estimates of the displacement capacity when using plastic hinge analyses. Thus, this will ultimately provide more accurate estimates of the capacity of RC structural (or shear) wall buildings in low-to-moderate seismic regions, such as Australia, and aid in providing more accurate vulnerability studies.

While this research primarily focused on the displacement capacity of RC walls due to flexural actions, the authors acknowledge the potential for other contributions to the overall displacement capacity of a RC wall, such as shear and slip, or other modes of failure, such as out-of-plane buckling due to lack of confinement. Therefore, the results and expressions derived from this research investigation are limited to the capabilities of the models used (e.g. VecTor2, VecTor3 and PHA) and issues, such as out-of-plane buckling, were neglected. It is recommended that further experimental testing be conducted on lightly reinforced and unconfined walls to gain a better understanding of these unwarranted failure modes.

7. Acknowledgements

The support of the Commonwealth of Australia through the Cooperative Research Centre program is acknowledged.

8. References

- ACI. (2011). *Building code requirements for structural concrete: (ACI 318-11) ; and Commentary*: American Concrete Institute.
- Adebar, P., & Lorzadeh, A. (2012). *Compression Failure of Thin Concrete Walls*. Paper presented at the 15 th World Conference on Earthquake Engineering.
- Albidah, A. (2016). *Vulnerability and Risks of Collapse of Structural Concrete Walls in Regions of Low to Moderate Seismicity*. (Doctor of Philosophy), The University of Melbourne.
- Albidah, A., Altheeb, A., Lam, N., & Wilson, J. (2013). *A Reconnaissance Survey on Shear Wall Characteristics in Regions of Low-to-Moderate Seismicity*. Paper presented at the Paper presented at the Australian Earthquake Engineering Society 2013 Conference, Hobart, VIC.
- Almeida, J. P., Tarquini, D., & Beyer, K. (2016). Modelling Approaches for Inelastic Behaviour of RC Walls: Multi-level Assessment and Dependability of Results. *Archives of Computational Methods in Engineering*, 23(1), 69-100.
- Altheeb, A. (2016). *Seismic Drift Capacity of Lightly Reinforced Concrete Shear Walls*. (Doctor of Philosophy), The University of Melbourne.
- ASCE. (2007). *Seismic rehabilitation of existing buildings* (Vol. 41): American Society of Civil Engineers Publications.
- Beca. (2011). *Investigation into the collapse of the Pyne Gould Corporation Building on 22nd February 2011, Report. 46 pp*. Retrieved from
- Belletti, B., Damoni, C., & Gasperi, A. (2013). Modeling approaches suitable for pushover analyses of RC structural wall buildings. *Engineering Structures*, 57, 327-338.
doi:http://dx.doi.org/10.1016/j.engstruct.2013.09.023
- Beyer, K. (2007). *Seismic design of torsionally eccentric buildings with U-shaped RC Walls*. (PhD), ROSE School. (ROSE-2008/OX)
- Beyer, K., Dazio, A., & Priestley, M. J. N. (2008a). Inelastic Wide-Column Models for U-Shaped Reinforced Concrete Walls. *Journal of Earthquake Engineering*, 12(sup1), 1-33.
doi:10.1080/13632460801922571
- Beyer, K., Dazio, A., & Priestley, M. J. N. (2008b). Quasi-Static Cyclic Tests of Two U-Shaped Reinforced Concrete Walls. *Journal of Earthquake Engineering*, 12(7), 1023-1053.
doi:10.1080/13632460802003272
- Beyer, K., Dazio, A., & Priestley, M. J. N. (2011). Shear Deformations of Slender Reinforced Concrete Walls under Seismic Loading. *ACI Structural Journal*, 108(2), 167-177.
- Bohl, A., & Adebar, P. (2011). Plastic Hinge Lengths in High-Rise Concrete Shear Walls. *ACI Structural Journal*, 108(2), 148-157.
- Bradley, B. A., Quigley, M. C., Van Dissen, R. J., & Litchfield, N. J. (2014). Ground motion and seismic source aspects of the Canterbury earthquake sequence. *Earthquake Spectra*, 30(1), 1-15.
- Brown, A., & Gibson, G. (2004). A multi-tiered earthquake hazard model for Australia. *Tectonophysics*, 390(1-4), 25-43.
- Cardenas, A. E., & Magura, D. D. (1972). Strength of High-Rise Shear Walls - Rectangular Cross Section. *Special Publication*, 36. doi:10.14359/17361
- CERC. (2012). Canterbury Earthquakes Royal Commission. Final report: Volume 2: The performance of Christchurch CBD Buildings. Wellington, NZ.
- Constantin, R. (2016). *Seismic behaviour and analysis of U-shaped RC walls*. École polytechnique fédérale de Lausanne, Lausanne, Switzerland.
- Constantin, R., & Beyer, K. (2016). Behaviour of U-shaped RC walls under quasi-static cyclic diagonal loading. *Engineering Structures*, 106, 36-52.
doi:http://dx.doi.org/10.1016/j.engstruct.2015.10.018

- Dai, H. (2011). *An Investigation of Ductile Design of Slender Concrete Structural Walls*. (Master of Science), Iowa State University, Ames, Iowa.
- ElMohandes, F. (2013). *Advanced Three-Dimensional Nonlinear Analysis of Reinforced Concrete Structures Subjected to Fire and Extreme Loads*. (Doctor of Philosophy), University of Toronto, Toronto, Canada.
- ElMohandes, F., & Vecchio, F. (2013). Vector3 and FormWorks Plus User Manual. Department of Civil Engineering, University of Toronto. Retrieved from http://www.civ.utoronto.ca/vector/user_manuals/manual6.pdf
- FEMA. (2010). HAZUS MH MR5 Technical Manual. Washington, D.C.
- Fenwick, R., & Dhakal, R. P. (2007). Material strain limits for seismic design of concrete structures. *SESOC: Journal of the NZ Structural Engineering Society*, 20(1), pp. 14-28.
- fib, F. I. d. B. (2012). *Model Code 2010 - Final draft, Volume 2. fib Bulletin No. 66*. Lausanne, Switzerland.
- Ghorbani-Renani, I., Velev, N., Tremblay, R., Palermo, D., Massicotte, B., & Léger, P. (2009). Modeling and Testing Influence of Scaling Effects on Inelastic Response of Shear Walls. *Structural Journal*, 106(3). doi:10.14359/56500
- Goldsworthy, H. M. (2012). Lessons on building design from the 22 February 2011 Christchurch earthquake. *Australian Journal of Structural Engineering*, 13(2), 159.
- Hannewald, P. (2013). *Seismic Behavior of Poorly Detailed RC Bridge Piers*. (PhD thesis), EPFL. Retrieved from <http://infoscience.epfl.ch/record/188364>
- Henry, R. S. (2013). Assessment of the Minimum Vertical Reinforcement Limits for RC Walls. *Bulletin of the New Zealand Society for Earthquake Engineering*, 46(2), 88.
- Hines, E. M., Restrepo, J. I., & Seible, F. (2004). Force-Displacement Characterization of Well-Confined Bridge Piers. *Structural Journal*, 101(4). doi:10.14359/13340
- Hoult, R. (2017). *Seismic assessment of reinforced concrete walls in Australia*. (PhD), University of Melbourne. Retrieved from <http://hdl.handle.net/11343/192443>
- Hoult, R., Goldsworthy, H., & Lumantarna, E. (2018). Plastic Hinge Length for Lightly Reinforced C-shaped Concrete Walls. *Journal of Earthquake Engineering*, 1-32. doi:10.1080/13632469.2018.1453419
- Hoult, R., Goldsworthy, H., & Lumantarna, E. (2017). Plastic Hinge Length for Lightly Reinforced Rectangular Concrete Walls. *Journal of Earthquake Engineering*. doi:10.1080/13632469.2017.1286619
- Ile, N., & Reynouard, J. M. (2005). Behaviour of U-shaped Walls Subjected to Uniaxial and Biaxial Cyclic Lateral Loading. *Journal of Earthquake Engineering*, 09(01), 67-94.
- Kazaz, I. (2013). Analytical Study on Plastic Hinge Length of Structural Walls. *Journal of Structural Engineering*(11), 1938.
- Krolicki, J., Maffei, J., & Calvi, G. M. (2011). Shear Strength of Reinforced Concrete Walls Subjected to Cyclic Loading. *Journal of Earthquake Engineering*, 15(sup1), 30-71. doi:10.1080/13632469.2011.562049
- Kupfer, H. B., & Gerstle, K. H. (1973). Behavior of Concrete under Biaxial Stresses. *Journal of the Engineering Mechanics Division*, 99(4), 13.
- Lestuzzi, P., & Bachmann, H. (2007). Displacement ductility and energy assessment from shaking table tests on RC structural walls. *Engineering Structures*, 29(8), 1708-1721. doi:<http://dx.doi.org/10.1016/j.engstruct.2006.09.009>
- Lowes, L., Lehman, D., Kuchma, D., Mock, A., & Behrouzi, A. (2013). Large-Scale Tests of C-shaped Reinforced Concrete Walls. from NEES Project Warehouse <http://nees.org/warehouse/project/104>
- Lu, Y., Henry, R. S., & Ma, Q. (2014). *Modelling and Experimental Plan of Reinforced Concrete Walls with Minimum Vertical Reinforcement*. Paper presented at the Tenth U.S. National Conference on Earthquake Engineering, Anchorage, Alaska.
- Lu, Y., Henry, R. S., Gultom, R., & Ma, Q. (2015). *Experimental testing and modelling of reinforced concrete walls with minimum vertical reinforcement*. Paper presented at the 2015 New Zealand Society for Earthquake Engineering Annual Technical Conference, Rotorua, New Zealand.

- Luu, H., Ghorbanirenani, I., Léger, P., & Tremblay, R. (2013). Numerical Modeling of Slender Reinforced Concrete Shear Wall Shaking Table Tests Under High-Frequency Ground Motions. *Journal of Earthquake Engineering*, 17(4), 517-542. doi:10.1080/13632469.2013.767759
- Maqsood, T., Wehner, M., Ryu, H., Edwards, M., Dale, K., & Miller, V. (2014). GAR15 Regional Vulnerability Functions *Record 2014/38*: Geoscience Australia: Canberra.
- Menegon, S. J., Tsang, H. H., & Wilson, J. L. (2015). *Overstrength and ductility of limited ductile RC walls: from the design engineers perspective*. Paper presented at the Proceedings of the Tenth Pacific Conference on Earthquake Engineering, Sydney, Australia.
- Menegon, S. J., Wilson, C. J. N., Lam, N. T. K., & Gad, E. F. (2017). Experimental Testing of Reinforced Concrete Walls in Regions of Lower Seismicity. *Bulletin of the New Zealand Society for Earthquake Engineering*, 50(4).
- Moehle, J. (2015). *Seismic design of reinforced concrete buildings*. New York, N.Y.: McGraw-Hill Education LLC.
- Morris, G. J., Bull, D. K., & Bradley, B. A. (2015). In Situ Conditions Affecting the Ductility Capacity of Lightly Reinforced Concrete Wall Structures in the Canterbury Earthquake Sequence. *Bulletin of the NZ Society of Earthquake Engineering*, 48(3), 191-204.
- Oesterle, R. G., Aristizabal-Ochoa, J. D., Fiorato, A. E., Russel, H. E., & Corley, W. G. (1979). *Earthquake Resistant Structural Walls: Tests of Isolated Walls : Phase II*. Skokie, IL: Construction Technology Laboratories, Portland Cement Association.
- Oesterle, R. G., Fiorato, A. E., Johal, L. S., Carpenter, J. E., Russell, H. G., & Corley, W. G. (1976). *Earthquake Resistant Structural Walls - Tests of Isolated Walls*.
- Park, R. (1989). Evaluation of ductility of structures and structural assemblages from laboratory testing. *Bulletin of the New Zealand National Society for Earthquake Engineering*, 22(3), 155-166.
- Paulay, T. (1986). *The Design of reinforced concrete ductile shear walls for earthquake resistance*: University of canterbury, Department of Civil Engineering.
- Paulay, T. (2002). The displacement capacity of reinforced concrete coupled walls. *Engineering Structures*, 24(9), 1165-1175. doi:http://dx.doi.org/10.1016/S0141-0296(02)00050-0
- Pegon, P., Plumier, C., Pinto, A., Molina, J., Gonzalez, P., Tognoli, P., & Hubert, O. (2000). U-shaped-wall: Description of the experimental set-up *TMR-ICONS-TOPIC5* (pp. 23): JRC Ispra.
- Peña, O. A. H. d. I. (2001). *Modelling and Analysis of Retrofitted Reinforced Concrete Structures*. (Master of Applied Science), University of Toronto. Retrieved from <https://tspace.library.utoronto.ca/bitstream/1807/16282/1/MQ58767.pdf>
- Priestley, M., & Kowalski, M. (1998). Aspects of Drift and Ductility Capacity of Cantilever Structural Walls. *Bulletin of the New Zealand National Society for Earthquake Engineering*, 31(2).
- Priestley, M. J. N., Calvi, G. M., & Kowalsky, M. J. (2007). *Displacement-based seismic design of structures / M. J. N. Priestley, Gian Michele Calvi, Mervyn J. Kowalsky*: Pavia : IUSS Press : Fondazione Eucentre, 2007.
- Priestley, M. J. N., & Kowalsky, M. J. (1998). *Aspects of drift and ductility capacity of rectangular cantilever structural walls* (Vol. 31). Wellington, New Zealand: New Zealand National Society for Earthquake Engineering.
- Priestley, M. J. N., & Park, R. (1984). Strength and Ductility of Bridge Substructures. National Roads Board, Wellington, New Zealand: RRU Bulletin 71.
- Priestley, M. J. N., Seible, F., & Calvi, G. M. (1996). *Seismic design and retrofit of bridges*: New York : Wiley, c1996.
- RLB. (2014). *Riders Digest 2014 Adelaide*, Australia Edition: Rider Levett Bucknall.
- Sittipunt, C., & Wood, S. L. (1993). *Finite element analysis of reinforced concrete shear walls*. Retrieved from
- Smyrou, E., Sullivan, T., Priestley, N., & Calvi, M. (2013). Sectional response of T-shaped RC walls. *Bulletin of Earthquake Engineering*, 11(4), 999-1019. doi:http://dx.doi.org/10.1007/s10518-012-9407-2

- Sritharan, S., Beyer, K., Henry, R. S., Chai, Y. H., Kowalsky, M., & Bull, D. (2014). Understanding Poor Seismic Performance of Concrete Walls and Design Implications. *Earthquake Spectra*, 30(1), 307-334. doi:10.1193/021713EQS036M
- Standards Australia. (2009). AS 3600-2009: Concrete Structures.
- Standards Australia/New Zealand. (2001). AS/NZS 4671:2001 : Steel Reinforcing Materials.
- Sullivan, T. J., Priestley, M. J. N., & Calvi, G. M. (2012). *A Model Code for the Displacement-based Seismic Design of Structures*. Pavia, Italy: IUSS Press.
- Thomsen, J., & Wallace, J. (2004). Displacement-Based Design of Slender Reinforced Concrete Structural Walls—Experimental Verification. *Journal of Structural Engineering*, 130(4), 618-630. doi:doi:10.1061/(ASCE)0733-9445(2004)130:4(618)
- Vecchio, F. (1992). Finite Element Modeling of Concrete Expansion and Confinement. *Journal of Structural Engineering*, 118(9), 2390-2406.
- Vecchio, F., Lai, D., Shim, W., & Ng, J. (2000). Disturbed Stress Field Model for Reinforced Concrete: Validation. *Journal of Structural Engineering*, 126(9), 1070.
- Wallace, J. W., & Moehle, J. P. (1992). Ductility and Detailing Requirements of Bearing Wall Buildings. *Journal of Structural Engineering*, 118(6), 1625-1644.
- Wibowo, A., Wilson, C. J. N., Lam, N., & Gad, E. (2016). Yield Penetration Displacement of Lightly Reinforced Concrete Columns. *Applied Mechanics and Materials*, 845, 119-125.
- Wibowo, A., Wilson, J., Lam, N. T. K., & Gad, E. F. (2013). Seismic performance of lightly reinforced structural walls for design purposes. *Magazine of Concrete Research*, 65, 809-828. Retrieved from
- Wight, J. K., Jirsa, J. O., & Corley, W. G. (1984). SP-084: Earthquake Effects on Reinforced Concrete Structures: U.S.- Japan Research. *Special Publication*, 84. doi:10.14359/14041
- Wong, P., Vecchio, F., & Trommels, H. (2013). Vector2 and FormWorks User Manual. Department of Civil Engineering, University of Toronto.
- Wood, S., Stark, R., & Greer, S. (1991). Collapse of Eight- Story RC Building during 1985 Chile Earthquake. *Journal of Structural Engineering*, 117(2), 600-619.
- Wood, S. L. (1989). Minimum tensile reinforcement requirements in walls. *ACI Structural Journal*, 86(5), 582-591.
- Zhang, Z. W., & Li, B. (2014). *Evaluation of seismic performance of slender L-shaped and T-shaped RC structural walls*. Paper presented at the Proceedings of the 2nd European conference on earthquake engineering and seismology. Paper.