Plastic Hinge Length for Lightly Reinforced Rectangular Concrete Walls

Journal:	<i>Journal of Earthquake Engineering</i>
Manuscript ID:	UEQE-2016-2442.R2
Manuscript Type:	Full Length Papers
Date Submitted by the Author:	n/a
Complete List of Authors:	Hoult, Ryan; The University of Melbourne, Department of Infrastructure Goldsworthy, Helen; University of Melbourne, Civil and Environmental Engineering Lumantarna, Elisa; The University of Melbourne, Civil and Environmental Engineering
Keywords:	wall, cracking, non-ductile, reinforced, concrete, plasticity

SCHOLARONE™
Manuscripts

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2

**Plastic Hinge Length for Lightly Reinforced
Rectangular Concrete Walls**

3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Ryan Hoult^{1,4}, Helen Goldsworthy^{2,4}, Elisa Lumantarna^{3,4}

1. Corresponding Author. PhD Candidate, Department of Infrastructure Engineering, University of Melbourne, Parkville, 3010, Australia. Email: rhoulth@student.unimelb.edu.au. Ph: +61401955374
2. Associate Professor, Department of Infrastructure Engineering, University of Melbourne, Parkville, 3010, Australia. Email: helenmg@unimelb.edu.au
3. Lecturer, Department of Infrastructure Engineering, University of Melbourne, Parkville, 3010, Australia. Email: elu@unimelb.edu.au
4. Bushfire and Natural Hazards Cooperative Research Centre, Melbourne, Australia

Abstract

This research investigates the plastic hinge length in lightly reinforced rectangular walls typically found in regions of low-to-moderate seismicity. Poor performance has been exhibited by lightly reinforced concrete walls in past earthquake events. A series of finite element analyses have been carried out which demonstrate that if the longitudinal reinforcement ratio in the wall is below a certain threshold value, there will not be sufficient reinforcement to cause secondary cracking, and instead fracture of the longitudinal reinforcement at a single crack could occur. A plastic hinge length equation has been derived based on the results from the numerical simulations.

1. Introduction

Reinforced concrete (RC) walls and cores are widely used throughout the building stock in areas of low-to-moderate seismic regions such as Australia. Such elements are used as the primary structure in resisting lateral loads, including those generated from seismic ground motions. Due to the inadequacy of the rules governing detailing in the material codes and the low values of earthquake actions used for design in regions of low-to-moderate seismicity, it is anticipated that some walls and cores in these buildings have very limited ductility (Hoult *et al.*, 2015; Wibowo *et al.*, 2013). Some lightly RC walls were observed to perform poorly in the February 22nd Christchurch earthquake, with several cases of a single crack forming at the base in contrast to the expected distributed cracks

(CERC, 2012). Moreover, it was common to find in these walls that some of the longitudinal reinforcing bars that crossed the crack had fractured prematurely due to the large concentration of inelastic deformations developing over such a small length (CERC, 2012). The Canterbury Earthquakes Royal Commission (CERC, 2012) noted that in the collapse of the Pyne Gould Corporation Building ‘it was unlikely that sufficient tension could have been transmitted to initiate a secondary crack in the concrete’ due to the low amount of vertical reinforcement, and subsequent ‘yielding of reinforcement being confined to a short length resulting in a single wide crack in the potential plastic region at level 1 [the base of the wall]’. This observation is of major concern for areas of low-to-moderate seismicity, such as Australia, where the great majority of the buildings incorporate RC walls with low longitudinal reinforcement ratios (Wibowo *et al.*, 2013). The current concrete material standard AS 3600 (Standards Australia, 2009) in Australia enforces a minimum longitudinal reinforcement ratio of 0.15% for RC walls, which has been derived for the control of shrinkage and thermal effects as stated in the AS 3600 Commentary (Standards Australia, 2014) and due consideration is not given to ductility. Moreover, this minimum requirement is comparable to the 0.16% that was used in the Gallery Apartments building, one of the buildings that failed with a single crack failure in the Christchurch earthquake event (Henry, 2013; Henry *et al.*, 2014; Sritharan *et al.*, 2014).

A single crack failure has also been observed in experimental testing on RC walls. One of the RC walls experimentally tested by Cardenas and Magura (1972) and further analysed by Wood (1989) was observed to form a single, primary crack at the base of the wall before fracturing of the reinforcing bars occurred. This observation led Wood (1989) to conclude that walls that have a longitudinal reinforcement ratio less than 1% are susceptible to premature fracture. Moreover, there is a growing emphasis in the recent literature of the need for a sufficient amount of longitudinal reinforcement in RC walls in order to achieve a ductile performance. A concentration of reinforcement at the boundary is recommended by Moehle (2015) for ‘promoting better distribution of flexural cracks’ and concern is expressed about the possibility of the tensile strength of the concrete being higher than the tensile strength of the longitudinal reinforcement at the (primary) cracked

section. The authors from SRIA (2015) comment on the potential for a lightly reinforced wall to develop localised strains when subjected to earthquake ground motions. Due to the recent observations from the Christchurch earthquake for lightly reinforced walls, there is a need to investigate the amount of longitudinal reinforcement required to initiate secondary cracking and allow a distribution of plasticity. If single-crack failures are to be expected in lightly reinforced walls, it is likely that the plastic hinge length equations, that have been developed with reference to walls in which a distribution of cracks occur, will overestimate the displacement capacity of these walls and be unsuitable. These results are essential knowledge for vulnerability studies of reinforced concrete buildings that are being carried out by the authors within the earthquake mitigation component of the Australian CRC (Cooperative Research Centre) for Bushfires and Natural Hazards.

2. Secondary Cracking – simple approach

Past research has indicated the dangers of lightly reinforced concrete walls inherently having an ultimate or yield moment (M_u and M_y respectively) capacity that is less than the cracking moment capacity (M_{cr}). A lower M_{cr} than M_u (or M_y) can result in the development of a single crack near the base with all of the inelastic (plastic) behaviour concentrated at this location (Goldsworthy & Gibson, 2012; Henry, 2013; Wibowo *et al.*, 2013). The cracking moment capacity of an RC wall can be calculated using the fundamental bending stress equation and incorporating the stress due to axial load. This calculation is shown in Equation 1, where $f'_{ct,f}$ is the characteristic flexural tensile strength of concrete, P is the axial load, A_g is the gross section area, t is the thickness of the wall and L_w is the length of the wall.

$$M_{cr} = \frac{\left(f'_{ct,f} + \frac{P}{A_g}\right) t L_w^2}{6}$$

1. The characteristic flexural tensile strength of the concrete ($f'_{ct,f}$) is useful in determining a lower bound for the moment at which flexural cracking first occurs. However, in the research being conducted here, it is more important to determine a realistic value for the concrete flexural tensile strength of the wall. The mean value of the flexure tensile strength of the concrete $f_{ct,fl}$ can be

calculated using the equation from the Model Code 2010 (fib, 2010); the $f_{ct,fl}$ is related to the mean value of the direct tensile strength of concrete (f_{ct}), as shown in Equations 2-4. Note that f_{cmi} is the mean in situ compressive strength of concrete. An upper and lower bound of $f_{ct,fl}$ can be found by multiplying f_{ct} (Equation 3) by 1.32 and 0.68 respectively (fib, 2010; Standards Association NZ, 2006b).

$$f_{ct,fl} = \frac{f_{ct}}{\alpha_f}$$

2.

$$f_{ct} = 0.3(f_{cmi})^{\frac{2}{3}}$$

3.

$$\alpha_f = \frac{0.06L_w^{0.7}}{1 + 0.06L_w^{0.7}}$$

4.

It is important to note that in the case of the Pyne Gould building, concrete strengths of some concrete structural elements were reportedly much higher than the specified 28-day cylinder strength (f'_c) value specified in the design of 24.1 MPa and 17.2 MPa for the columns and beams; the columns had a mean compressive strength (f_{cmi}) of 47.3 MPa, while the beams had an f_{cmi} of 40.7 MPa. The increased strength factor, κ , defined as the ratio of the mean in situ compressive strength at the time of testing (or of loading in the case of a building) to the specified characteristic strength of the concrete, was found to be 2.0 and 2.4 for the columns and the beams respectively (Hyland, 2011). This factor is 'used to increase the concrete strength due to the initial variability in the concrete and increase of the strength with age' (Hoult *et al.*, 2015). Moreover, similar concrete testing by Holmes Solutions (Smith & England, 2012) of the failed RC wall in the Gallery Apartments building indicated that the cylinder compressive strengths ranged from 46.5 MPa to 56 MPa, a corresponding increased strength factor (κ) of up to 1.86 for the f'_c of 30 MPa used in design. Henry (2013) further suggests that even when the ultimate moment capacity of the wall is significantly higher than the cracking moment capacity, the plasticity can still be concentrated over a relatively short height of the wall. In this case

the lack of distributed plasticity (inelastic deformation) is driven by the low tensile force produced by the small number of longitudinal reinforcing steel bars that cross a primary crack. Consequently, the maximum stress that can be developed in the concrete above the first crack (σ_{crack}) may be insufficient to exceed the flexural tensile strength of the concrete ($f_{ct,fl}$) and hence secondary cracks are unable to form. Following the recommendations given in CERC (2012), equations can be derived to estimate whether secondary cracking will occur above the “primary crack”. This approach is used here to give an approximate assessment of the longitudinal reinforcement ratio required to ensure that secondary cracks can form, and that distributed plasticity is able to develop at the base of the wall. An assumption that is made in the following approach is that the longitudinal reinforcement is distributed evenly throughout the wall, as commonly practiced in low-to-moderate seismic regions. The effective area of the concrete (A_{eff}) that surrounds the longitudinal reinforcing bars can be calculated using Equation 5 and is equivalent to the shaded region illustrated in Figure 1.

$$A_{eff} = t_{eff}s$$

5.

$$t_{eff} = t - (n_t \cdot d_{bt})$$

6.

where t_{eff} is the effective thickness of the wall, t is the thickness of the wall, n_t is the number of grids of transverse reinforcing bars (for example $n_t = 2$ in Figure 1), d_{bt} is the diameter of the transverse reinforcing bars and s is the spacing of the longitudinal reinforcement.

$$T = n_l A_b f_u$$

7.

where T is the tensile force produced by the longitudinal bars, n_l is the number of grids of longitudinal reinforcing bars (for example $n_l = 2$ in Figure 1), A_b is the area of one of the longitudinal bars and f_u is the ultimate tensile strength of the reinforcing steel.

The average stress across A_{eff} that can be developed in the concrete above the first crack can be calculated by:

$$\sigma_{crack} = \frac{T}{A_{eff}}$$

8.

Using the calculations above, the “cracking stress ratio” can be calculated, which is the ratio of σ_{crack} to $f_{ct,fl}$. If the cracking stress ratio (csr) is greater than or equal to 1 the wall has a sufficient amount of longitudinal reinforcement to allow secondary cracking. Rearranging Equations 5-8, and assuming the csr is equal to 1, gives an equation for the minimum amount of longitudinal reinforcement to initiate secondary cracking ($\rho_{wv,min}$).

$$\rho_{wv,min} = \frac{(t - n_t d_{bt}) f_{ct,fl}}{f_u t}$$

9.

The longitudinal reinforcement ratio required to cause secondary cracking was calculated for typical reinforced concrete wall parameters used in places of low-to-moderate seismicity. Mean and standard deviation values for the material properties of the reinforcing steel were obtained from the study by Menegon *et al.* (2015) for the D500N bars which are commonly used in Australia. For the ultimate tensile strength (f_u), the mean value is 660.5 MPa and there is a standard deviation of 37.65 MPa. The mean, lower and upper characteristic values of f_u were used in the calculations for finding the minimum longitudinal reinforcement ratio ($\rho_{wv,min}$) for rectangular walls with a range of f_{cmi} values, as illustrated in Figure 2(a). It should be noted that the mean value of $f_{ct,fl}$ has been used for calculations in deriving the values given in Figure 2(a). For the 3 metre wall used, it is assumed that all of the transverse and longitudinal reinforcement is distributed evenly in two grids. The wall thickness was assumed to be 200 mm and the longitudinal and transverse diameter reinforcing bars (d_{bl} and d_{bt}) were both 12 mm. Varying the thickness of the wall, t , over the range of values typically used in practice had only a small influence on the csr . Figure 2(a) illustrates that even for low levels of f_{cmi} the $\rho_{wv,min}$ needed to cause secondary cracking is greater than the value of 0.15% specified in AS 3600 (Standards Australia, 2009). This minimum limit for reinforcement content is highly dependent on the assumed flexural tensile strength of the concrete ($f_{ct,fl}$), as is shown in Figure 2(b) when using mean, lower and upper characteristic values of $f_{ct,fl}$ (and a mean value for f_u in all of these cases). For walls with L_w of 3 metres, Equation 9 provides an estimate for the longitudinal reinforcement ratios of approximately 0.50% and 0.65% need to be utilised for f_{cmi} values of 40 MPa and 60 MPa

154 respectively if secondary cracks are to occur (where the mean values of the $f_{ct,fl}$ and f_u are used). It
155 should be noted that larger wall lengths will slightly decrease the reinforcement ratio required as the
156 $f_{ct,fl}$ is reduced (Equation 4). However, this difference is negligible for the range of L_w (3, 6 and 9
157 metres) being considered for this study. If secondary cracks are unable to form at the base of the wall
158 then the plasticity will be limited to a very short length.

159

160 **3. Plastic Hinge Length**

161 The flexural displacement profile of a cantilever wall is typically the summation of two components:
162 the yield displacement profile and the plastic displacement profile. RC walls with an aspect ratio
163 greater than 2 are typically governed by flexural action, rather than shear mechanisms (Wibowo *et al.*,
164 2013; Wood, 1989), with plastic behaviour at the base of the wall (it is assumed here that the
165 longitudinal reinforcement is constant over the full height). The aspect ratio (A_r) of the RC walls is
166 defined in Equation 10, where M/VL_w is the flexure-to-shear ratio.

167

168

$$A_r = \frac{M}{VL_w} = \frac{H_e}{L_w}$$

169

170 where M is the moment, V is the shear and H_e is the effective height of the wall.

171 To find the plastic deformations, the strains and corresponding curvatures need to be determined, and
172 these will vary considerably up the height of a cantilevered wall. However, it is common practice to
173 simply assume that the inelastic curvature is uniform for a height above the base that is equivalent to
174 the plastic hinge length (L_p) (Bohl & Adebar, 2011; Fenwick & Dhakal, 2007; Paulay & Priestley,
175 1992; Priestley & Park, 1987). This is a reasonable approximation and has been utilised by authors
176 such as Priestley *et al.* (2007) in the equations given for the displacement profile of a cantilevered
177 wall:

178

$$\Delta_i = \Delta_y + \Delta_p = \frac{\varepsilon_y H_i^2}{L_w} \left(1 - \frac{H_i}{3H_n}\right) + \theta_p H_i$$

179

where Δ_y and Δ_p are the yield and plastic displacements respectively, ε_y is the yield strain, H_i is the height of the wall at level i , H_n is the height of the wall at roof level and θ_p is the plastic rotation.

$$\theta_p = (\phi_u - \phi_y)L_p$$

12.

where ϕ_u is the ultimate curvature and ϕ_y is the yield curvature.

The plastic hinge length and idealised curvature distribution are illustrated in Figure 3(a). The elastic curvature distribution is assumed to vary linearly up the cantilever wall, which tends to compensate for the increase in displacement due to tension shift effects and shear deformation (Priestley *et al.*, 2007). Figure 3(b) illustrates the idealised expected steel strain distribution at ultimate condition (closest to the extreme tension fibre edge) of unconfined reinforced concrete walls that either form a single crack, or form a distribution of cracks up the wall height. It should be noted for the purpose of this study, as will be discussed later in Section 4.2, the ultimate concrete and steel strains for an unconfined RC section have been taken as 0.003 and 0.05 respectively. The wall with well distributed yielding in Figure 3(b) has lower steel strains, as expected, and is likely to fail in compression (concrete strains governing).

If a single, primary crack is formed in an RC wall, the strain penetration (or “yield penetration”) length becomes the only source of plastic deformation (Morris *et al.*, 2015). The strain penetration length is the depth that the inelastic strains of the reinforcing steel can penetrate (Patel *et al.*, 2015). This length is shown in Figure 3(b), where the ultimate steel strain is reached in the extreme tension fibre region of the wall, with inelastic strains penetrating either side of the crack (into the wall and into the foundation). Therefore, the height over the wall in which yielding of the reinforcement occurs is severely reduced in comparison to a wall with distributed cracking, thus decreasing the L_p that would be used in calculating the displacement capacity. As discussed in Morris *et al.* (2015), in this situation the elongation of the steel reinforcing bars is dependent on the amount the steel can strain and the true length of strain penetration either side of the primary crack. This dependency on the straining of steel reinforcement is particularly an issue for regions of low-to-moderate seismicity, where the uniform elongation strain (ε_{su}) of typical reinforcing bars (e.g. D500N bars in Australia) is

low in comparison to bars used in regions of higher seismicity (e.g. D300E bars in New Zealand). Recent field observations from the Christchurch earthquake in New Zealand indicated strain penetration lengths into the foundation as low as 1 to $2d_{bl}$ (Morris *et al.*, 2015). As illustrated in Figure 3(b), the plastic hinge length (L_p) for walls with a single crack is approximately $2L_{yp}$, where L_{yp} is the strain penetration length measured on one side of the crack. Empirical equations are given later in this section that make estimates of L_p based solely on the strain penetration length. There are many different empirical equations available for the plastic hinge length (L_p) for situations in which secondary cracking is expected to occur. Some of these equations, which will later be scrutinised as to their applicability for lightly RC walls, include L_p estimations from Bohl and Adebar (2011) (Equation 13), Kazaz (2013) (Equation 14), Priestley *et al.* (2007) (Equation 15 and 16), ICBO (1997) (Equation 17) and Thomsen and Wallace (2004) (Equation 18). It should be noted that Equation 17 has been utilised in the 1997 Uniform Building Code (UBC) (ICBO, 1997) and more recently in NZS 3101:2006 (Standards Association NZ, 2006a); it is a lower bound value that many researchers have recommended (Moehle, 1992; Paulay, 1986; Priestley & Park, 1984; Wallace & Moehle, 1992).

$$L_p = (0.2L_w + 0.05H_e)\left(1 - \frac{1.5P}{f'_c A_g}\right) \leq 0.8L_w$$

13.

where A_g is the gross section area of the wall, L_w is the wall length, H_e is the effective height (equivalent to M/V ratio), P is the axial load and f'_c is the compressive strength of concrete.

$$L_p = 0.27L_w \left(1 - \frac{P}{A_g f'_c}\right) \left(1 - \frac{f_y \rho_{wh}}{f'_c}\right) \left(\frac{M}{V}\right)^{0.45}$$

14.

where f_y is the yield strength of steel and ρ_{wh} is the horizontal (transverse) reinforcement in the wall.

$$L_p = kH_e + 0.1L_w + L_{sp}$$

15.

where k is a constant reflecting the distribution of plasticity dependent on the ratio of the ultimate strength to yield strength of the reinforcing steel ($k = 0.2(f_u/f_y - 1) \leq 0.08$), H_e is the effective height, and L_{sp} is the strain penetration length defined as:

$$L_{sp} = 0.022f_{ye}d_{bl}$$

16.

f_{ye} is the expected yield stress of the steel ($1.1f_y$).

$$L_p = 0.5L_w$$

17.

$$L_p = 0.33L_w$$

18.

However, these equations for the plastic hinge length have been derived from numerical or experimental results for RC walls that are not representative of lightly RC walls in regions of low-to-moderate seismicity. For instance, most of the experimental results that were used in deriving these equations were from tests on RC walls with well confined boundary regions and reinforcing steel with mechanical properties that would not be used in regions of low-to-moderate seismicity. Morris *et al.*, (2015) emphasise the importance of the f_u/f_y ratio in determining the extent of plasticity at the base of an RC wall. The importance of this has been recognised previously by other researchers, for example in Equation 15 for the L_p estimation by Priestley *et al.* (2007). Strain hardening ratio (f_u/f_y) values are given in Table 1 for reinforcing steel types that are common in Australia, types L and N, as well as for type E which is commonly used in New Zealand. The lower characteristic values are obtained from the Australian Standard for steel reinforcing materials AS/NZS 4671:2001 (Standards Australia/New Zealand, 2001), while the mean values have been given in Menegon *et al.* (2015). The f_u/f_y values for D500N reinforcing bars are lower than the 1.625 and 1.3 values used for plastic hinge length studies by Bohl and Adebar (2011) and Kazaz (2013) respectively. Both of these studies also focused on RC walls with a higher concentration of longitudinal reinforcement and confinement at the boundary ends than would be typically used in low-to-moderate seismic regions.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

248 It should be noted that the equations for L_p determined by Equations 13-18 are known to be
249 approximate since although L_p has been shown to be dependent on the axial load ratio ($ALR = P/f'_c A_g$)
250 (Bohl and Adebar, 2011) these equations, with the exception of Equations 13 and 14, do not include
251 this variable.

252 A recent study by Altheeb *et al.* (2015) used scaled down experiments on lightly reinforced concrete
253 elements to derive a plastic hinge length (Equation 19) based on the strain penetration length from the
254 formation of a single crack.

$$L_p = \frac{(f_u - f_y)d_{bl}^{1.2}}{4\sqrt{f'_c}}$$

255 19.

256 Wibowo *et al.* (2013) have proposed an alternative equation (Equation 20) for the plastic hinge length
257 for when M_{cr} is larger than M_u at the critical section in the RC walls. Wibowo *et al.* (2014) recognise
258 the possibility of a single crack forming for some lightly reinforced walls, consequentially reducing
259 'the plastic hinge length to a function of the yield penetration length'.

$$L_p = 15d_{bl}$$

260 20.

261 As there is insufficient experimental data currently available to evaluate and develop empirical
262 models for plastic hinge lengths of lightly reinforced walls, a numerical study has been undertaken
263 using a nonlinear finite element program VecTor2 (Wong & Vecchio, 2002). The plastic hinge length
264 has been estimated for a series of rectangular RC walls with parameters that represent walls in a low-
265 to-moderate seismic region such as Australia. Using these results, the accuracy of the different
266 equations that have been proposed to calculate the plastic hinge length will be evaluated in terms of
267 their applicability to the lightly RC walls considered here.

268

269 **4. Equivalent Plastic Hinge Length**

270 In this study, the equivalent plastic hinge method has been adopted to investigate a series of walls that
271 incorporate detailing that is typical of that used in low-to-moderate seismic regions, such as Australia.
272 The Equivalent Plastic Hinge Length (EPHL) method has been used in past studies (Fenwick &

Dhakal, 2007; Henry, 2013; Mortezaei & Ronagh, 2012) and has also been used to derive the plastic hinge length and curvature limits set in NZS 3101 (Standards Association NZ, 2006a). The curvature distribution up the the height of a cantilever wall can be used to determine the rotation at the base; as is well known from the first moment area theorem, the rotation between two points up the the height of the wall is equal to the area under the curvature distribution. Figure 3 illustrates that the curvature distribution can be idealised into elastic and plastic regions, and likewise for the rotations. The purpose of this study is to determine the extent of plasticity occurring at the wall base and hence to estimate the plastic hinge length. Distributions of cracks and of the curvature have been obtained using VecTor2 for a range of walls.

4.1 VecTor2 Model Validation

VecTor2 (Wong & Vecchio, 2002) is a state-of-the-art nonlinear finite element modelling program for plane RC sections that is based on the disturbed stress field model (DSFM) (Vecchio *et al.*, 2000).

VecTor2 has been used in a variety of past research for modelling RC walls (Beyer, 2007; Bohl & Adebar, 2011; Dai, 2011; Ghorbani-Renani *et al.*, 2009; Lu *et al.*, 2014; Luu *et al.*, 2013; Sritharan *et al.*, 2014).

A range of material and constitutive models have been incorporated in VecTor2 to represent modelling of the concrete and steel materials. The Popovics normal-strength and the Popovics high-strength models were used for strengths up to 45 MPa and higher than 45 MPa, respectively in accordance with recommendations from Palermo & Vecchio (2007). The preliminary parameter studies conducted in Mohr (2007) suggested that the compression softening model that relies only on stress, rather than both stress and strain, gave better approximations at large displacements. Therefore, Vecchio 1992-B (ϵ_1/ϵ_0 -Form) (Vecchio, 1992) was chosen to model the compression softening of concrete. The Modified Bentz model (default) was used for the modelling of tension stiffening in the concrete. This model is essentially the same as the Bentz (1999) model for when 'the steel is aligned with the x or y-axis (no skew steel)' (Bohl, 2003). The model is used in the Modified Compression Field Theory (MCFT) for programs such as Response-2000 (Bentz, 2000). Of the numerous bilinear models that are proposed by different researchers for the prediction of tension

softening, the CEB-FIP (1990) model is utilised by VecTor2 and provides a bilinear model for the stress-strain relationship of concrete. Importantly, the default concrete fracture energy value of 75 N/m has been used in VecTor2, which is a similar assumption to that used by other researchers (Bohl, 2003). The concrete hysteretic response was modelled with the Palermo option (Palermo & Vecchio, 2002), as it has been shown to be a more suitable option for capturing the stiffness and overall behaviour in another study (Sagbas, 2007). The dilation model chosen for the lateral expansion of concrete is the ‘Variable – Orthotropic’ model (default), which is based on a Poisson’s ratio that increases nonlinearly as the concrete compressive strain increases. The cracking criterion models estimate the decrease of cracking strength due to the increase of the transversely acting compressive stresses. The CEB-FIP Model is chosen specifically for the cracking criterion, which is based on a linear relationship proposed in Kupfer and Gerstle (1973). The compressive stresses of concrete elements close to cracks are required to be limited, mainly due to tensile strains in concrete close to cracks exceeding the calibration range of the compression softening models, which may permit additional softening. The crack width check reduces the average compressive stresses for when the crack width exceeds a set limit. The default was chosen (‘Agg/2.5 Max Crack Width’) as the limiting crack width. VecTor2 accounts for the strains due to shear slip along cracks with the element slip distortion models. The default model from Walraven (1981) was chosen for these calculations. The stress-strain curve from Seckin (1981) is used for the reinforcing steel. The Kupfer/Richart confinement model (Kupfer *et al.*, 1969; Richart *et al.*, 1928) was used even though unconfined walls have been considered in this study. It was found in earlier wall analyses using VecTor2, in which the enhancement due to confinement was turned off completely, that the compressive strains reached were unrealistically low. Professor F. Vecchio (personal communication, March 2, 2016) recommended the use of the Kupfer/Richart model, even though the concrete is unconfined, because it was likely to give a better representation of effects of phenomena such as lateral expansion. The actual strength enhancement factor incorporated as a result of using this model is very close to one in the case of walls without out-of-plane reinforcement, i.e. no enhancement. Bond-slip, using the Eligehausen (1983) model, was only considered for VecTor2 models that use truss and link elements to model the longitudinal reinforcement and bond behaviour respectively. For this model, the bond

properties for the link elements were set to ‘Embedded Deformed Rebars’ with a Confinement Pressure Factor of zero, corresponding to an unconfined case. For the other models, an assumption of perfect bond was assumed, as has been successfully adopted in other studies (Lu *et al.*, 2015; Palermo & Vecchio, 2007). Very little experimental testing has been conducted on lightly reinforced unconfined RC walls. Although Cardenas & Magura (1972) tested a lightly reinforced concrete wall which formed a single crack, as discussed previously in Section 1, the experimental data for this wall is sparse and not ideal for the purposes of validation. The RC wall specimens R1 from Oesterle *et al.* (1976) and C1 from Lu *et al.* (2015) were deemed suitable for the purposes of validating the chosen material models that will be used in VecTor2.

4.1.1 Wall R1 (Oesterle *et al.*, 1976)

The specimen R1 {Oesterle, 1976 #484} was a 4572 mm high, 1905 mm long ($h_e/l_w = 2.4$), and 102 mm thick RC wall that was subjected to reverse cyclic loading. The wall failed in flexure with fracturing of the reinforcement before crushing of the concrete. The longitudinal reinforcement consisted of two layers of 6 mm diameter longitudinal bars at a spacing of 229 mm in the web, while there was a concentration of 4#3 bars ($d_{bl} = 9.525$ mm) spaced at 140 mm at the boundary ends. Table 2 and Table 3 give the wall specimen details and the reinforcement properties respectively. A fraction of the reported uniform elongation strain of the steel (ϵ_{su}) was used due to the research findings by Wood (1989) that indicated the steel fractured at a reduced strain. A value of $0.6 \epsilon_{su}$ was adopted, as used by Priestley *et al.* (2007) to account for the possibility of low cycle fatigue. The wall specimen R1 was modelled in VecTor2 with the foundation block at the base, illustrated in Figure 4. Plane stress rectangular elements were used to model the concrete wall, which are four-noded elements with uniform thickness (Wong, 2002). The size of plane stress elements were within the 3:2 aspect ratio as recommended by Wong (2002). Palermo & Vecchio (2007) further suggest that 14 - 16 elements are to be used in the short direction of the wall (parallel to the wall length) and this recommendation has also been adhered to, although a smaller mesh size, in the direction parallel to

the wall length, was used to model some RC wall specimens at the boundary ends in order to facilitate the creation of nodes for discrete truss elements.

The longitudinal reinforcement was modelled using two different methods; (i) the bars were modelled using smeared reinforcement throughout the concrete plane stress rectangular elements and, (ii) the bars were modelled discretely using truss and link ("truss-link") elements. The second option including link elements was employed to model the behaviour of bond slip between the concrete and reinforcing bars. While the use of this option increased the number of nodes required in the model, this modelling option provided information on the strain penetration of the longitudinal reinforcing bars into the foundation. The sensitivity of the overall results to the inclusion of strain penetration needed to be investigated. Although the more computationally efficient smeared reinforcement approach has been shown in previous research to provide comparative results to those from analyses using truss elements in previous research (Beyer, 2007; Bohl & Adebar, 2011; Ghorbani-Renani *et al.*, 2009; Luu *et al.*, 2013; Palermo & Vecchio, 2007; Sritharan *et al.*, 2014), no previous research is available that provides well correlated results for lightly reinforced concrete walls when comparing these two modelling decisions. Hence, it was decided to investigate this further in this study. Three different concrete materials were used, which consisted of different percentages of smeared reinforcement that were used to represent the different boundary, web and footing regions of the wall specimen. An axial load of 20.75 kN was held constant during the analysis and was distributed along the nodes at the top of the wall section. The lateral loading applied to both models was monotonic and reverse cyclic (corresponding to the experimental testing) and was distributed evenly over all of the nodes at the top of the wall.

Figure 5 presents the force-displacement hysteresis results from VecTor2. The immediate observation is the reasonably well correlated predictions from VecTor2 in comparison to the experimental results from Oosterle *et al.* (1976) for the wall being subjected to either reverse cyclic or monotonic loading. Moreover, there is a good correlation between the results using smeared reinforcement in Figure 5(a) and the results using the discrete truss-link elements in Figure 5(b). The flexural strengths predicted by VecTor2, using the values for the concrete and reinforcement properties from the testing by Oosterle *et al.* (1976), are slightly overestimated. However, this observation was to be expected as it

was also observed by Oesterle *et al.* (1976), who stated ‘the observed strengths were somewhat lower than the flexural strengths calculated using measured material properties including strain hardening in the reinforcement’. For example, the maximum force that was predicted by VecTor2 from all of the models and loading conditions considered was 146.2 kN, whereas the maximum measured load from Oesterle *et al.* (1976) for R1 was 118.3 kN. This correlated with the observations from Oesterle *et al.* (1976), where the maximum observed experimental force of all the specimens tested varied from 77% to 91% of the flexural capacities that they had calculated. The sharp drop in strength in both of the smeared and truss models for monotonic loading corresponded to the ultimate strain being reached or exceeded ($0.6\epsilon_{su} = 58.8$ mm/m) at either the extreme tension fibre edge or the closest truss element to the tension edge respectively. There was a difference of displacement capacity for the walls modelled using smeared reinforcement compared to the model that used truss-link elements; displacements of 108 mm and 91 mm (for monotonic loading) corresponded with the outermost longitudinal reinforcing bars reaching or exceeding $0.6\epsilon_{su}$ for the smeared and truss-link models respectively. The first observations by Oesterle *et al.* (1976) of a reinforcing bar fracturing occurred in cycle 26, which corresponded with one of the outermost bars at a displacement of around 101 mm. This experimental observation compares well to the displacement capacity estimated in VecTor2. It should be noted that the ultimate strain used in VecTor2 is 60% of the uniform elongation strain value reported by Oesterle *et al.* (1976) from the monotonic material tests. The reduced value was used to account for low cycle fatigue effects and this reduced ultimate strain limit has led to a good comparison between the predicted and observed displacement capacity.

VecTor2 was able to predict the force-displacement performance of the lightly reinforced wall specimen R1. However, for the purposes of studying the equivalent plastic hinge length (L_p), it is important that VecTor2 is able to predict the tension strain distribution up the wall height. Figure 6 and Figure 7 present the tension strains in the steel from VecTor2 for the smeared and truss-link models respectively. The strains are presented as discrete values since these are average strain values across the element height (plotted at the centre of each element). Superimposed in these figures are the strain distributions as given in Oesterle *et al.* (1976) at several different levels of displacement at the top of the wall. It is important to note that the strain gauges attached to the reinforcing steel bars

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

412 in the experiment by Oesterle *et al.* (1976) for wall specimen R1 debonded between a strain of 15
413 mm/m and 30 mm/m. Hence, the strain reading from the experiment is limited to 12.5 mm/m in many
414 of the readings for the higher displacements so there is a limited scope for comparison between the
415 experimental and the finite element results. It is noted here that the strain distribution from the
416 experimental results at a displacement at the top of the wall of 101 mm is compared with the VecTor2
417 truss-link results at the ultimate displacement predicted by VecTor2 of 91 mm.
418 Overall, at locations where comparisons are able to be made, there is a good fit between the strains
419 predicted in VecTor2 and the observations from the experiment. The VecTor2 results provide a good
420 fit to the available data for the higher lateral displacements. For the strain distributions at the final
421 displacement, the smeared reinforcement model results from VecTor2 give as good a match, or better,
422 to the experimental data when compared with the truss-link results. It was experimentally observed
423 that the yielding zone ($\epsilon_{sy} \approx 2.67$ mm/m) only occurred in the lower 1.83m of the wall (Oesterle *et al.*,
424 1976), and the smeared reinforcement model predicts this well (Figure 6c). However, the truss-link
425 model had a longer “yield zone”, with larger strains than that observed experimentally (Figure 7c).
426 Moreover, these strains for the truss-link model occurred at a smaller displacement (91 mm) of the
427 wall compared to the displacement (101 mm) that corresponded to the experimentally captured
428 strains. These results indicate that the VecTor2 model that uses smeared reinforcement gives results
429 with a similar degree of accuracy to those obtained using the VecTor2 model with truss elements.
430 Importantly, the steel strain into the foundation was small for the model that utilised discrete truss-
431 link elements. For example, the highest average steel strain into the foundation estimated by VecTor2
432 was found to be 1.096 mm/m. This strain is small when compared with the average strain reached in
433 the element just above the foundation of 43.5 mm/m at the same displacement (91 mm, Figure 7c) for
434 the same discrete reinforcing bar. Moreover, given that these strains are less than the approximate
435 yield strain (ϵ_{sy}) of 2.66 mm/m, the strains below the foundation are likely to make little contribution
436 to the plastic hinge length. Insignificant strains into the foundation were also observed by Kazaz
437 (2013) for all of the walls analysed using a different finite element program. A similar situation was
438 also observed by Bohl & Adebar (2011). This analytical observation suggests that modelling the
439 foundation block is unnecessary in VecTor2 for the purposes of calculating the effective plastic hinge

length. Modelling the foundation is particularly unnecessary if smeared reinforcement is to be used to model the longitudinal reinforcement. Hence in the study, the foundation block was ignored as the elements were modelled as smeared elements. Neglecting to model the foundation block was also followed in the analyses reported in Bohl (2003) in which the foundation block was not included in the models when using VecTor2 to calculate plastic hinge lengths.

Strain distributions across the wall are also important in the calculation of curvature. As mentioned previously, due to debonding of the strain gauges at large wall displacements, no relevant data is available for the vertical strains at the base of the wall. However, vertical strains at 3ft (914.4 mm) from the base of the wall corresponding to a displacement at the top of the wall of 51 mm are available (Oesterle *et al.*, 1976). Importantly, this was within the ‘yielding zone’. Figure 8 presents the strain distribution together with the superimposed VecTor2 results at the same height of the wall. The estimated strain values across the cross section from VecTor2 correspond well to the experimentally observed strains from Oesterle *et al.* (1976).

It is important that VecTor2 is able to accurately predict the distribution of cracks in the wall. Figure 9 compares the experimentally observed cracking pattern for the lower 1.83 metre of specimen R1 Oesterle *et al.* (1976) to the VecTor2 predictions (smeared model, monotonic loading) at a displacement at the top of the wall of 76 mm. The cracking patterns are similar, with the lower 0.91 metre of the wall ‘completely traversed by several predominately horizontal cracks’ (Oesterle *et al.*, 1976). Although this wall specimen is considered to be lightly reinforced, a number of cracks have formed at the base of the wall. If the longitudinal reinforcement ratio in the web of R1 (Table 2) was used in the secondary cracking model introduced in Section 2, there would be an indication that this wall would not have sufficient reinforcement to initiate secondary cracking. However, the area of reinforcement that is lumped at the boundary ends is sufficient to produce a locally higher reinforcement ratio which generates the observed well distributed cracks.

The VecTor2 predictions of the performance of wall specimen R1 (Oesterle *et al.*, 1976), with the chosen material models, has been shown to compare reasonably well to the relevant experimental data. Moreover, similar validation is carried out for another lightly reinforced wall specimen C1 from Lu *et al.* (2015).

4.1.2 Wall C1 (Lu *et al.*, 2015)

Lu *et al.*, 2015 reported on an experimental program which was conducted to evaluate the seismic performance of RC walls with minimum longitudinal reinforcement in accordance with NZS 3101 (Standards Association NZ, 2006a). The wall specimen C1, with cross-section shown in Figure 10, was designed to represent a 50% scale of a multi-story flexure-dominant RC wall with limited ductility (Lu *et al.*, 2015) and was tested under reverse cyclic conditions. Following the same approach as that in Section 4.1.1, two different methods of modelling the longitudinal reinforcement in VecTor2 were undertaken; Model 1 which uses smeared reinforcement and Model 2 which uses discrete truss elements with link elements (truss-link). The strain distribution at 1.5% drift (top wall displacement of 42 mm) was also reported in Lu *et al.* (2015), and this will be compared to the VecTor2 results at the same lateral drift.

Figure 11(a) illustrates the mesh and element setup for Model 1. The foundation block at the base was assumed to be 500 mm x 1820 mm (x 350 mm high). The concrete compressive strength was 38.5 MPa, while the tensile strength of the concrete was 2.88 MPa. The yield and ultimate stress of the 10 mm diameter longitudinal reinforcing bars were 300 MPa and 409 MPa respectively. The ultimate strain was taken as $0.6\epsilon_{su}$ as discussed previously in Section 4.1.1, which is approximately 92 mm/m in this case. Model 2, which utilises the link elements, uses the Eligehausen (1983) concrete bond model to predict the amount of strain penetration into the foundation, the same approach as that used previously when modelling wall specimen R1 in Section 4.1.1. In both models the horizontal reinforcement was modelled with smeared reinforcement. A total axial load of 294 kN ($ALR = 3.5\%$) was uniformly distributed to all nodes at the top of the wall (held constant throughout the analysis), while the same nodes were subjected to a lateral displacement for both the monotonic or reverse cyclic loading scenarios.

Figure 12 presents the results from VecTor2 for both monotonic and reverse cyclic conditions for Model 1 (smeared) and Model 2 (truss-link). Superimposed on these figures are the experimental

494 results from Lu *et al.* (2015). The results from VecTor2 match well with the force-displacement
495 hysteresis observed experimentally.

496 Figure 13 presents the strain distribution results in the steel from VecTor2 at the extreme fibre edge of
497 the wall in tension for Model 1 (smeared) and Model 2 (truss-link). Superimposed on this figure are
498 the strain distributions recorded by Lu *et al.* (2015). The strain distributions predicted by VecTor2
499 for Model 1 (smeared) in Figure 13(a) correlate well with the experimental observations.

500 Furthermore, the strains predicted with cyclic loading did not differ much from the predictions with
501 the wall subjected to monotonic loading, which was an observation also reported by Hannewald
502 (2013). Model 2 (truss-link) predicts a similar steel strain distribution up the wall height as shown in
503 Figure 13(b). However, this model (truss-link) over predicts the steel strains in comparison with the
504 experimental observations from Lu *et al.* (2015) and also when compared with Model 1 (smeared)
505 shown in Figure 13(a). Model 2 (truss-link), which uses the Eligehausen (1983) bond model, also
506 predicts a higher steel strain into the foundation in comparison to Model 1 (smeared). For example,
507 the strains of the truss elements into the foundation at the extreme tension fibre edge of the wall for
508 Models 1 and 2 were found to be 0.002 mm/m and 0.504 mm/m respectively at a top displacement of
509 the wall of 42mm. However, these strain values were deemed to be insignificant in comparison to the
510 strains predicted by VecTor2 just above the foundation. Insignificant strains into the foundation were
511 similarly observed for the truss-link elements model used to simulate the performance of wall
512 specimen R1 (Oesterle *et al.*, 1976) in Section 4.1.1. Furthermore, the strains predicted by Model 2
513 with the truss-link elements into the foundation did not reach yield ($\epsilon_{sy} \approx 2.00\text{mm/m}$) throughout the
514 analysis (1.28 mm/m at a top displacement of 70 mm).

515 Overall, VecTor2 has been shown to provide well correlated results to the experimental observations
516 from wall specimens R1 (Oesterle *et al.*, 1976) and C1 (Lu *et al.*, 2015). Importantly, the strain
517 distributions up the wall height are well correlated, particularly for the VecTor2 model that uses
518 smeared reinforcement. Although the reliability of experimental strain data captured from strain
519 gauges is questionable, the VecTor2 results corroborate well with the available strain data from the
520 two experimental walls analysed here, both of which relied upon strain gauges. The VecTor2 results

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

521 of the strains into the foundation using truss-link elements is questionable considering the small strain
522 value achieved by the finite element modelling program in comparison to the expected yielding of
523 reinforced bars over some length into the foundation. However, as mentioned in Section 3, recent
524 observations have revealed strain penetration lengths (into the foundation) that are as low as $1.0d_{bl}$.
525 Therefore, numerical analyses have been conducted on walls representative of those found in regions
526 of low-to-moderate seismicity, adopting a conservative approach in VecTor2 to calculate the effective
527 plastic hinge length; smeared reinforcement, which assumes perfect bond, will be used in the
528 subsequent VecTor2 analyses. Consequently, the calculated L_p using the EPHL method (Section 4)
529 does not include plasticity from the strain penetration into the footing, similar to the method used in
530 the plastic hinge length study by Kazaz (2013).

531

532 **4.2 VecTor2 Analyses for Lightly Reinforced Walls**

533 In total, 378 lightly RC walls with varying parameters have been analysed in VecTor2 for calculation
534 of plastic hinge length. The range of parameters considered in VecTor2 is summarised in Table 4.
535 The effective height (H_e) is estimated to be $0.7H_n$ as recommended by Priestley *et al.* (2007) and all of
536 the walls' aspect ratios are greater than 2 (governed by flexure). The ALRs have been chosen to
537 represent the majority of the building stock in low-to-moderate seismic regions, where ALRs of less
538 than 5% are common in walls with low vertical reinforcement (Henry, 2013). Moreover, the RC
539 walls investigated by Albidah *et al.* (2013) for low-to-moderate seismic regions indicated that most of
540 the walls had ALRs less than 5%, and the highest ALR did not exceed 10%. The longitudinal
541 reinforcement ratio (ρ_{vv}) was varied between 0.15 to 1%, which has been said to 'represent the great
542 majority of building stock in low-to-moderate seismic regions such as Australia' (Wibowo *et al.*,
543 2013). The two f_{cmi} values of the walls considered in this study were 40 MPa and 60 MPa, which are
544 realistic values for walls designed originally with a characteristic compressive strength (f'_c) of 32 MPa
545 and 40 MPa, given that the target strength would have been higher than this and that the concrete
546 strength will increase with time. The f_{cmi} values adopted correspond to κ values of 1.25 and 1.50
547 respectively; these are values representative of concrete that has aged over several years as indicated
548 in Moehle (2015). Mean values of the material properties for the reinforcing steel were adopted from

Menegon *et al.*, (2015) for D500N bars which conform to AS/NZS 4671 (Standards Australia/New Zealand, 2001). The f_y used was 551 MPa with an E of 200,000 MPa and $f_u/f_y = 1.20$. The ultimate strain for the purpose of the wall assessments was taken as 60% of the mean value of the uniform elongation strain, i.e. $0.6\epsilon_{su}$ ($0.6 \times 94.6 \text{ mm/m} = 57 \text{ mm/m}$), based on the recommendations from Priestley *et al.* (2007) as discussed previously in Section 4.1.1.

A refined mesh size was used for the lower section of the walls (over a height of L_w), whereas the rectangular elements above this predicted “yielding zone” had an incrementally increasing vertical mesh size to reduce the number of nodes and elements required. The resize of mesh decreased the computation time while improving the accuracy of cracking distributions (vertically and horizontally) at the base of the wall. This approach has been used successfully by other researchers (Bohl & Adebar, 2011). In order to capture the expected highly localised strains in a single crack, a minimum element size corresponding to $0.5t$ was adopted for the walls, which was similar to the sizing of the elements used to validate VecTor2 in Section 4.1. The 3:2 aspect ratio recommendation by Wong (2002) for the plane stress elements was adhered to for the “yielding zone” of the wall. The axial load on the wall was held constant throughout the analyses, whereas the lateral displacement was monotonically increased at the top of the wall (H_e) until failure. Curvature distributions were obtained when the strains in either the concrete or steel reached the strain values corresponding to the “collapse prevention” limit state. An unconfined concrete strain value of 0.003 (0.3%) and steel strain value of 0.05 (5%), were used to represent the collapse prevention limit state for an unconfined concrete wall with N-type longitudinal reinforcement. The equivalent plastic hinge length (L_p) was calculated using the equivalent plastic hinge length method discussed previously in Section 4.

Results for the L_p as a function of the ρ_{wv} range used for each wall are shown in Figure 14(a) and (b) for f_{cmi} values of 40 MPa and 60 MPa respectively. Superimposed in these figures (red square-dot line) are indications of the respective $\rho_{wv,min}$ calculated from the secondary cracking model presented in Section 2. The $\rho_{wv,min}$ from the secondary cracking model clearly gives a good prediction of the onset of secondary cracking and consequently of distributed plasticity. For the walls with ρ_{wv} less than $\rho_{wv,min}$, a small L_p can be observed, corresponding to strains being concentrated at a single, primary crack. Similarly, Figure 15(a) and (b) show the L_p results as a function of the ratio of the

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

ultimate moment capacity (M_u) to the cracking moment (M_{cr}) of the walls for f_{cmi} values of 40 MPa and 60 MPa respectively. It should be noted that M_{cr} has been calculated from Equation 1 using the mean flexural tensile strength ($f_{ct,f}$) value rather than the characteristic flexural tensile strength ($f'_{ct,f}$) value. It is shown that a ratio of M_u/M_{cr} of about 2.0 is needed to achieve a good distribution of inelastic behaviour. This is larger than the $1.2M_{cr}$ that is required when designing beams in accordance with AS 3600 (Standards Australia, 2009), and by implication for the design of some RC walls, as suggested by Beletich *et al.* (2013). Paulay and Priestley (1992) have recommended that minimum reinforcement to provide an ultimate capacity of at least $1.5M_{cr}$ be used and Morris *et al.* (2015) further suggests 1.5 to 2.0 times M_{cr} be used, the latter of which appears to agree with the VecTor2 results.

As expected, for walls in which distributed plasticity does occur, the length of the plastic hinge zone is limited by the low value of the ultimate strain in compression for unconfined concrete (0.003). In Figure 16, it is shown that for walls that have a ρ_{wv} higher than $\rho_{wv,min}$, the ultimate concrete strain governs rather than the steel tensile strain limit.

591

592 **5. Plastic Hinge Lengths for Lightly Reinforced Walls**

As shown in Figure 14, a significant L_p is achieved for walls that have a reinforcement ratio greater than $\rho_{wv,min}$ with a plateau approximately being achieved for most walls after $1.2\rho_{wv,min}$, where $\rho_{wv,min}$ is calculated using the secondary cracking model from Section 2. In contrast, the L_p is much smaller and reasonably insensitive to the parameters for walls with ρ_{wv} less than $\rho_{wv,min}$ due to the formation of a single-crack. Therefore, only the L_p results for walls with a longitudinal reinforcement content greater than $1.2\rho_{wv,min}$ will be used to derive a plastic hinge length equation (in total, 162 walls); a low, constant value will provide an adequate representation of the plastic hinge length for the walls with reinforcement ratios less than $\rho_{wv,min}$. Using the results, Figure 17 shows the calculated effective plastic hinge length (L_p) normalised to the respective wall length (L_w) is plotted against various wall design parameters. These three key parameters (L_w , ALR and a) have previously been observed to influence the spread of plasticity in the wall (Kazaz, 2013). However, as illustrated in Figure 17(a), in the case of the walls analysed here, the wall length (L_w) had less of an influence on the plastic hinge

length than previous research would indicate (Bohl & Adebar, 2011; Kazaz, 2013). In contrast, the axial load had a greater effect on reducing the plastic hinge length in the walls in comparison to that reported in other research (Kazaz, 2013). This is most likely a result of the lower concrete strain capacity in comparison to walls that had been designed for seismic loading (with confinement). As illustrated in Figure 17(b), higher axial loads subject the wall to larger concrete stresses (and strains), thus leading to the strain capacity of the concrete (0.003) being reached at lower displacements. The aspect ratio ($A_r = M/VL_w = H_e/L_w$) of the wall increases the spread of plasticity, as shown with the correlation found in Figure 17(c).

A multiple linear regression analysis was used to derive the plastic hinge length expression for unconfined lightly reinforced concrete rectangular walls (Equation 25).

$$L_p = (0.10L_w + 0.075H_e)(1 - 6.0 \left(\frac{P}{A_g f_{cmi}} \right)) \leq 0.5L_w$$

25.

The maximum limit of $0.5L_w$ used here is the same as that proposed by many authors, as discussed in Section 3. It is clear in Figure 17 that very few walls in this study surpassed this limit. Using the standard errors calculated from the multiple linear regression analysis for each of the relevant parameters, Equation 26 was derived to represent a lower bound estimate of L_p (mean minus two standard deviations).

$$L_p = (0.05L_w + 0.050H_e)(1 - 5.5 \left(\frac{P}{A_g f_{cmi}} \right)) \leq 0.5L_w$$

26.

It is recommended that Equation 26 be used for design purposes when calculating the displacement capacity of unconfined lightly reinforced concrete rectangular walls commonly used in low-to-moderate seismic regions which have a vertical reinforcement ratio greater than $1.2\rho_{vv,min}$. On the other hand, Equation 25 can be used for assessment purposes since it provides a more realistic and less conservative value.

Figures 18(a-e) plot the VecTor2 results for L_p (for walls with ρ_{vv} greater than $1.2\rho_{vv,min}$) against the L_p estimates from the expressions introduced in Section 3 (Equations 13 - 18). The majority of these

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

629 expressions overestimate the L_p for the lightly reinforced, unconfined RC walls analysed in this study.
630 Not surprisingly, the expression derived in this study (Equation 25), plotted (black circles) in Figure
631 18(f), gives the result with the best correlation ($R^2 = 0.87$). The results using the lower bound L_p
632 expression from Equation 26 are also plotted in Figure 18(f) (red-broken circles) and the use of this
633 equation is shown to provide a lower bound to the predictions from VecTor2.
634 For walls that are likely to exhibit a single-crack failure a conservative value of L_p is warranted for use
635 in design due to the brittle nature of these walls. The mean (μ) and standard deviation (σ) of L_p for the
636 3, 6 and 9 metre walls with a ρ_{wy} less than or equal to the corresponding $\rho_{wy,min}$ were calculated and are
637 given in Table 5. However, it should be noted that these values in Table 5 have been obtained from
638 VecTor2 models that use smeared reinforcement and therefore perfect bond was assumed. It has been
639 shown previously by Priestley and Park (1984) that the deterioration of the bond strength between the
640 concrete and reinforcing bar will increase the strain penetration length. Therefore, a constant value of
641 100 mm represents a conservative estimate of the lower bound plastic hinge length for single-crack-
642 failure walls. Nevertheless, Equations 16, 19 and 20 from Section 3, which all attempt to include the
643 effects of strain penetration into the foundation, estimate L_p values of 145 mm, 70 mm and 150 mm
644 respectively, which are similar to the value proposed here. These estimates will all lead to low values
645 for the displacement capacity of walls with a single crack at the base. The use of a conservative value
646 is warranted due to the potentially brittle failure mode.

647

648 **6. Validation of proposed Plastic Hinge Length equation**

649 Recent experimental testing on rectangular RC wall elements has provided an opportunity to compare
650 the proposed plastic hinge length (L_p) equation (Equation 25) to experimental observations. Albidah
651 (2016) and Altheeb (2016) conducted experimental testing for seismic performance of three lightly
652 reinforced concrete rectangular walls; two of these three walls (W1 and W2) had parameters which
653 conformed to the limitations of the proposed plastic hinge length equation and values used in the
654 numerical study given in Section 4.2. Importantly, the walls had detailing typical of that used in the
655 low-to-moderate seismic region of Australia and also incorporated D500N reinforcing bars as the

longitudinal reinforcement. The N-type steel is commonly used in Australia and has normal ductility (as opposed to E type steel that is used in regions of high seismicity and has greater ductility). The details for the walls are given in Table 6 while the cross-sections are shown in Figure 19. The mechanical properties of steel for both walls are given in Table 7.

Wall specimen 1 (W1) had a ρ_{wv} of 0.33%, lower than the estimated $\rho_{wv,min}$ of 0.47% (using Equation 9). The experimental observations from Altheeb (2016) indicate that two primary cracks formed during the cyclic loading, with the larger crack at the base extending to approximately 9.8 mm from the edge of the wall for a top wall displacement of 50 mm. At a top wall displacement of 70 mm, fracturing of the outermost longitudinal reinforcing bars occurred, confirming that the strain in the steel had been concentrated at the primary crack at the base. The damage states of the wall at these displacements are shown in Figure 20. Altheeb (2016) concluded that the performance of wall specimen W1 was primarily governed by strain penetration deformations. These results are consistent with the secondary cracking model (SCM) that has been introduced in Section 2 and indicate that Wall W1 had an insufficient amount of longitudinal reinforcement to allow secondary cracking.

Wall specimen 2 (W2) had a longitudinal reinforcement ratio of 0.66%, which is higher than the estimated $\rho_{wv,min}$ of 0.47%. Albidah (2016) and Altheeb (2016) observed that W2 was influenced more by its flexural response in comparison to W1. The curvature distribution at a top wall displacement of 80 mm for W2 is shown in Figure 21. These curvature values were calculated based on measurements from string potentiometers (Albidah, 2016; Altheeb, 2016). This curvature distribution can be used in conjunction with the EPHL method (Section 3) to calculate the equivalent plastic hinge length (L_p). Using a yield curvature (ϕ_y) value of 5.6 rad/km, the resulting L_p is estimated to be 235.5 mm, as indicated in Table 8. Following this, the estimated L_p from the experimental results is compared to calculated values from the range of plastic hinge length equations given in Section 3, as well as the L_p equation proposed in this study (Equation 25). Table 8 shows that not only does the proposed L_p equation (Equation 25) result in the closest length to the experimentally obtained value, but it is also the only one that underestimates the plastic hinge length, i.e. the only conservative estimate.

7. Conclusion

The aim of this research was to derive a plastic hinge length equation suitable for the assessment of the lightly reinforced concrete walls that are commonly used in low-to-moderate seismic regions such as Australia and to compare this with existing equations. A minimum longitudinal reinforcement ratio $\rho_{wv,min}$ was found to be necessary to initiate secondary cracking at the base of the wall. It can be estimated using the secondary cracking model introduced in Section 2. This minimum longitudinal reinforcement ratio was found to be much larger than the minimum that is currently stipulated in some provisions, including AS 3600 (Standards Australia, 2009). It was shown in Section 5 that the empirical plastic hinge length equations that are commonly used in the displacement-based design and assessment are inappropriate for lightly reinforced walls. Expressions for the plastic hinge length have been derived from an extensive numerical study and are given as follows:

$$L_p = 100 \text{ mm for } \rho_{wv} < \rho_{wv,min}$$

$$L_p = (0.10L_w + 0.075H_e)(1 - 6.0 \left(\frac{P}{A_g f_{cmi}} \right)) \leq 0.5L_w \text{ for } \rho_{wv} \geq \rho_{wv,min}$$

For $\rho_{wv} < \rho_{wv,min}$, the constant value of 100 mm will give a conservative estimate of the plastic hinge length for walls that fail due to brittle fracture of longitudinal steel bars at a single crack at the base of the wall.

There are some limitations on the use of the equations due to the range of parameters used to derive them; it is important to determine, for instance, whether it provides reasonable results for larger values of L_w and H_e than those used in this study. Equation 25 and 26 are specific to rectangular, unconfined RC walls with distributed longitudinal reinforcement and a longitudinal reinforcement ratio upper limit of 1%. The axial load ratio is limited to 10%, the maximum value used in this study. The aspect ratio of the walls should be equal to or greater than 2, since the behaviour of the RC wall will be governed by flexural actions in this case. As discussed in Section 3, the f_u/f_y ratio will also have an influence on the spread of plasticity. Therefore, the derived L_p equation is also limited to walls with N-type reinforcement. However, it is possible that the L_p equation derived will give a conservative result (with the exception of L-type reinforcing steel) for unconfined and lightly reinforced walls with

other types of reinforcing bars, considering that N-type reinforcing typical has a low f_u/f_y value in comparison to other types used in high seismic regions. This research has highlighted the vulnerability of lightly reinforced rectangular RC walls in low-to-moderate seismic regions. Further research on the plastic hinge length for lightly reinforced concrete walls is warranted and an experimental program is currently being conducted as part of the CRC project.

8. Acknowledgements

The support of the Commonwealth of Australia through the Cooperative Research Centre program is acknowledged.

9. References

- ABCB. (2007). Final Regulation Impact Statement for Decision - Proposal to Amend the Earthquake Provisions of the Building Code of Australia.
- Albidah, A., Altheeb, A., Lam, N., & Wilson, J. (2013). *A Reconnaissance Survey on Shear Wall Characteristics in Regions of Low-to-Moderate Seismicity*. Paper presented at the Paper presented at the Australian Earthquake Engineering Society 2013 Conference, Hobart, VIC.
- Albidah, A. (2016). *Vulnerability and Risks of Collapse of Structural Concrete Walls in Regions of Low to Moderate Seismicity*. (Doctor of Philosophy), The University of Melbourne.
- Altheeb, A., Albidah, A., & Lam, N. (2015, 6-8 Novemeber, 2015). *Analytical modelling of strain penetration deformation in reinforced concrete members*. Paper presented at the Proceedings of the Tenth Pacific Conference on Earthquake Engineering, Sydney, Australia.
- Altheeb, A. (2016). *Seismic Drift Capacity of Lightly Reinforced Concrete Shear Walls*. (Doctor of Philosophy), The University of Melbourne.
- Beletich, A. S., Hymas, I. D., Reid, S. G., & Uno, P. J. (2013). *Reinforced concrete : the designers handbook*. Baulkham Hills, N.S.W. Cement and Concrete Services, 2013.
- Bentz, E. C. (1999). *Sectional Analysis of Reinforced Concrete Structures*. (PhD), University of Toronto, Toronto, Ontario.
- Bentz, E. C. (2000). RESPONSE-2000: Sectional Analysis of Reinforced Concrete Members (Version 1.0.5). University of Toronto. Retrieved from <http://www.ecf.utoronto.ca/~bentz/r2k.htm>
- Beyer, K. (2007). *Seismic design of torsionally eccentric buildings with U-shaped RC Walls*. (PhD), ROSE School. (ROSE-2008/0X)
- Bohl, A. (2003). *Plastic Hinge Length in High-Rise Concrete Shear Walls*. (Masters of Applied Science), The University of British Columbia.
- Bohl, A., & Adebar, P. (2011). Plastic Hinge Lengths in High-Rise Concrete Shear Walls. *ACI Structural Journal*, 108(2), 148-157.
- Cardenas, A. E., & Magura, D. D. (1972). Strength of High-Rise Shear Walls - Rectangular Cross Section. *Special Publication*, 36. doi:10.14359/17361
- CEB-FIP, C. E.-I. d. B. (1990). CEB-FIP Model Code 1990. London: Thomas Telford.
- CERC, C. E. R. C. (2012). Final report: Volume 2: The peromance of Christchurch CBD Buildings. Wellington, NZ.
- Dai, H. (2011). *An Investigation of Ductile Design of Slender Concrete Structural Walls*. (Master of Science), Iowa State University, Ames, Iowa.

- Eligehausen, R. (1983). Local bond stress-slip relationships of deformed bars under generalized excitations : experimental results and analytical model. In E. P. Popov & V. V. Bertero (Eds.). Berkeley, Calif. :: Earthquake Engineering Research Center, College of Engineering, University of California :.
- Fenwick, R., & Dhakal, R. P. (2007). Material strain limits for seismic design of concrete structures. *SESOC: Journal of the NZ Structural Engineering Society*, 20(1), pp. 14-28.
- fib (2012). *Model Code 2010 - Final draft, Volume 2. fib Bulletin No. 66*. Lausanne, Switzerland.
- Ghorbani-Renani, I., Velev, N., Tremblay, R., Palermo, D., Massicotte, B., & Léger, P. (2009). Modeling and Testing Influence of Scaling Effects on Inelastic Response of Shear Walls. *Structural Journal*, 106(3).
- Goldsworthy, H. M., & Gibson, G. (2012). *Changes in Seismic Design Philosophy for RC Structures in Areas of Low to Moderate Seismicity Following the Christchurch Earthquake*. Paper presented at the 15th World Conference in Earthquake Engineering, Lisbon, Portugal.
- Hannewald, P. (2013). *Seismic Behavior of Poorly Detailed RC Bridge Piers*. EPFL. Retrieved from <http://infoscience.epfl.ch/record/188364>
- Henry, R. S. (2013). Assessment of the Minimum Vertical Reinforcement Limits for RC Walls. *Bulletin of the New Zealand Society for Earthquake Engineering*, 46(2), 88.
- Henry, R. S., Ingham, J., & Lu, Y. (2014). *Experimental testing and modelling to address the performance of RC walls during the 2010/2011 Canterbury earthquakes*. Paper presented at the Tenth U.S. National Conference on Earthquake Engineering, Anchorage, Alaska.
- Henry, R. S., Lu, Y., Seifi, P., & Ingham, J. M. (2015, 6-8 Novemeber, 2015). *Recent Research to Improve the Seismic Performance of Lightly Reinforced and Precast Concrete Walls*. Paper presented at the Proceedings of the Tenth Pacific Conference on Earthquake Engineering, Sydney, Australia.
- Hoult, R. D., Goldsworthy, H. M., Lumantarna, E. (2015). *Improvements and difficulties associated with the seismic assessment of infrastructure in Australia*. Australasian Fire and Emergency Service Authorities Council (AFAC) 2015 Conference, Adelaide, South Australia.
- Hyland. (2011). Pyne Gould Corportation Building Site Examination and Materials Tests: Report prepared for: Department of Building and Housing.
- International Council of Building Officials (1997). 1997 Uniform Building Code, Vol. 2. Whittier, CA.
- Kazaz, I. (2013). Analytical Study on Plastic Hinge Length of Structural Walls. *Journal of Structural Engineering*(11), 1938.
- Kupfer, H. B., & Gerstle, K. H. (1973). Behavior of Concrete under Biaxial Stresses. *Journal of the Engineering Mechanics Division*, 99(4), 13.
- Kupfer, H., Hilsdorf, H. K., & Rusch, H. (1969). Behavior of Concrete Under Biaxial Stresses. *Journal Proceedings*, 66(8). doi: 10.14359/7388
- Lu, Y., Henry, R. S., & Ma, Q. (2014). *Modelling and Experimental Plan of Reinforced Concrete Walls with Minimum Vertical Reinforcement*. Paper presented at the Tenth U.S. National Conference on Earthquake Engineering, Anchorage, Alaska.
- Lu, Y., Henry, R. S., Gultom, R., & Ma, Q. (2015). *Experimental testing and modelling of reinforced concrete walls with minimum vertical reinforcement*. Paper presented at the 2015 New Zealand Society for Earthquake Engineering Annual Technical Conference, Rotorua, New Zealand.
- Luu, H., Léger, P., & Tremblay, R. (2013). Seismic demand of moderately ductile reinforced concrete shear walls subjected to high-frequency ground motions. *Canadian Journal of Civil Engineering*, 41(2), 125-135.
- Menegon, S.J., H.H. Tsang, and J.L. Wilson. *Overstrength and ductility of limited ductile RC walls: from the design engineers perspective*. in *Proceedings of the Tenth Pacific Conference on Earthquake Engineering*. 2015. Sydney, Australia.
- Moehle, J. P. (1992). Displacement-Based Design of RC Structures Subjected to Earthquakes. *Earthquake Spectra*, 8(3), 403-428. doi:doi:10.1193/1.1585688
- Moehle, J. (2015). *Seismic design of reinforced concrete buildings*. New York, N.Y.: McGraw-Hill Education LLC.

- Mohr, D. S. (2007). *Nonlinear Analysis and Performance Based Design Methods for Reinforced Concrete Coupled Shear Walls*. (Master of Science in Civil Engineering), University of Washington, Seattle, U.S.A.
- Morris, G. J., Bull, D. K., & Bradley, B. A. (2015). In Situ Conditions Affecting the Ductility Capacity of Lightly Reinforced Concrete Wall Structures in the Canterbury Earthquake Sequence. *Bulletin of the NZ Society of Earthquake Engineering*, 48(3), 191-204.
- Mortezaei, A., & Ronagh, H. R. (2012). Plastic hinge length of FRP strengthened reinforced concrete columns subjected to both far-fault and near-fault ground motions. *Scientia Iranica*, 19(6), 1365-1378.
- Oesterle, R. G., Fiorato, A. E., Johal, L. S., Carpenter, J. E., Russell, H. G., & Corley, W. G. (1976). Earthquake Resistant Structural Walls - Tests of Isolated Walls (pp. 318). Skokie, Illinois: Report to the National Science Foundation, Construction Technology Laboratories, Portland Cement Association.
- Palermo, D., & Vecchio, F. (2002). Behaviour and Analysis of Reinforced Concrete Walls Subjected to Reversed Cyclic Loading. *Publication No. 2002-01, Department of Civil Engineering, University of Toronto*, 351 pp.
- Palermo, D., & Vecchio, F. J. (2007). Simulation of Cyclically Loaded Concrete Structures Based on the Finite-Element Method. *Journal of Structural Engineering*, 133(5), 728-738. doi: 10.1061/(ASCE)0733-9445(2007)133:5(728)
- Patel, V. J., Van, B. C., Henry, R. S., & Clifton, G. C. (2015). Effect of reinforcing steel bond on the cracking behaviour of lightly reinforced concrete members. *Construction and Building Materials*, 96, 238-247. doi: <http://dx.doi.org/10.1016/j.conbuildmat.2015.08.014>
- Paulay, T. (1986). *The Design of reinforced concrete ductile shear walls for earthquake resistance*: University of Canterbury, Department of Civil Engineering.
- Paulay, T., & Priestley, M. J. N. (1992). *Seismic design of reinforced concrete and masonry buildings*: New York : Wiley, c1992.
- Priestley, M. J. N., Calvi, G. M., & Kowalsky, M. J. (2007). *Displacement-based seismic design of structures / M. J. N. Priestley, Gian Michele Calvi, Mervyn J. Kowalsky*: Pavia : IUSS Press : Fondazione Eucentre, 2007.
- Priestley, M. J. N., & Park, R. (1984). Strength and Ductility of Bridge Substructures. *RRU Bulletin 71*, National Roads Board, Wellington, New Zealand.
- Priestley, M. J. N., & Park, R. (1987). Strength and Ductility of Concrete Bridge Columns Under Seismic Loading. *Structural Journal*, 84(1). doi:10.14359/2800
- Richart, F. E., Brandtzaeg, A., & Brown, R. L. (1928). A study of the failure of concrete under combined compressive stresses. *University of Illinois Bulletin*; v. 26, no. 12.
- Sagbas, G. (2007). *Nonlinear Finite Element Analysis of Beam-Column Subassemblies*. (Master of Applied Science), University of Toronto, Toronto, Canada.
- Seckin, M. (1981). *Hysteretic Behaviour of Cast-in-Place Exterior Beam-Column-Slab Subassemblies*. (Ph.D. Thesis), University of Toronto, Toronto, Canada.
- Smith, P., & England, V. (2012). Independent Assessment on Earthquake Performance of Gallery Apartments - 62 Gloucester Street: Report prepared for the Canterbury Earthquakes Royal Commision, available at <http://canterbury.royalcommission.govt.nz/documents-by-key/20120217.3188>.
- SRIA. (2015). *Guide to Seismic Design and Detailing of Reinforced Concrete Buildings in Australia* (P. McBean, J. W. Woodside, S. Munter, & E. Lume Eds. First ed.): Steel Reinforcement Institute of Australia.
- Sritharan, S., Beyer, K., Henry, R. S., Chai, Y. H., Kowalsky, M., & Bull, D. (2014). Understanding Poor Seismic Performance of Concrete Walls and Design Implications. *Earthquake Spectra*, 30(1), 307-334.
- Standards Association NZ. (2006a). NZS 3101: Part1:2006, Concrete Structures Standard - The Design of Concrete Structures.
- Standards Association NZ. (2006). NZS 3101: Part2:2006, "Concrete Structures Standard Part 2 - Commentary on the Design of Concrete Structures".
- Standards Australia. (2009). AS 3600-2009: Concrete Structures.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

860 Standards Australia. (2014). AS 3600-2009 Supp 1:2014 : Concrete structures - Commentary
861 (Supplement to AS 3600-2009).
862 Standards Australia/New Zealand. (2001). AS/NZS 4671:2001 : Steel Reinforcing Materials.
863 Thomsen, J., & Wallace, J. (2004). Displacement-Based Design of Slender Reinforced Concrete
864 Structural Walls—Experimental Verification. *Journal of Structural Engineering*, 130(4), 618-
865 630. doi: doi:10.1061/(ASCE)0733-9445(2004)130:4(618)
866 Vecchio, F. (1992). Finite Element Modeling of Concrete Expansion and Confinement. *Journal of*
867 *Structural Engineering*, 118(9), 2390-2406.
868 Vecchio, F., Lai, D., Shim, W., & Ng, J. (2000). Disturbed Stress Field Model for Reinforced
869 Concrete: Validation. *Journal of Structural Engineering*, 126(9), 1070.
870 Wallace, J. W., & Moehle, J. P. (1992). Ductility and Detailing Requirements of Bearing Wall
871 Buildings. *Journal of Structural Engineering*, 118(6), 1625-1644.
872 Walraven, J. C. (1981). Fundamental Analysis of Aggregate Interlock. *Journal of the Structural*
873 *Division*, 107(11), 25.
874 Wibowo, A., Wilson, J., Lam, N. T. K., & Gad, E. F. (2013). Seismic performance of lightly
875 reinforced structural walls for design purposes. *Magazine of Concrete Research*, 65, 809-828.
876 Wibowo, A., Wilson, J., Lam, N., Gad, E. F., Lu, Y., & Henry, R. S. (2014). Discussion: Seismic
877 performance of lightly reinforced structural walls for design purposes. *Magazine of Concrete*
878 *Research*, 66, 1073-1074.
879 Wong, P., & Vecchio, F. (2002). Vector2 and FormWorks User Manual. Department of Civil
880 Engineering, University of Toronto.
881 Wood, S. L. (1989). Minimum Tensile Reinforcement Requirements In Walls. *ACI Structural*
882 *Journal*, 86(5), 582-591.

Figure 1 Cross section of a typical RC wall with shaded area A_{eff}

Figure 2 Minimum longitudinal reinforcement ratio required for a range of concrete strengths with lower, mean and upper bound (a) ultimate strength of steel and (b) flexural tensile strength of concrete

Figure 3 (a) Curvature distribution (solid line) along RC cantilever wall with idealised profile (dotted line) and (b) expected strain distribution results

Figure 4 Mesh setup in VecTor2 for wall specimen R1 (Oesterle *et al.*, 1976) with truss elements

Figure 5 Force-displacement results from VecTor2 using (a) smeared vertical reinforcement and (b) discrete truss-link elements

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Figure 6 VecTor2 steel strain distribution results from the smeared model (where VHP & VHR correspond to the strain gauges on the west toe of the wall and VAP & VAR are the gauges on the east toe)

Figure 7 VecTor2 steel strain distribution results from the truss-link model (where VHP & VHR correspond to the strain gauges on the west toe of the wall and VAP & VAR are the gauges on the east

Figure 8 Vertical strains through the cross section of wall R1 at 3ft (914.4mm)

Figure 9 Cracking pattern at 76mm deflection for (a) specimen R1 (Oesterle *et al.*, 1976) and (b) VecTor2

Figure 10 Cross section of wall specimen C1 (Lu *et al.*, 2015)

For Peer Review Only

Figure 11 (a) Mesh setup and cracking distribution from VecTor2 monotonic and (b) experimental observations from Lu *et al.* (2015)

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Figure 12 Force-displacement results from VecTor2 for wall C1 with (a) smeared and (b) truss-link models

Figure 13 Steel strain distribution comparison for (a) Model 1 (smeared) and (b) Model 2 (truss-link) at a wall drift of 1.5% (42mm top displacement)

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Figure 14 Plastic hinge length results as a function of longitudinal reinforcement ratio for all of the walls with a f_{cmi} of (a) 40 MPa and (b) 60 MPa

Figure 15 Plastic hinge length results as a function of the ultimate to cracking moment ratio for all of the walls with a f_{cmi} of (a) 40 MPa and (b) 60 MPa

Figure 16 Governing strains in the walls as a function of the longitudinal reinforcement content for walls with a f_{cmi} of (a) 40MPa and (b) 60MPa

Figure 17 Results of plastic hinge length normalised to the respective wall length with wall parameters (a) wall length (b) axial load ratio and (c) aspect ratio

Figure 18 Comparison of VecTor2 plastic hinge length results to the proposed estimations from various studies

Figure 19 Cross-sections of wall specimens (a) W1 and (b) W2 from Altheeb (2016)

Figure 20 Damage state of wall specimen W1 (Altheeb, 2016) at top wall displacement of (a) 50mm and (b) 70mm

Figure 21 Curvature distribution for W2 (Albidah, 2016) at 80 mm top wall displacement

Table 1 Strain hardening ratio values for common steel reinforcing bars in Australia

Type	f_u/f_y	
	AS 4671:2001	Menegon <i>et al.</i> (2015)
D500L	1.030	1.056
D500N	1.080	1.201
D500E	1.150	1.245

Table 2 Details of the RC wall specimen R1

f'_c (MPa)	$f_{ct,fl}$ (MPa)	L_w (mm)	t_w (mm)	H_e (mm)	ALR (%)	ρ_{wv}^1 (%)	ρ_{wh} (%)	ρ_{wb}^2 (%)
44.7	4.5	1905	101	4572	0.4	0.25	0.31	1.74

¹ reinforcement ratio in the web
² longitudinal reinforcement ratio in the boundary ends

Table 3 Steel reinforcing properties for specimen R1

d_{bl} (mm)	E_s (MPa)	f_y (MPa)	f_u (MPa)	$0.6\epsilon_{su}$ (mm/m)
6	216,495	522	700	73.0
9.525	191,674	511	765	58.8

Table 4 Walls used in VecTor2 with varying parameters

L_w (m)	t (m)	a	H_e (m)	ALR (%)	f_{cmi} (MPa)	ρ_{wv} (%)	ρ_{wh} (%)
3	0.2	2.5, 4.1, 5.7	7.35, 12.25, 17.15	1.5, 5, 10	40, 60	0.15-1.0	0.25
6	0.2	2.0, 3.3, 4.1	12.25, 19.60, 24.50	1.5, 5, 10	40, 60	0.15-1.0	0.25
9	0.25	2.7, 3.8, 4.9	24.50, 34.30, 44.10	1.5, 5, 10	40, 60	0.15-1.0	0.25

Table 5 Mean and standard deviations of plastic hinge length from the VecTor2 results

L_w (m)	μ (mm)	σ (mm)
3	135.8	73.3
6	128.8	26.5
9	195.4	0.7

Table 6 Details of the RC wall specimen W1

	f'_c (MPa)	$f_{ct,fl}$ (MPa)	L_w (mm)	t_w (mm)	H_e (mm)	ALR (%)	ρ_{wv} (%)	ρ_{wh} (%)
W1	35.2	3.7	900	120	2750	5	0.33	0.30
W2	34.7	3.6	900	120	2750	5	0.66	0.30

Table 7 Steel reinforcing properties for specimens W1 and W2

d_{bl} (mm)	E_s (MPa)	f_y (MPa)	f_u (MPa)
10	200,000	500	720

Table 8 Plastic hinge length estimates for wall specimen W2

	Experimental (W2)	This Study (Eqn. 25)	Bohl & Adebar (2011)	Kazaz (2013)	Priestley <i>et al.</i> (2007)	ICBO (1997)	Thomsen & Wallace (2004)
L_p (mm)	235.5	207.4	293.7	365	453	450	297