Experimental and Analytical Assessment of the Flexural Behaviour of Cantilevered RC Walls Subjected to Impact Actions

Arnold C.Y. Yong¹, Nelson T.K. Lam², Scott J. Menegon³ and Emad F. Gad⁴

Abstract

Reinforced concrete (RC) impact-resistance barriers, such as rockfall barriers, often consist of a cantilever RC wall, which is expected to experience flexural bending under impact loading to resist the associated design actions. In order to investigate the flexural response behaviour of an RC cantilever wall, a large-scale experiment was carried out on a fixed base RC cantilevered barrier wall measured 1.5 m in height, 3 m in length and 0.23 m in thickness. Two “torpedo” shaped steel impactors with mass of 280 kg and 435 kg were released from controlled heights ranging from 0.2 m to 1.4 m in pendulum style to strike the top of the wall. The first half of this paper presents an overview, findings and results of this large-scale, original experimental work. The second half of the paper presents a displacement-based analytical model, which can be used to assess and determine important design parameters for cantilever RC barrier walls of this nature; including, deflection demand and material strains. Systematic comparisons of the experimental results and the proposed analytical model demonstrate the accuracy and reliability of the proposed model for assessing cantilevered RC barrier walls subject to impact actions.

Keywords: large-scale impact test; displacement-based, reinforced concrete, rockfall barrier

¹ Research Fellow, Department of Infrastructure Engineering, The University of Melbourne, Parkville, Victoria 3010, Australia. Email: arnold.yong@unimelb.edu.au.

² Professor, Department of Infrastructure Engineering, The University of Melbourne, Parkville, Victoria 3010, Australia. Email: ntkl@unimelb.edu.au.

³ Research fellow, Department of Civil and Construction Engineering, Swinburne University of Technology, Hawthorn, Victoria 3122, Australia. Email: smenegon@swin.edu.au.

⁴ Professor, Dean of School of Engineering, Faculty of Science Engineering and Technology, Swinburne University of Technology, Hawthorn, Victoria 3122, Australia. E-mail: egad@swin.edu.au.

1 Introduction

Impact actions need to be considered in the design of reinforced concrete (RC) rockfall barriers, which are exposed to actions of landslide debris and boulder impact. As shown in field measurements, the amplitude of transient forces generated by the impact of boulders can be several orders of magnitude higher than forces that are associated with fluid pressure generated by debris flow (Hu *et al.* 2006, Hu *et al.* 2011, Zhang 1993). The cantilevered wall component of a RC barrier is commonly designed in accordance with force-based approaches (e.g. American Association of State Highway and Transportation Officials (2012), ASTRA (2008), Austroads (2013), Japan Road Association (2000), Kwan (2012), Standards Australia (2004)), which involve applying a pre-determined quasi-static force on the targeted structure. In reality, the impact force developed at the point of contact between the boulder and the surface of the concrete is usually of very high intensity but lasts only for a very short duration, unlike the quasi-static force to be used in design (Perera *et al.* 2016, 2017, Sun *et al.* 2014). If the highly transient contact force is to be simulated, the inertial resistance developed in the target (i.e. the concrete barrier) must also be simulated in order to accurately predict the resulting flexural response behaviour of the cantilevered RC wall. An alternative approach to the design of an impact resistant barrier is to employ the equal energy approach; wherein the amount of energy delivered by the impactor is equated to the energy of absorption of the wall, which is associated with the bending of the cantilevered wall (Eurocode 1 2008, Jiang *et al.* 2004). This equal energy approach may over-state the flexural action if mitigating effects such as dissipation of energy on impact and inertial resistance generated from within the wall have not been accounted for. Both force-based and equal energy approaches as described can result in an overly-conservative design of the RC barrier (Kishi *et al.* 2009, Lam *et al.* 2018a).

In view of the shortcomings of existing guidelines for design and analysis, a displacement-based (DB) procedure has been developed as an alternative method of assessing impact actions. Undertaking major repair work on a failed barrier which is adjacent to a highway, or a train track, can be very disruptive and hence costly. The proposed assessment procedure is therefore based on pre-yield conditions of the RC wall with a view to limit the amount of repair work following an impact incident. The DB method is aimed at making accurate predictions of the displacement demand of the impacted wall in pre-yield conditions. The proposed model has previously been validated using small-scale experimental testing, which involved dropping a small impactor object onto a mild steel bar or a wooden joist (e.g. Ali *et al.* (2014), Lam and Gad (2016), Lam *et al.* (2018b), Yang *et al.* (2012)). This paper will present an experimental validation of the proposed DB model using a large-scale RC wall test specimen. The experimental validation of the proposed algebraic expression for predicting the displacement demand of the impact is an achievement of high practical significance.

Apart from considerations of flexural failure of the impacted wall, risks of failure by punching (shear) or by other phenomena localised around the point of contact also requires assessment, and much depends on the nature of the impact. Assessment of risks associated with these localised phenomena deserves separate treatment and is outside the scope of considerations of the article. Some relevant experimental investigations were carried out and reported by authors such as Dancygier *et al.* (2007), Heckötter and Vepsä (2015), Kojima (1991), Zhang *et al.* (2005). These experiments normally involved the use of gas gun or gun powder to fire the impactor. Such setup allows much higher impact velocity as compared to the drop hammer setup or pendulum setup used in this paper. However, the impactor mass is limited to the capacity and operation range of the gas gun/power gun. Studies focused on the localised impact response behaviour of concrete are low impactor mass and high impact velocity in nature, as opposed to the studies on global behaviour (e.g. this paper) which involve the use of much

heavier impactor at a lower impact velocity. An experimental work on low velocity penetration has been reported by Tamagna and Riera (1993). Based on the test results, empirical and semi-empirical formula have been developed which relate contact force (or stress) to penetration depth (Tamagna and Riera 1998), and the relationship was found to be affected by both the impactor material and contact surface.

Experimental investigations of different scales have been carried out over the years to better understand the behaviour of RC structures to impact actions. Many of these tests made use of a simply-supported beam (Fujikake *et al.* 2009, Kishi and Bhatti 2010, Tachibana *et al.* 2010, Zhan *et al.* 2015) or a RC slab (Chen and May 2009, Hummeltenberg *et al.* 2011, Mougin *et al.* 2005, Othman and Marzouk 2016, Zineddin and Krauthammer 2007) as the targeted specimen. These tests were typified by the use of a drop hammer, or the like, and hence not ideal for validating an analytical model for simulating, say, the horizontal impact of a boulder on a rockfall barrier. Some studies involved large scale horizontal impact testings in the field but little instrumental data were captured (Ahmed *et al.* 2013, Aminata *et al.* 2008, El-Salakawy *et al.* 2002, Ng *et al.* 2016), since the level of instrumentation can be compromised by the scale of the experiment. Much of the tests reported in literature did not take direct measurement of the bending action of the wall in the form of material strains (e.g. neither data on displacement nor material strains were captured in tests carried out by Su *et al.* (2015)). Currently, the literature on the design of barriers to impact actions has no experimentally validated provisions for determining the tensile stresses and strains on the longitudinal reinforcement for resisting bending actions.

The DB model to be introduced in this article for predicting the displacement demand of the impact considers inertial effects as well as energy losses occurring on impact, and has been shown to provide accurate estimates of the maximum deflection of a target when subjected to

the impact of a moving object up to the limit of yield of the target. The predictive expression has been validated by a 1.5 m tall and 3 m long fixed base RC barrier which was well-instrumented to take measurements of the deflection of the wall and the tensile strains of the longitudinal reinforcements along the length of the wall. A pendulum device that was fitted with a torpedo-shaped solid steel impactor was used to deliver horizontal impact to the top of the cantilevered wall. The experimental investigation was scoped to cover pre-yield conditions of the wall. Details of the specimen, impactors, instrumentation, experimental set up and procedures will be described in this paper followed by a summary of the results from the impact tests. The second half of the paper presents the derivation and use of expressions for predicting maximum displacement of the cantilevered RC walls subjected to impact actions. The expressions can also be used to determine maximum tensile strain of the vertical reinforcement.

2 Experimental Impact Testing of RC Wall

2.1 General Set Up

The RC barrier specimen had a cantilevered wall with dimensions of 1.5 m tall, 3 m long and 0.23 m thick. The wall was cast on top of a wall footing of 0.5 m thick and 1.23 m wide, as shown in Figure 1 (a). Standard strength grade N40 concrete to AS 1379 (Standards Australia 2007), which had a minimum characteristic compressive strength of 40 MPa (based on 28 days of standard curing), was used to construct the specimen. The concrete mix had standard density of 2400 kg/m³ and maximum aggregate size of 20 mm. Compression tests were carried out on six concrete cylinders during the time the impact tests were carried out and the in-situ concrete strength was found to be 47 MPa.

Grade D500N reinforcing steel bars to AS/NZS 4671 (Standards Australia and Standards New Zealand 2001) were used as vertical and horizontal reinforcement in the wall, as well as in the wall footing, as shown in Figure 1 (b). The minimum characteristic yield strength and the strain

hardening ratio of these reinforcing bars were 500 MPa and 1.08 respectively. N20 (i.e. grade D500N with nominal diameter of 20 mm) bars at 200 mm spacing were used for both the vertical and horizontal reinforcement in the wall. There were 15 tensile bars and 15 compressive bars in total. Similar reinforcement arrangement was used for the wall footing to ensure that the cantilevered wall was fixed rigidly to the foundation which was in turn held down onto the strong floor of the laboratory. Tensile tests were carried out on six bar samples to obtain the in-situ material properties of the reinforcement, which was as follows: yield stress of 543 MPa; 636 MPa; strain hardening ratio of 1.17; ultimate strain of 9.6%; and elastic modulus of 194,000 MPa. Concrete cover of 30 mm was specified. The wall had a reinforcement ratio of more than 0.8% for grade N40 concrete, which ensured that the concrete would experience a well distributed crack pattern when subject to flexural actions (Menegon *et al.* 2018).

Figure 1 Reinforced concrete specimen: (a) 3D drawing, (b) wall dimensions reinforcement details (units of length in mm)

Two impactors made of solid steel with density of 7850 kg/m^3 were used to strike the RC barrier wall specimen. Solid steel “torpedo” shaped objects (with a hemispherical surface at the point of contact) were employed as impactor objects in order that the impact tests are both repeatable and reproducible. The hemispherical fitting had the same diameter as the cylindrical body. At the other end (flat end), a 1/4-28 UNF-2B hole was tapped for securing an accelerometer to the impactor object. On the curved cylindrical surface, three M20 holes were tapped for the purpose of lifting, with the middle hole tapped at the centre of mass of the impactor. Eye nuts were secured onto the holes. The flexural response behaviour of the stem wall was mainly dependent on the amount of kinetic energy delivered by the strike and the mass ratio λ (i.e. target mass / impactor mass). The mechanical properties of the impactor material such as compressive stiffness behaviour and projectile shape had no significant influence except for the re-bounce behaviour affecting energy losses. It is widely recognised that the shape of the impactor can be a controlling factor in the prediction of localised damage (Adeli and Amin 1985, Ben-Dor *et al.* 2006, Perera *et al.* 2016). This factor becomes less dominant in predicting the response of the wall to the impulsive action of the impact (affecting the wall bending and stability behaviour) which is the subject matter of interest in this article. Shape effects may still have some minor influence on the re-bounce behaviour of the impact in the context of predicting bending actions of the wall. Such influences can be incorporated into the proposed predictive model through the coefficient of restitution parameter (refer Section 3). Thus, the deflection behaviour of the test wall generated by the impact of a piece of boulder can be emulated by the use of a solid steel impactor of the same weight and delivering the same amount of impact energy. The impactors are numbered and summarised in Table 1 and alongside in Figure 2, which shows the dimensions of the impactor object. A photograph of the impactor objects is shown in Figure 3.

155

Table 1 Impactor object dimensions

Impactor	Mass (kg)	a (mm)	b (mm)
Impactor 1	280	400	300
Impactor 2	435	700	300

156

Figure 2 Torpedo shaped impactor object

Figure 3 Photograph of impactor objects

157 Instrumentation (as shown in Figures 4 (a) and (b)) was used to capture displacement data,
158 material strains and curvatures of the dynamically responding barrier as well as the velocity of
159 the impactors over the course of impact. This included:

- 160 • Post-yield strain gauges which were attached to the base of the wall on each
161 longitudinal reinforcing bar. These strain gauges were designed to measure the strain
162 in the longitudinal bars when subject to both elastic and inelastic (post-yield) strains. A
163 trial run of the test showed that the resolution of the strain gauges was in approximately
164 of ± 1 micro-strain.
- 165 • Linear variable differential transformers (LVDTs) were attached to the concrete surface
166 on both sides of the wall to measure longitudinal concrete strain up the height and along
167 the base of the stem wall.
- 168 • Laser sensors with measurement frequency of up to 750 Hz were placed behind the
169 specimen to measure deflection at various location across the width and up the height

of the wall, as shown by red dots in Figure 4 (a) and red boxes in Figure 4 (b). Additional sensors were used to detect any unintended sliding and uplift movement of the specimen, which were expected to be negligible as the specimen was supposedly fully fixed to the ground. A total of 12 pieces of laser displacement sensors were adopted in the testing.

- An accelerometer with measurement range of up to 2500 g and frequency response of up to 10 kHz was screwed onto the flat end of the impactor objects (1/4-28 UNF-2B tapped hole) to record the acceleration time-history as shown in Figure 4 (b). The recorded results were then multiplied by the mass of impactor to calculate the amount of contact force that was delivered at the point of contact in an impact.
- A high speed camera (HSC), which was capable of recording video images at a rate of up to 25,000 frames-per-second at full resolution of 1280 x 800, was used to capture images taken at the impact location in order to: (i) determine the velocity of the impactor prior to and following impact with the wall; and (ii) visualise actual conditions (at the point of contact) during the course of the impact. The frame that was recorded by the HSC is shown in Figure 4 (b) as a green box.

Figure 4 (a) Rear view (compressive side) and (b) side view of specimen showing instrumentation (units of length in mm)

A 3D drawing displaying an overview of the planned test set-up including the specimen, the impactor objects and details of the instrumentation is shown in Figure 5, alongside a photograph showing the actual test set-up featuring two steel frames fixed to the ground (Figure 6). The first steel frame that was positioned close to the specimen was used to secure the impactor object in place. Each impactor object was initially positioned at the centreline of the specimen and at 250 mm from the top of the wall. A quick release hook was attached to its centre of mass. The hook was in turn secured to a cable extending from a hand winch via a pulley which was attached to the second steel frame. During the course of lifting, a laser level was used to ensure that the impactor had been raised to the desired height with good accuracies. The impactor was then released using the quick release hook. In order to ensure a fully fixed foundation, the wall footing of the barrier specimen was bolted to the strong floor of the laboratory (which is approximately 1 m thick) using six threaded M36 rods on both sides of the wall. Each of these threaded rods was post-tensioned to 200 kN to prevent any uplift or sliding of the foundation.

Figure 5 Drawing showing overview of test set up

Figure 6 Photograph showing overview of test set up

2.2 Testing Protocol

The wall specimen was tested repeatedly to fulfil the objective of studying the change in the deflection demand on the wall and the associated tensile strain demand on the longitudinal reinforcement with changes in (i) amount of kinetic energy delivered by the impact, (ii) mass of the impactor or target (and hence ratio of target mass : impactor mass), (iii) material at the contact surface, and (iv) state of crack of concrete.

The first part of the test was carried out with a protective steel plate with dimensions: 500×500 mm × 32 mm thick, which was attached to the top of the wall at the location of impact, as shown in Figures 4 (b) and 6. This steel plate was used to ensure that the bending behaviour of the wall was comparable across multiple tests without being distorted by cumulative localised damage surrounding the point of contact. Strain and deflection profiles of the wall were constantly monitored to confirm that the wall had not yielded. Eight tests (i.e. 8 impacts to the wall) were carried out in the first part of the test and these tests were numbered as Test #1 to #8. Impactor 1 was used to strike the steel plate from various increasing release heights H (Figure 7) in Test #1 to #4 to deliver different amount of impact energy. Test #5 to #7 used

Impactor 2. The drop heights for Impactor 2 were selected such that the theoretical impact energy in Tests #5 to #7 were the same as Tests #1 to #3, respectively to investigate the effect of varying the impactor mass while keeping the impact energy constant. Impact test corresponding to impact energy of 3.85 kJ (i.e. Test #4) was omitted for Impactor 2 because the wall would be too close to the threshold of yield. Following completion of the test series using Impactor 2, the final test in the first part of the test (Test #8) was conducted using Impactor 1 at 0.2 m release height. Test #8 was similar to Test #1 except that the RC wall was fully cracked in Test #8 as compared to the fresh uncracked wall in Test #1. The purpose of conducting Test #8 was to observe how the change in flexural stiffness of the wall affected the structural response.

In the second part of the test, the steel plate was removed in order to investigate the wall response behaviour when subject to the direct impact of the torpedo shaped striker without any protection. Four tests (numbered as Test #9 to #12) were carried out using Impactor 1 with the four release heights used previously in Test #1 to #4. By keeping the impactor mass and release height the same, the difference in wall response behaviour with and without the steel plate can be observed. Details of the conditions of impact for all relevant tests are summarised in Table 2.

Figure 7 Sketch illustrating release height H

Table 2 Impact conditions for all tests

Test #	Impactor Mass (kg)	H (m)	Expected Impact Energy (kJ)	Protective Layer
1	280	0.2	0.55	Steel Plate
2	280	0.5	1.37	Steel Plate
3	280	0.9	2.47	Steel Plate
4	280	1.4	3.85	Steel Plate
5	435	0.129	0.55	Steel Plate
6	435	0.322	1.37	Steel Plate
7	435	0.579	2.47	Steel Plate
8	280	0.2	0.55	Steel Plate
9	280	0.2	0.55	N/A
10	280	0.5	1.37	N/A
11	280	0.9	2.47	N/A
12	280	1.4	3.85	N/A

242 **2.3 Observations from the Impact Tests**

243 The maximum deflection of the wall was found by reading off from the recorded time-history
 244 data and then correlated with its level up the height of the wall as shown in Figures 8 (a) and
 245 (b) (for tests using Impactor 1 and 2 respectively) when a steel plate was attached to the wall
 246 to receive the impact, and in Figure 8 (c) for tests on a bare wall without the protective steel
 247 plate. In addition, the maximum deflection value has also been correlated with the amount of
 248 impact energy as shown in Figure 9. Maximum deflection values recorded from Test #1-8 and
 249 Test #9-12 (which are characterised by similar amount of impact energy) are compared in
 250 Figure 9 to show the significant increase in the deflection of the wall when the steel plate has
 251 been removed (in Test #9-12). It is also shown that a higher ratio of the target mass : impactor
 252 mass would always result in the wall deflecting less when amount of impact energy is kept the
 253 same. For example, the added mass of a steel plate would result in a higher target mass, and

hence a higher mass ratio. The test wall would accordingly deflect less in response to the same impact. Delivering the same amount of energy using a smaller impactor (hence a higher mass ratio) would also result in a reduced deflection demand. This is evident by comparison of test results across Test #1 and #5; #2 and #6; and #3 and #7. In addition, Test #1 and #8 involved the same impactor and release height but resulted in different deflection profiles. These observed differences can also be explained by the wall possessing different flexural stiffnesses when subject to different states of cracking following repetitive testing; the wall was only partially cracked in Test #1 and more extensively cracked in Test #8 following multiple strikes. This proposition is supported by the amount of cracking that was observed on the wall surface as shown in Figure 10 (as represented by red lines). Similar inferences can be drawn from the reinforcement strain profiles which will be presented in a later section of the paper.

Figure 8 Maximum wall deflection from tests (a) with steel plate employing Impactor 1, (b) with steel plate employing Impactor 2, and (c) without steel plate employing Impactor 1

Figure 9 Maximum wall deflection vs impact energy

Figure 10 Crack pattern observed in Test #8

The response behaviour of the wall was observed to be dominated by flexural deformation, whilst minimum shear deformation was observed. The component of flexural deformation in the wall was approximated by calculating a flexural deformation displacement profile of the wall, which is shown in Figure 11 for Test #7, where it can be seen to approximately equal the total displacement of the wall. The flexural displacement profile was approximated by double integrating the curvature profile of the wall, which was determined using LVDTs that were stacked up the height of the wall at its centreline (as shown in Figures 4 (a) and (b)). Further, no measurable displacement due to rocking nor sliding of the foundation was observed throughout the test program, which was monitored using instrumentation mounted at the base

279 of the wall specimen (as shown in Figures 4 (a) and (b)). In summary, the deflection of the
 280 wall was pre-dominantly due to flexure.

281 **Figure 11 Comparison of wall deflection in Test #7 recorded from laser and integrated from**
 282 **LVDT results (a) along the wall height, (b) at 1475 mm from base, and (c) at 975 mm from base**

283 The duration of the wall to reach its maximum strain was recorded to be between 10 to 20 ms.
 284 That corresponds to maximum strain rates of 0.05 to 0.3 s^{-1} for steel reinforcement and 0.04 to
 285 0.17 s^{-1} for concrete, and this range of strain rate has been shown to have no significant effects
 286 on the Young's modulus of concrete (Rostasy *et al.* 1984, Schmidt-Hurtienne 2000) and
 287 reinforcement steel (Berner 1981, Levings and Sritharan 2012). It has also been shown from
 288 the test results reported by Berner (1981), Levings and Sritharan (2012) that a strain rate of less
 289 than 0.3 s^{-1} would not have much significant effects on the tensile strength of the reinforcing
 290 bars. A dynamic increase factor (DIF) can be used to estimate the increase in concrete
 291 compressive strength under the range of strain rate recorded from the impact tests. The value

292 of DIF may be estimated with the use of Equation (1) for strain rate $\dot{\epsilon}_c$ of less than 30 s^{-1} as
 293 recommended by Comit Euro-Internationale du Beton (1993). Equation (1) alongside another
 294 expression for $\dot{\epsilon}_c$ of larger than 30 s^{-1} have been compared and verified based on some 30 sets
 295 of test results which were collected and compiled by Bischoff and Perry (1991) from the
 296 literature. In the current study, the increase in compressive strength of concrete due to strain
 297 rate effect was estimated to be between 17 to 20 %. The effects of such a minor change in the
 298 compressive strength of concrete on the impact generated deflection behaviour of the wall can
 299 be neglected.

$$\frac{f'_{cd}}{f'_c} = \left(\frac{\dot{\epsilon}_c}{30 \times 10^{-6}} \right)^{1.026\alpha} \quad (1a)$$

$$\alpha = \frac{1}{5 + \frac{9f'_c}{10}} \quad (1b)$$

300 For Test #9-12, the steel plate was removed from the specimen and photographs were taken at
 301 the point of contact after each test to document the localised damage (Figure 12). This localised
 302 damage was minor and was generally limited to only minimal surface cracks at the vicinity of
 303 impact with indentation depths of less than 4 mm. No spalling of concrete, perforation or
 304 penetration were observed.

305 **Figure 12 Localised cracks developed at vicinity of impact from Test #9-12**

The velocity of impact can be inferred from images taken from the HSC. The measured velocity values of impact (v_0) are listed in Table 3 alongside calculated values (based on principles of conservation of energy for a given height of release, i.e. $0.5mv_0^2 = mgH$). Discrepancies between the two sets of results are shown to be minor (within 5%). The velocity of the impactor object on re-bounce (v_1) have also been obtained from a similar manner to provide an estimate of energy loss occurring over the course of the impact. It was observed that the impactor either did not rebound at all but instead brought to a stop or pounding on the wall, and bouncing off from it, multiple number of times. It is noted that such repetitive re-bounce behaviour was immaterial to the deflection demand behaviour of the wall as the wall always deflected to the maximum extent at the first strike when measurement was taken.

Table 3 Velocities prior to and following impact

Test #	H (m)	Calculated v_0 (m/s)	Measured v_0 (m/s)	v_1 (m/s)
1	0.2	1.98	1.93	0
2	0.5	3.13	3.08	-0.26
3	0.9	4.20	4.17	-0.57
4	1.4	5.24	5.18	-0.92
5	0.129	1.59	1.55	-0.17
6	0.322	2.51	2.48	-0.34
7	0.579	3.37	3.66	-0.69
8	0.2	1.98	1.91	-0.1
9	0.2	1.98	1.93	-0.17
10	0.5	3.13	3.08	-0.34
11	0.9	4.2	4.26	-0.34
12	1.4	5.24	5.1	-0.6

Some key experimental results are summarised and listed in Table 4. Note that the maximum compressive strain in concrete and maximum curvature at the base of wall were inferred from measurements of the strain gauges.

Table 4 Summary of Experimental Results

Test #	H (m)	Impactor Mass (kg)	Actual Impact Energy (kJ)	Maximum Wall Deflection (mm)	Contact Force (kN)	Maximum Tensile Strain in Reinforcement	Maximum Compressive Strain in Concrete	Maximum Curvature at Base (rad/m)
1	0.2	280	0.52	4.0	623	0.0007	0.0009	0.010
2	0.5	280	1.33	5.7	931	0.0010	0.0012	0.013
3	0.9	280	2.43	8.9	1208	0.0015	0.0015	0.018
4	1.4	280	3.76	12.0	1485	0.0020	0.0018	0.022
5	0.129	435	0.52	5.9	418	0.0010	0.0011	0.012
6	0.322	435	1.34	9.5	800	0.0017	0.0015	0.018
7	0.579	435	2.91	13.0	1121	0.0021	0.0017	0.023
8	0.2	280	0.51	5.2	511	0.0009	0.0010	0.011
9	0.2	280	0.52	5.2	315	0.0009	0.0010	0.011
10	0.5	280	1.33	8.2	533	0.0014	0.0013	0.016
11	0.9	280	2.54	11.5	695	0.0019	0.0016	0.020
12	1.4	280	3.64	14.4	799	0.0023	0.0017	0.023

3 Predictions of Deflection and Bending Behaviour of Wall

3.1 Displacement-based Analytical Model

A displacement-based (DB) model developed by the authors was used to predict the performance behaviour of the reinforced concrete barrier when subjected to the impact of a boulder on the cantilevered wall causing it to deflect and bend. The model was derived by the authors based on fundamental principles of energy and momentum. Analytical expressions for predicting the displacement demand of the impact have until now only been verified by impact on miniature models made of steel or wooden materials (refer Ali *et al.* (2014), Lam and Gad (2016), Lam *et al.* (2018b), Yang *et al.* (2012)). For the design of a RC barrier walls, which are expected to respond within the elastic limit, the model takes the form of Equation (2).

$$\Delta = \frac{mv_0^2}{\sqrt{mk_{eff}}} \sqrt{\lambda \left(\frac{1 + \text{COR}}{1 + \lambda} \right)^2} \quad (2)$$

For an impact scenario defined by the boulder mass (m) and impact velocity (v_0), the remaining input parameters to Equation (2) to be determined are the mass ratio (λ), coefficient of restitution (COR) and cracked stiffness (k_{eff}) of the stem wall. In the scenario where the barrier is struck by a boulder at an oblique angle θ , v_0 is taken as the horizontal component of the actual boulder velocity (v), i.e. $v_0 = v \times \cos \theta$. Parameter λ defines the ratio of the generalised mass of the target (λm) to the mass of the impactor (m). The value of λm may be taken as a quarter of the mass of the stem wall based on established structural dynamics principles (Ali *et al.* 2014, Sun *et al.* 2016). This was derived based on the shape profile of a cantilevered wall, and will remain unaffected by crack formation as long as the limit of yield has not been surpassed. The expression of Equation (3) for determining the value of the COR parameter is based on Newton's impact hypothesis.

$$COR = \frac{v_1 + v_2}{v_0} \quad (3)$$

where v_1 is the velocity of the boulder on re-bounce from the wall surface, and v_2 is the velocity of the idealised lumped mass representing the responding stem wall. The value of v_2 can be calculated using Equation (4) which is based conservation of momentum principles.

$$v_2 = \frac{v_0 + v_1}{\lambda} \quad (4)$$

It is important to note that the model is applicable to fully cracked RC walls that remain elastic (i.e. model is applicable for $M_{cr} < M < M_y$). If the impactor is not expected to crack the wall ($M < M_{cr}$), k_{eff} can simply be based on the gross stiffness k_g to provide a more accurate deflection estimate. Calculation for the value of the k_{eff} parameter representing the stiffness properties of the stem wall will be covered in detail in Section 3.2.

It is assumed in the model that the steel bars across the length of the wall are subject to uniform tensile stress and strain. The effective length of the wall is taken to be twice the height of the stem wall (measured above the base of the footing) based on a distribution angle of 45 degree. The real behaviour of the wall is more complicated than that portrayed by the model in the sense that the tensile stresses and strains vary approximately linearly across the length of the wall reaching a maximum value at the location where the impactor strikes. The proposed model is found on the premise of providing a reasonably accurate estimate of the maximum level of stress that is experienced by the wall responding at its centreline when responding to the impact action. Refer schematic diagram of Figure 13 which illustrates the modelling concept.

A series of numerical simulations have been carried out by the author using program LS-DYNA (details reported by Yong (2019)). It has been found that the strain distribution pattern corresponds

to an angle of distribution of 45 degree approximately. Importantly, the numerically simulated maximum tensile strain is close to estimates by the proposed analytical model which is based on uniform strain assumption. In a subsequent parametric study, the numerical simulations were repeated for the same stem wall but with the ratio of the reinforcement content in the horizontal to vertical direction (H:V) varying between 1:1 to 1:4. The difference in the strain distribution was shown to be minor. The H:V ratio of the reinforcement content has therefore not been incorporated as a design parameter in the analytical model. Consequently, the calculation procedure described herein may be adopted irrespective of the H:V ratio of the reinforcement.

Figure 13 Distribution of tensile strain across the length of the stem wall at the base

3.2 Cracked Bending Stiffness of Reinforced Concrete Stem Wall

The expression of Equation (5) for calculating the bending stiffness of a cracked reinforced concrete stem wall based on structural dynamics principles is identical to the expression for calculating the static stiffness of a cantilever member.

$$k_{eff} = \frac{3EI_{eff}}{h^3} \quad (5)$$

An important assumption with the calculated value of k_{eff} (and hence EI_{eff}) is that it represents the stiffness of the entire reinforced concrete wall. In fact, this only holds true if the cracks formed on the concrete are well distributed, as shown in the schematic diagram of Figure 14 (a) and further discussed in Menegon *et al.* (2018). It has been shown in the literature that lightly reinforced concrete section can result in undesirable displacement behaviour as distributed cracks cannot be developed (Hoult *et al.* 2017, Lu 2017), as shown in Figure 14 (b). Menegon *et al.* (2018) proposed the minimum reinforcement values summarised in Table 5 to ensure a desirable formation of distributed cracks. The recently revised 2018 version of the Australian concrete standard, AS 3600 (Standards Australia 2018) has included similar minimum reinforcement values to ensure distributed cracking in scenarios where a ductile response is required. The Grade N40 RC specimen presented in Section 2 had reinforcement content of approximately 1.3 % and hence the minimum reinforcement requirement has been met.

Figure 14 Plastic hinge models for RC walls (Menegon *et al.* 2018)

Table 5 Minimum reinforcement ratio to ensure distributed cracking in RC walls (Menegon *et al.* 2018)

Concrete Grade*	Minimum Reinforcement Ratio (%)
N32	0.7
N40	0.8
N50	0.9
N65	1.0

*the concrete grade designation is based on Australian convention because Menegon *et al.* (2018) reports the results of investigation undertaken in Australia

Given that the height of the stem wall (h) is readily known, the only remaining input parameter to Equation (5) is the wall flexural rigidity (El_{eff}). Note that subscript *eff* denotes cracked concrete. Three methods may be used for calculating the value of El_{eff} :

1. Method 1 - by moment-curvature analysis which is executable using program *Response 2000* (Bentz 2000).
2. Method 2 - moment-curvature analysis by fibre-element analysis which can be implemented on an Excel spreadsheet as proposed by Lam *et al.* (2011).
3. Method 3 - Simplified method of calculation employing Equations (6) to (8). Equation (7) was derived by Priestley *et al.* (2007) based on extensive moment-curvature analyses carried out on lightly (axially) loaded structural element which is consistent to the conditions of the stem wall of a rockfall barrier.

$$M_y = \phi M_u = 0.8 A_{st} f_y (0.9d) \quad (6)$$

$$\phi_y = \frac{1.7 \varepsilon_{sy}}{D} \quad (7)$$

$$EI_{eff} = \frac{M_y}{\phi_y} \quad (8)$$

As shown in Figure 15, curves showing the moment-curvature relationships as calculated from method nos. 1 and 2 are in very good agreement. The values of M_y and ϕ_y were found to be 376 kNm and 0.023 rad/m respectively. The slope representing the initial stiffness in the bi-linear model may be taken as the value of the parameter EI_{eff} . It has been found from sensitivity analyses undertaken by the authors that the moment-curvature behaviour of a lightly-loaded wall is insensitive to changes in the grade of concrete nor its Young's modulus.

Figure 15 Moment-curvature relationship with bi-linear line of best fit

When applying method no. 3, parameters required for input into Equations (6) – (8) may be taken from values listed in Table 6. The values of M_y and ϕ_y can be calculated by substituting the listed values into Equations (6) and (7) respectively. The resulting value of EI_{eff} is then compared with that obtained from Figure 15 alongside values of k_{eff} as listed in Table 7. Values of EI_{eff} and k_{eff} as derived from the alternative methods of calculation have been

found to be in very good agreement (refer Table 7). Results presented herein will be used in analyses presented in the later part of the paper.

Table 6 Parameters required for Equations (6) and (7)

Parameters	Values
Section Depth, D	230 mm
Wall Length, B	3000 mm
Reinforcement Arrangement	N20-200
Cover	30 mm
d^*	170 mm
Tensile Bar Area, A_{st}	4712 mm ²
Yield Strength, f_y	543 MPa
Yield Strain, ϵ_{sy}	0.0028
Concrete Strength, f'_c	47 MPa

* d is defined as the distance between the compressive surface of concrete and the centre of tensile reinforcing bar

Table 7 Comparison of EI_{eff} and k_{eff} values calculated from different methods

Parameters	Figure 15	Equations (6) – (8)
EI_{eff} (kNm ²)	16176	15139
k_{eff} (kN/m)	14379	13457

3.3 Comparison of Predictions from the Proposed Model with Experimental Measurements

All input parameters into the model are dependent on the impact scenario except for the value of the k_{eff} parameter which may be taken as constant: $k_{eff} = 14379$ kN/m across all scenarios. These input parameters to Equation (2) are listed in Table 8. For Test #1 to #8, the mass of the protective steel plate (62.8 kg) is considered to be part of the “target”. The value

of COR was calculated using Equation (3) and the velocity of impactor inferred from the HSC. The predicted maximum deflection values of the stem wall as calculated using the analytical solution of Equation (2) are compared with experimental measurements (refer Figure 16).

Table 8 Input parameters to Equation (2)

Test #	m (kg)	λm (kg)	λ	v_0 (m/s)	v_2 (m/s)	COR
1	280	683.8	2.44	1.93	0.79	0.41
2	280	683.8	2.44	3.08	1.15	0.29
3	280	683.8	2.44	4.17	1.47	0.22
4	280	683.8	2.44	5.18	1.74	0.16
5	435	683.8	1.57	1.55	0.88	0.46
6	435	683.8	1.57	2.48	1.36	0.41
7	435	683.8	1.57	3.66	1.89	0.33
8	280	683.8	2.44	1.91	0.74	0.34
9	280	621	2.22	1.93	0.79	0.32
10	280	621	2.22	3.08	1.24	0.29
11	280	621	2.22	4.26	1.77	0.34
12	280	621	2.22	5.1	2.03	0.28

In Figure 16, a sample of the maximum deflection value as calculated from the proposed model is shown as a straight line when overlaid on a graph in which the time-history of the deflection of the stem wall is presented. The maximum values of the deflection as obtained from calculation and from experimental measurements are then compared in the form of a bar chart as shown in Figure 17, and they are shown to be in good agreement. Over-predictions can be seen in Test #1 and #2 in which case the stem wall was not fully cracked, and yet the calculations were based on the assumption of a fully cracked wall (with stiffness equal to k_{eff}). In a follow-up test (Test #8) repeating the same impact scenario (as Test #1) on a fully cracked wall, the calculated maximum deflection value was in much better agreement with the recorded value.

Figure 16 Comparison of deflection recorded from experiment (Test #8) and calculated from Equation (2)

Figure 17 Maximum deflection recorded from experiments across all the tests in comparison with estimation by use of Equation (2)

3.4 Estimation of Maximum Tensile Reinforcement Strain

Given that the value of the yield curvature (ϕ_y) of the stem wall has been calculated in Section 3.2, being 0.023 rad/m, the value of the yield deflection (Δ_{yi}) can be estimated using Equation (9), being 12.1 mm. Note that h_i refers to the height of impact measured from the base of the wall (i.e. 1.25 m), and hence Δ_{yi} corresponds to the yield deflection at the same height. Yield deflection at the top of the wall (Δ_y) can then be estimated based on fundamental mechanics of material as presented by Equation (10), being 15.7 mm.

$$\Delta_{yi} = \frac{\phi_y h_i^2}{3} \quad (9)$$

$$\Delta_y = \Delta_{yi} \left(\frac{3h - h_i}{2h_i} \right) \quad (10)$$

The maximum strain ε_s of the tensile reinforcement may be linearly correlated with the maximum deflection of the wall as shown by Equations (11) and (12) in which the limit of yield (ε_{sy}) can be taken as 0.0028 (refer Section 2.1).

$$\frac{\varepsilon_s}{\varepsilon_{sy}} = \frac{\Delta}{\Delta_y} \quad (11)$$

$$\varepsilon_s = \varepsilon_{sy} \times \frac{\Delta}{\Delta_y} \quad (12)$$

457 By substituting the deflection values calculated from Section 3.3 into Equation (12), the value
 458 of ε_s for each test can be estimated by the presented analytical model. The calculated strain
 459 value is shown by a straight line when overlaid on a chart presenting experimental
 460 measurements from a row of strain gauges positioned at the base of the stem wall across its
 461 length (refer Figure 18 for a sample display of maximum strains recorded from the array of
 462 strain gauges). The maximum experimentally recorded strain value for each test is then
 463 compared with the respective analytically predicted value in the form of a bar chart
 464 demonstrating good agreement consistently across many tests (Figure 19). Where there are
 465 discrepancies the errors are always on the safe side.

Figure 18 Tensile reinforcement strains recorded from experiment (Test # 8) in comparison with estimation by use of Equation (12)

Figure 19 Maximum tensile reinforcement strains recorded from experiments across all the tests in comparison with estimation by use of Equation (12)

3.5 Contact Force vs Quasi-static Force

The term “contact force” refers to the force developed at the point of contact between the impactor object and the surface of the target, and is not to be confused with the term “quasi-static force” (or “reaction force”) which is defined as the force to emulate the maximum deflection demand of the impact. The quasi-static force (or reaction force) can be obtained by multiplying the wall deflection measured from the experiment by the estimated flexural stiffness of the wall (refer Section 3.2). An example (Test #1) of comparison between contact force and quasi-static force is shown in Figure 20. It is shown in the comparison that the amount of contact force delivered by the impactor is an order of magnitude larger than the actual reaction force experienced by the wall at its base, and at a much shorter duration. Similar observations can also be seen across all 12 tests, as demonstrated in Figure 21. The differences between the two types of forces is the result of a significant amount of inertia force that can be generated from within the wall when experiencing deflection in response to the impact action. Thus, applying contact force in a quasi-static manner to the target would give misleading predictions of the global response behaviour of the targeted structure. In summary, the analytical model proposed in Section 3.1 takes into account the effects of inertial resistance to accurately predict the global response behaviour of the target instead of the contact force.

Figure 20 Comparison of experimentally measured contact force and quasi-static force (Test #1)

Figure 21 Comparison of experimentally measured peak contact force and quasi-static force

4 Conclusions

This paper presents the findings and results of a recent experimental and analytical study into cantilevered reinforced concrete (RC) rock fall barriers. The experimental program consisted of a full-scale RC wall, which was struck with steel impactors of different sizes dropped from multiple heights. The results of the experimental program were used to validate a displacement-based (DB) method developed by the authors for predicting the impact induced flexural response of cantilevered RC walls. The main findings are summarised as follows:

1. An impact scenario cannot be defined by impact energy alone, since the ratio of the mass of the target and that of the impactor (λ) can have a significant influence on the outcome of the impact. Experimental results show that a heavier impactor with lower velocity and equivalent impact energy can result in a significantly higher deflection demand on the wall following impact.
2. The use of the cracked stiffness (i.e. k_{eff}) of the RC wall for calculating the deflection demand of the impact has been shown to give predictions that match reasonably well with experimental measurements.
3. The contact force delivered by the impact has been shown to be of much higher intensity (but lasts for a much shorter duration) than the quasi-static force, or reaction force. Thus, applying contact force on the cantilevered wall in a quasi-static manner to simulate the impact response could result in overpredicting the bending deformation of the wall.
4. The proposed DB model has been shown to provide accurate predictions of both the maximum horizontal deflection of the stem wall and the maximum tensile strain of the vertical reinforcement in the wall.

506 **5 Funding Information**

507 This work was supported by the Australian Research Council (ARC) Discovery Project (DP)
508 entitled *New Approach for Design of Barriers For Impact* [grant numbers DP170101858].

509 **6 Notation**

510 The following notations were used in this paper:

A_{st}	=	total area of reinforcement at tensile side
B	=	wall length
COR	=	coefficient of restitution
d	=	distance between compressive surface of concrete and centre of tensile bar
D	=	depth of concrete section
El_{eff}	=	effective flexural rigidity of cracked concrete
f'_c	=	concrete strength
f'_{cd}	=	dynamic concrete strength
f_y	=	tensile strength of reinforcement
g	=	gravitational acceleration
h	=	wall height
h_i	=	impact height
H	=	release height of impactor
k_{eff}	=	effective cracked stiffness
k_g	=	gross stiffness
m	=	impactor's mass
M_{cr}	=	cracking moment
M_u	=	ultimate moment capacity
M_y	=	yield moment capacity
v	=	impact velocity at an oblique angle to barrier
v_0	=	impact velocity
v_1	=	velocity of impactor on rebound in opposite direction
v_2	=	velocity of target following impact
Δ	=	maximum deflection of stem wall
Δ_y	=	deflection of stem wall at yield limit
Δ_{yi}	=	yield deflection at impact height
$\dot{\epsilon}_c$	=	concrete strain rate
ϵ_s	=	maximum tensile strain of reinforcement
ϵ_{sy}	=	yield strain of reinforcement
λ	=	ratio of target's generalised mass to impactor's mass
ϕ_y	=	yield curvature
θ	=	angle between direction of impact and target

511 7 References

- 512 Adeli, H., & Amin, A. M. (1985). Local effects of impactors on concrete structures. *Nuclear*
513 *Engineering and Design*, 88(3), 301-317.
- 514 Ahmed, E. A., Dulude, C., & Benmokrane, B. (2013). Concrete bridge barriers reinforced with
515 glass fibre-reinforced polymer: static tests and pendulum impacts. *Canadian Journal of Civil*
516 *Engineering*, 40(11), 1050-1059.
- 517 Ali, M., Sun, J., Lam, N., Zhang, L., & Gad, E. (2014). Simple hand calculation method for
518 estimating deflection generated by the low velocity impact of a solid object. *Australian Journal*
519 *of Structural Engineering*, 15(3), 243-259.
- 520 American Association of State Highway and Transportation Officials. (2012). AASHTO
521 LRFD Bridge Design Specifications, 6th edition. Washington DC, U.S.
- 522 Aminata, D., Yashima, A., Sawada, K., Sung, E., Sugimori, K., & Inoue, S. (2008). New
523 Protection Wall Against Rockfall Using a Ductile Cast Iron Panel. *Journal of Natural Disaster*
524 *Science*, 30(1), 25-33.
- 525 ASTRA. (2008). Einwirkungen infolge Steinschlags auf Schutzgalerien (in German).
526 Richtlinie, Bundesamt für Strassen, Baudirektion SBB, Eidgenössische Drucksachen-und
527 Materialzentrale, Bern.
- 528 Austroads. (2013). *Standardised Bridge Barrier Design*. Sydney: Austroads Ltd.
- 529 Ben-Dor, G., Dubinsky, A., & Elperin, T. (2006). Modeling of High-Speed Penetration Into
530 Concrete Shields and Shape Optimization of Impactors. *Mechanics Based Design of Structures*
531 *and Machines*, 34(2), 139-156.
- 532 Bentz, E. C. (2000). *Sectional analysis of reinforced concrete members*: University of Toronto
533 Toronto.
- 534 Berner, K. (1981). Der Einfluss der Dehngeschwindigkeit auf das mechanische Verhalten von
535 Betonstählen, 12. *Forschungskolloquium des Deutschen Ausschusses für Stahlbeton, BAM,*
536 *Berlin*.
- 537 Bischoff, P. H., & Perry, S. H. (1991). Compressive behaviour of concrete at high strain rates.
538 *Materials and Structures*, 24(6), 425-450.
- 539 Chen, Y., & May, I. M. (2009). Reinforced concrete members under drop-weight impacts.
540 *Proceedings of the ICE - Structures and Buildings*, 162(1), 45-56.
- 541 Comite Euro-Internationale du Beton. (1993). CEB-FIP model code 1990. *Bulletin*
542 *d'Information*(213-214).

543 Dancygier, A. N., Yankelevsky, D. Z., & Jaegermann, C. (2007). Response of high
544 performance concrete plates to impact of non-deforming projectiles. *International Journal of*
545 *Impact Engineering*, 34(11), 1768-1779.

546 El-Salakawy, E., Brière, F., Masmoudi, R., & Benmokrane, B. (2002). *Impact Test of GFRP*
547 *Reinforced Concrete Bridge Barriers with New Non-Metallic Connection*. Paper presented at
548 the 4th Structural Specialty Conference of the Canadian Society for Civil Engineering,
549 Montréal, Canada.

550 Eurocode 1. (2008). Eurocode 1 - Actions on structures - Part 1-7: General actions - accidental
551 actions (S.P. Committee, Ed.). London: European Committee for Standardization.

552 Fujikake, K., Li, B., & Soeun, S. (2009). Impact Response of Reinforced Concrete Beam and
553 Its Analytical Evaluation. *Journal of Structural Engineering*, 135(8), 938-950.

554 Heckötter, C., & Vepsä, A. (2015). Experimental investigation and numerical analyses of
555 reinforced concrete structures subjected to external missile impact. *Progress in Nuclear Energy*,
556 84, 56-67.

557 Hoult, R., Goldsworthy, H., & Lumantarna, E. (2017). Plastic Hinge Length for Lightly
558 Reinforced Rectangular Concrete Walls. *Journal of Earthquake Engineering*, 1-32.

559 Hu, K., Wei, F., Hong, Y., & Li, X. (2006). Field measurement of impact force of debris flow.
560 *Yanshilixue Yu Gongcheng Xuebao/Chinese Journal of Rock Mechanics and Engineering*, 25,
561 2813-2819.

562 Hu, K., Wei, F., & Li, Y. (2011). Real-time measurement and preliminary analysis of debris-
563 flow impact force at Jiangjia Ravine, China. *Earth Surface Processes and Landforms*, 36(9),
564 1268-1278.

565 Hummeltenberg, A., Beckmann, B., Weber, T., & Curbach, M. (2011). Investigation of
566 concrete slabs under impact load. *Applied Mechanics and Materials*, 82, 398-403.

567 Japan Road Association. (2000). Manual for Anti-impact Structures against Falling Rock (in
568 Japanese).

569 Jiang, T., Grzebieta, R. H., & Zhao, X.-L. (2004). Predicting impact loads of a car crashing
570 into a concrete roadside safety barrier. *International journal of crashworthiness*, 9(1), 45-63.

571 Kishi, N., & Bhatti, A. Q. (2010). An equivalent fracture energy concept for nonlinear dynamic
572 response analysis of prototype RC girders subjected to falling-weight impact loading.
573 *International Journal of Impact Engineering*, 37(1), 103-113.

574 Kishi, N., Okada, S.-Y., & Kon-No, H. (2009). Numerical impact response analysis of rockfall
575 protection galleries. *Structural Engineering International*, 19(3), 313-320.

576 Kojima, I. (1991). An experimental study on local behavior of reinforced concrete slabs to
577 missile impact. *Nuclear Engineering and Design*, 130(2), 121-132.

578 Kwan, J. S. H. (2012). *Supplementary technical guidance on design of rigid debris-resisting*
579 *barriers (GEO Report No. 270)*. Retrieved from Geotechnical Engineering Office, the
580 Government of the Hong Kong Special Administrative Region:

581 Lam, C., Yong, A. C. Y., Kwan, J. S. H., & Lam, N. T. K. (2018a). Overturning stability of L-
582 shaped rigid barriers subjected to rockfall impacts. *Landslides*.

583 Lam, N., & Gad, E. (2016). *The estimation of impact forces based on first principles*. Paper
584 presented at the Australasian Structural Engineering Conference: ASEC 2016.

585 Lam, N., Wilson, J., & Lumantarna, E. (2011). Force-deformation behaviour modelling of
586 cracked reinforced concrete by EXCEL spreadsheets. *Computers and Concrete*, 8(1), 43-57.

587 Lam, N. T. K., Yong, A. C. Y., Lam, C., Kwan, J. S. H., Perera, J. S., Disfani, M. M., & Gad,
588 E. (2018b). Displacement-based approach for the assessment of overturning stability of
589 rectangular rigid barriers subjected to point impact. *Journal of engineering mechanics*, 144(2).

590 Levings, J., & Sritharan, S. (2012). Effects of Cold Temperature and Strain Rate on the Stress-
591 Strain Behavior of ASTM A706 Grade 420(60) Steel Reinforcement. *Journal of Materials in*
592 *Civil Engineering*, 24(12), 1441-1449.

593 Lu, Y. (2017). *Siesmic design of lightly reinforced concrete walls*. The University of Auckland.

594 Menegon, S. J., Wilson, J. L., Lam, N. T. K., & McBean, P. (2018). RC walls in Australia:
595 seismic design and detailing to AS 1170.4 and AS 3600. *Australian Journal of Structural*
596 *Engineering*, 19(1), 67-84.

597 Mougine, J. P., Perrotin, P., Mommessin, M., Tonnelo, J., & Agbossou, A. (2005). Rock fall
598 impact on reinforced concrete slab: an experimental approach. *International Journal of Impact*
599 *Engineering*, 31(2), 169-183.

600 Ng, C. W. W., Choi, C. E., Su, A. Y., Kwan, J. S. H., & Lam, C. (2016). Large-scale successive
601 boulder impacts on a rigid barrier shielded by gabions. *Canadian Geotechnical Journal*, 53(10),
602 1688-1699.

603 Othman, H., & Marzouk, H. (2016). An experimental investigation on the effect of steel
604 reinforcement on impact response of reinforced concrete plates. *International Journal of*
605 *Impact Engineering*, 88, 12-21.

606 Perera, S., Lam, N., Pathirana, M., Zhang, L., Ruan, D., & Gad, E. (2016). Deterministic
607 solutions for contact force generated by impact of windborne debris. *International Journal of*
608 *Impact Engineering*, 91, 126-141.

- 609 Perera, S., Lam, N., Pathirana, M., Zhang, L., Ruan, D., & Gad, E. (2017). Use of static tests
610 for predicting damage to cladding panels caused by storm debris. *Journal of Building*
611 *Engineering*, 12, 109-117.
- 612 Priestley, M. J. N., Calvi, G. M., & Kowalsky, M. J. (2007). *Displacement-Based Seismic*
613 *Design of Structures*. Pavia, Italy: IUSS Press.
- 614 Rostasy, F., Scheuermann, J., & Sprenger, K. (1984). Mechanical behaviour of some
615 construction materials subjected to rapid loading and low temperature. *Betonwerk+ Fertigteil-*
616 *Technik*, 50(6), 393-401.
- 617 Schmidt-Hurtienne, B. (2000). *Ein dreiaxiales Schädigungsmodell für Beton unter Einschluss*
618 *des Dehnrateneffekts bei Hochgeschwindigkeitsbelastung*: Inst. für Massivbau und
619 Baustofftechnologie.
- 620 Standards Australia. (2004). AS5100.2 Bridge Design Part 2: Design Loads. New South Wales,
621 Australia.
- 622 Standards Australia. (2007). AS 1379 Specification and supply of concrete. New South Wales,
623 Australia.
- 624 Standards Australia. (2018). AS 3600 Concrete structures. New South Wales, Australia.
- 625 Standards Australia, & Standards New Zealand. (2001). AS/NZS 4671 Steel reinforcing
626 materials. New South Wales, Australia and Wellington, New Zealand.
- 627 Su, Y., Chen, R., Hong, Y., Song, D., Qiao, J., & Ng, C. W. W. (2015). *Pilot study of*
628 *cushioning effects of gabions and other impact absorption materials subject to dynamic impact*
629 *load*. Retrieved from Hong Kong:
- 630 Sun, J., Lam, N., Zhang, L., Gad, E., & Ruan, D. (2014). Contact forces generated by fallen
631 debris. *Structural Engineering and Mechanics*, 50(5), 589-603.
- 632 Sun, J., Lam, N., Zhang, L., Ruan, D., & Gad, E. (2016). Computer Simulation of Contact
633 Forces Generated by Impact. *International Journal of Structural Stability and Dynamics*.
634 Retrieved from doi:10.1142/S0219455417500055
- 635 Tachibana, S., Masuya, H., & Nakamura, S. (2010). Performance based design of reinforced
636 concrete beams under impact. *Natural Hazards and Earth System Science*, 10(6), 1069-1078.
- 637 Tamagna, A., & Riera, J. (1993). *Dynamics load penetration functions for impact analysis*.
638 Paper presented at the Transactions of the 12. international conference on Structural Mechanics
639 in Reactor Technology (SMiRT). Volume J: Structural dynamics and extreme loads analysis.
- 640 Tamagna, A., & Riera, J. D. (1998). Low speed penetration in solids. *Nuclear Engineering and*
641 *Design*, 179(2), 125-133.

- 642 Yang, Y., Lam, N. T. K., & Zhang, L. (2012). Evaluation of simplified methods of estimating
643 beam responses to impact. *International Journal of Structural Stability and Dynamics*, 12(3),
644 1250016-1250011-1250016-1250024.
- 645 Yong, A. C. Y. (2019). *Impact-resistance of Reinforced Concrete Structures*.
- 646 Zhan, T., Wang, Z., & Ning, J. (2015). Failure behaviors of reinforced concrete beams
647 subjected to high impact loading. *Engineering Failure Analysis*.
- 648 Zhang, M. H., Shim, V. P. W., Lu, G., & Chew, C. W. (2005). Resistance of high-strength
649 concrete to projectile impact. *International Journal of Impact Engineering*, 31(7), 825-841.
- 650 Zhang, S. (1993). A comprehensive approach to the observation and prevention of debris flows
651 in China. *Natural Hazards*, 7(1), 1-23.
- 652 Zineddin, M., & Krauthammer, T. (2007). Dynamic response and behavior of reinforced
653 concrete slabs under impact loading. *International Journal of Impact Engineering*, 34(9), 1517-
654 1534.
655

Minerva Access is the Institutional Repository of The University of Melbourne

Author/s:

Yong, ACY;Lam, NTK;Menegon, SJ;Gad, EF

Title:

Experimental and Analytical Assessment of Flexural Behavior of Cantilevered RC Walls Subjected to Impact Actions

Date:

2020-04

Citation:

Yong, A. C. Y., Lam, N. T. K., Menegon, S. J. & Gad, E. F. (2020). Experimental and Analytical Assessment of Flexural Behavior of Cantilevered RC Walls Subjected to Impact Actions. Journal of Structural Engineering, 146 (4), pp.04020034-04020034. [https://doi.org/10.1061/\(asce\)st.1943-541x.0002578](https://doi.org/10.1061/(asce)st.1943-541x.0002578).

Persistent Link:

<http://hdl.handle.net/11343/247735>