Mn₁₃-clusters based coordination polymer as co-catalyst of CdS for enhanced visible-light driven H₂ evolution

Received 00th January 20xx,
Accepted 00th January 20xx

Tian Wen^a, Lei Zhang^{a*} and Wolfgang Schmitt^b

DOI: 10.1039/x0xx00000x

www.rsc.org/

A coordination cluster-based polymer was used for the first time as a noble-metal-free co-catalyst of CdS, giving rise to significantly enhanced photocatalytic H₂ production. This work demonstrates the feasibility of cluster materials in assembling highly-active and low-priced photocatalysts.

Photocatalytic water-splitting H₂ production is considered to be a promising solution for the global energy and environmental crisis. In the past decades, semiconductor photocatalysts, especially metal sulfides (e.g. CdS), have been intensively studied due to advantageous characteristics such as low cost, facile preparation and excellent visible light response.¹⁻⁵ Despite some tremendous achievements, the activities and applications of pure metal sulfides are still greatly obstructed due to the fast recombination of photogenerated electron-hole pairs. To overcome this shortage, the use of co-catalyst composites has proven to be a successful method for improving the efficiency and stability of semiconductor photocatalysts.⁶⁻⁹ However, the most active H₂ evolution co-catalysts are usually expensive and involve scarce noble metals (e.g. Pt), greatly limiting the practical applications of these photocatalytic systems. Therefore, the development of inexpensive and active co-catalysts remains a great challenge for the future to establish large-scale photocatalytic H₂ production.

Recently, several earth-abundant co-catalyst systems for the semiconductor-based H₂ evolution have been studied, involving transition metal oxides, sulfides and carbides.¹⁰⁻¹³ Especially, in the use of porous materials and assemblies of titanium-oxo clusters can also greatly increase the CdS-derived H₂ production.¹⁴⁻¹⁶ On the other hand, inspired by the catalytically active Mn₄CaO₅ cubane cluster in the PS II, several Mn-oxo complexes have been investigated as photocatalysts

to promote the water oxidation reaction to produce O₂.¹⁷ However, to the best of our knowledge the application of Mn-oxo clusters as co-catalyst for H₂ production has not yet been investigated.

Scheme 1 The illustration of idealized assembly of the Mn₁₃-polymer/CdS composites. Red, O; green, P; Gray, C; Blue, N; Pink, Mn.

In this work, to explore the use of a new earth-abundant co-catalysts for hydrogen evolution from H₂O, we loaded CdS nanoparticles to a porous Mn₁₃-cluster based coordination polymer and tested the corresponding photocatalytic performances (Scheme 1).¹⁸ The main reasons of selecting this Mn₁₃-type material are as following: i) This coordination polymer is highly porous and characterised by large voids (and defined hydrophilic channels) (Figure S2); ii) the Mn₁₃ building units present labile Jahn–Teller sites that can be used for guest exchange (possible water absorption); iii) the red/brown-coloured crystals of the Mn₁₃-polymer may further increase the efficiency of the visible light absorption; iv) the Mn₁₃-polymer containing distinctive, well-distributed electronegative atoms (P, N) might facilitate enhanced electronic coupling with the CdS particles. Prior to the catalytic test reactions, the obtained Mn₁₃-polymer/CdS composites were well characterized by transmission electron microscopy (TEM) and related photochemical analysis. In comparison to pure CdS catalysts under visible-light irradiation, these composite catalysts displayed significantly enhanced H₂ evolution activity. Further the activity is dependent on the loaded Mn₁₃-polymer amount whereby samples that contain 7 wt% Mn₁₃-polymer give highest H₂ production reaching values of 3600 μmol h⁻¹ g⁻¹.

^a School of Chemistry, The University of Melbourne, Parkville, Victoria 3010, Australia. E-mail: lei.zhang1@unimelb.edu.au

^b School of Chemistry & CRANN, University of Dublin, Trinity College, Dublin 2, Ireland.

Electronic Supplementary Information (ESI) available: Materials, synthesis and physical measurements. See DOI: 10.1039/x0xx00000x

In the crystal structure of the selected Mn₁₃-polymer, the 1D chains with positive charges assembled from Mn₁₃-oxo clusters and 4,4'-trimethylenedipyridine ligands are packed together to form porous architecture.¹⁸ It has been already well established that such supramolecular channels can be used for guests pass ways (Figure S2). A simple and effective mechanical grinding method was then applied involving a freshly produced Mn₁₃-polymer and CdS nanoparticles to produce effective catalysts for the photocatalytic H₂-production. Firstly, the successful synthesis of the CdS nanoparticles (NPs) was corroborated by the TEM and powder X-ray diffraction (PXRD) analyses (Figures S3-4). Then, the pristine samples of the Mn₁₃-polymer and CdS were mixed in an agate mortar and grinded for *ca.* 30 min (see ESI for details). The high resolution TEM images (Figure 1a), energy dispersive X-ray (EDX) spectra (Figure S5) and EDX elemental mapping images (Figure 1c) of the finer fraction imply that the Mn₁₃-polymer was successfully loaded onto the surface of the CdS nanoparticles *via* electrostatic interactions to give homogeneous samples of Mn₁₃-polymer/CdS.

Figure 1 (a) HRTEM image of CdS nanoparticles. (b) The typical TEM image of samples of Mn₁₃-polymer/CdS. (c) The EDX mapping images of samples of Mn₁₃-polymer/CdS.

The photocatalytic water-splitting H₂ production experiments were performed using a white-light emitting-diode (LED) as the light source and Mn₁₃-polymer/CdS composites as catalysts at room temperature, along with triethanolamine (TEOA 16 vol.%) as sacrificial reagent, respectively. For comparative studies, samples with various Mn₁₃-polymer loadings were applied. Remarkably, the coupling of the Mn₁₃-polymer with CdS indeed leads to an enhancement in the photocatalytic activity. As displayed in Figure 2a, pristine CdS showed a very low photocatalytic activity, producing 680 $\mu\text{mol h}^{-1} \text{g}^{-1}$ of H₂. When a small quantity of the Mn₁₃-polymer (2.4 wt.%) was loaded, the H₂ production was greatly increased to 1090 $\mu\text{mol h}^{-1} \text{g}^{-1}$. Then,

by increasing the loading of Mn₁₃-polymer, the photocatalytic activities of the obtained Mn₁₃-polymer/CdS samples were gradually enhanced. Using the optimal loading of 7.0 wt% Mn₁₃-polymer, the corresponding Mn₁₃-polymer/CdS composite gave the highest photocatalytic H₂ production rate of 3600 $\mu\text{mol h}^{-1} \text{g}^{-1}$, exceeding about 5 times that of bare CdS.

It has been recently proven that the hetero-structured photocatalysts could successfully enhance the activity for H₂ production by binding different building blocks through electrostatic interactions.¹⁹⁻²⁴ Therefore, the superior activity of the investigated Mn₁₃-polymer/CdS composites may be ascribed to the combination between CdS and Mn₁₃-polymer, which greatly facilitates a rapid interfacial charge transfer. Interestingly, a further increase in the loading of the Mn₁₃-polymer leads to an obvious decrease of the photocatalytic activity. It is noteworthy that the pure Mn₁₃-polymer displayed no activity towards H₂ production, whilst its PXRD pattern remained unchanged under the corresponding experimental conditions, highlighting the stability of the co-catalyst under visible light illumination (Figure S1). So, one can expect that excess Mn₁₃-polymer co-catalysts blocks the active surface sites and impedes the light absorption of the CdS catalyst. Moreover, the obtained Mn₁₃-polymer/CdS composites are characterized by relatively high photocatalytic stability (Figure 2b). These results suggest that the Mn₁₃-polymer is an excellent co-catalyst for CdS in order to significantly promote its photocatalytic H₂ production.

Figure 2 (a) Mn₁₃-polymer loading amount dependent photocatalytic H₂ evolution activities of Mn₁₃-polymer/CdS. (b) Stability test of 7 wt% Mn₁₃-polymer/CdS with prolonged visible light irradiation for 9 h.

To further characterize the obtained Mn₁₃-polymer/CdS catalysts and get some mechanistically insights into the above described H₂ production, additional photochemical studies were carried out. Firstly, the light harvesting capability of the CdS nanoparticles, the Mn₁₃-polymer, and their composites were tested by the UV-Vis diffuse reflectance spectroscopy (Figure 3a). The fresh Mn₁₃-polymer showed strong light absorption between 400–800 nm. Thus, the light absorption characteristics of the Mn₁₃-polymer/CdS composites became more pronounced in the region of 550–800 nm in comparison to the pure CdS materials. However, the absorption edge of the Mn₁₃-polymer/CdS showed no significant shift compared to CdS, indicating that doping effects, whereby electron-rich non-metallic elements such as N, O and P are incorporated into the crystal structure of CdS, do not occur. Similar characteristics were also observed for various Mn₁₃-polymer loadings (Figure S6), thus confirming the structural stability of CdS in the catalyst composites. Further, electrochemical measurements and X-ray photoemission spectroscopy (XPS)

studies were carried out to investigate the charge separation and transfer. As can be seen from the polarization curves in Figure 3b, the Mn_{13} -polymer/CdS composite shows a remarkably smaller onset potential than CdS for electrocatalytic HER. Moreover, as compared to pure CdS, the Mn_{13} -polymer/CdS composite also features a smaller semicircle in electrochemical impedance spectroscopy (EIS; Figure 3c), indicating faster interfacial electron transfer. To achieve such rapid interfacial charge transfer between the Mn_{13} -polymer and CdS, the formation of strong electronic interactions is essential. The XPS spectrum of the Mn_{13} -polymer/CdS composite shows two peaks located at 406.61/411.35 eV, 160.90/162.02 eV attributed to the Cd $3d_{5/2}$ /Cd $3d_{3/2}$, S $2p_{3/2}$ /S $2p_{1/2}$, respectively. Clearly, these signals of Mn_{13} -polymer/CdS samples have been lowered by ca. 0.21–0.23 and 0.29–0.34 eV compared to pristine CdS samples, respectively, confirming relative strong electronic coupling between the Mn_{13} -polymer and the CdS nanoparticles (Figures S7–8). Thus, the direct electron transfer from CdS to Mn_{13} -polymer upon respective combination can be expected. It seems reasonable to assume that the *tert*-butylphosphonate and the 4,4'-trimethylenedipyridine ligands that locate at the periphery of the Mn_{13} -polymer interact with the CdS nanoparticles whereby electronegative atoms with lone pairs, e.g. the P and N atoms provide pathways for electron transport. Consequently, this strong electronic coupling arises from a weak electronic push-pull effect between the CdS and Mn_{13} -polymer components. This effect involving electronegative ligand-atoms may be further facilitated by complementary charges of the polymer and the surface charges of the CdS particles, thus contributing to the effective interfacial charge separation and transfer in the Mn_{13} -polymer/CdS system. Finally, transient photocurrent (TPC) spectra were applied to interpret the charge-carrier separation and transfer efficiency. As shown in Figure 3d, the TPC value was significantly increased after the Mn_{13} -polymer loading, further confirming that the efficiency of charge separation is greatly improved in the composite material.

Figure 3 (a) Ultraviolet-visible absorption spectra of CdS, Mn_{13} -polymer, and Mn_{13} -polymer/CdS. (b) Polarization curves of sample electrodes in 0.5M Na_2SO_4 solution. (c) EIS Nyquist plots of CdS and Mn_{13} -polymer/CdS electrodes measured under the open-circle potential and visible-light irradiation in 0.5M Na_2SO_4 . (d) The transient photocurrent responses of CdS and Mn_{13} -polymer/CdS electrodes in 0.2M Na_2S + 0.04M Na_2SO_3 mixed aqueous solution under visible-light irradiation.

In conclusion, for the first time, Mn coordination clusters have been applied as highly active noble-metal-free co-catalysts facilitating enhanced visible-light driven H_2 evolution in the presence of CdS. Taking the advantage of a convenient mechanical grinding strategy, a series of Mn_{13} -polymer/CdS composite catalysts were prepared. Interestingly, the combination of the Mn_{13} -polymer and CdS nanoparticles resulted in enhanced photocatalytic H_2 production activities which were highly dependent on the loading quantities of the Mn_{13} -polymer. It was also demonstrated that the photocatalytic activity of the Mn_{13} -polymer/CdS system stems from the intimate electrostatic interaction between the Mn_{13} -polymer and CdS NPs, thus facilitating efficient charge mobility. Therefore, this work highlights the potential of Mn coordination clusters as low-cost co-catalyst for the photocatalytic H_2 production. The presented system points towards alternatives to noble metal catalysts and highlights new opportunities for the construction of hetero-structural materials towards energy related applications.

This work is supported by the Australian Research Council (DE150100901). The authors also thank the Science Foundation Ireland (SFI; 13/IA/1896), the European Research Council (SURAMOL CoG 2014 – 647719).

Conflicts of interest

There are no conflicts of interest to declare

References

- 1 J. Ran, J. Zhang, J. Yu, M. Jaroniec and S. Z. Qiao, *Chem. Soc. Rev.*, 2014, **43**, 7787.
- 2 J. Ran, T. Y. Ma, G. Gao, X.-W. Du and S. Z. Qiao, *Energy Environ. Sci.*, 2015, **8**, 3708.
- 3 W.-J. Ong, L.-L. Tan, Y. H. Ng, S.-T. Yong and S.-P. Chai, *Chem. Rev.*, 2016, **116**, 7159.
- 4 Q. Wang, T. Hisatomi, Q. Jia, H. Tokudome, M. Zhong, C. Wang, Z. Pan, T. Takata, M. Nakabayashi, N. Shibata, Y. Li, I. D. Sharp, A. Kudo, T. Yamada and K. Domen, *Nat. Mater.*, 2016, **15**, 611.
- 5 P. Zhang, T. Wang, X. Chang and J. Gong, *Acc. Chem. Res.*, 2016, **49**, 911.6.
- 6 J. Yang, D. Wang, H. Han and C. Li, *Acc. Chem. Res.* 2013, **46**, 1900.
- 7 J. Chen, X.-J. Wu, L. Yin, B. Li, X. Hong, Z. Fan, B. Chen, C. Xue and H. Zhang, *Angew. Chem. Int. Ed.* 2015, **54**, 1210.
- 8 D. Zheng, X.-N. Cao, X. Wang, *Angew. Chem. Int. Ed.* 2016, **55**, 11512.
- 9 P. Zhang, T. Wang, X. Chang and J. Gong, *Acc. Chem. Res.* 2016, **49**, 911.
- 10 J. Ran, G. Gao, F.-T. Li, T.-Y. Ma, A. Du and S.-Z. Qiao, *Nat. Commun.*, 2017, **8**, 13907.
- 11 J. Ran, J. G. Yu and M. Jaroniec, *Green Chem.*, 2011, **13**, 2708.
- 12 Y. Zhou, L. Zhang, J. Liu, X. Fan, B. Wang, M. Wang, W. Ren, J. Wang, M. Li and J. Shi, *J. Mater. Chem. A*, 2015, **3**, 3862
- 13 F. Dong, Z. Zhao, T. Xiong, Z. Ni, W. Zhang, Y. Sun and W. K. Ho, *ACS Appl. Mater. Interfaces*, 2013, **5**, 11392.
- 14 Y. Liu, Q. P. Lin, Q. C. Zhang, X. H. Bu and P. Y. Feng, *Chem. Eur. J.* 2014, **20**, 8297.

- 15 D. W. Jing and L. J. Guo, *J. Phys. Chem. B* 2006, **110**, 11139.
- 16 Z. Q. Jiang, J. X. Liu, M. Y. Gao, X. Fan, L. Zhang and J. Zhang, *Adv. Mater.* 2017, **29**, 1603369.
- 17 H. J. M. Hou, *Materials* 2011, **4**, 1693.
- 18 L. Zhang, R. Clérac, C. I. Onet, M. Venkatesan, P. Heijboer and W. Schmitt, *Chem. Eur. J.*, 2012, **18**, 13984.
- 19 H. Wang, L. Zhang, Z. Chen, J. Hu, S. Li, Z. Wang, J. Liu and X. Wang, *Chem. Soc. Rev.*, 2014, **43**, 5234.
- 20 K. Chang, Z. Mei, T. Wang, Q. Kang, S. Ouyang and J. Ye, *ACS Nano*, 2014, **8**, 7078.
- 21 J. Hu, A. Liu, H. Jin, D. Ma, D. Yin, P. Ling, S. Wang, Z. Lin and J. Wang, *J. Am. Chem. Soc.*, 2015, **137**, 11004.
- 22 J. Chen, X.-J. Wu, L. Yin, B. Li, X. Hong, Z. Fan, B. Chen, C. Xue and H. Zhang, *Angew. Chem. Int. Ed.*, 2015, **54**, 1210.
- 23 Y. Chen, Shu Zhao, X. Wang, Q. Peng, R. Lin, Y. Wang, R. Shen, X. Cao, L. Zhang, G. Zhou, J. Li, A. Xia and Y. Li, *J. Am. Chem. Soc.*, 2016, **138**, 4286.
- 24 M. Liu, Y. Chen, J. Su, J. Shi, X. Wang and L. Guo, *Nat. Energy*, 2016, **1**, 16151.

Minerva Access is the Institutional Repository of The University of Melbourne

Author/s:

Wen, T;Zhang, L;Schmitt, W

Title:

A Mn₁₃-cluster based coordination polymer as a co- catalyst of CdS for enhanced visible-light driven H₂ evolution

Date:

2018-08-28

Citation:

Wen, T., Zhang, L. & Schmitt, W. (2018). A Mn₁₃-cluster based coordination polymer as a co- catalyst of CdS for enhanced visible- light driven H₂ evolution. DALTON TRANSACTIONS, 47 (32), pp.10857-10860. <https://doi.org/10.1039/c8dt01755g>.

Persistent Link:

<http://hdl.handle.net/11343/250812>