Aggregate Geometry Generation Method using a Structured Light 3D Scanner, Spherical Harmonics based Geometry Reconstruction and Placing Algorithms for Mesoscale Modelling of Concrete

**Petikirige Sadeep Madhushan Thilakarathna¹; Kasun Shanaka Kristombu Baduge^{2*},
Ph.D.; Priyan Mendis³, Ph.D.; Egodawaththa Ralalage Kanishka Chandrathilaka⁴,
Vanissorn Vimonsatit⁵, Ph.D.; Hyuk Lee⁶, Ph.D.**

¹Ph.D. Student, Dept. of Infrastructure Engineering, Univ. of Melbourne, Parkville, VIC 3052, Australia. Email:

pthilakarath@student.unimelb.edu.au

²Postdoctoral Research Fellow, Dept. of Infrastructure Engineering, Centre for Advanced Manufacturing of
Prefabricated Housing, Univ. of Melbourne, Parkville, VIC 3052, Australia (corresponding author). ORCID:

<https://orcid.org/0000-0001-5183-701X>. Email: kasun.kristombu@unimelb.edu.au

³Professor, Dept. of Infrastructure Engineering, Univ. of Melbourne, Parkville, VIC 3052, Australia. ORCID:

<https://orcid.org/0000-0003-4068-8201>. Email: pamendis@unimelb.edu.au

⁴Ph.D. Student, Dept. of Infrastructure Engineering, Univ. of Melbourne, Parkville, VIC 3052, Australia Email:

kegodawathth@student.unimelb.edu.au

⁵Associate Professor, School of Engineering, Macquarie University, Macquarie Park, NSW 2109, Australia. ORCID:

<https://orcid.org/0000-0002-6212-9446>. Email: sorn.vimonsatit@mq.edu.au

⁶Research Associate, School of Civil and Mechanical Engineering, Curtin University, Bentley, WA 6102, Australia.

ORCID: <https://orcid.org/0000-0002-7578-2049>. Email: Lee.Lee@curtin.edu.au

ABSTRACT

Mesoscale numerical modelling is an effective method of representing concrete as a three-phase material. Accurate aggregate geometry representation is an important aspect in numerical mesoscale modelling of concrete to predict mechanical properties as well as the damage initiation and fracture propagation. In this paper, a novel approach of 3D scanning of aggregates

26 using a structured light 3D scanner is presented and parametric geometry reconstruction of
27 aggregate geometries using spherical harmonics is carried out. This novel method of scanning
28 aggregates is a faster, safer, economical and a convenient method of obtaining the 3D geometry
29 compared with other methods. A comprehensive database of aggregate geometries is developed
30 and an innovative aggregate placing algorithm for these aggregates is presented to develop the
31 mesostructure. In addition to the proposed geometry generation method, a novel parametric
32 based geometry generation and distribution method for polyhedral aggregate shapes is
33 presented including flaky and elongated particles. Finally, aggregate transferring methods to
34 finite element software and mesh generation methods are discussed with the challenges and
35 possible methods to overcome these issues.

36 **AUTHOR KEYWORDS :** Mesoscale Modelling; Spherical Harmonics; Take and Place Method; 3D
37 Scanning; Aggregate Shape Analysis; X-Ray Computed Tomography

38 1 INTRODUCTION

39 Mesoscale modelling of concrete represents concrete in the mesoscale as a three-phase material
40 consisting of aggregates, mortar and Interfacial Transition Zone (ITZ) and this technique is an
41 efficient method to investigate about fracture and damage mechanics of concrete, local
42 deformation mechanisms, durability characteristics of concrete and various concrete
43 formulations (Comby-Peyrot et al. 2009). Mesoscale modelling is the most useful and practical
44 method to model the heterogeneities in concrete and understand how these heterogeneities
45 affect the macro behavior of concrete (Thilakarathna et al. 2020a).

46 Coarse aggregate is one of the three phases in the mesoscale which significantly contributes to
47 the performance of concrete (Shanaka 2016). In mesoscale models, only coarse aggregates are
48 modelled due to the limitations in computational capacity and fine aggregates are assumed to be
49 contained in the mortar phase (Li et al. 2019). Aggregate characteristics such as aggregate
50 shape, aggregate size, aggregate volume fraction, mechanical properties of aggregate and
51 particle size distribution curve (PSD) will influence the nonlinear behavior of concrete in
52 mesoscale and hence representation of aggregates accurately is important (Kristombu Baduge
53 et al. 2018; Trawiński et al. 2018).

54 To investigate the effect of aggregate parameters on the stress-strain behavior of the concrete, a
55 robust methodology of aggregate shape generation and placing algorithms according to any
56 given PSD is needed. These aggregate assemblies will serve as the core of the geometry in the
57 mesoscale models. Mesoscale aggregate assemblies can be generated in 2D (Jiang et al. 2019;
58 Rodrigues et al. 2016; Snozzi et al. 2012; Wang et al. 2015; Zhou et al. 2019) as well as in 3D
59 (Häfner et al. 2006; Li et al. 2016; Pan et al. 2018; Zhang et al. 2018b; Zhou et al. 2017). With the
60 increasing computational capacities and some limitations of 2D models, 3D mesoscale modelling

61 has become prevalent and hence in this paper, generation of 3D aggregate assemblies are
62 discussed.

63 This paper presents comprehensive shape generation algorithms for polyhedral shaped
64 aggregates as well as a spherical harmonics-based algorithm to reconstruct the exact geometric
65 shapes of real aggregates using the scanned aggregate geometries using a structured light 3D
66 scanner. Also, an algorithm is proposed to disperse the 3D scanned aggregates until a particular
67 volume fraction is achieved. Challenges of generating and placing aggregate particles to achieve
68 a prescribed volume fraction are also discussed and methods to overcome those challenges are
69 presented.

70

71 2 METHODOLOGY

72 Aggregate generation procedures, placing algorithms, aggregate shape analysis and geometry
73 reconstruction methodologies are discussed in this section for scanned aggregate shapes as well
74 as parameterized aggregate shapes. Results of the aggregate generation procedures and shape
75 analysis are also included in this section.

76 2.1 3D SCANNING OF AGGREGATE GEOMETRIES

77 There are numerous methods to model aggregate geometry in mesoscale models and 3D
78 scanning is one of the main techniques. X-ray computed tomography (XCT) scanning is a widely
79 used 3D scanning method to scan aggregates and concrete samples to generate the
80 mesostructure of concrete (Huang et al. 2015; Liu et al. 2018a; b; Ren et al. 2015; Shuguang and
81 Qingbin 2015; Thilakarathna et al. 2020b). However, it is time-consuming and costly to scan
82 aggregate particles using XCT (Anochie-Boateng et al. 2013) and XCT has a strict safety and
83 radiation monitoring specifications (Anochie-Boateng et al. 2012). Hence, a more convenient
84 method is needed to obtain the actual aggregate shapes. 3D laser scanning is another method

85 used to scan and obtain 3D aggregate shapes (Kim et al. 2003; Lanaro and Tolppanen 2002;
86 Mazzucco et al. 2018). However, these 3D laser scanners are comparatively slower than the
87 structured light scanners (Laga et al. 2019).

88 In this study, a novel aggregate scanning method using a handheld structured light scanner is
89 proposed to obtain the accurate geometries of aggregate particles. Previous researchers have
90 mainly used XCT and laser scanning methods to obtain the accurate aggregate geometries and
91 the proposed scanning method has numerous advantages compared to those scanning methods.
92 Structured light scanners are much safer than the 3D laser scanners and XCT scanners. These
93 scanners also produce a higher detail level with dense and accurate data compared with the laser
94 scanners. This scanner is very convenient to operate due to its portability. However, this does
95 not penetrate the samples as in XCT to produce a comprehensive 3D mesh with internal
96 heterogeneities and number of particles. The number of particles which can be processed per
97 hour depends on the 3D scanner type and the portable one can process around 500 particles per
98 hour and this is comparatively lower than the XCT. For mesoscale modelling purposes,
99 aggregates are assumed to be homogenous and hence this is a safer, less expensive and a
100 convenient method of obtaining the accurate 3D geometry.

101 Schematic diagram of 3D scanning process of aggregates is shown in **Fig. 1**. Artec Space Spider
102 3D scanner was used in this study to scan aggregates placed on a turntable. This scanner has a
103 3D resolution of 0.1 mm and a 3D point accuracy of 0.05 mm. This has a linear field of view of 90
104 × 70 mm at the closest range and 180 × 140 mm at the furthest range.

105 3D scanning and processing sequence using the structured light scanner is shown in **Fig. 2**. Each
106 of the steps in the sequence of scanning the aggregates are further described in the next sub-
107 sections.

108 2.1.1 Scanning

109 This step involves taking the 3D scans of the aggregates using the structured light scanner and
110 transferring those scans to the computer for further processing. An aggregate was placed on the
111 turntable as shown in **Fig. 1** and then it was scanned by rotating the turntable slowly until a
112 sufficient number of frames were scanned to capture the surface variations of the aggregate. **Fig.**
113 **3** shows a collection of scanned frames.

114 After completing this scan, the aggregate was turned upside down and followed the same
115 procedure to capture the areas which were not scanned in the previous step. Additional scans
116 can be done to make sure all the surfaces are included in the scans. However, in this scenario
117 two scans per aggregate were sufficient.

118 Ambient lighting was used for the scans and structured light scanner uses LED flashes to
119 illuminate the scanning area and hence, scans can be obtained even in a completely dark
120 environment. Capture rate of the scanner in this study was 7.5 frames/second and while
121 scanning captured frames are automatically aligned using the features in overlapping areas.
122 Rotating speed of the turntable was approximately 4 rpm and the scanner is incapable of
123 capturing important features if the turntable is rotated too fast. Optimal distance between the
124 scanner and the object for was around 250 mm and a 3D resolution of 0.2 mm was used.

125 2.1.2 Cleaning

126 It can be seen from **Fig. 3** that parts of the turntable have also been scanned and some outliers
127 are clearly visible. In this step, rough cleaning of the scans was done by removing outliers and
128 the parts of the scanned turntable.

129 Outliers are unnecessary noise visible in the scanned frames and if these are not removed, they
130 can be attached on to the final 3D geometry as fragments. Parts of the scanned turntable were
131 also deleted in this step. Aggregate scans after deleting the outliers and the base are shown in
132 **Fig. 4.**

133 Artec Studio (Artec3D 2020) software uses a statistical algorithm to determine the mean
134 distance and standard deviation between each point in the model and a set of adjacent points
135 and compares that with an interval defined by considering global mean distances and standard
136 deviations. If the distances of the considered points are greater than the distances defined in this
137 interval, it is considered as an outlier and removed from the model.

138 2.1.3 Alignment

139 In this step, different scans were aligned to make one complete scan. Data in the scans were
140 converted into one coordinate system using pairs of points. At least three sets of points are
141 needed to carry out the alignment step. Selection of points need not to be precise in this step as
142 in the registration step, accurate registration is done.

143 2.1.4 Registration

144 After aligning the scans, global registration of the frames was carried out. In this step, the global
145 registration algorithm present in Artec studio (Artec3D 2020) uses all the frames captured by
146 the scanner and converts the object surfaces in these frames in to a single coordinate system by
147 identifying the mutual positions of the features present in the surfaces. This is done by picking a
148 set of geometry points in one frame and searching for matching pairs of points present in the
149 other frames. For this, an initial approximation is required, and this initial approximation is
150 obtained by the selected points in the aligning step.

151 2.1.5 Fusion

152 In the fusion step, a 3D polygonal model of the scanned geometry was created. In this step, the
153 resolution of the model can be specified to define the mean distance between the two points of
154 the model. When generating the polygonal model, defects can appear on the reconstructed
155 geometry due to incomplete scans and these can be avoided by ensuring the quality of the scans

156 and number of scans are sufficient. To improve the quality of the scan, speed of rotation of the
157 turntable can be reduced or the rate of capture can be increased.

158 If these defects are minor, these can be repaired to obtain a defect-free polygonal model. If there
159 are holes that can't be mitigated by increasing the number of scans, those can be filled to obtain
160 a watertight mesh. In this hole-filling algorithm, edge fragments are connected by a surface
161 which follows the curvature of the neighboring surfaces. Some of the scanned aggregates after
162 fusion are shown in **Fig. 5**.

163 2.1.6 Postprocessing

164 The scanned geometry consists of a significant number of polygons and the number of polygons
165 needs to be reduced to be used in the mesoscale model. This mesh simplification was done using
166 meshlab software (Cignoni et al. 2008). A Database of aggregates was developed by scanning
167 various aggregates with different sizes. Also, using meshlab software, some of the obtained
168 meshes were scaled uniformly to ensure that an aggregate particle database with a wide range
169 of sizes was obtained.

170 It should be noted that to numerically model a concrete specimen, a large number of aggregate
171 particles with different shapes and sizes are needed. It is time-consuming to scan a massive
172 number of aggregate particles. Hence, a mathematical representation of the real shape of
173 aggregates is vital so that varying the parameters, different shapes and sizes can be generated.

174 Using spherical harmonics, the scanned aggregate surfaces can be mathematically represented,
175 and this method can be used to regenerate new aggregates with realistic aggregate shapes and
176 sizes by adjusting the parameters of the Fourier expansion. To reconstruct the accurate
177 aggregate shapes, SPHARM-MAT (Shen et al. 2009b) code was used. This method is further
178 explained in the following section.

179 2.2 AGGREGATE GEOMETRY BY SPHERICAL HARMONICS

180 Spherical harmonic is an effective method of accurately representing 3D geometries based on
181 Fourier expansion. Spherical harmonics has been used to represent and reconstruct geometries
182 in various fields including civil engineering (Lu and Garboczi 2014; Qian et al. 2016), medical
183 image analysis (Chung et al. 2007; Gerig et al. 2001), graphics (Bülow 2004; Funkhouser et al.
184 2003; Gu et al. 2003; Shen and Makedon 2006; Zhou et al. 2004), biology (McPeck et al. 2008,
185 2009; Shen et al. 2009a) and bioinformatics (Cai et al. 2002; Ritchie and Kemp 1999; Shen et al.
186 2007b).

187 3D spherical harmonic representation of aggregates was pioneered by Garboczi (Garboczi 2002)
188 where aggregates were scanned by a XCT scanner and SH was used to reconstruct the
189 aggregates. Since then, Combination of XCT and SH has been used to reconstruct many particle
190 shapes for coarse aggregates (Erdogan et al. 2006; Thomas et al. 2016), fine aggregates (Erdoğan
191 et al. 2017; Erdoğan et al. 2007; Lu et al. 2020; Taylor et al. 2006) cement particles (Bullard and
192 Garboczi 2013; Erdoğan et al. 2010; Holzer et al. 2010), slag (Liu et al. 2011) etc. . Shape analysis
193 of particles (Garboczi and Bullard 2004; Mahmoud et al. 2010), effect of aggregate shapes on
194 concrete rheology (Erdogan 2005) and effect of aggregate shapes on damage and fracture
195 propagation are some of the main applications of the generated aggregates using SH. Most of the
196 previous studies (Erdogan 2005; Erdoğan et al. 2017; Erdoğan et al. 2007; Garboczi and Garboczj
197 2002) have used a voxel mesh resulting from the scanning to fit the SH series to the geometry.
198 However, the proposed method in this paper using the SPHARM code can fit a SH series to voxel
199 mesh as well as a triangular mesh. In this paper, SH series is fitted to a triangular mesh obtained
200 using the structured light 3D scanner.

201 Also, most of the previous researchers have used SH to model star shaped particles only
202 (Garboczi and Bullard 2017) and in the parameterized method used in this study which was
203 initially proposed by Brechbuhler et al. (Brechbuhler et al. 1995) can generate non-star shaped

204 particles compared to the conventional spherical harmonic method (Ballard and Brown 1982).
205 Hence, particles with overhanging protrusions can be modelled using this method and this is
206 important to obtain the accurate geometries for mesoscale simulations.

207 Three steps are needed to obtain a spherical harmonics shape description of the input mesh
208 (Shen et al. 2009d). Those are 1) Spherical parameterization 2) Spherical harmonic expansion
209 and 3) Spherical harmonic alignment.

210 2.2.1 Spherical Harmonic Parameterization

211 The first step is to parameterize the input shape using the spherical parameterization. In this
212 step, a uniform and continuous bijective mapping was created from the object surface to the
213 surface of a unit sphere so that every vertex v in the input mesh is assigned to a pair of spherical
214 coordinates (θ, φ) in the unit sphere (Shen et al. 2009c, 2017).

$v(\theta, \varphi) = (x(\theta, \varphi), y(\theta, \varphi), z(\theta, \varphi))^T$	(1)
---	-------

215 Spherical coordinates (θ, φ) convention as shown in **Fig. 6** is used in this parameterization
216 process. In this coordinate system, θ is taken as the colatitudinal coordinate and φ is taken as
217 the longitudinal coordinate. Here, θ is in the range of $[0, \pi]$ and φ is in the range of $[0, 2\pi)$.
218 When this bijective mapping of each vertex of input mesh to the unit sphere is done, distortions
219 of the length, angles, and the areas of the triangles can occur. However, these distortions need to
220 be minimized for a good mapping. Three types of mappings are there to minimize these
221 distortions (Shen and Makedon 2006). Those are 1) isometric mapping where the length of the
222 arc in the input mesh and the unit sphere is equal 2) conformal mapping where the angles
223 between a pair of intersecting arcs in the input mesh is the same as that of the unit sphere 3)
224 equiareal mapping where each part on the input mesh is mapped on to the unit sphere with the
225 same area.

226 In the SPARM-MAT code, an equiareal mapping algorithm proposed by Shen and Makedon (Shen
 227 and Makedon 2006) called CALD (Control of Area and Length Distortions) has been used. This
 228 algorithm attempts to minimize the area distortions when the bijective mapping is done at the
 229 same time attempting to minimize the length distortions (Shen and Makedon 2006). This
 230 algorithm consists of mainly three steps. The first step is the initial parameterization step where
 231 each vertex of the input triangular mesh is mapped on to a unit sphere. This step is an extension
 232 of the method proposed by Brechbuhler et al. (Brechbuhler et al. 1995) to a triangular mesh.
 233 In the initial mapping of the mesh to the unit sphere, north pole ($\theta = 0$) and the south pole ($\theta =$
 234 π) of the sphere are selected as two vertices such that their projections to the principle axis of
 235 the scanned aggregate are furthest apart. Then, in the next step, two systems of equations are
 236 solved to obtain the colatitudinal coordinates (θ) and the longitudinal coordinates (φ) for the all
 237 the mesh vertices (Shen and Makedon 2006).

238 After the initial parameterization, global mesh smoothing, and local mesh smoothing steps were
 239 initiated to improve the parameterization quality. Using the CALD algorithm a mapping with
 240 high quality can be achieved. It should be noted the above-mentioned mapping is only applicable
 241 to genus-zero objects. Aggregates are genus zero objects and hence aggregates surface mesh can
 242 be mapped using this method. A mapping of a scanned aggregate particle to a unit sphere using
 243 the CALD algorithm is shown in **Fig. 7**.

244 2.2.2 Spherical Harmonic Expansion

245 The second step is the spherical harmonic expansion where the input mesh surface is expanded
 246 into a complete set of spherical harmonic basis functions Y_m^l . If x , y and z are Cartesian input
 247 mesh coordinates and θ and φ are polar coordinates in the parameter space, above
 248 parameterization process will result in three explicit functions $x(\theta, \varphi)$, $y(\theta, \varphi)$, and $z(\theta, \varphi)$
 249 which describe the input mesh surface. These three explicit functions can be described using
 250 Fourier spherical harmonic functions as given in Equations (2), (3) and (4).

$x(\theta, \varphi) = \sum_{l=0}^{\infty} \sum_{m=-l}^l c_{lx}^m Y_l^m(\theta, \varphi)$	(2)
$y(\theta, \varphi) = \sum_{l=0}^{\infty} \sum_{m=-l}^l c_{ly}^m Y_l^m(\theta, \varphi)$	(3)
$z(\theta, \varphi) = \sum_{l=0}^{\infty} \sum_{m=-l}^l c_{lz}^m Y_l^m(\theta, \varphi)$	(4)

251 Above three equations can be combined into one equation as given in Equation (5).

$v(\theta, \varphi) = \sum_{l=0}^{\infty} \sum_{m=-l}^l c_l^m Y_l^m(\theta, \varphi)$	(5)
---	-----

252 where $v(\theta, \varphi) = (x(\theta, \varphi), y(\theta, \varphi), z(\theta, \varphi))^T$ and $c_l^m = (c_{xl}^m, c_{yl}^m, c_{zl}^m)^T$. In the above equations c_l^m
253 are the Fourier coefficients and $Y_l^m(\theta, \varphi)$ is the spherical harmonic basis function which is given
254 by Equation (6).

$Y_l^m(\theta, \varphi) = \sqrt{\frac{(2l+1)(l-m)!}{4\pi(l+m)!}} P_l^m(\cos \theta) e^{im\varphi}$	(6)
--	-----

255 where $P_l^m(\cos \theta)$ are the associated Legendre polynomials. In these basis functions, spherical
256 harmonic degree is denoted by l and order is denoted by m . Hierarchy of the spherical harmonic
257 functions can be depicted using **Fig. 8**. Zero-degree spherical harmonic is represented by a
258 sphere and higher degree harmonics represent a distortion of the shape.

259 The ultimate objective is to calculate the Fourier coefficients $c_l^m = (c_{xl}^m, c_{yl}^m, c_{zl}^m)^T$ to a user-
260 specified maximum degree. These Fourier coefficients will determine the shape of the
261 regenerated aggregate particles and these coefficients can be complex numbers. These Fourier
262 coefficients c_l^m can be solved using standard least-squares estimation. The process of obtaining
263 these Fourier coefficients are described below by taking $x(\theta, \varphi)$ as an example.

264 If the functional values for an input spherical function $x(\theta, \varphi)$ are given by $x_i = x(\theta_i, \varphi_i)$ for $1 \leq$
265 $i \leq n$ where n is the number of points, a linear system as given in Equation (7) can be developed
266 according to Equation (2).

$$\begin{pmatrix} y_{1,1} & y_{1,2} & y_{1,3} & \cdots & y_{1,k} \\ y_{2,1} & y_{2,2} & y_{2,3} & \cdots & y_{2,k} \\ \vdots & \vdots & \vdots & \ddots & \vdots \\ y_{n,1} & y_{n,2} & y_{n,3} & \cdots & y_{n,k} \end{pmatrix} \begin{pmatrix} a_1 \\ a_2 \\ a_3 \\ \vdots \\ a_k \end{pmatrix} = \begin{pmatrix} x_1 \\ x_2 \\ x_3 \\ \vdots \\ x_n \end{pmatrix} \quad (7)$$

267 In the above linear system, $y_{ij} = Y_l^m(\theta_i, \varphi_i)$, $j = l^2 + l + m + 1$ and $k = (L_{max} + 1)^2$. Unique
 268 index j is assigned for each pair of (l, m) . For almost all the scenario $k < n$ and hence the above
 269 linear system can be solved using least square fitting. For example, in this study the simplified
 270 mesh of the scanned aggregates had around 100,000 vertices (i.e. $n=100,000$) and the maximum
 271 degree considered was 30 ($L_{max} = 30$). So, $k=961$ and $k < n$, and hence the linear system could
 272 be solved using least square fitting. study Hence, $(a_1, a_2, a_3, \dots, a_n)^T$ can be obtained and these
 273 are estimates for the original coefficients c_{lx}^m and using these coefficients the geometry can be
 274 reconstructed according to the following equation.

$$\check{x}(\theta, \varphi) = \sum_{l=0}^{L_{max}} \sum_{m=-l}^l \check{c}_{lx}^m Y_l^m(\theta, \varphi) \approx x(\theta, \varphi) \quad (8)$$

275 From spherical harmonic expansion using the estimated coefficients, x, y, z coordinates of the
 276 regenerated aggregate particle can be obtained and using Matlab, the mesh can be generated
 277 using the triangular elements once the coordinates of the regenerated particle is known.
 278 When a higher number of degree is specified (i.e. L_{max} is increased) geometry reconstruction is
 279 more accurate. In terms of the coefficients, the absolute value of the coefficients decreases when
 280 the number of degrees increases implying that when the number of degrees increases, the
 281 geometry converges to the actual geometry. Matlab data files for these coefficients for different
 282 degrees are attached in the supplementary materials. The same procedure is applied to obtain
 283 coefficients $\check{c}_{ly}^m$ and $\check{c}_{lz}^m$ and these coefficients are used to reconstruct the geometry in 3D.

284 2.2.3 Spherical Harmonic Alignment

285 The third step of the process is spherical harmonic alignment. In this step, the reconstructed
 286 object is placed into a common reference system as the original scanned object mesh. This is
 287 beneficial when comparing the reconstructed surface and the original scanned surface (Shen et

al. 2007a). However, this is not discussed in this paper in detail because when mesoscale model is generated, a random rotation is assigned to the reconstructed aggregate shapes when aggregate is placed and hence this step is not essential.

2.2.4 Case Study of Reconstruction of Aggregate Geometry

Spherical harmonic reconstruction of a scanned aggregate particle is shown in **Fig. 9**. When the spherical harmonic degree was increased, a more accurate geometry could be obtained. It should be noted that, if the number of degrees is L then the number of coefficients in the spherical harmonic expansion is $(L+1)^2$. Hence, the computation time increases when the number of degrees is increased. It could be observed that the number of degrees around 30 can accurately represent the geometry of the aggregates.

2.3 PLACING ALGORITHMS FOR SCANNED AGGREGATES

In this section, a placing algorithm is proposed to develop the mesoscale aggregate distribution using the scanned aggregates or the reconstructed aggregates using the spherical harmonics. Previous researchers have used various algorithms to distribute the aggregates inside the bounding geometry as reviewed in (Thilakarathna et al. 2020b). However, most of the algorithms are for parameterized aggregate shapes such as spheres (Shahbeyk et al. 2011; Wriggers and Moftah 2006), ellipsoids (Häfner et al. 2003), convex polyhedrons (Zhou et al. 2017) etc. and placing algorithms for scanned particles with realistic shapes are not yet established properly. Qian et al. (Qian et al. 2016) proposed an algorithm to distribute star-shaped particles with realistic aggregate geometry obtained using XCT and the intersection checking algorithm in that study was based on solving contact equations. However, the proposed algorithm in this paper uses a different particle intersection checking algorithm based on the face-vertex data of the mesh and hence can be used to generate aggregate packing assemblies

311 with non-star shaped particles and particle shapes where the parameterized equation is
312 unknown.

313 A database of aggregates was created using the scanned aggregates. Polygon number of the
314 scanned aggregates were reduced before generating the aggregate filled cylinder to reduce the
315 computational demand. This database consists of 52 scanned aggregate particles with diameters
316 spanning from 6mm to 25mm and some of the aggregate sizes are shown in **Fig. 10**. Some of the
317 aggregates were scaled to ensure that there is a wide range of diameters within the database.
318 This scaling and polygon reduction procedure was implemented in meshlab software (Cignoni
319 et al. 2008).

320 Aggregates were distributed inside a cylinder with a radius of 50mm and a height of 200mm in
321 this scenario. Any type of geometry such as a cylinder, cube etc. can be selected as the bounding
322 geometry. Following three conditions were satisfied when aggregates were distributed inside
323 the cylinder.

- 324 • Placed aggregates should be completely inside the bounding cylinder
- 325 • There should not be any overlaps between placed aggregate particles
- 326 • There should be a minimum distance between two aggregate particles to represent the
327 coating of mortar in between aggregate particles

328 Aggregate distribution process was carried out according to a Particle Size Distribution (PSD)
329 curve. In this investigation, Fuller's particle size distribution curve (W.B. and S.E. 1907) was
330 used. Fuller's curve is widely regarded as the grading curve which gives the optimum
331 compaction, density and strength in concrete and also a good workability and a good segregation
332 resistance (Wriggers and Moftah 2006) and hence it has been used by many researchers to
333 develop aggregate assemblies for mesoscale models (Zhang et al. 2019a, 2017).

334 Aggregate percentage by weight passing through a sieve diameter D according to the Fuller's
335 curve can be calculated from Equation (9).

$$Y = 100 \left(\frac{D}{D_{max}} \right)^n \quad (9)$$

In the above equation, D_{max} is the diameter of the largest aggregate and Y is the percentage of aggregate by weight passing through a sieve with diameter D aperture and n is a constant parameter generally between 0.45 and 0.7 (Sheng et al. 2016). In this paper, n was taken to be 0.5.

Volume of the aggregates within a grading segment between the sieve diameters d_s and d_{s+1} is given by Equation (10).

$$V_p[d_s, d_{s+1}] = \left(\frac{P(d_s) - P(d_{s+1})}{P(d_{max}) - P(d_{min})} \right) \times v_p \times V \quad (10)$$

where, $V_p[d_s, d_{s+1}]$ is the volume of aggregate within the grading segment $[d_s, d_{s+1}]$, d is the sieve diameter, d_{max} and d_{min} are the largest and smallest sieve diameter v_p is the volume fraction of aggregates and V is the total volume of the concrete.

The above-mentioned aggregate database consists of .stl files and face-vertex information of all the aggregates in the database were read and stored. While reading the face-vertex information of the aggregate particles, the minimum bounding box of the aggregate particle in 3D was determined using the vertices of the aggregate particle as shown in **Fig. 11**. In this scenario, it is assumed that a particle passes through a sieve with a diameter D if the second-largest length of the bounding box (L) is less than D . After reading all the aggregates in the database, those aggregates were sorted according to dimension L .

Aggregate distribution inside the cylinder was done until a required volume fraction is achieved. However, it should be noted that due to the large number of polygons in the scanned aggregates, the time to generate the aggregate filled geometry will be increased with the increasing volume fraction.

Sieve diameters were specified, and Fuller's PSD was used in this scenario to calculate the volume of aggregates within each sieve segment. Aggregates in the database were then classified

358 into the sieving sections and number of aggregates in each grading segment was calculated using
359 the previously read data.

360 Then, the aggregates were randomly distributed from the largest particle to the smallest particle.
361 Efficiency of the algorithm increases when the distribution is carried out from the largest particle
362 to the smallest particle rather than selecting a random particle within the grading segment.
363 Random position inside the cylinder was selected by first selecting a point on the vertical axis of
364 the cylinder as the z coordinate and then randomly generating a radius and a rotating angle to
365 define the x and y coordinates. Bounds of the x, y and z coordinated were decided so the
366 aggregate is completely inside the cylinder by considering the largest length of the aggregate
367 bounding box.

368 Aggregates were placed randomly until the calculated volume of each grading segment is
369 achieved. This was done by calculating the enclosed volume of the selected aggregate mesh and
370 reducing that volume from the required volume of that grading segment until the volume left is
371 smaller than any aggregate particle within that grading segment. In that scenario, the volume
372 left was transferred to the next grading segment and the process was repeated for the next
373 grading segment. It should be ensured that there are enough aggregate particles in the database
374 within a particular grading segment to achieve the calculated volume of the particles within that
375 grading segment. However, if the number of particles is not sufficient, the same set of particles
376 within the same grading segment were repeated.

377 Placing of the aggregates are done one after another sequentially. When placing the aggregates,
378 first the aggregate was placed at the origin of the cylinder. Then this aggregate was rotated
379 randomly around its centroid so that each placing aggregate has different orientations. Then this
380 aggregate is translated to the random location which was determined initially. All these rotations
381 and translations are done using matrix operations to the coordinates of the mesh.

382 This rotation was done using Euler's rotation theorem as shown in **Fig. 12**. First rotation is by
 383 an angle of α around z-axis, second rotation is by an angle of β around former x-axis and the third
 384 rotation is by an angle of γ around Z' axis.

385 The rotation matrices corresponding to these three rotations can be specified as in Equations
 386 (11), (12) and (13).

$Z(\alpha) = \begin{bmatrix} \cos \alpha & -\sin \alpha & 0 & 0 \\ \sin \alpha & \cos \alpha & 0 & 0 \\ 0 & 0 & 1 & 0 \\ 0 & 0 & 0 & 1 \end{bmatrix}$	(11)
$N(\beta) = \begin{bmatrix} 1 & 0 & 0 & 0 \\ 0 & \cos \beta & -\sin \beta & 0 \\ 0 & \sin \beta & \cos \beta & 0 \\ 0 & 0 & 0 & 1 \end{bmatrix}$	(12)
$Z'(\gamma) = \begin{bmatrix} \cos \gamma & -\sin \gamma & 0 & 0 \\ \sin \gamma & \cos \gamma & 0 & 0 \\ 0 & 0 & 1 & 0 \\ 0 & 0 & 0 & 1 \end{bmatrix}$	(13)

387 Hence, the combined rotation matrix can be specified as,

$R = Z(\alpha)N(\beta)Z'(\gamma)$	(14)
-----------------------------------	------

388 The coordinates of the nodes after rotating the particle can be obtained by (15).

$X_2 = RX_1$	(15)
--------------	------

389 Where X_2 is the coordinates after rotation, R is the rotation matrix and X_1 is the coordinates
 390 before the rotation. α , β and γ are randomly selected using a random number k using Equations
 391 (16), (17) and (18).

$\alpha = k * 2 * \pi$	(16)
$\beta = k * \pi$	(17)
$\gamma = k * 2 * \pi$	(18)

392 After rotating the aggregate, it was translated to the randomly selected location using the
 393 translation matrix given in (19).

$$T = \begin{bmatrix} 1 & 0 & 0 & D_x \\ 0 & 1 & 0 & D_y \\ 0 & 0 & 1 & D_z \\ 0 & 0 & 0 & 1 \end{bmatrix} \quad (19)$$

where, D_x , D_y , and D_z represent the displacements in x, y, and z directions respectively.

First aggregate was placed randomly inside the cylinder using the procedure described above and from the second aggregate onwards, intersection check between aggregates were checked to ensure that there will be no overlap between aggregate particles as well as there is a sufficient gap between aggregates to represent the mortar. For this intersection check, two-step procedure was followed.

First, the minimum bounding spheres of the aggregates were calculated using the vertices and then the intersection check was carried out by checking whether the sum of the two radii of the bounding spheres is less than the distance between the two centroids of the bounding spheres using Equation (20).

$$\sqrt{(x_A - x_B)^2 + (y_A - y_B)^2 + (z_A - z_B)^2} \geq 1.1 \times [r_A + r_B] \quad (20)$$

where x_A , y_A , z_A and x_B , y_B , z_B are the coordinates of the centers of the bounding spheres of aggregates A and B and r_A and r_B are the radii of the bounding spheres of aggregates A and B. It should be noted that a factor of 1.1 was used to multiply with the sum of radii of the bounding spheres to ensure that there is a sufficient gap in-between aggregates to represent the mortar. Allocating this gap is helpful when meshing the mortar phase in the meso scale model when finite element analysis is carried out and it should be noted that in reality the actual gap between the aggregates might be less than this. If the bounding spheres do not intersect with each other, the aggregates inside the bounding spheres will not intersect. Hence, if this criterion is satisfied for all the previously placed aggregates, then the aggregate is placed inside the cylinder. However, if that criterion is not satisfied, a further check is needed to check whether the aggregates inside the bounding spheres intersect with each other.

415 In the second step, first, it was checked whether the distance between the centroids of the
416 bounding spheres of the aggregates is greater than the radius of the larger particle and if this
417 condition was satisfied, the algorithm was proceeded to check whether the vertices of the two
418 aggregates are inside the other aggregate. When this check was carried out, new aggregate was
419 expanded by multiplying the vertices by a factor as shown in **Fig. 13** to ensure that there will be
420 a sufficient gap between the aggregates to represent the mortar.

421 All the nodes in one aggregate were checked to see whether any of the vertices of one aggregate
422 is inside the other aggregate. If any of the vertices is inside the other aggregate, two aggregates
423 intersect with each other and the new aggregate position is discarded, and a new random
424 position is sought. To check whether a vertex is inside the aggregate, rays were emanated from
425 the all the vertices of one aggregate in X, Y and Z directions as shown in **Fig. 14**. Since all the
426 scanned aggregates are watertight geometries, if the checking node is inside the aggregate,
427 number of intersections of the passing rays with the facets of the aggregates should be an even
428 number (Patil and Ravi 2005). Also, the edge to tri mesh surface intersection check was carried
429 out additionally using the algorithm proposed by Sunday (Sunday n.d.) to ensure that there will
430 be no edge to face intersection.

431 After checking for the intersection of the new aggregate with the previously placed aggregates,
432 new aggregate was placed in that position if it does not intersect with any of the previously
433 placed aggregate particles. This process was repeated until the required volume fraction is
434 achieved. Around 200 particles were needed to achieve 25% volume fraction and this test took
435 few hours to complete. Generated aggregate assemblies inside a cylinder are shown in **Fig. 15**.

436 2.4 SPHERICAL AND ELLIPSOIDAL PARTICLES

437 Parametric surfaces can also be used to generate aggregate particles instead of scanning the
438 particles or reconstructing it. Real aggregate particles can be in various shapes and these shapes
439 are represented using parameter-based equations.

Spherical (Gal et al. 2008; Li et al. 2016, 2019; Shahbeyk et al. 2011; Xu and Chen 2016) and ellipsoidal (Liu et al. 2014; Unger and Eckardt 2011; Xu and Chen 2012) particle shapes have been widely used by researchers due to the simplicity. However, generation of placing algorithms of these particles are well established and hence those are not discussed in this paper. Some of the generated spherical and ellipsoidal particles are shown in **Fig. 16**.

2.5 POLYHEDRAL AGGREGATES GENERATION AND PLACEMENT

Convex polyhedrons can be used to represent the geometry of the crushed aggregates in mesoscale concrete models. In a convex polyhedron, a line connecting any two vertices of the polyhedron always lies in the interior of the polyhedron. A novel three-step procedure was proposed to check the intersection and place the polyhedral particles in this paper.

First, the aggregates were distributed randomly according to Fuller's curve. It was assumed that a polyhedral particle belongs to the grading segment of $[d_s, d_{s+1}]$ if the diameter of the bounding sphere of the aggregate is less than the aperture of the sieve with diameter d_s and larger than the aperture of the sieve with diameter d_{s+1} . Spheres were generated according to the PSD and polyhedral particles were generated by randomly selecting 20 points on the surface of the spheres as the vertices of the polyhedrons so that the spheres would be circumscribed spheres of the polyhedrons. These vertices were selected so that the center of the circumscribed sphere is contained inside the polyhedron.

Three-step procedure was followed to check the intersection of the polyhedron aggregates. First, the intersection of the bounding spheres was checked. This check was carried out by checking whether the distance between the two aggregate particles is less than the sum of the radii of the bounding spheres. If the bounding spheres do not intersect, the aggregate particles also do not intersect and if the bounding spheres intersect with each other, a further check was done to investigate whether the polyhedrons would intersect.

464 In the second step, it was checked whether the distance between the two centers of the bounding
 465 spheres is greater than the radius of the larger particle. If this condition is not satisfied, then a
 466 new location for the placing aggregate is sought. If this condition is satisfied, then the third
 467 condition was checked.

468 The third condition was checked by checking the distance of nodes of one aggregate with respect
 469 to the triangular surfaces of the other aggregates. Normal vectors to the triangular faces were
 470 calculated by taking the cross product between the edge vectors and by convention, the surface
 471 normals are presumed to be pointed outwards from the aggregates. Equation of triangular mesh
 472 planes can be denoted by the following Equation (21).

$Ax + By + Cz + D = 0$	(21)
------------------------	------

473 where A , B , C and D are the constant coefficients of the plane depending on the location and the
 474 orientation of the plane and x, y, z are the coordinates of any point lying in the plane.

475 If the above equation is not satisfied by a point in the space, then that point is either inside or
 476 outside depending on the sign of the distance to the point. In this scenario, nodes of one
 477 polyhedron are checked against all the triangular surfaces of the other expanded polyhedron to
 478 check whether those points are inside the polyhedron. This check was repeated by interchanging
 479 the nodes to the polyhedron and polyhedron to the nodes as shown in **Fig. 17**. Also, edge to tri
 480 mesh surface intersection check was carried out additionally using the algorithm proposed by
 481 Sunday (Sunday n.d.) to ensure that there will be no edge to face intersection.

482 After the intersection check was done, the new aggregate was placed inside the cylinder if it does
 483 not intersect with previously placed particles and this process was repeated until the required
 484 volume fraction is achieved.

485 Generated aggregate assemblies using polyhedron particles inside a cylinder is shown in **Fig. 18**.

486 Using this new algorithm, polyhedral aggregate volume fractions up to 40% can be generated.

487 This volume fraction is sufficient to simulate mesoscale concrete in most of the general cases
488 and if very high aggregate volume fractions are needed for specific investigations, polyhedral
489 aggregate generation method proposed by Zhang et al. (Zhang et al. 2018a, 2019c; b) can be
490 used.

491 It should be noted that, since the random points on the surface of the sphere are selected as the
492 vertices of the polyhedron, generated aggregate particles generally have equal dimensions in
493 each three directions. However, flaky aggregates and elongated aggregates can also be generated
494 by scaling the generated aggregate along a dimension. Aggregates can be identified as flaky
495 aggregates if the least dimension of the aggregate (thickness) is less than 0.6 times the mean
496 sieve size of the aggregate grading segment and aggregates are elongated if the largest
497 dimension of the aggregate is greater than 1.8 times the mean sieve size of the aggregate grading
498 segment (Kwan et al. 1999). Generation of an elongated and a flaky aggregate using the same
499 aggregate is shown in **Fig. 19**.

500 2.6 TRANSFERRING GEOMETRY TO FINITE ELEMENT PROGRAM

501 All the above discussed parameterized geometries were generated using MATLAB. These
502 meshes are surface meshes with a set of vertices and faces. However, for finite element analysis
503 of mesoscale concrete model, a solid mesh is needed and transferring surface mesh into solid
504 mesh is a challenge. This section discusses effective methods to obtain a solid model using the
505 surface meshes developed in MATLAB.

506 Geometry information from the MATLAB can be saved and then using another program, solid
507 geometries can be generated. Most of the finite element software have the capability of
508 generating simple shapes like spheres using inbuilt functions. For example, in spherical
509 aggregate assemblies, center coordinates and diameters of the particles were saved and using
510 this information solid spheres were generated to obtain the solid aggregate assemblies.

Another method is to save the face-vertex information from MATLAB and generate a solid mesh from bottom up using finite element programs. It should be noted that when placing the aggregates using previously discussed algorithms, for each aggregate vertex numbers start from 1 and the faces are defined according to these vertex numbers as shown in **Fig. 20** (a). However, to generate the full assembly of the aggregates, these nodes should be renumbered as shown in **Fig. 20** (b) depending on the number of vertices on each aggregate and then the faces should be defined using these renumbered vertices. Then this can be saved, and a bottom-up geometry can be generated in the finite element software.

Another method is to write these face vertex information directly to a standard mesh file such as *.stl* and *.ply* directly from MATLAB. However, these mesh files will be surface meshes and by using third-party software such as Ansys Spaceclaim and Freecad, these surface meshes can be volumized. When volumizing these surfaces meshes, errors can be occurred due to band mesh quality or defects in the surface meshes. In that case, the surface meshes need to be preprocessed before volumizing is carried out.

3 DISCUSSION

Aggregate shape, volume fraction and the distribution are important aspects of concrete and these aspects will affect the macroscopic behavior of concrete including fracture and damage initiation and propagation, strength in compression and tension, fracture energy of the concrete etc. Also, shape and the size of the interfacial transition zone (ITZ) will also depend on the aggregate shapes. ITZ has been found to be one critical aspect in concrete where the damage initiates and progresses and to accurately model the shape and volume of the ITZ, accurate shape of the aggregates is vital. 3D scanning of the aggregates as well as the spherical harmonic geometry reconstruction algorithm combined with the proposed aggregate distribution algorithm can be used in this scenario to accurately represent the aggregate geometry.

535 Different algorithms for placing different aggregate shapes were discussed in this paper and the
536 efficiency of these algorithms depends on the aggregate shape, PSD, required volume fraction
537 and volume of the bounding geometry. It was found that when the number of polygon count is
538 higher in an aggregate, more time will be consumed to check the intersection of the aggregates
539 and hence more time is needed to achieve a given volume fraction. However, it should be noted
540 that too much reduction of polygon numbers will result in failure to capture important geometric
541 features of the particles. Hence, a compromise is required to reduce the generation time while
542 the important features of the geometry are present.

543 Aggregate volume fractions up to 40% can be achieved for polyhedral aggregate particles and
544 up to 30% can be achieved for scanned aggregates. It should be noted that this is due to the
545 increase of running time due to the complexity of the mesh of the aggregates with higher polygon
546 number. Also, the volume fraction depends on the PSD and the sieve sizes as well. Higher volume
547 fractions can be achieved when the PSD curve has a higher percentage of aggregates with small
548 diameter because the packing and search for a location for the placing can be efficiently carried
549 out.

550 According to AS 2758.1 (Standards Australia 2014), the flakiness index of the aggregates used in
551 the concrete should not exceed 35% and using this algorithm, any specified percentage of
552 flakiness index and elongation index can be achieved.

553 4 SUMMARY AND CONCLUSIONS

554 Aggregate generation is an important aspect for mesoscale modelling of concrete. In this paper,
555 aggregates with various shapes were generated inside a cylinder and these aggregates were
556 distributed without any overlap to achieve a realistic volume fraction. A novel method was
557 proposed to scan aggregates with a 3D structured light scanner and distribute those aggregates
558 inside a cylinder by creating a real aggregate shape database in 3D. Spherical harmonics-based

parameterization method was proposed to reconstruct these actual aggregate geometries using parameters. Also, parametric aggregate shape generation for polyhedral shapes was discussed with an efficient placing algorithm. Following conclusions can be derived from this investigation.

- Accurate geometrical models of aggregates can be obtained using a 3D structured light scanner and this method is faster and convenient compared with the XCT scanning method.
- Mesh simplification should be carried out for the scanned aggregates because the scanned object mesh density is very high and after this simplification important features of the aggregate geometry should prevail.
- Accurate scanned geometry can be reconstructed using spherical harmonics based parametric method and various aggregate shapes can be generated by changing the parameters of the Fourier expansion.
- Crushed aggregate shapes can be accurately represented using convex polyhedrons and using the proposed algorithm aggregate volume fractions up to 40% can be obtained. Flaky and elongated particles can be generated by the proposed method for specific applications.
- Various methods can be obtained to transfer the surface geometries to finite element analysis software where solid geometries are used and errors when volumizing can be mitigated by improving the mesh quality.

5 Data Availability Statement

Some or all data, models, or code generated or used during the study are available in a repository or online in accordance with funder data retention policies. (Thilakarathna, S. (2020), “3D Scanned Aggregates”, Mendeley Data, v1 <http://dx.doi.org/10.17632/x5dbx8yxdw.1>)

582 6 ACKNOWLEDGEMENT

583 P.S.M Thilakarathna would like to thank The University of Melbourne, Australia for providing
584 Melbourne Graduate Research Scholarship Award.

585 7 REFERENCES

- 586 Anochie-Boateng, J. K., Komba, J. J., and Mvelase, G. M. (2013). "Three-dimensional laser scanning
587 technique to quantify aggregate and ballast shape properties." *Construction and Building*
588 *Materials*, Elsevier, 43, 389–398.
- 589 Anochie-Boateng, J. K., Komba, J., and Tutumluer, E. (2012). "Aggregate Surface Areas Quantified
590 through Laser Measurements for South African Asphalt Mixtures." *Journal of Transportation*
591 *Engineering*, 138(8), 1006–1015.
- 592 Artec3D. (2020). "Artec Studio 15 User Guide."
- 593 Ballard, D. ., and Brown, C. . (1982). *Computer Vision*. PrenticeHall , Inc .
- 594 Brechbuhler, C. H., Gerig, G., and Kubler, O. (1995). "Parametrization of closed surfaces for 3-D
595 shape description." *Computer Vision and Image Understanding*, Academic Press, 61(2), 154–
596 170.
- 597 Bullard, J. W., and Garboczi, E. J. (2013). "Defining shape measures for 3D star-shaped particles:
598 Sphericity, roundness, and dimensions." *Powder Technology*, Elsevier, 249, 241–252.
- 599 Bülow, T. (2004). "Spherical diffusion for 3D surface smoothing." *IEEE Transactions on Pattern*
600 *Analysis and Machine Intelligence*, 26(12), 1650–1654.
- 601 Cai, W., Shao, X., and Maigret, B. (2002). "Protein-ligand recognition using spherical harmonic
602 molecular surfaces: Towards a fast and efficient filter for large virtual throughput
603 screening." *Journal of Molecular Graphics and Modelling*, 313–328.
- 604 Chung, M. K., Dalton, K. M., Shen, L., Evans, A. C., and Davidson, R. J. (2007). "Weighted Fourier
605 series representation and its application to quantifying the amount of gray matter." *IEEE*

606 *Transactions on Medical Imaging*, 26(4), 566–581.

607 Cignoni, P., Callieri, M., Corsini, M., Dellepiane, M., Ganovelli, F., and Ranzuglia, G. (2008).
608 “MeshLab: an Open-Source Mesh Processing Tool.” *Eurographics Italian Chapter Conference*,
609 V. Scarano, R. De Chiara, and U. Erra, eds., Pisa, Italy.

610 Comby-Peyrot, I., Bernard, F., Bouchard, P.-O., Bay, F., and Garcia-Diaz, E. (2009). “Development
611 and validation of a 3D computational tool to describe concrete behaviour at mesoscale.
612 Application to the alkali-silica reaction.” *Computational Materials Science*, Elsevier, 46(4),
613 1163–1177.

614 Erdogan, S. T. (2005). “Determination of Aggregate Shape Properties Using X-ray Tomographic
615 Methods and the Effect of Shape on Concrete Rheology.” The University of Texas at Austin.

616 Erdoğan, S. T., Forster, A. M., Stutzman, P. E., and Garboczi, E. J. (2017). “Particle-based
617 characterization of Ottawa sand: Shape, size, mineralogy, and elastic moduli.” *Cement and*
618 *Concrete Composites*, Elsevier Ltd, 83, 36–44.

619 Erdoğan, S. T., Garboczi, E. J., and Fowler, D. W. (2007). “Shape and size of microfine aggregates:
620 X-ray microcomputed tomography vs. laser diffraction.” *Powder Technology*, Elsevier,
621 177(2), 53–63.

622 Erdoğan, S. T., Nie, X., Stutzman, P. E., and Garboczi, E. J. (2010). “Micrometer-scale 3-D shape
623 characterization of eight cements: Particle shape and cement chemistry, and the effect of
624 particle shape on laser diffraction particle size measurement.” *Cement and Concrete*
625 *Research*, Pergamon, 40(5), 731–739.

626 Erdogan, S. T., Quiroga, P. N., Fowler, D. W., Saleh, H. A., Livingston, R. A., Garboczi, E. J., Ketcham,
627 P. M., Hagedorn, J. G., and Satterfield, S. G. (2006). “Three-dimensional shape analysis of
628 coarse aggregates: New techniques for and preliminary results on several different coarse
629 aggregates and reference rocks.” *Cement and Concrete Research*, Pergamon, 36(9), 1619–
630 1627.

631 Funkhouser, T., Min, P., Kazhdan, M., Chen, J., Halderman, A., Dobkin, D., and Jacobs, D. (2003). "A
632 search engine for 3D models." *ACM Transactions on Graphics*, 22(1), 83–105.

633 Gal, E., Ganz, A., Hadad, L., and Kryvoruk, R. (2008). "Development of a Concrete Unit Cell."
634 *International Journal for Multiscale Computational Engineering*, Begel House Inc., 6(5), 499–
635 510.

636 Garboczi, E. J. (2002). "Three-dimensional mathematical analysis of particle shape using X-ray
637 tomography and spherical harmonics: Application to aggregates used in concrete." *Cement
638 and Concrete Research*, Pergamon, 32(10), 1621–1638.

639 Garboczi, E. J., and Bullard, J. W. (2004). "Shape analysis of a reference cement." *Cement and
640 Concrete Research*, Elsevier Ltd, 34(10), 1933–1937.

641 Garboczi, E. J., and Bullard, J. W. (2017). "3D analytical mathematical models of random star-
642 shape particles via a combination of X-ray computed microtomography and spherical
643 harmonic analysis." *Advanced Powder Technology*, Elsevier B.V.

644 Garboczi, E. J., and Garboczi, E. J. (2002). *Three-dimensional mathematical analysis of particle
645 shape using X-ray tomography and spherical harmonics: Application to aggregates used in
646 concrete. Cement and Concrete Research*.

647 Gerig, G., Styner, M., Shenton, M. E., and Lieberman, J. A. (2001). "Shape versus size: Improved
648 understanding of the morphology of brain structures." *Lecture Notes in Computer Science
649 (including subseries Lecture Notes in Artificial Intelligence and Lecture Notes in
650 Bioinformatics)*, Springer Verlag, 24–32.

651 Gu, X., Wang, Y., Chan, T. F., Thompson, P. M., and Yau, S. T. (2003). "Genus zero surface conformal
652 mapping and its application to brain surface mapping." *Lecture Notes in Computer Science
653 (including subseries Lecture Notes in Artificial Intelligence and Lecture Notes in
654 Bioinformatics)*, 2732, 172–184.

655 Häfner, S., Eckardt, S., and Könke, C. (2003). "A geometrical inclusion-matrix model for the finite

656 element analysis of concrete at multiple scales." *Proceedings of the 16th IKM 2003*,
657 *Gurlebeck, Hempel, Könke (eds.), Weimar, Germany, June 10-12.*

658 Häfner, S., Eckardt, S., Luther, T., and Könke, C. (2006). "Mesoscale modeling of concrete:
659 Geometry and numerics." *Computers & Structures*, Pergamon, 84(7), 450–461.

660 Holzer, L., Flatt, R. J., Erdoğan, S. T., Bullard, J. W., and Garboczi, E. J. (2010). "Shape Comparison
661 between 0.4-2.0 and 20-60 μm Cement Particles." *Journal of the American Ceramic Society*,
662 93(6), 1626–1633.

663 Huang, Y., Yang, Z., Ren, W., Liu, G., and Zhang, C. (2015). "3D meso-scale fracture modelling and
664 validation of concrete based on in-situ X-ray Computed Tomography images using damage
665 plasticity model." *International Journal of Solids and Structures*, Pergamon, 67–68, 340–352.

666 Jiang, Z. L., Gu, X. L., Huang, Q. H., and Zhang, W. P. (2019). "Statistical analysis of concrete
667 carbonation depths considering different coarse aggregate shapes." *Construction and*
668 *Building Materials*, Elsevier Ltd, 229, 116856.

669 Kim, H., Haas, C. T., Rauch, A. F., and Browne, C. (2003). "3D image segmentation of aggregates
670 from laser profiling." *Computer-Aided Civil and Infrastructure Engineering*, Blackwell
671 Publishing Inc., 18(4), 254–263.

672 Kristombu Baduge, S., Mendis, P., and Ngo, T. (2018). "Stress-strain relationship for very-high
673 strength concrete (>100 MPa) confined by lateral reinforcement." *Engineering*
674 *Structures*, Elsevier, 177, 795–808.

675 Kwan, A. K. H., Mora, C. F., and Chan, H. C. (1999). "Particle shape analysis of coarse aggregate
676 using digital image processing." *Cement and Concrete Research*, Elsevier Science Ltd, 29(9),
677 1403–1410.

678 Laga, H., Guo, Y., Tabia, H., Fisher, R. B., and Bennamoun, M. (2019). *3D Shape Analysis*
679 *Fundamentals, Theory, and Applications Hamid. Spring*, Wiley-Blackwell.

680 Lanaro, F., and Tolppanen, P. (2002). "3D characterization of coarse aggregates." *Engineering*

681 *Geology*, Elsevier, 65(1), 17–30.

682 Li, X., Chen, X., Jivkov, A. P., and Zhang, J. (2019). “3D mesoscale modeling and fracture property
683 study of rubberized self-compacting concrete based on uniaxial tension test.” *Theoretical
684 and Applied Fracture Mechanics*, Elsevier B.V., 104, 102363.

685 Li, X., Xu, Y., and Chen, S. (2016). “Computational homogenization of effective permeability in
686 three-phase mesoscale concrete.” *Construction and Building Materials*, Elsevier, 121, 100–
687 111.

688 Liu, L., Shen, D., Chen, H., and Xu, W. (2014). “Aggregate shape effect on the diffusivity of mortar:
689 A 3D numerical investigation by random packing models of ellipsoidal particles and of
690 convex polyhedral particles.” *Computers & Structures*, Pergamon, 144, 40–51.

691 Liu, T., Qin, S., Zou, D., Song, W., and Teng, J. (2018a). “Mesoscopic modeling method of concrete
692 based on statistical analysis of CT images.” *Construction and Building Materials*, Elsevier Ltd,
693 192, 429–441.

694 Liu, X., Garboczi, E. J., Grigoriu, M., Lu, Y., and Erdoğan, S. T. (2011). “Spherical harmonic-based
695 random fields based on real particle 3D data: Improved numerical algorithm and
696 quantitative comparison to real particles.” *Powder Technology*, Elsevier, 207(1–3), 78–86.

697 Liu, Y., Gong, F., You, Z., and Wang, H. (2018b). “Aggregate morphological characterization with
698 3D optical scanner versus X-ray computed tomography.” *Journal of Materials in Civil
699 Engineering*, American Society of Civil Engineers (ASCE), 30(1), 04017248.

700 Lu, Y., and Garboczi, E. J. (2014). “Bridging the Gap between Random Microstructure and 3D
701 Meshing.” *Journal of Computing in Civil Engineering*, American Society of Civil Engineers
702 (ASCE), 28(3), 04014007.

703 Lu, Y., Islam, M. A., Thomas, S., and Garboczi, E. J. (2020). “Three-dimensional mortar models
704 using real-shaped sand particles and uniform thickness interfacial transition zones:
705 Artifacts seen in 2D slices.” *Construction and Building Materials*, Elsevier Ltd, 236, 117590.

706 Mahmoud, E., Gates, L., Masad, E., Erdoğan, S., and Garboczi, E. (2010). "Comprehensive
 707 Evaluation of AIMS Texture, Angularity, and Dimension Measurements." *Journal of Materials*
 708 *in Civil Engineering*, American Society of Civil Engineers, 22(4), 369–379.

709 Mazzucco, G., Xotta, G., Pomaro, B., Salomoni, V. A., and Faleschini, F. (2018). "Elastoplastic-
 710 damaged meso-scale modelling of concrete with recycled aggregates." *Composites Part B:*
 711 *Engineering*, Elsevier, 140, 145–156.

712 McPeck, M. A., Shen, L., and Farid, H. (2009). "The correlated evolution of three-dimensional
 713 reproductive structures between male and female damselflies." *Evolution*, 63(1), 73–83.

714 McPeck, M. A., Shen, L., Torrey, J. Z., and Farid, H. (2008). "The tempo and mode of three-
 715 dimensional morphological evolution in male reproductive structures." *American*
 716 *Naturalist*, 171(5), E158-78.

717 Pan, Z., Chen, A., Ma, R., Wang, D., and Tian, H. (2018). "Three-dimensional lattice modeling of
 718 concrete carbonation at meso-scale based on reconstructed coarse aggregates." *Construction and Building Materials*, Elsevier Ltd, 192, 253–271.

720 Patil, S., and Ravi, B. (2005). "Voxel-based representation, display and thickness analysis of
 721 intricate shapes." *Proceedings - Ninth International Conference on Computer Aided Design*
 722 *and Computer Graphics, CAD/CG 2005*, 415–420.

723 Qian, Z., Garboczi, E. J., Ye, G., and Schlangen, E. (2016). "Anm: a geometrical model for the
 724 composite structure of mortar and concrete using real-shape particles." *Materials and*
 725 *Structures/Materiaux et Constructions*, Kluwer Academic Publishers, 49(1–2), 149–158.

726 Ren, W., Yang, Z., Sharma, R., Zhang, C., and Withers, P. J. (2015). "Two-dimensional X-ray CT
 727 image based meso-scale fracture modelling of concrete." *Engineering Fracture Mechanics*,
 728 Pergamon, 133, 24–39.

729 Ritchie, D. W., and Kemp, G. J. L. (1999). "Fast computation, rotation, and comparison of low
 730 resolution spherical harmonic molecular surfaces." *Journal of Computational Chemistry*,

John Wiley & Sons, Ltd, 20(4), 383–395.

Rodrigues, E. A., Manzoli, O. L., Bitencourt Jr., L. A. G., and Bittencourt, T. N. (2016). “2D mesoscale model for concrete based on the use of interface element with a high aspect ratio.” *International Journal of Solids and Structures*, Pergamon, 94–95, 112–124.

Shahbeyk, S., Hosseini, M., and Yaghoobi, M. (2011). “Mesoscale finite element prediction of concrete failure.” *Computational Materials Science*, Elsevier, 50(7), 1973–1990.

Shanaka, K. (2016). “Ductility design of very-high strength concrete columns (100 MPa-150 MPa) (Ph.D Thesis).” The University of Melbourne.

Shen, L., Cong, S., and Inlow, M. (2017). “Statistical Shape Analysis for Brain Structures.” *Statistical Shape and Deformation Analysis: Methods, Implementation and Applications*, Elsevier Inc., 351–378.

Shen, L., Farid, H., and McPeck, M. A. (2009a). “Modeling three-dimensional morphological structures using spherical harmonics.” *Evolution*, 63(4), 1003–1016.

Shen, L., Farid, H., and McPeck, M. A. (2009b). “Modeling three-dimensional morphological structures using spherical harmonics.” *International Journal of Organic Evolution*, John Wiley & Sons, Ltd, 63(4), 1003–1016.

Shen, L., Firpi, H. A., Saykin, A. J., and West, J. D. (2009c). “Parametric surface modeling and registration for comparison of manual and automated segmentation of the hippocampus.” *Hippocampus*, NIH Public Access, 19(6), 588–595.

Shen, L., Huang, H., Makedon, F., and Saykin, A. J. (2007a). “Efficient registration of 3D SPHARM surfaces.” *Proceedings - Fourth Canadian Conference on Computer and Robot Vision, CRV 2007*, IEEE, 81–88.

Shen, L., Kim, S., and Saykin, A. J. (2009d). “Fourier method for large-scale surface modeling and registration.” *Computers and Graphics (Pergamon)*, Elsevier Ltd, 33(3), 299–311.

Shen, L., and Makedon, F. (2006). “Spherical mapping for processing of 3D closed surfaces.”

756 *Image and Vision Computing*, Elsevier Ltd, 24(7), 743–761.

757 Shen, L., Saykin, A. J., Chung, M. K., and Huang, H. (2007b). “Morphometric analysis of
758 hippocampal shape in mild cognitive impairment: An imaging genetics study.” *Proceedings*
759 *of the 7th IEEE International Conference on Bioinformatics and Bioengineering, BIBE*, 211–
760 217.

761 Sheng, P., Zhang, J., and Ji, Z. (2016). “An advanced 3D modeling method for concrete-like
762 particle-reinforced composites with high volume fraction of randomly distributed
763 particles.” *Composites Science and Technology*, Elsevier, 134, 26–35.

764 Shuguang, L., and Qingbin, L. (2015). “Method of meshing ITZ structure in 3D meso-level finite
765 element analysis for concrete.” *Finite Elements in Analysis and Design*, Elsevier, 93, 96–106.

766 Snozzi, L., Gatuingt, F., and Molinari, J. F. (2012). “A meso-mechanical model for concrete under
767 dynamic tensile and compressive loading.” *International Journal of Fracture*, Springer
768 Netherlands, 178(1–2), 179–194.

769 Standards Australia. (2014). “AS 2758.1:2014 - Aggregates and rock for engineering purposes -
770 Part 1: Concrete aggregates.”

771 Sunday, D. (n.d.). “Intersections of Rays, Planes and Triangles (3D).”
772 <[http://geometryalgorithms.com/Archive/%0Aalgorithm 0105/algorithm.html%0D](http://geometryalgorithms.com/Archive/%0Aalgorithm%200105/algorithm.html%0D)>.

773 Taylor, M. A., Garboczi, E. J., Erdogan, S. T., and Fowler, D. W. (2006). “Some properties of
774 irregular 3-D particles.” *Powder Technology*, Elsevier, 162(1), 1–15.

775 Thilakarathna, P. S. M., Kristombu Baduge, K. S., Mendis, P., Chandrathilaka, E. R. K., Vimonsatit,
776 V., and Lee, H. (2020a). “Understanding fracture mechanism and behaviour of ultra-high
777 strength concrete using mesoscale modelling.” *Engineering Fracture Mechanics*, Elsevier
778 Ltd, 234, 107080.

779 Thilakarathna, P. S. M., Kristombu Baduge, S., Mendis, P., Vimonsatit, V., and Lee, H. (2020b).
780 “Mesoscale Modelling of Concrete – A Review of Geometry Generation, Placing Algorithms,

781 Constitutive Relations and Applications." *Engineering Fracture Mechanics*.

782 Thomas, S., Lu, Y., and Garboczi, E. J. (2016). "Improved Model for Three-Dimensional Virtual
783 Concrete: Anm Model." *Journal of Computing in Civil Engineering*, American Society of Civil
784 Engineers (ASCE), 30(2), 04015027.

785 Trawiński, W., Tejchman, J., and Bobiński, J. (2018). "A three-dimensional meso-scale modelling
786 of concrete fracture, based on cohesive elements and X-ray μ CT images." *Engineering
787 Fracture Mechanics*, Elsevier Ltd, 189, 27–50.

788 Unger, J. F., and Eckardt, S. (2011). "Multiscale Modeling of Concrete." *Archives of Computational
789 Methods in Engineering*, Springer Netherlands, 18(3), 341–393.

790 W.B., F., and S.E., T. (1907). "THE LAWS OF PROPORTIONING CONCRETE." *ASIAN JOURNAL OF
791 CIVIL ENGINEERING TRANSPORT*.

792 Wang, X. F., Yang, Z. J., Yates, J. R., Jivkov, A. P., and Zhang, C. (2015). "Monte Carlo simulations of
793 mesoscale fracture modelling of concrete with random aggregates and pores." *Construction
794 and Building Materials*, Elsevier, 75, 35–45.

795 Wriggers, P., and Moftah, S. O. (2006). "Mesoscale models for concrete: Homogenisation and
796 damage behaviour." *Finite Elements in Analysis and Design*, Elsevier, 42(7), 623–636.

797 Xu, W. X., and Chen, H. S. (2012). "Microstructural characterization of fresh cement paste via
798 random packing of ellipsoidal cement particles." *Materials Characterization*, Elsevier, 66,
799 16–23.

800 Xu, Y., and Chen, S. (2016). "A method for modeling the damage behavior of concrete with a
801 three-phase mesostructure." *Construction and Building Materials*, Elsevier, 102, 26–38.

802 Zhang, H., Sheng, P., Zhang, J., and Ji, Z. (2019a). "Realistic 3D modeling of concrete composites
803 with randomly distributed aggregates by using aggregate expansion method." *Construction
804 and Building Materials*, Elsevier Ltd, 225, 927–940.

805 Zhang, J., Wang, Z., Yang, H., Wang, Z., and Shu, X. (2018a). "3D meso-scale modeling of

reinforcement concrete with high volume fraction of randomly distributed aggregates.”
Construction and Building Materials, Elsevier, 164, 350–361.

Zhang, J., Yang, H., Zhang, Y., Wang, Z., Wang, Z., and Shu, X. (2018b). “Numerical investigations on the effect of reinforcement on penetration resistance of concrete slabs using a 3D meso-scale method.” *Construction and Building Materials*, Elsevier Ltd, 188, 793–808.

Zhang, Y., Chen, Q., Wang, Z., Zhang, J., Wang, Z., and Li, Z. (2019b). “3D mesoscale fracture analysis of concrete under complex loading.” *Engineering Fracture Mechanics*, Elsevier Ltd, 220, 106646.

Zhang, Y., Wang, Z., Zhang, J., Zhou, F., Wang, Z., and Li, Z. (2019c). “Validation and investigation on the mechanical behavior of concrete using a novel 3D mesoscale method.” *Materials*, MDPI AG, 12(16).

Zhang, Z., Song, X., Liu, Y., Wu, D., and Song, C. (2017). “Three-dimensional mesoscale modelling of concrete composites by using random walking algorithm.” *Composites Science and Technology*, Elsevier, 149, 235–245.

Zhou, K., Bao, H., and Shi, J. (2004). “3D surface filtering using spherical harmonics.” *CAD Computer Aided Design*, Elsevier, 36(4), 363–375.

Zhou, R., Song, Z., and Lu, Y. (2017). “3D mesoscale finite element modelling of concrete.” *Computers & Structures*, Pergamon, 192, 96–113.

Zhou, Y., Jin, H., and Wang, B. (2019). “Modeling and mechanical influence of meso-scale concrete considering actual aggregate shapes.” *Construction and Building Materials*, Elsevier Ltd, 228.

Minerva Access is the Institutional Repository of The University of Melbourne

Author/s:

Thilakarathna, PSM;Kristombu Baduge, S;Mendis, P;Chandrathilaka, ERK;Vimonsatit, V;Lee, H

Title:

Aggregate Geometry Generation Method Using a Structured Light 3D Scanner, Spherical Harmonics-Based Geometry Reconstruction, and Placing Algorithms for Mesoscale Modeling of Concrete

Date:

2021-08-01

Citation:

Thilakarathna, P. S. M., Kristombu Baduge, S., Mendis, P., Chandrathilaka, E. R. K., Vimonsatit, V. & Lee, H. (2021). Aggregate Geometry Generation Method Using a Structured Light 3D Scanner, Spherical Harmonics-Based Geometry Reconstruction, and Placing Algorithms for Mesoscale Modeling of Concrete. *Journal of Materials in Civil Engineering*, 33 (8), [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0003851](https://doi.org/10.1061/(ASCE)MT.1943-5533.0003851).

Persistent Link:

<http://hdl.handle.net/11343/275098>