IN VIVO TISSUE ENGINEERING OF AN ADIPOSE TISSUE FLAP USING FAT GRAFTS AND ADIPOGEL

SHORT RUNNING TITLE: In vivo tissue engineering of an adipose tissue flap

AUTHORS

Heidi Debels, M.D. ^{1, 4, 5}

Jason Palmer, B.Sc. (Hons) ^{1, 2}

Xiao-Lian Han, M.Sc. ¹

Christopher Poon, B.Sc., Ph.D. ^{1, 2}

Keren Abberton, M.Rep.Sci., Ph.D. ^{1, 2, 3}

Wayne Morrison, M.D.B.S., F.R.A.C.S. ^{1, 2, 3}

¹ O'Brien Institute Department, St Vincent's Institute, 42 Fitzroy Street, Fitzroy, VIC. 3065, Australia

² University of Melbourne Department of Surgery, St. Vincent's Hospital Melbourne, Fitzroy VIC.

3065, ³ Australian Catholic University, Faculty of Health Sciences, Fitzroy VIC 3065, Australia

⁴ Free University Brussels (VUB), Campus Jette, Laarbeeklaan 103, 1090 Brussel, Belgium

⁵ Maastricht University, Universiteitssingel 60, 6229 ER Maastricht, The Netherlands

CORRESPONDING AUTHOR

This is the author manuscript accepted for publication and has undergone full peer review but has not been through the copyediting, typesetting, pagination and proofreading process, which may lead to differences between this version and the Version of Record. Please cite this article as doi: [10.1002/term.3027](https://doi.org/10.1002/term.3027)

Jason Palmer

O'Brien Institute Department, St Vincent's Institute, 42 Fitzroy Street, Fitzroy, VIC. 3065, Australia

Email: jpalmer@svi.edu.au

IN VIVO TISSUE ENGINEERING OF A PEDICLED ADIPOSE TISSUE FLAP USING FAT GRAFTS AND ADIPOGEL

ABSTRACT

For decades, plastic surgeons have spent considerable effort exploring anatomical regions for free flap design. More recently, tissue-engineering approaches have been utilised in an attempt to grow transplantable tissue flaps in-vivo. The aim of this study was to engineer a fat flap with a vascular pedicle by combining autologous fat grafts and a novel acellular hydrogel (Adipogel) in an established tissue engineering model comprising a chamber and blood vessel loop. An arteriovenous loop was created in the rat groin from the femoral vessels and positioned inside a perforated polycarbonate chamber. In Group 1 the chamber contained minced, centrifuged autologous fat, in Group 2 Adipogel was added to the graft while in Group 3 Adipogel alone was used. Constructs were histologically examined at 6 and 12 weeks. In all groups new tissue was generated. Adipocytes, while appearing viable in the graft at the time of insertion, were predominantly non-viable at 6 weeks. However by 12 weeks new fat had formed in all groups and was significantly greater in the combined fat/Adipogel group. No significant difference was seen in final construct total volume or construct neovascularization between the groups. This study demonstrated that a pedicled adipose flap can be generated in rats by combining a blood vessel loop, an adipogenic hydrogel and a lipoaspirate equivalent. Success appears to be based on adipogenesis rather than on adipocyte survival, and

consistent with our previous work this adipogenesis occurred subsequent to graft death and remodelling. The regenerative process was significantly enhanced in the presence of Adipogel.

KEYWORDS

Adipose tissue engineering; adipose tissue flap; adipogenesis; fat grafting; hydrogel; arterio-venous loop chamber model

INTRODUCTION

For decades, plastic surgeons have spent considerable effort exploring optimal anatomical regions for free tissue-flap design. Such vascularised fat flaps remain the favoured approach for reconstruction of soft-tissue defects where larger volumes of adipose tissue are required than can be provided by conventional free fat grafting techniques (Dolderer et al., 2007; Kelly et al., 2006). We have used tissue-engineering approaches in pre-clinical models (Dolderer et al., 2007; Dolderer et al., 2011; Findlay et al., 2011; Messina et al., 2005) and in a limited clinical trial (Morrison et al., 2016) in an attempt to grow vascularised fat flaps in-vivo. One approach to engineer such an adipose tissue flap is to combine free fat grafts with a space-protecting chamber (Findlay et al., 2011; Kelly et al., 2006; Stillaert et al., 2007; Ting et al., 2014). With an appropriate chamber configuration and vascular

supply, the ideal outcome would be a construct filling the chamber that has its own vascular supply and could be grown in situ or transplanted to the desired recipient site.

A major concern with free fat grafting is the strong tendency for graft absorption and volume loss over time (Harrison, Malafa, Davis, & Rohrich, 2015; Zielins, Brett, Longaker, & Wan, 2016). Recent studies by other groups provide strong support for the hypothesis that when fat grafting is successful, this is explained by graft remodelling by stem cells rather than by adipocyte survival (Doi et al., 2015; Dong et al., 2015; Eto et al., 2012; Kato et al., 2014; Zhang et al., 2018). Furthermore, we have reported that the vast majority of grafted adipocytes die when human fat grafts are implanted in a flow-through chamber model (Stillaert et al., 2007) or subcutaneously in the scalp (Tang et al., 2018) in mice, and yet new fat growth was seen in each case that was largely host-derived. We (Tang et al., 2018) and others (Kato et al., 2014) have also suggested that after such adipocyte death, these dead cells, along with their lipid content and surrounding extracellular matrix, still likely play a positive role in maintaining graft volume during the subsequent regenerative process.

Here we investigate the capacity to develop a vascularised fat flap by implanting an autologous free fat graft into a larger chamber containing an arterio-venous (AV) loop in the rat. In this model we have shown in multiple studies that tissue can grow within a perforated polycarbonate chamber housing a blood vessel loop extension of the femoral vessels (Choi, Matsuda, Disting, Morrison, & Dilley, 2010; Hachisuka, Disting, Abberton, Morrison, & Jiang, 2008; Hofer et al., 2003; Lokmic, Stillaert, Morrison, Thompson, & Mitchell, 2007; Matsuda et al., 2013; Mian et al., 2000; Morritt et al., 2007; Tanaka, Tsutsumi, Crowe, Tajima, & Morrison, 2000). We also postulated that the addition of an adipogenic matrix to the lipoaspirate could lead to enhanced fat flap formation. We have

developed such a matrix, Adipogel, made from de-cellularised adipose tissue (Poon et al., 2013). The combination of Adipogel and adipose tissue stromal-vascular fraction (SVF) cells was shown to enhance the growth of host-derived fat in the subcutaneous fat-grafting model described above (Tang et al., 2018). We thus implanted AV-loop chambers with either fat graft alone (group 1), fat graft enriched with 1mL of porcine-derived Adipogel (group 2) or Adipogel alone (group 3). Constructs were assessed for total volume, graft-adipocyte survival, neo-vascularisation and regional morphology at 6 and 12 week time points, in order to characterise the regenerative response seen.

METHODS

Materials

Adipogel was prepared using the method described previously (Poon et al., 2013). Briefly, porcine fat was homogenised, decellularised with dispase, the lipids removed by multiple washes and proteins extracted with urea and dialysed against Tris-buffered saline. The un-extracted proteins remaining were separately digested with pepsin, dialysed and added back to the first extract. This was then sterilised by dialysis against chloroform to yield the final Adipogel product, a thermosensitive gel which solidifies at 37°C and is rich in the extra-cellular matrix proteins and growth factors from

adipose tissue. It was stored at -20°C prior to thawing for 1 hour before use in our chamber model, where polycarbonate perforated hemispheric chambers with an internal capacity of 2mL were used.

Animal model

The study was approved by the St. Vincent's Hospital Animal Ethics Committee and conducted according to National Health and Medical Research Council Guidelines (Australia). Male Sprague-Dawley rats (weight 350-750g) were anaesthetized and a 1mL fat biopsy taken from the left groin. This fat was minced and then centrifuged at 3000 RPM (1286g) for 3 minutes, and the entire tube contents subsequently used. It was either kept in the same tube for 1.5 hours at 37°C prior to use (Group 1), or mixed with 1mL Adipogel (Group 2) and allowed to set at 37°C for 1.5 hours. Meanwhile in the same animal a chamber containing an arterio-venous loop was microsurgically created in the right groin (Fig. 1). Briefly, the femoral vessels of both legs were exposed between the inguinal ligament proximally and the bifurcation of the saphenous and popliteal vessels distally. A 10 mm vein graft was dissected from the left femoral vein and interposed between the proximal stumps of the divided right femoral vessels with micro-anastomoses to create an arterio-venous loop. The circular disc base of the polycarbonate chamber was placed underneath the loop and fixed to the underlying muscle fascia.

In Group 1, the processed fat graft was carefully packed around the loop before closure, whilst for Groups 2 (mixture) and 3 (Adipogel alone) the contents were set in the dome prior to placing onto the loop and suturing in place. The fat from the group 3 rats was harvested and minced as per Groups 1 and 2 and used for time-point 0 analysis. 6 of these samples were centrifuged as above, whilst the other 6 were not. All were maintained at 37°C for 1.5 hours prior to fixation as below.

Harvest and assessment

Chamber tissue was harvested at either 6 weeks (n= 2-6) or 12 weeks (n=6) post implantation. Under anaesthesia, the chamber was exposed and the femoral artery and vein were assessed for patency and then ligated 5 mm proximal to the chamber entrance. The lid was opened and the construct removed and assessed for mass and volume using a standard displacement method. The tissue was fixed in neutral buffered formalin, cut into 2 mm thick vertical slices sectioning the AV loop transversely and routinely processed to paraffin wax. Serial 5µm sections were made from each vertical tissue slice whilst the timepoint 0 samples were sectioned through their midpoints. Routine haematoxylin and eosin (H&E) staining was performed on a section of each slice prior to immunostaining as below.

Immunohistochemistry

Perilipin, von Willebrand Factor (vWF), CD34 and alpha smooth muscle actin (α SMA) immunoperoxidase staining was performed with a DAB (Dako, Glostrup, Denmark) label on a section from each slice. Perilipin (1:250; Cell Signaling Technology Inc., Danvers, Massachusetts, USA) was used to distinguish viable from non-viable adipocytes. vWF (1:200; Millipore, Temecula, California, USA) was used for blood vessels. CD34 (1:400; Santa Cruz, Dallas, TX) was used for stromal/stem cells and as a second blood vessel marker. α SMA (1:500; Dako) was used to label activated (myo-) fibroblasts.

Histomorphometry

To quantify viable adipocytes as a percentage of construct volume histomorphometry was performed on a perilipin-stained section of each chamber slice. An Olympus BH-2 microscope and video camera (Tokyo, Japan) was used in conjunction with the Computer Assisted Stereological Toolbox (CAST, Olympus) system for point counting using a 20x objective. Estimation of percent vascular volume was similarly performed on vWF-labelled sections. The vascular pedicle volume was calculated separately for each construct and subtracted from the gross construct volume, giving a net construct volume and allowing accurate determination of percent neo-vascularisation.

Statistical Analysis

Statistical analysis was performed using GraphPad Prism 8 software (La Jolla, Calif., USA) . Results were compared using one way analysis of variance (ANOVA) and Tukey's post hoc test or student t test as appropriate. P-values < 0.05 were considered statistically significant and results are expressed as means $\pm$ standard error of the mean (SEM).

RESULTS

Centrifuged fat composition

H&E staining of the centrifuged fat grafts at time of insertion showed that most of the adipocytes were located in the upper part of the tube (Fig. 2A). For about two thirds of their volume, both non-centrifuged and centrifuged groups consisted of adipocytes ($67.5\% \pm 5.6$ and $64.1\% \pm 2.4$

respectively, Fig. 2B). Samples were stained for perilipin to visualise viable adipocytes and point counting performed (Fig. 2B, C). Adipocytes with no perilipin staining or reduced staining were considered dying or dead, while cells with a continuous perilipin rim were considered viable. The great majority of adipocytes were alive at the time of insertion ($86.1\% \pm 3.8$ non-centrifuged and $78.8\% \pm 4.4$ centrifuged). No significant differences between the 2 groups could be detected either in adipocyte percentage or viable adipocyte percentage. On this basis and because we wanted to mimic clinical practice, centrifuged fat was used for fat grafting.

Macroscopic Appearance at Harvest and Total Volume of Construct Tissue

Externally, chambers were covered by a thin fibrotic capsule (Fig. 3A-C). Tissue within the chamber was continuous with this external capsule through the perforations in the dome, and often appeared to fill the chamber. In these samples, after the capsule was stripped away, the connections severed and the dome removed, there was usually some retraction away from the internal chamber surface and apparent volume reduction of the underlying construct. Constructs had a hemispheric shape with several nubbins present at the surface, the remnants of the connections to the external capsule. These nubbins had a red, richly-vascularised appearance, and there were no obvious differences in overall macroscopic appearance between the 3 groups at either time point (Fig 3D-F). *A video showing the appearance of the construct tissue (Group 2, 12 weeks) immediately after dome removal can be seen in in the Supplementary Materials.*

At 6 weeks total construct volume in the fat alone group (Group 1) was only slightly reduced compared to the original inserted volume ($885\mu\text{l} \pm 270$ vs $1000\mu\text{l}$) (Fig. 3G). Construct volumes in

Groups 2 and 3 were very similar ($851\mu\text{l} \pm 40$ and $889\mu\text{l} \pm 122$ respectively). At 12 weeks there was a slight but not significant increase in volume in groups 1 ($1154\mu\text{l} \pm 121$) and 3 ($946\mu\text{l} \pm 66$) over that seen at 6 weeks, whilst for group 2 the increase was significant ($1117\mu\text{l} \pm 79$; $p=0.03$).

A preliminary analysis of Group 3 samples only has been previously published (Debels, 2015).

Viable Adipocyte Fraction

At 6 weeks, perilipin staining made it readily apparent that there were large regions of dead adipocytes as well as oil cysts in the 2 groups receiving fat grafts (Fig. 4A, B). Some chamber contents were sufficiently necrotic and liquefied that tissue suitable for histological processing could not be obtained. These samples had to be excluded from the study, leaving $n=2$ and $n=4$ for groups 1 and 2 respectively. Quantitation of the remaining samples nonetheless revealed a significant reduction in the volume of viable adipocytes in both groups ($13.5\mu\text{l} \pm 11.5$; $p=0.0002$ and $74.2\mu\text{l} \pm 7.3$; $p<0.0001$) (Fig. 4G) compared to the $504.0\mu\text{l} \pm 34.0$ viable adipocytes (Fig. 2B) per ml of minced centrifuged fat at the time of insertion. In the Adipogel-alone group (3) a small number of viable (new) adipocytes had formed ($29.3\mu\text{l} \pm 18.0$) (Fig. 4C, F).

At 12 weeks all chambers produced solid tissue without gross necrosis or infection. Histology showed the total viable adipocyte volumes had substantially increased in all groups compared with 6 weeks. Group 1, $172.5\mu\text{l} \pm 60.6$ vs $13.5\mu\text{l} \pm 11.5$ ($p=0.18$); group 2, $428.9\mu\text{l} \pm 61.3$ vs $74.2\mu\text{l} \pm 7.3$ ($p<0.002$); group 3, $134.8\mu\text{l} \pm 30.9$ vs $29.3\mu\text{l} \pm 18.0$ ($p=0.01$), evidence of neo-adipogenesis in all

groups (Fig. 4D-F). At 12 weeks significantly more viable adipocytes were present in group 2 compared with groups 1 ($p=0.01$) and 3 ($p<0.003$).

Regional Morphology, Vascularisation and Adipogenesis of Construct

The construct vascularisation response was clearly visualised with both CD34 and vWF endothelial labeling in samples at 6 weeks. In the Adipogel-alone group, quantitation revealed a trend towards greater percent vascular volume at 6 weeks compared with the other 2 groups ($7.33 \pm 1.39\%$ vs $3.44 \pm 1.12\%$ and $3.81 \pm 0.61\%$ in Groups 1 and 2 respectively ($P=0.12$)) (Fig. 5). Vessels appeared to sprout easily from the AV loop into the adjacent gel and be relatively large when compared with the other 2 groups (Fig. 6A-C) where mostly necrotic fat was adjacent to the loop. Vessel sprouting was always from the vein component of the loop rather than the vein graft or artery.

Despite the most florid vascular response occurring near the loop in the Adipogel-alone group, perilipin staining revealed that there was very little adipogenesis in this region at 6 weeks. Those minimal viable adipocytes that were noted were either here or within the nubbins, as was also true for the Fat-alone group (G1) (Fig. 6D, F, perilipin). For the FAT + Adipogel (G2) group, where there were more viable adipocytes, this was more likely to be closer to the loop than the nubbins, despite relatively little angiogenesis in this region (Fig. 6E). Whilst necrotic regions in the fat-graft groups had relatively low vascularity, small capillary-like vessels were none-the-less consistently seen by this time point amongst dead adipocytes and lipid-cysts (Fig. 6H, FAT + Adipogel, CD34). Though less

frequently, similar vessels were also observed in the Adipogel-alone group, centrally within the construct, i.e. not directly adjacent to the AV loop (Fig. 6I). In all three groups, there was little evidence for the presence of stromal / stem cells in these regions at this time point as assessed by combined CD34 expression and stem cell like morphology, although they were often noted in the adventitia of the loop artery (Fig. 6G, Fat-alone, CD34).

At 12 weeks, mean percent vascular volumes were now similar for all 3 groups ($4.58 \pm 0.74\%$, $4.37 \pm 0.66\%$, $5.34 \pm 0.43\%$, Groups 1-3 respectively, $p=0.50$, Fig. 5). Vascular density was higher in those regions where mature-like fat was present, as exemplified by constructs from Group 2 (FAT + Adipogel), where viable adipocytes along with blood vessels were often present throughout the chamber space (Fig. 6K, CD34; Fig 4E perilipin; Supp. Fig. 1A). In this group adipocyte masses originating from both near the loop and the nubbins have merged, thus replacing the necrotic graft tissue seen at 6 weeks. In the other two groups, although viable fat masses showed a tendency to expand towards the centre of the construct from the loop and/or nubbins compared to 6 weeks, there still often remained areas with dead adipocytes / lipid cysts and fibrotic elements (Group 1, Fig. 6J, 4D, perilipin) or looser connective tissue / degraded Adipogel (Group 3, Fig 6L, 4F). In all groups, fat present within the nubbins was always separated from any external fat by the fibrous capsule external to the chamber previously described (Fig. 3A, B) and was clearly therefore not the result of this external fat penetrating or expanding in through the chamber pores.

A connective tissue capsule, macroscopically similar to the external one described above, was noted in those superficial regions of the construct directly adjacent to the internal solid polycarbonate

chamber wall, in all groups and at both time points. . Fat within the chamber was often continuous with nubbin fat, and a thick, perilipin-negative capsule visible in sections at each side of this (*Supp. Fig. 1A*). Alpha smooth muscle actin staining demonstrated the extent of this capsule, which contained many activated (Zeisberg & Kalluri, 2013) fibroblasts (*Supp. Fig. 1B*, FAT + Adipogel, 12 weeks). This was observed in tissue adjacent to both the internal chamber surface as well as the surfaces of the perforations, where the nubbin tissue was located. Vascular, mature looking fat can also be seen in the nubbin in this image.

DISCUSSION

This study demonstrates that within the protected environment of a chamber, a vascularized adipose tissue flap can be generated in vivo when a fat graft is combined with an adipogenic gel. Neither of these components alone was effective at producing a comparable volume of vascularized fat. Although we were unable to demonstrate that the addition of Adipogel significantly enhanced survival of the graft's constituent adipocytes in Group 2, by 12 weeks substantial construct remodelling had led to the development of new, mature-looking adipose tissue despite the presence of very few viable adipocytes at 6 weeks. In fact, the total volume of viable, regenerated adipocytes at 12 weeks was more than double that compared to when Adipogel was absent (429 vs 173 μ l, $p=0.01$, and had almost returned to the volume of viable adipocytes in the original, centrifuged fat graft (504 μ l).

Despite high adipocyte viability (nearly 80%) at the time of insertion in the fat graft groups, all samples showed a minimal number of viable adipocytes at 6 weeks, clearly indicating the large extent of adipocyte death within this period. Adipogel could not be demonstrated to improve adipocyte survival in Group 2 compared with Group 1 (fat-alone), although surgical complications leading to n=2 only for the latter at 6 weeks made a strong comparison difficult ($p=0.11$, one way ANOVA). That the bulk of graft adipocytes die is not surprising, and has been demonstrated in numerous recent experimental studies (Doi et al., 2015; Dong et al., 2015; Eto et al., 2012; Kato et al., 2014; Stillaert et al., 2007; Tang et al., 2018; Zhang et al., 2018). The chamber model of this experiment, where the protected space was filled with a large volume of grafted fat (with or without Adipogel), closely parallels the clinical scenario where despite the use of diffuse injection patterns, cumulative volumes inevitably coalesce leading to exponential ischemia of the cell content. Adipocytes have a high metabolic rate and are therefore prone to ischemia. Early cell death, even within the first 24 hours, has been reported (Eto et al., 2012).

It is becoming increasingly clear from a number of recent studies that if there is adipocyte survival in grafted fat, this is restricted to the very outermost (100-300 μ m) layer (Doi et al., 2015; Dong et al., 2015; Eto et al., 2012; Kato et al., 2014; Tang et al., 2018; Zhang et al., 2018), termed the “survival zone” (Eto et al., 2012). We were unable to identify such a zone in our constructs, and indeed both adipocytes and ASCs (discussed below) throughout the graft showed very poor survival. In a completely sealed chamber model, such poor survival might be at least partly explained by the minimal contact between grafted fat within the chamber and the living tissue external to the chamber, when compared with the close contact that exists when fat grafts are injected directly into the tissues. This could result in inadequate diffusion and cellular death in the early period prior to

construct vascularization. In our study, we used a perforated chamber since previously we have demonstrated that perforations do result in superior construct vascularisation and adipogenesis when compared with non-perforated chambers (Dolderer et al., 2007; Dolderer et al., 2011), and we hypothesized that this may in part be due to greater graft survival. Despite using a perforated chamber however, graft survival was poor, and it seems this perforation-derived vascularization may have occurred too late to save the grafted cells from ischaemic death.

In comparison to adipocytes, adipose-derived stem cells (ASCs) are thought to have a greater tolerance of ischemic conditions (Eto et al., 2012), and may contribute to tissue regeneration after graft adipocyte death by acting as a source of adipocyte precursors, or in a paracrine manner as a source of various growth factors and immunomodulatory agents (Garza et al., 2015). In our recent study (Tang et al., 2018) on fat graft survival in a mouse scalp (non-chamber) model, we were able to identify numerous graft-derived, surviving ASC/stromal cells, based on CD34-expression and characteristic morphology. These cells survived only at the periphery of the graft and appeared to be activated and proliferating in response to the dying graft adipocytes. They did not differentiate into adipocytes but contributed to the neo-vasculature. In the current study, by comparison, although we saw similar CD34-positive cells in the adventitia of the AV loop artery, very few such cells were noted in or around the dead adipocytes at either 6 or 12 weeks. Of note, CD34-positive ASCs have been previously described in an adventitial location (Maumus et al., 2011; Zimmerlin et al., 2010). In regards to our observations, the absence of CD34-positive stromal/stem cells amongst the dying adipocytes suggest that the ASCs in the original graft do not survive the ischaemia of this model. If this is the case, then adipocyte precursors would need to come either from circulating cells migrating from the growing chamber vasculature, from an influx of stem cells from the surrounding tissue

through the chamber perforations, or from the adventitial cells (CD34-positive) noted on the AV loop. Precursors for the Adipogel-alone group would also have to be from one of these sources.

Vascularisation and adipogenesis are tightly coordinated events during both development and adulthood (Christiaens & Lijnen, 2010; Han et al., 2011), and vascularisation that is both timely and pervasive is a key aim in adipose tissue engineering (Debels et al., 2013; Kawaguchi et al., 1998; Zhang et al., 2018). When used by itself, Adipogel (Group 3) seemed to facilitate vascular invasion from the AV loop at the earliest time point, compared with Group 2 where the presence of necrotic adipocytes may have impeded invasion through the gel component. This likely explains the higher percent vascularisation observed in Group 3 across the entire chamber cross-section, although this trend did not reach statistical significance. The florid vascularisation seen did not however result in significant adipogenesis at the same time point. The two fat-graft groups (1 and 2) also had minimal viable adipocyte numbers at this point, and it was not clear as to whether those that were indeed seen near the loop were survivors from the original graft or newly generated cells. It is quite possible that they are new cells, and the neo-adipogenesis seen so obviously at 12 weeks has already begun by 6 weeks, after total graft adipocyte death. In terms of vascularisation within necrotic fat, at 6 weeks a small, yet consistent number of CD34 and vWF-positive vessels were noted, but, as above, we could not be clear as to whether they were surviving vessels from the graft or newly grown from stem/precursor cells. The small size, and capillary-like appearance of these vessels does however suggest that they may be newly-formed vessels. If this is the case, the graft or host origin of their precursors is unknown.

By 12 weeks, percent vascular volumes were similar across all groups and Adipogel, whether by itself or with a fat graft, had no apparent advantage in facilitating or improving vascularisation compared with the fat-alone group (1). The degree of vascularisation in any given region, and for all groups, appeared to closely match the size and maturity of the adipocyte masses there. Where mature-like fat was seen at the nubbins, vascular density was relatively high, suggesting again that vascular infiltration from surrounding tissue through the chamber perforations was important in helping to vascularise the outer part of the construct and thus maximise the viable fat produced in the chambers (Dolderer et al., 2007; Dolderer et al., 2011). Nutrition provided by the AV loop and its sprouting vessels would similarly support the neo-adipogenesis occurring in that region of the chamber.

In the two fat graft groups, even though the bulk of the adipocytes died, they remained present and retained much of their spatial volume at least up till 12 weeks. As previously noted by us (Tang et al., 2018) and others (Kato et al., 2014) the dying graft seems to function as a scaffold, maintaining space and facilitating neovascularization, remodelling and regeneration. Adipogel by itself however (Group 3) was less able to maintain its original volume, and construct volume shrank down from an initial 2ml volume to 889 μ l at 6 weeks, although stabilized at 946 μ l by 12 weeks. Despite the tendency of Adipogel to lose volume soon after injection, as earlier studies also document (Poon et al., 2013; Tang et al., 2018), it nonetheless clearly has a beneficial effect on adipose tissue growth. This may be by way of growth factor release into adjacent regions, since Adipogel, like Matrigel, has been shown to contain both important matrix components and numerous growth factors (Poon et al., 2013). Although the current study in itself sheds little light on the mechanism(s) by which Adipogel, when used in combination with a fat graft, had its beneficial effect, earlier studies by our group provide

important clues and suggest a plausible sequence of events. (1) An initial inflammatory stimulus is the key early event, and we have shown that this can be provided by Zymosan (yeast-derived particles (Thomas et al., 2008)) monocyte chemoattractant protein (MCP-1) (Hemmrich et al., 2007), or in the current study, the dying graft in Groups 1 and 2. Other researchers have made similar findings (Hattori & Ishihara, 2015; Li et al., 2016; Peng et al., 2014). (2) This leads to macrophage, and subsequent stem cell infiltration into the chamber within the first few days (Lilja et al., 2013). We have also shown that when macrophages are locally depleted with Clodronate liposomes, vascularization and adipogenesis are severely impeded (Debels et al., 2013). (3) Vascularization follows within 1-2 weeks, and (4) at some point between 6 and 12 weeks, the Adipogel stimulates the stem cells present to differentiate, as has been shown in vitro (Poon et al., 2013), into mature adipocytes.

Although clearly defining the origin of regenerated adipocytes and blood vessels was not possible in this study due to the use of autologous grafts, the use of autologous fat nonetheless maximised the chances of graft-host compatibility and cell survival when compared with comparable studies using xenografts or allografts. That cellular survival was still poor in our model despite this, is entirely consistent with our previous work over numerous studies and multiple models of fat grafting and tissue engineering, and further supports the concept of inductive adipogenesis whereby the key elements of regeneration are an initial graft-derived inflammatory stimulus and subsequent adipogenesis from host-derived precursors (Debels et al., 2013; Hemmrich et al., 2007; Lilja et al., 2013; Messina et al., 2005; Stillaert et al., 2007; Tang et al., 2018; Thomas et al., 2008; Ting et al., 2014).

We did not in this study perform assessments of vascular perfusion to show that the fatty tissue derived from the nubbins is functionally connected to that derived from the central vascular pedicle, and so cannot prove that this peripheral fat would remain healthy had we transferred the pedicled-construct to another site. We acknowledge that this makes our designation of the construct as a tissue flap somewhat questionable. However it was not the purpose of this study to demonstrate the viability of this construct by transfer to another site, since we have done this previously in rats (Dolderer et al. 2011) and pigs (Findlay et al., 2011). In the current study fusion of fat masses from AV loop and nubbin-derived locations seen in the Fat plus Adipogel group was seen frequently and one would assume the vasculatures would also merge and make it likely that the tissue if transplanted would survive without peripheral necrosis. In any case, a key message of our study, that a construct can be generated by neo-adipogenesis despite negligible graft-cell survival, remains strong.

CONCLUSION

This study demonstrated that a pedicled adipose flap can be generated in rats by combining a novel acellular matrix (Adipogel) with a fat graft. 12 weeks after implantation of a chamber containing a blood vessel loop, substantial adipogenesis was seen. Adipogel, with its hydrogel properties and angiogenic and adipogenic growth factor profile, has clear potential as an adjunct to fat grafting to improve outcomes. Furthermore, this study supports the concept that fat graft success is based on adipogenesis rather than on adipocyte survival, and consistent with our previous work, this adipogenesis occurred in the setting of significant graft death and remodelling.

ACKNOWLEDGEMENTS

We gratefully acknowledge the funding support from the Victorian State Government Grant for the Neopec Grant, through its Science, Technology and Innovation Program. We also received valuable support from the National Breast Cancer Foundation Australia (Grant NC 11-01) and the Victorian State Governments Department of Business Innovation Operational Infrastructure Support Plan. The authors acknowledge the surgical assistance of the staff of the Experimental Medical and Surgical Unit, St Vincent's Hospital, Melbourne (Sue McKay, Liliana Pepe, Anna Deftereos and Amanda Rixon) and the Department of Chemical and Biomolecular Engineering, University of Melbourne for their collaboration.

CONFLICT OF INTEREST STATEMENT

The authors have no conflict of interest to declare.

REFERENCES

- Choi, Y. S., Matsuda, K., Dusting, G. J., Morrison, W. A., & Dilley, R. J. (2010). Engineering cardiac tissue in vivo from human adipose-derived stem cells. *Biomaterials*, 31(8), 2236-2242. doi:10.1016/j.biomaterials.2009.11.097
- Christiaens, V., & Lijnen, H. R. (2010). Angiogenesis and development of adipose tissue. *Mol Cell Endocrinol*, 318(1-2), 2-9. doi:10.1016/j.mce.2009.08.006
- Debels, H. (2015). Advances in tissue engineering; a novel technology making use of an in vivo vascularized chamber. *Acta Chir Belg*, 115(2), 104-110.
- Debels, H., Galea, L., Han, X. L., Palmer, J., van Rooijen, N., Morrison, W., & Abberton, K. (2013). Macrophages play a key role in angiogenesis and adipogenesis in a mouse tissue engineering model. *Tissue Eng Part A*, 19(23-24), 2615-2625. doi:10.1089/ten.TEA.2013.0071

- Doi, K., Ogata, F., Eto, H., Kato, H., Kuno, S., Kinoshita, K., . . . Yoshimura, K. (2015). Differential contributions of graft-derived and host-derived cells in tissue regeneration/remodeling after fat grafting. *Plast Reconstr Surg*, 135(6), 1607-1617. doi:10.1097/PRS.0000000000001292
- Dolderer, J. H., Abberton, K. M., Thompson, E. W., Slavin, J. L., Stevens, G. W., Penington, A. J., & Morrison, W. A. (2007). Spontaneous large volume adipose tissue generation from a vascularized pedicled fat flap inside a chamber space. *Tissue Eng*, 13(4), 673-681. doi:10.1089/ten.2006.0212
- Dolderer, J. H., Thompson, E. W., Slavin, J., Trost, N., Cooper-White, J. J., Cao, Y., . . . Abberton, K. M. (2011). Long-term stability of adipose tissue generated from a vascularized pedicled fat flap inside a chamber. *Plast Reconstr Surg*, 127(6), 2283-2292. doi:10.1097/PRS.0b013e3182131c3e
- Dong, Z., Peng, Z., Chang, Q., Zhan, W., Zeng, Z., Zhang, S., & Lu, F. (2015). The angiogenic and adipogenic modes of adipose tissue after free fat grafting. *Plast Reconstr Surg*, 135(3), 556e-567e. doi:10.1097/PRS.0000000000000965
- Eto, H., Kato, H., Suga, H., Aoi, N., Doi, K., Kuno, S., & Yoshimura, K. (2012). The fate of adipocytes after nonvascularized fat grafting: evidence of early death and replacement of adipocytes. *Plast Reconstr Surg*, 129(5), 1081-1092. doi:10.1097/PRS.0b013e31824a2b19
- Findlay, M. W., Dolderer, J. H., Trost, N., Craft, R. O., Cao, Y., Cooper-White, J., . . . Morrison, W. A. (2011). Tissue-engineered breast reconstruction: bridging the gap toward large-volume tissue engineering in humans. *Plast Reconstr Surg*, 128(6), 1206-1215. doi:10.1097/PRS.0b013e318230c5b2
- Garza, R. M., Rennert, R. C., Paik, K. J., Atashroo, D., Chung, M. T., Duscher, D., . . . Wan, D. C. (2015). Studies in fat grafting: Part IV. Adipose-derived stromal cell gene expression in cell-assisted lipotransfer. *Plast Reconstr Surg*, 135(4), 1045-1055. doi:10.1097/PRS.0000000000001104
- Hachisuka, H., Dusting, G. J., Abberton, K. M., Morrison, W. A., & Jiang, F. (2008). Role of NADPH oxidase in tissue growth in a tissue engineering chamber in rats. *J Tissue Eng Regen Med*, 2(7), 430-435. doi:10.1002/term.115
- Han, J., Lee, J. E., Jin, J., Lim, J. S., Oh, N., Kim, K., . . . Koh, G. Y. (2011). The spatiotemporal development of adipose tissue. *Development*, 138(22), 5027-5037. doi:10.1242/dev.067686
- Harrison, B. L., Malafa, M., Davis, K., & Rohrich, R. J. (2015). The discordant histology of grafted fat: a systematic review of the literature. *Plast Reconstr Surg*, 135(3), 542e-555e. doi:10.1097/PRS.0000000000000973
- Hattori, H., & Ishihara, M. (2015). Altered protein secretions during interactions between adipose tissue- or bone marrow-derived stromal cells and inflammatory cells. *Stem Cell Res Ther*, 6, 70. doi:10.1186/s13287-015-0052-y
- Hemmrich, K., Thomas, G. P., Abberton, K. M., Thompson, E. W., Rophael, J. A., Penington, A. J., & Morrison, W. A. (2007). Monocyte chemoattractant protein-1 and nitric oxide promote adipogenesis in a model that mimics obesity. *Obesity (Silver Spring)*, 15(12), 2951-2957. doi:10.1038/oby.2007.352
- Hofer, S. O., Knight, K. M., Cooper-White, J. J., O'Connor, A. J., Perera, J. M., Romeo-Meeuw, R., . . . Messina, A. (2003). Increasing the volume of vascularized tissue formation in engineered constructs: an experimental study in rats. *Plast Reconstr Surg*, 111(3), 1186-1192; discussion 1193-1184. doi:10.1097/01.PRS.0000046034.02158.EB

- Kato, H., Mineda, K., Eto, H., Doi, K., Kuno, S., Kinoshita, K., . . . Yoshimura, K. (2014). Degeneration, regeneration, and cicatrization after fat grafting: dynamic total tissue remodeling during the first 3 months. *Plast Reconstr Surg*, 133(3), 303e-313e. doi:10.1097/PRS.0000000000000066
- Kawaguchi, N., Toriyama, K., Nicodemou-Lena, E., Inou, K., Torii, S., & Kitagawa, Y. (1998). De novo adipogenesis in mice at the site of injection of basement membrane and basic fibroblast growth factor. *Proc Natl Acad Sci U S A*, 95(3), 1062-1066.
- Kelly, J. L., Findlay, M. W., Knight, K. R., Penington, A., Thompson, E. W., Messina, A., & Morrison, W. A. (2006). Contact with existing adipose tissue is inductive for adipogenesis in matrigel. *Tissue Eng*, 12(7), 2041-2047. doi:10.1089/ten.2006.12.2041
- Li, Z., Xu, F., Wang, Z., Dai, T., Ma, C., Liu, B., & Liu, Y. (2016). Macrophages Undergo M1-to-M2 Transition in Adipose Tissue Regeneration in a Rat Tissue Engineering Model. *Artif Organs*, 40(10), E167-E178. doi:10.1111/aor.12756
- Lilja, H. E., Morrison, W. A., Han, X. L., Palmer, J., Taylor, C., Tee, R., . . . Abberton, K. M. (2013). An adipoinductive role of inflammation in adipose tissue engineering: key factors in the early development of engineered soft tissues. *Stem Cells Dev*, 22(10), 1602-1613. doi:10.1089/scd.2012.0451
- Lokmic, Z., Stillaert, F., Morrison, W. A., Thompson, E. W., & Mitchell, G. M. (2007). An arteriovenous loop in a protected space generates a permanent, highly vascular, tissue-engineered construct. *FASEB J*, 21(2), 511-522. doi:10.1096/fj.06-6614com
- Matsuda, K., Falkenberg, K. J., Woods, A. A., Choi, Y. S., Morrison, W. A., & Dilley, R. J. (2013). Adipose-derived stem cells promote angiogenesis and tissue formation for in vivo tissue engineering. *Tissue Eng Part A*, 19(11-12), 1327-1335. doi:10.1089/ten.TEA.2012.0391
- Maurus, M., Peyrafitte, J. A., D'Angelo, R., Fournier-Wirth, C., Bouloumie, A., Casteilla, L., . . . Bourin, P. (2011). Native human adipose stromal cells: localization, morphology and phenotype. *Int J Obes (Lond)*, 35(9), 1141-1153. doi:10.1038/ijo.2010.269
- Messina, A., Bortolotto, S. K., Cassell, O. C., Kelly, J., Abberton, K. M., & Morrison, W. A. (2005). Generation of a vascularized organoid using skeletal muscle as the inductive source. *FASEB J*, 19(11), 1570-1572. doi:10.1096/fj.04-3241je
- Mian, R., Morrison, W. A., Hurley, J. V., Penington, A. J., Romeo, R., Tanaka, Y., & Knight, K. R. (2000). Formation of new tissue from an arteriovenous loop in the absence of added extracellular matrix. *Tissue Eng*, 6(6), 595-603. doi:10.1089/10763270050199541
- Morrison, W. A., Marre, D., Grinsell, D., Batty, A., Trost, N., & O'Connor, A. J. (2016). Creation of a Large Adipose Tissue Construct in Humans Using a Tissue-engineering Chamber: A Step Forward in the Clinical Application of Soft Tissue Engineering. *EBioMedicine*, 6, 238-245. doi:10.1016/j.ebiom.2016.03.032
- Morrison, A. N., Bortolotto, S. K., Dilley, R. J., Han, X., Kompa, A. R., McCombe, D., . . . Morrison, W. A. (2007). Cardiac tissue engineering in an in vivo vascularized chamber. *Circulation*, 115(3), 353-360. doi:10.1161/CIRCULATIONAHA.106.657379
- Peng, Z., Dong, Z., Chang, Q., Zhan, W., Zeng, Z., Zhang, S., & Lu, F. (2014). Tissue engineering chamber promotes adipose tissue regeneration in adipose tissue engineering models through induced aseptic inflammation. *Tissue Eng Part C Methods*, 20(11), 875-885. doi:10.1089/ten.TEC.2013.0431
- Poon, C. J., Pereira, E. C. M. V., Sinha, S., Palmer, J. A., Woods, A. A., Morrison, W. A., & Abberton, K. M. (2013). Preparation of an adipogenic hydrogel from subcutaneous adipose tissue. *Acta Biomater*, 9(3), 5609-5620. doi:10.1016/j.actbio.2012.11.003

- Stillaert, F., Findlay, M., Palmer, J., Idrizi, R., Cheang, S., Messina, A., . . . Thompson, E. W. (2007). Host rather than graft origin of Matrigel-induced adipose tissue in the murine tissue-engineering chamber. *Tissue Eng*, 13(9), 2291-2300. doi:10.1089/ten.2006.0382
- Tanaka, Y., Tsutsumi, A., Crowe, D. M., Tajima, S., & Morrison, W. A. (2000). Generation of an autologous tissue (matrix) flap by combining an arteriovenous shunt loop with artificial skin in rats: preliminary report. *Br J Plast Surg*, 53(1), 51-57. doi:10.1054/bjps.1999.3186
- Tang, H. H., Han, X. L., Debels, H., Tan, B., Palmer, J., Poon, C., . . . Morrison, W. (2018). Fate of Free Fat Grafts with or without Adipogenic Adjuncts to Enhance Graft Outcomes. *Plast Reconstr Surg*, 142(4), 939-950. doi:10.1097/PRS.00000000000004739
- Thomas, G. P., Hemmrich, K., Abberton, K. M., McCombe, D., Penington, A. J., Thompson, E. W., & Morrison, W. A. (2008). Zymosan-induced inflammation stimulates neo-adipogenesis. *Int J Obes (Lond)*, 32(2), 239-248. doi:10.1038/sj.ijo.0803702
- Ting, A. C., Craft, R. O., Palmer, J. A., Gerrand, Y. W., Penington, A. J., Morrison, W. A., & Mitchell, G. M. (2014). The adipogenic potential of various extracellular matrices under the influence of an angiogenic growth factor combination in a mouse tissue engineering chamber. *Acta Biomater*, 10(5), 1907-1918. doi:10.1016/j.actbio.2013.11.019
- Zeisberg, M., & Kalluri, R. (2013). Cellular mechanisms of tissue fibrosis. 1. Common and organ-specific mechanisms associated with tissue fibrosis. *Am J Physiol Cell Physiol*, 304(3), C216-225. doi:10.1152/ajpcell.00328.2012
- Zhang, Y., Cai, J., Zhou, T., Yao, Y., Dong, Z., & Lu, F. (2018). Improved Long-Term Volume Retention of Stromal Vascular Fraction Gel Grafting with Enhanced Angiogenesis and Adipogenesis. *Plast Reconstr Surg*, 141(5), 676e-686e. doi:10.1097/PRS.00000000000004312
- Zielins, E. R., Brett, E. A., Longaker, M. T., & Wan, D. C. (2016). Autologous Fat Grafting: The Science Behind the Surgery. *Aesthet Surg J*, 36(4), 488-496. doi:10.1093/asj/sjw004
- Zimmerlin, L., Donnenberg, V. S., Pfeifer, M. E., Meyer, E. M., Peault, B., Rubin, J. P., & Donnenberg, A. D. (2010). Stromal vascular progenitors in adult human adipose tissue. *Cytometry A*, 77(1), 22-30. doi:10.1002/cyto.a.20813

FIGURE LEGENDS

Fig. 1. Surgical procedure. (A and B) The femoral artery (a) and vein (v) and accompanying epigastric branches (*,+) are dissected in the right groin. A femoral vein graft (v'), taken from the left groin, is used to interconnect the distally cut femoral artery (a) and vein (v). The epigastric branches (+', * and +) are kept intact. The chamber base is placed underneath the loop and fixed to the underlying

muscle fascia. (C) A 1mL fat biopsy is taken from the left groin, minced and centrifuged. (D and E) In the fat-only group, this fat is placed on top of the AV loop and the perforated chamber dome sutured in place. (F) In groups 2 and 3, the Adipogel +/- fat is allowed to set in the dome at 37°C prior to placement over loop and the overlying skin closed with sutures.

Fig. 2. Centrifuged fat composition. Most adipocytes (white tissue fraction) were located in the upper part of the centrifuge tube, with denser (pink) tissue at the bottom (A, H&E). For both groups, approximately two thirds of the tissue consisted of adipocytes and centrifugation led only to a minimal reduction in viability (B). Viability was assessed on the basis of perilipin expression (brown rimmed cells, C). Scale bars 2mm.

Fig. 3. Macroscopic appearance at harvest and total construct volumes. Chambers from all 3 groups had a similar appearance (6 week Group 2 chamber shown). After exposing the chamber, the femoral artery (a) and vein (v) were tied just proximal to the chamber entrance (A). Tissue within the chamber was continuous with a thin external capsule (shown intact (A) and being removed (B)) through the dome perforations, and contracted down to a smaller volume when the dome was removed (C and D). Construct nubbins corresponding to the perforations are clearly visible (E) and the construct is shown after slicing for tissue processing to paraffin. In terms of construct volume, in the fat alone group, the original 1ml volume was only slightly reduced at 6 weeks and had been regained by 12 weeks. In group 2 construct volume was significantly greater at 12 vs 6 weeks (*P ≤ 0.05).

Fig. 4: Perilipin staining and quantitation for viable adipocytes. Representative cross-sections of constructs in the Fat (A), Fat+Adipogel (B) and Adipogel alone (C) group at 6 weeks, low magnification. Most of the graft adipocytes appear non-viable (A-B), while a small number of viable adipocytes can be seen in the nubbins in the Fat (A) and Adipogel (C) groups. (D-F) Representative cross-sections of constructs at 12 weeks. More viable adipocytes are clearly present compared to the 6 week constructs from the same groups (directly above), extending now through much of the chamber space in the Fat+Adipogel group (E), as well as in some nubbins. There are fewer viable adipocytes in the other groups (D and F). Scale bars are 2mm and higher magnification images are shown in Fig. 6. Graph (G) shows a significant reduction in viable adipocyte volume at 6 weeks compared to that at the time of insertion for the 2 groups with a fat graft, and a significant increase in viable adipocyte volume in the fat + Adipogel group at 12 weeks compared with the other 2 groups. (* $P \leq 0.05$, ** $P \leq 0.01$, *** $P \leq 0.001$, **** $P \leq 0.0001$)

Fig. 5: Percent vascular volume. As assessed on vWF-stained sections, at 6 weeks there was a trend towards greater percent vascular volume in the Adipogel group compared to the other two groups. By 12 weeks the percentage had dropped for this group and all groups had similar values

Fig. 6: Vascularisation and adipogenesis at 6 and 12 weeks

In all images antibody labelling is visualised with DAB (brown) and counterstaining is with haematoxylin (blue). Left column shows Fat alone, middle column Fat + Adipogel and right column Adipogel alone. (A-C) Vascularisation around the vein component of AV loop (left-hand side of images) at 6 week time point, CD34 IHC. Direct vascular sprouting (s) from vein is seen in Adipogel group (C), and there are many new vessels of various size seen in the nearby tissue, where remnant

Adipogel (a) is blue. Constructs in the two fat-containing groups (A-B) showed less vascularisation in this region, where there were many dead adipocytes and fat cysts (da). Perilipin IHC shows localised adipogenesis (* = perilipin-positive adipocytes) within a nubbin in Fat group (D). In the two Adipogel-containing groups, viable adipocytes were usually located close to the AV loop (av) and not at the nubbins (n) (E-F). Dead adipocytes (da) and remnant Adipogel (a) can also be seen in E. CD34-positive stromal cells (sc) were often seen in the adventitia of the loop artery, but rarely elsewhere for all groups (tm=tunica media) (G, Fat alone). In the necrotic regions of both fat graft groups, small CD34-positive vessels (v) could be seen amongst the larger dead adipocytes and cysts (da) (H, Fat + Adipogel), though less frequently with Adipogel-alone (I). By 12 weeks (below black line), adipocyte masses in many constructs had expanded centrally from apparent origins near the AV loop and the nubbins, as shown clearly here for Adipogel alone (L, perilipin). In the Fat alone group (J, perilipin) the new adipocytes (*) were often interspersed amongst dead adipocytes, whilst in the Fat + Adipogel group (K, CD34) these dead adipocytes were less frequent and much of the construct had the appearance of mature, vascular adipose tissue. Vascular density was higher in those constructs and regions with mature-like fat tissue than in those regions without adipocytes (v=vessels). Scale bars: 200µm A-D; 500µm E, L; 200µm F; 50µm G-I; 100µm J, K

Supplementary materials

Video: Movie showing the appearance of a construct from the Adipogel + fat group (2) at 12 weeks immediately following dome removal at the time of construct harvest. The chamber base is removed and the femoral artery and vein immediately outside the chamber entrance are highlighted. Whitish,

adipose tissue can be seen in the construct when the capsule adjacent to the entrance is partially retracted. The soft, fatty-like consistency of the construct tissue is readily-apparent when it is probed with forceps.

Supplementary Fig 1. Connective tissue capsule and nubbin at 12 weeks. (A, Perilipin, Fat + Adipogel) AV loop and nubbin-origin fat had often merged in constructs from this group, as can be seen here. Part of the thick, non-adipocyte capsule (c) can also be seen to the left and right of this fat. (B, Fat + Adipogel) Dense patches of alpha smooth muscle actin-positive, activated fibroblasts can be seen in the capsule where the construct tissue is in contact with the chamber material in this nubbin (ic= tissue adjacent to internal chamber surface, in = tissue adjacent to internal pore surface). Scale bar 500 μ m A, 200 μ m B.

TERM_3027_F1.tif

TERM_3027_F2.tif

TERM_3027_F3.tif

TERM_3027_F4.tif

TERM_3027_F5.tif

TERM_3027_F6.tif

Fig. 1. Surgical procedure

Fig. 2. Centrifuged fat composition

Fig. 3. Macroscopic appearance at harvest and total construct volumes

Fig. 4. Perilipin staining and quantitation for viable adipocytes

Fig. 5. Percent vascular volume.

Fig. 6 Vascularisation and adipogenesis at 6 and 12 weeks