Running head: Development of a Waste-Based Eco-Friendly Structural Mortar**Development of a Waste-Based Eco-Friendly Structural Mortar without Portland****Cement and Natural Sand**Aliakbar Gholampour¹, Togay Ozbakkaloglu^{2*}, Tuan D. Ngo³**ABSTRACT**

The aim of this study is to develop a new eco-friendly structural mortar for reducing the CO₂ emissions inherent in the use of cement in concrete together with extracting non-renewable natural sands. This clean production is achieved by full replacing cement with glass powder (GP), ground granulated blast furnace slag (GGBS) and fly ash (FA) as industrial by-products, and natural sand (NS) with glass sand (GS) and foundry sand (FS) as waste-based sands. To this end, 26 mortar batches were prepared, and their compressive and direct tensile strength and flowability were studied. Scanning electron microscopy (SEM) and energy dispersive x-ray (EDX) spectroscopy were employed to link the microstructure of the mortars with the obtained properties. The results show that waste-based mortars (WBMs) with NS has a higher flowability compared with those with GS (up to 44%) and FS (up to 47%). The results also reveal that the strengths of WBMs with GS are identical to those with NS, whereas these properties of mortars containing FS are slightly lower (up to 6%). In addition, the results show that when 80% of cement is replaced with GGBS and 100% of NS is replaced with GS or FS,

¹ Postdoctoral Research Fellow, Department of Infrastructure Engineering, The University of Melbourne, Vic, Australia. ORCID: 0000-0001-5069-2963

² (Corresponding author) Professor, Ingram School of Engineering, Texas State University, TX, USA. E: togay.oz@txstate.edu. ORCID: 0000-0003-3015-736X

³ Professor, Department of Infrastructure Engineering, The University of Melbourne, Vic, Australia. ORCID: 0000-0002-9831-8580

This is the author manuscript accepted for publication and has undergone full peer review but has not been through the copyediting, typesetting, pagination and proofreading process, which may lead to differences between this version and the Version of Record. Please cite this article as doi: [10.1002/suco.202000096](https://doi.org/10.1002/suco.202000096)

the strength marginally reduces (up to 7%) compared with the conventional mortar, which is attributed to their similar hydration products amounts at the interfacial transition zones (ITZs) of binder-sand. At cement replacement levels of 90-100% the strength of the WBM degrades, however, the loss in strength is limited to ~20-30%. These promising results indicate the possibility of developing new eco-friendly mortars for structural applications by completely replacing cement and NS with waste materials.

Keywords: Waste-based mortar (WBM); Foundry sand; Glass sand; Fly ash; Glass powder; Ground granulated blast furnace slag (GGBS).

1. Introduction

Owing to their favorable mechanical and durability properties, cementitious materials are widely used in construction around the world (Xie, Gholampour, & Ozbakkaloglu, 2018). However, cement production is responsible for ~5-8% of global CO₂ emissions, which contributes to climate change (Zhang, Li, & Ellis, 2018). Thus, finding alternative eco-friendly materials to cement in order to reduce CO₂ emissions is important (Hajimohammadi, Ngo, & Vongsvivut, 2019). Meantime, the request for natural fine aggregates (e.g. river sand) for the concrete production in large quantity led to the significant reduction of this material which is non-renewable in a few fast-growing countries (such as Singapore and China) (Bravard, Goichot, & Gaillot, 2013). Thus, it is also important to seek a suitable clean material as an alternative to natural sand.

Ground granulated blast furnace slag (GGBS), glass powder (GP) and fly ash (FA) as industrial by-products are the most extensively utilized alternative materials to cement in concrete production (Gholampour, Ozbakkaloglu, Etemadi, & Vincent, 2019; Mastali, Abdollahnejad, & Pacheco-Torgal, 2018). It was reported that about 750 Mt of FA, 530 Mt of GGBS and 130 Mt of waste glass is generated annually, with only 25, 65 and 25% currently being recycled, respectively (Gholampour, Ho, & Ozbakkaloglu, 2019; Gholampour, Ozbakkaloglu, et al., 2019). Therefore, there is significant potential for these pozzolanic materials to be considered as replacements for cement to lessen the environmental effect of waste materials and cement. In addition, sands from waste materials like glass sand (GS) and foundry sand (FS) are currently being considered as alternative materials to natural river sand (NS) (Al-Kerttani, 2018; Gholampour, Ho, et al., 2019; Singh & Siddique, 2012). Owing to their favorable properties, GS and FS are suitable materials for production of concrete for structural applications (Limbachiya, 2009; Makul & Sokrai, 2018; Siddique, De Schutter, & Noumowe, 2009; Taha & Nounu, 2009). Furthermore, FS is a by-product of ferrous and non-ferrous metal casting industrial processes, which is considered as sand-like material and recognized as a high quality silica sand with uniform physical properties (Siddique, Singh, & Singh, 2018). It was reported that about 15 million tons of waste FS is currently generated annually in the US, with only 15% being recycled (Siddique et al., 2009; Siddique et al., 2018). Thus, great potential exists for GS and FS to be considered as an alternative to NS in concrete for reducing the environmental impact of both disposing of waste-based materials in landfill and depletion of NS. This study for the first time in the literature assesses the use of FA, GGBS and GP as

cement alternatives and GS and FS as NS alternatives to produce waste-based mortar (WBM) with 100% cement and sand replacement levels, a concept proposed by the second author.

Many studies were performed to date to investigate the performance of mortars incorporating waste-based materials (e.g. (Benli, 2019; Bilir, Gencel, & Topcu, 2015; Z. Chen & Poon, 2017; Gholampour, Ozbakkaloglu, et al., 2019; Hui, Poon, & Ling, 2013; Lu, Duan, & Poon, 2017; Matos & Sousa-Coutinho, 2016; Öz, Demirel, & Güneş, 2019; Penacho, de Brito, & Veiga, 2014; Supit, Shaikh, & Sarker, 2014)), which showed that these mortars can exhibit desirable mechanical and durability performance. However, none of the them investigated mortars that are entirely composed of waste-based binders, as a replacement for cement, and waste-based sands, as a replacement for natural river sand, simultaneously. Only two studies have been reported to date that investigated mortars with the sand component entirely replaced with GS (Ling & Poon, 2011; Tan & Du, 2013). However, the mortars in these studies were ordinary Portland cement-based mixes.

To address the above-mentioned research gap, this paper presents the first study on the performance of WBM, a new eco-friendly composite material developed by the research group led by the second author, whereby the cement is fully replaced with GGBS, GP and FA and NS with GS and FS. To this effect, compression and tension tests were performed, and a microstructural analysis was conducted on WBMs. The technology presented in this study is promising and has great potential to contribute towards a cleaner construction material as an alternative to conventional concrete by: i) the conservation of NS resources which are non-

renewable; ii) reduction of high CO₂ footprint of cement; and iii) reduction of disposing of waste materials in landfill spaces.

2. Experimental program

2.1. Materials

NS was provided from McLaren Vale Quarry, Fleurieu Peninsula, in South Australia (SA); FS was sourced from Peter Virgin Castings in SA; and GS was sourced from Glass Recovery Service in Victoria. Table 1 and Figure 1 present properties and particle size distribution of NS, FS and GS, respectively.

Binders of high early strength cement (HESC), Class-F FA and GGBS were obtained from Adelaide Brighton Cement Ltd. and GP (with particle size of less than 150 µm) was obtained from Glass Recovery Service in Victoria. The chemical composition of HESC, FA, GGBS and GP used in this study is listed in Table 2.

2.2. Specimens

Table 3 illustrates the mixture proportions. 26 batches of WBMs were produced, including 10 batches with NS at 100% level, 9 batches with GS at 100% level and 7 batches with FS at 100% level. Binders were considered with HESC of 100 (as the control mix), 85, 20, 10 and 0% content level. The effective water-binder (w_{eff}/b) ratio used in all the mortar mixes was 0.65. Flow test together with compression and direct tension tests were conducted on each unique mix to evaluate the performance of WBMs. According to ASTM standards, in the compression

tests cubic samples with 50 mm in size were considered (ASTM-C109/C109M-13, 2013), and dog-bone shaped samples with 25 ± 0.5 mm test region width and depth were considered for direct tension tests (ASTM-C307-03, 2012). Three nominally similar samples were considered for each unique mix. It is notable that owing to the mixture preparation issues the results of FS mixes with 100% GGBS, 15% GP and 75% GGBS/15% GP, and the GS mix with 70% GGBS/10% FA were unavailable.

2.3. Specimens preparation and testing

The mortar mixtures were prepared using NS, GS and FS under the saturated surface dry condition. A fog room with a 23 ± 2 °C temperature was used for curing the demolded samples until test days.

The flowability of the mortars in fresh state was assessed by a flow test, which was performed right after the mortar mixing, according to ASTM standard C1437-15 (ASTM-C1437-15, 2015). Using a universal testing machine, the compressive strength of the hardened mixes was investigated at 7, 14, 28 and 56 days of curing, and the direct tensile strength test was performed at 28 days of curing. Scanning electron microscopy (SEM) analysis was considered to investigate the morphology of fine aggregates, binders and mortars through a High Resolution Field Emission Scanning Electron Microscope (FEI Quanta 450) and energy dispersive x-ray (EDX) spectroscopy was utilized to investigate the constituent elements of the mortars.

For labelling of the specimens listed in Table 3, H, F, G and P letters represent HESC, FA, GGBS and GP, respectively. Following these letters, the numbers point to the wt% of the binder. N, G and F letters at the end represent mixes with 100% NS, GS and FS, respectively. For example, H20G70P10F is a mix produced with FS as fine aggregate, and 20% HESC, 70% GGBS and 10% GP as binder.

3. Test results and observations

3.1. Flowability

Figure 2 illustrates the results of flow test on different mortar mixes. It can be observed that the NS mixes developed the highest flowability for a same type of binder, which was followed by the GS and FS mixes, respectively. The lower flow of GS and FS mixes compared with NS mixes agrees with past research on cement-based mortars (Hui et al., 2013; Monosi, Tittarelli, Giosuè, & Ruello, 2013; Navarro-Blasco, Fernández, Duran, Sirera, & Alvarez, 2013; Tan & Du, 2013) and concretes (Guney, Sari, Yalcin, Tuncan, & Donmez, 2010; Limbachiya, 2009; Singh & Siddique, 2012; H.-Y. Wang, 2009). The lower flow of the GS mixes compared with that of the NS mixes is due to the somewhat smaller size and higher angularity of GS particles than those of NS particles, which leads to forming thicker water layers and lower interparticle friction in NS mixes, as pointed to in Section 3.4.1. In addition, the slightly higher flow of GS mixes compared with FS mixes can be because of the higher permeability of FS than that of GS, which resulted in the formation of thicker water layer around GS compared with FS, as discussed in Section 3.4.1.

It can be observed in Figure 2(a) that mixes with a higher GGBS content had a lower flowability than those with a lower GGBS content for a given sand type. This agrees with previous studies on concretes (Gholampour & Ozbakkaloglu, 2017; C. Wang, Yang, Liu, Wan, & Pu, 2012) and mortars (Güneyisi, Gesoğlu, & Özbay, 2009; Işıkdag & Topçu, 2013) containing NS as fine aggregate. This is because GGBS has a much more rapid reaction with water compared with cement (Divsholi, Lim, & Teng, 2014; Wainwright & Rey, 2000). NS, GS and FS mixes prepared with 90% GGBS experienced a 32%, 50% and 53% lower flow in comparison with the counterpart mixes with 100% HESC, respectively. When GGBS was used at 100% level, the NS and GS mixes developed 36% and 55% lower flow in comparison with the counterpart mixes with 100% HESC, respectively. As seen in Figure 2(b), in the mixes containing FA, those with a higher FA content had a higher flowability than those mixes with a lower FA content. This observation agrees with past research on concretes (Bingöl & Tohumcu, 2013; Şahmaran, Yaman, & Tokyay, 2009) and mortars (Hou et al., 2013; Supit et al., 2014) prepared with NS and concretes (Pathak & Siddique, 2012) prepared with FS. This is because FA has a slower reaction with water compared with that of GGBS and cement (Qiang, Mengxiao, & Dengquan, 2016; Zhao, Sun, Wu, & Gao, 2015).

From Figure 2 it can be observed that only mixes with 85% HESC and 15% GP developed a higher flow in comparison with their counterpart mixes with 100% HESC at a given type of sand. The higher flow of mixes produced with GP compared with that of conventional cement mortar mixes agrees with past research on NS concretes (Schwarz, Cam, & Neithalath, 2008; Soliman & Tagnit-Hamou, 2016) and mortars (Aliabdo, Elmoaty, & Aboshama, 2016; Islam,

Rahman, & Kazi, 2017). This is due to the smaller size of HESC compared with that of GP, which is discussed in detail in Section 3.4.

3.2. Compressive strength

The impact of GGBS, FA and GP content on the compression behavior of the mortar mixes are shown in Figures 3(a)-(c) at 7 to 56 days, respectively. It is shown that mixes prepared with GS developed a similar compressive strength to the companion mixes prepared with NS. As discussed in Section 3.4, this is due to the similar hydration products content in the microstructure of GS mixes to those of companion NS mixes. It is also shown in the figures that the strength of FS mixes was slightly lower (up to 6%) than those of the companion NS mixes, which is due to the less compact microstructure and slightly lower amount of hydration products at the interfacial transition zone (ITZ) of binder-sand of FS mixes compared with those of NS mixes, as discussed in Section 3.4. It is observed in Figure 3 that, at a given type of sand, the compressive strength of 100% HESC mixes was the highest among all the mixes at all curing ages and it decreased with a decreased HESC content. As discussed in Section 3.4, this is due to the higher porosity and lower hydration products content of mixes with a lower HESC content.

As can be seen in Figure 3(a), the mortar mixes with 80% GGBS had a slightly lower compressive strength compared with those produced with 100% HESC. At 7, 14, 28 and 56 days of curing the reductions in compressive strength were respectively 12, 8, 7 and 5% in the NS mixes; 7, 5, 4 and 3% in the GS mixes; and 7, 6, 5 and 2% in the FS mixes. As discussed

in Section 3.4.2, the higher rate of strength gained in the H20G80 mixes compared with that in the H100 mixes at beyond 7 days of curing age is due to the higher silicon and aluminum content in H20G80, leading to the hydration with an extended period. It can also be seen in Figure 3(a) that, for a given curing age, an increased GGBS content beyond 80% led to a decreased compressive strength. This observation agrees with previous research investigating the concrete compressive strength (Gholampour & Ozbakkaloglu, 2017; Kuder, Lehman, Berman, Hannesson, & Shogren, 2012) and is related to the point that mixes with a higher GGBS content had a lower hydration products content and a higher void density in their microstructure, which is discussed in Section 3.4. H10G90 mixes had a strength loss of ~20% at 28 and 56 days in comparison with H100 mixes. In addition, NS and GS mortar mixes with 100% GGBS performed well, at 28 and 56 days exhibiting a strength loss of ~30%.

As shown in Figure 3(b), incorporating FA in WBM with HESC and GGBS led to a decreased compressive strength, agreeing with previous research on the compression behavior of concrete containing HESC, GGBS and FA (Gholampour & Ozbakkaloglu, 2017). This is due to the decreased hydration products content in FA mixes, which will be discussed in detail in Section 3.4.2. At 7, 14, 28 and 56 days of curing, H20G70F10N exhibited 12, 7, 4 and 8% lower compressive strength compared with H20G80N, and H20G70F10F exhibited 16, 10, 6 and 10% lower compressive strength compared with H20G80F, respectively. It is shown in Figure 3(b) that WBMs containing 20% FA experienced a lower compressive strength compared with those containing 10% FA, which is because FA had a significantly lower CaO compared with GGBS and HESC, thereby leading to a less hydration level (Li & Zhao, 2003). H20G60F20

mixes exhibited approximately 12% and 10% lower compressive strength at 28 and 56 days than the H20G80 mixes, respectively. However, as observed in Figure 3(b), replacing 90% of HESC with 70% GGBS and 20% FA resulted in a strength loss of ~22% at 28 and 56 days with respect to the H100 mixes.

As observed in Figure 3(c), the compressive strength of WBM containing HESC and GGBS slightly decreased with incorporating GP. This is because GP had a significantly lower CaO compared with GGBS and HESC (Li & Zhao, 2003). It can be seen in Figures 3(b) and (c) that, for a given sand type and 80% cement replacement, H20G70P10 mortar mixes developed very similar strengths to H20G70F10 mortar mixes. As reported in Table 2, this may be due to the very similar combined content of SiO₂, CaO and Al₂O₃ in FA and GP. From Figures 3(a) and 3(c) it can be seen that H85P15 mortar mixes performed well, exhibiting approximately 9% lower strength at 28 and 56 days when compared with those of H100 mixes. It is also shown that the H85P15 mortar mixes had an identical but a slightly lower compressive strength than H20G80 mortar mixes, which is the best performing WBM. As discussed in Section 3.4, this is because the microstructure of H85P15 mortar mixes was slightly more porous compared with that of H20G80 mortar mixes. As seen in Figure 3(c), replacing 80% of HESC with 70% GGBS and 10% GP led to a decrease of only 16, 12 and 11% in the compressive strength at 28 and 56 days of NS, GS and FS mortar mixes, respectively. Replacing 90% of HESC with 75% GGBS and 15% GP led to a decrease of approximately 30% in the 28-day and 56-day compressive strength of NS and GS mortar mixes.

In summary, the strength reduction of WBMs causing from the replacement of 80% of cement with industrial by-products was relatively small. At 28 days the reduction ranged from ~7% (80% GGBS) to 17% (60% GGBS and 20% FA) and at 56 days it ranged from ~5% (80% GGBS) to 13% (60% GGBS and 20% FA). When 90% of HESC was replaced with industrial by-products, the strength reduction increased to ~20% at 90% GGBS and 30% at 75% GGBS/15% GP and 70% GGBS/20% FA. The strength reduction was limited to 30% when 100% of HESC was replaced with GGBS. These results point to the satisfactory development of compressive strength of WBMs when cement and sand are replaced with waste-based counterparts at high levels, indicating the possibility of developing structural grade mortars by fully and simultaneously replacing cement and NS with waste materials.

3.3. Direct tensile strength

Figure 4 shows direct tension test results at 28 days of curing. It is observed that, GS mixes had an identical tensile strength to and FS mixes had a slightly lower tensile strength than NS mixes at a given binder type. This observation agrees with the 28-day compression test results. It is also shown in the figure that, among the WBM mixes, H20G80G exhibited a similar tensile strength to H100G, and the tensile strength of H20G80N (7%) and H20G80F (4%) was slightly lower than the companion H100 mixes. As shown in Figure 4(a), at a given type of sand, an increased GGBS content over 80% led to a decreased tensile strength (up to 32% at 100% GGBS), which again agrees with the trend observed in the compression tests. As shown in Figure 4(b), the tensile strength of WBMs 10% decreased with an increased FA content from 10% to 20%. This agrees with previous research investigating the flexural and splitting tensile

strength of concretes (Jalal, Pouladkhan, Harandi, & Jafari, 2015; Şahmaran et al., 2009). As can be seen in Figures 4(b) and (c), for the same content of FA and GP, H20G70F10 mortar mixes exhibited a very similar direct tensile strength to H20G70P10 mortar mixes, agreeing with the obtained results from the compression tests.

By comparing the tensile strengths shown in Figures 4(a)-(c), it is observed that the tensile strength reduction at 80% HESC replacement was relatively small and ranged from ~7% for H20G80 mortar mixes (except for those containing GS) to 13% for H20G60F20 mortar mixes when compared to H100 mortar mixes. When 90% of HESC was replaced, the loss of tensile strength ranged from ~20% in H10G90 mortar mixes to 27% in H10G75P15 mortar mixes. At 100% HESC replacement level, the loss of tensile strength was 33% for G100 mortar mixes. These results once again point to the great potential for developing WBM with structural grade in which cement is replaced at 80% replacement level. It is also possible to develop structural grade WBM containing 100% industrial by-products if their strength reduction is accepted.

3.4. Microstructural analysis

3.4.1 SEM

The SEM micrographs of different binders and fine aggregates used in this study are illustrated in Figures 5(a)-(g). As shown in Figures 5(a) and (b), particles of HESC and GP were angular and HESC was finer compared with GP, causing the WBM with GP to exhibit a higher flow compared with the control mix. As shown in Figures 5(c) and (d), the shape of FA was spherical, but the shape of GGBS was irregular (with more irregularity than that of HESC). As

observed in Figures 5(e) and (f), the shape of GS was more angular than that of NS, resulting in a lower flow in GS mixes due to the lower interparticle friction between NSs compared with that between GSs. By comparing Figures 5(f) and (g), it can be seen that the surface of FS had more voids compared with that of GS, resulting in a less water absorption and thicker water layer on the surface of GS compared with those of FS. This would explain why FS mixes had lower flowability than GS mixes.

Figures 6(a)-(c) illustrates low-magnification SEM micrographs of H20G80N, H20G80G and H20G80F after compression tests at 28 days, respectively. As shown in Figures 6(a) and (b), GS mixes had nearly similar microstructure compactness at ITZ of binder-sand compared with NS mixes. In addition, by comparing Figures 6(a)-(c), it can be seen that the microstructure of FS mixes was less compact at ITZ of binder-sand compared with NS and GS mixes. These would be the reason of the identical strengths seen in the companion NS and GS mixes, and slightly lower strengths of FS than those of NS and GS mixes.

Figures 7(a)-(d) show the high-magnification SEM micrographs of H100N, H20G80N, H10G90N and G100N, respectively. As can be seen in Figures 7(a) and (b), similar to the H100N, the H20G80N had a well-compacted microstructure, causing a strength comparable to the H100N. However, as can be seen in Figures 7(c) and (d), an increased GGBS content to 100% caused a decreased microstructure compactness of the mixes, due to the decreased hydration products amount (Rashad, 2015; Yazıcı, Yardımcı, Yiğiter, Aydın, & Türkel, 2010),

explaining the strength reduction seen in the WBM with an increased GGBS content beyond 80%.

Figure 8 illustrates the SEM images with high magnification for NS mixes prepared with HESC, GGBS and FA. It can be observed that H20G60F20 mortar mixes exhibited microstructure with a lower porosity and more compactness compared with the H10G70F20 mortar mixes, resulting in lower strengths in the latter mortar mixes. The SEM micrographs with low magnification for WBM prepared with HESC, GGBS and GP are shown in Figure 9. It can be observed in Figures 9(a)-(c) that H85P15 mixes had the highest microstructure compactness at the ITZ of binder-sand, which was followed by H20G70P10 and H10G75P15 mixes, respectively. This observation indicates that further replacing HESC over 80% caused an increased void content owing to the decreased hydration products amount in the microstructure of WBM, thereby causing a decreased strength. By comparing Figures 9(a) and 6(a), it can be seen that H85P15N had a microstructure with less compactness at the ITZ compared with H20G80N, resulting in higher strengths of the latter mix. This is because the particle size of most of GPs in this study were larger than 75 μm (as was shown in Figure 5(b)) and hence they remained unreacted in the microstructure of the H85P15N mix. In contrast, GGBS particles in H20G80N reacted in the mixture. The no reactivity of GPs when their particle size was larger than 75 μm was also reported in previous studies (C. Chen, Huang, Wu, & Yang, 2006; Schwarz & Neithalath, 2008; Shao, Lefort, Moras, & Rodriguez, 2000).

3.4.2. EDX

The results of EDX composition analysis on 28-day mortar mixes are illustrated in Table 4. It can be seen that the main constituent elements of WBM are oxygen (O), silicon (Si), calcium (Ca), aluminum (Al) and sodium (Na). H20G80G developed a similar amount (combined) of Si, Ca, Al and Na (70%) to H20G80N, and H20G80F had a slightly lower amount of these constituent elements (69%) than H20G80N and H20G80G. This can explain why GS series mixes had similar mechanical properties to the companion NS series mixes and why FS mixes had slightly lower mechanical properties. This observation suggests that GS and FS had a partial reaction with water during the process of hydration, likely resulting in the improvements in the strengths of GS and FS mixes. As shown in the table, the combined amount of Si-Ca-Al-Na decreased with a decreased HESC content, leading to a decreased in the strengths of the mortars. As can also be seen in Table 4, the combined amount of Si-Ca-Al-Na decreased from 70% to 66% with an increased GGBS content from 80% to 100%, respectively. This observation points to a decreased content of hydration products when GGBS content increased over 80%. H20G60F20N experienced a lower combined amount of Si-Ca-Al-Na (68%) than H20G80N (70%). This observation explains the reduction in the strength of WBM when FA was added. H20G80N had a slightly higher combined amount of Si-Ca-Al-Na (70%) than H85P15N (69%), explaining the reason why H20G80 mixes exhibited a slightly higher compressive and tensile strength compared with H85P15 mixes at 28 days. Furthermore, H100N had a lower Si content compared with H20G80N and H85P15N, indicating that GP and GGBS had a pozzolanic reaction with calcium hydroxide of the cement, as was also reported previously (Kuder et al., 2012; Soliman & Tagnit-Hamou, 2016). This can be the reason of

why beyond curing age of 7 days H85P15 and H20G80 mixes had a higher strength gains rate compared with H100 mixes.

4. Conclusions

This paper reported the results of the first study on the behavior of WBM, which were composed of FA, GGBS and GP as replacements for cement, and GS or FS as replacements for sand. Based on the experimental results and discussions, the following consequences can be drawn:

1. Due to the less angular shape of NS particles than that of GS and FS, WBM prepared with NS have a higher flowability compared with those prepared with GS and FS. The flowability of WBM decreases with an increased content of GGBS for a given type of sand, whereas when FA content increases the flowability of WBM increases. Due to the smaller size of HESC in comparison with that of GP, an increased GP content results in an increased flowability of WBM.
2. WBM with 20% HESC/80% GGBS develop a very similar compressive and tensile strength to conventional mortars, which is attributed to their nearly identical porosity and amount of hydration products. At 90% HESC replacement and 100% NS replacement, the strength loss is ranged from 20% (for 90% GGBS content) to 30% (for 75% GGBS/15% GP content) with respect to conventional cement mortars, which demonstrates their satisfactory mechanical properties.
3. When HESC is fully replaced with GGBS, the loss of strength with respect to conventional mortar is limited to 30%, which is a very promising finding that can lead

to developing a WBM in which cement and sand are fully and simultaneously replaced with waste-based counterparts.

4. The SEM images of WBMs showed that GS mixes exhibit nearly identical microstructure compactness at the binder-sand ITZ to that of NS. Thus, companion GS mixes develop similar mechanical properties to those of NS mixes. In addition, the SEM images revealed that FS mixes have a less compact microstructure compared with NS and GS mixes, resulting in slightly lower mechanical properties than those of NS and GS mixes.
5. The EDX analysis results revealed that GS mixes exhibit a similar combined amount of Si, Ca, Al and Na to NS mixes, and FS mixes exhibit slightly lower combined amount of Si, Ca, Al and Na compared with NS and GS mixes, which is because of the partial reaction of GS and FS with water during the process of hydration. As a result, GS mixes develop a similar strength to NS mixes, and FS mixes develop slightly lower strength compared with NS and GS mixes. In addition, a decreased HESC content results in a decreased combined amount of Si, Ca, Al and Na, leading to decreased strengths of WBMs.

These promising findings reveal that it is possible to develop new eco-friendly structural grade mortars with significant environmental benefits by using industrial by-products as binder and waste-based sands as fine aggregate.

5. Acknowledgements

The authors would like to thank Messrs. Harris, Aquilina, Pradhan and Dalle-Nogare for performing the experiments at the University of Adelaide. The authors also thank the School of Civil, Environmental and Mining Engineering of the University of Adelaide for supporting this work.

REFERENCES

- Al-Kerttani, O. M. G. (2018). Fresh and shrinkage properties of self-compacted concrete when using recycled glass as aggregate. *Structural Concrete*, 19(4), 1245-1254. doi:10.1002/suco.201700069
- Aliabdo, A. A., Elmoaty, A. E. M. A., & Aboshama, A. Y. (2016). Utilization of waste glass powder in the production of cement and concrete. *Construction and Building Materials*, 124, 866-877. doi:10.1016/j.conbuildmat.2016.08.016
- ASTM-C109/C109M-13. (2013). Standard Test Method for Compressive Strength of Hydraulic Cement Mortars. In. USA: ASTM International.
- ASTM-C307-03. (2012). Standard Test Method for Tensile Strength of Chemical-Resistant Mortar, Grouts, and Monolithic Surfacing. In. USA: ASTM International.
- ASTM-C1437-15. (2015). Standard Test Method for Flow of Hydraulic Cement Mortar. In. USA: ASTM International.
- Benli, A. (2019). Mechanical and durability properties of self-compacting mortars containing binary and ternary mixes of fly ash and silica fume. *Structural Concrete*, 20(3), 1096-1108. doi:10.1002/suco.201800302

- Bilir, T., Gencel, O., & Topcu, I. B. (2015). Properties of mortars with fly ash as fine aggregate. *Construction and Building Materials*, 93, 782-789. doi:10.1016/j.conbuildmat.2015.05.095
- Bingöl, A. F., & Tohumcu, İ. (2013). Effects of different curing regimes on the compressive strength properties of self compacting concrete incorporating fly ash and silica fume. *Materials & Design*, 51, 12-18. doi:10.1016/j.matdes.2013.03.106
- Bravard, J.-P., Goichot, M., & Gaillot, S. (2013). Geography of sand and gravel mining in the Lower Mekong River. First survey and impact assessment. *EchoGéo*(26). doi:10.4000/echogeo.13659
- Chen, C., Huang, R., Wu, J., & Yang, C. (2006). Waste E-glass particles used in cementitious mixtures. *Cement and Concrete Research*, 36(3), 449-456. doi:10.1016/j.cemconres.2005.12.010
- Chen, Z., & Poon, C. S. (2017). Comparative studies on the effects of sewage sludge ash and fly ash on cement hydration and properties of cement mortars. *Construction and Building Materials*, 154, 791-803. doi:10.1016/j.conbuildmat.2017.08.003
- Divsholi, B. S., Lim, T. Y. D., & Teng, S. (2014). Durability properties and microstructure of ground granulated blast furnace slag cement concrete. *International Journal of Concrete Structures and Materials*, 8(2), 157-164. doi:10.1007/s40069-013-0063-y
- Gholampour, A., Ho, V. D., & Ozbakkaloglu, T. (2019). Ambient-cured geopolymer mortars prepared with waste-based sands: Mechanical and durability-related properties and microstructure. *Composites Part B: Engineering*, 160, 519-534. doi:10.1016/j.compositesb.2018.12.057

- Gholampour, A., & Ozbakkaloglu, T. (2017). Performance of sustainable concretes containing very high volume Class-F fly ash and ground granulated blast furnace slag. *Journal of Cleaner Production*, 162, 1407-1417. doi:10.1016/j.jclepro.2017.06.087
- Gholampour, A., Ozbakkaloglu, T., Etemadi, E., & Vincent, T. (2019). Sustainable mortars containing fly ash, glass powder and blast-furnace and lead-smelter slag. *Magazine of Concrete Research*, 1-13. doi:10.1680/jmacr.19.00355
- Guney, Y., Sari, Y. D., Yalcin, M., Tuncan, A., & Donmez, S. (2010). Re-usage of waste foundry sand in high-strength concrete. *Waste Management*, 30(8-9), 1705-1713. doi:10.1016/j.wasman.2010.02.018
- Güneyisi, E., Gesoğlu, M., & Özbay, E. (2009). Effects of marble powder and slag on the properties of self compacting mortars. *Materials and Structures*, 42(6), 813-826. doi:10.1617/s11527-008-9426-2
- Hajimohammadi, A., Ngo, T., & Vongsvivut, J. (2019). Interfacial chemistry of a fly ash geopolymer and aggregates. *Journal of Cleaner Production*, 231, 980-989. doi:10.1016/j.jclepro.2019.05.249
- Hou, P.-k., Kawashima, S., Wang, K.-j., Corr, D. J., Qian, J.-s., & Shah, S. P. (2013). Effects of colloidal nanosilica on rheological and mechanical properties of fly ash–cement mortar. *Cement and Concrete Composites*, 35(1), 12-22. doi:10.1016/j.cemconcomp.2012.08.027
- Hui, Z., Poon, C. S., & Ling, T. C. (2013). Properties of mortar prepared with recycled cathode ray tube funnel glass sand at different mineral admixture. *Construction and Building Materials*, 40, 951-960. doi:10.1016/j.conbuildmat.2012.11.102

- Işıkdağ, B., & Topçu, İ. B. (2013). The effect of ground granulated blast-furnace slag on properties of Horasan mortar. *Construction and Building Materials*, 40, 448-454. doi:10.1016/j.conbuildmat.2012.11.016
- Islam, G. S., Rahman, M., & Kazi, N. (2017). Waste glass powder as partial replacement of cement for sustainable concrete practice. *International Journal of Sustainable Built Environment*, 6(1), 37-44. doi:10.1016/j.ijbsbe.2016.10.005
- Jalal, M., Pouladkhan, A., Harandi, O. F., & Jafari, D. (2015). Comparative study on effects of Class F fly ash, nano silica and silica fume on properties of high performance self compacting concrete. *Construction and Building Materials*, 94, 90-104. doi:10.1016/j.conbuildmat.2015.07.001
- Kuder, K., Lehman, D., Berman, J., Hannesson, G., & Shogren, R. (2012). Mechanical properties of self consolidating concrete blended with high volumes of fly ash and slag. *Construction and Building Materials*, 34, 285-295. doi:10.1016/j.conbuildmat.2012.02.034
- Li, G., & Zhao, X. (2003). Properties of concrete incorporating fly ash and ground granulated blast-furnace slag. *Cement and Concrete Composites*, 25(3), 293-299. doi:10.1016/S0958-9465(02)00058-6
- Limbachiya, M. C. (2009). Bulk engineering and durability properties of washed glass sand concrete. *Construction and Building Materials*, 23(2), 1078-1083. doi:10.1016/j.conbuildmat.2008.05.022

- Ling, T.-C., & Poon, C.-S. (2011). Utilization of recycled glass derived from cathode ray tube glass as fine aggregate in cement mortar. *Journal of hazardous materials*, 192(2), 451-456. doi:10.1016/j.jhazmat.2011.05.019
- Lu, J.-x., Duan, Z.-h., & Poon, C. S. (2017). Fresh properties of cement pastes or mortars incorporating waste glass powder and cullet. *Construction and Building Materials*, 131, 793-799. doi:10.1016/j.conbuildmat.2016.11.011
- Makul, N., & Sokrai, P. (2018). Influences of fine waste foundry sand from the automobile engine-part casting process and water-cementitious ratio on the properties of concrete: A new approach to use of a partial cement replacement material. *Journal of Building Engineering*, 20, 544-558. doi:10.1016/j.jobe.2018.09.004
- Mastali, M., Abdollahnejad, Z., & Pacheco-Torgal, F. (2018). Performance of waste based alkaline mortars submitted to accelerated carbon dioxide curing. *Resources, Conservation and Recycling*, 129, 12-19. doi:10.1016/j.resconrec.2017.10.017
- Matos, A. M., & Sousa-Coutinho, J. (2016). ASR and sulphate performance of mortar containing industrial waste. *Structural Concrete*, 17(1), 84-95. doi:10.1002/suco.201400095
- Monosi, S., Tittarelli, F., Giosuè, C., & Ruello, M. L. (2013). Effect of two different sources and washing treatment on the properties of UFS by-products for mortar and concrete production. *Construction and Building Materials*, 44, 260-266. doi:10.1016/j.conbuildmat.2013.02.029
- Navarro-Blasco, Í., Fernández, J. M., Duran, A., Sirera, R., & Alvarez, J. I. (2013). A novel use of calcium aluminate cements for recycling waste foundry sand (WFS).

Construction and Building Materials, 48, 218-228.

doi:10.1016/j.conbuildmat.2013.06.071

Öz, H. Ö., Demirel, S., & Güneş, M. (2019). Curing effect on the properties of high-performance mortars incorporating recycled glass powder. *Structural Concrete*, 20(5), 1644-1655. doi:10.1002/suco.201800310

Pathak, N., & Siddique, R. (2012). Effects of elevated temperatures on properties of self-compacting-concrete containing fly ash and spent foundry sand. *Construction and Building Materials*, 34, 512-521. doi:10.1016/j.conbuildmat.2012.02.026

Penacho, P., de Brito, J., & Veiga, M. R. (2014). Physico-mechanical and performance characterization of mortars incorporating fine glass waste aggregate. *Cement and Concrete Composites*, 50, 47-59. doi:10.1016/j.cemconcomp.2014.02.007

Qiang, W., Mengxiao, S., & Dengquan, W. (2016). Contributions of fly ash and ground granulated blast-furnace slag to the early hydration heat of composite binder at different curing temperatures. *Advances in Cement Research*, 28(5), 320-327. doi:10.1680/jadcr.15.00077

Rashad, A. M. (2015). An investigation of high-volume fly ash concrete blended with slag subjected to elevated temperatures. *Journal of Cleaner Production*, 93, 47-55. doi:10.1016/j.jclepro.2015.01.031

Şahmaran, M., Yaman, İ. Ö., & Tokyay, M. (2009). Transport and mechanical properties of self consolidating concrete with high volume fly ash. *Cement and Concrete Composites*, 31(2), 99-106. doi:10.1016/j.cemconcomp.2008.12.003

- Schwarz, N., Cam, H., & Neithalath, N. (2008). Influence of a fine glass powder on the durability characteristics of concrete and its comparison to fly ash. *Cement and Concrete Composites*, 30(6), 486-496. doi:10.1016/j.cemconcomp.2008.02.001
- Schwarz, N., & Neithalath, N. (2008). Influence of a fine glass powder on cement hydration: Comparison to fly ash and modeling the degree of hydration. *Cement and Concrete Research*, 38(4), 429-436. doi:10.1016/j.cemconres.2007.12.001
- Shao, Y., Lefort, T., Moras, S., & Rodriguez, D. (2000). Studies on concrete containing ground waste glass. *Cement and Concrete Research*, 30(1), 91-100. doi:10.1016/S0008-8846(99)00213-6
- Siddique, R., De Schutter, G., & Noumowe, A. (2009). Effect of used-foundry sand on the mechanical properties of concrete. *Construction and Building Materials*, 23(2), 976-980. doi:10.1016/j.conbuildmat.2008.05.005
- Siddique, R., Singh, G., & Singh, M. (2018). Recycle option for metallurgical by-product (Spent Foundry Sand) in green concrete for sustainable construction. *Journal of Cleaner Production*, 172, 1111-1120. doi:10.1016/j.jclepro.2017.10.255
- Singh, G., & Siddique, R. (2012). Effect of waste foundry sand (WFS) as partial replacement of sand on the strength, ultrasonic pulse velocity and permeability of concrete. *Construction and Building Materials*, 26(1), 416-422. doi:10.1016/j.conbuildmat.2011.06.041
- Soliman, N., & Tagnit-Hamou, A. (2016). Development of ultra-high-performance concrete using glass powder–Towards ecofriendly concrete. *Construction and Building Materials*, 125, 600-612. doi:10.1016/j.conbuildmat.2016.08.073

- Supit, S. W., Shaikh, F. U., & Sarker, P. K. (2014). Effect of ultrafine fly ash on mechanical properties of high volume fly ash mortar. *Construction and Building Materials*, 51, 278-286. doi:10.1016/j.conbuildmat.2013.11.002
- Taha, B., & Nounu, G. (2009). Utilizing waste recycled glass as sand/cement replacement in concrete. *Journal of Materials in Civil Engineering*, 21(12), 709-721. doi:10.1061/(ASCE)0899-1561(2009)21:12(709)
- Tan, K. H., & Du, H. (2013). Use of waste glass as sand in mortar: Part I–Fresh, mechanical and durability properties. *Cement and Concrete Composites*, 35(1), 109-117. doi:10.1016/j.cemconcomp.2012.08.028
- Wainwright, P. J., & Rey, N. (2000). The influence of ground granulated blastfurnace slag (GGBS) additions and time delay on the bleeding of concrete. *Cement and Concrete Composites*, 22(4), 253-257. doi:10.1016/S0958-9465(00)00024-X
- Wang, C., Yang, C., Liu, F., Wan, C., & Pu, X. (2012). Preparation of ultra-high performance concrete with common technology and materials. *Cement and Concrete Composites*, 34(4), 538-544. doi:10.1016/j.cemconcomp.2011.11.005
- Wang, H.-Y. (2009). A study of the effects of LCD glass sand on the properties of concrete. *Waste Management*, 29(1), 335-341. doi:10.1016/j.wasman.2008.03.005
- Xie, T., Gholampour, A., & Ozbakkaloglu, T. (2018). Toward the development of sustainable concretes with recycled concrete aggregates: comprehensive review of studies on mechanical properties. *Journal of Materials in Civil Engineering*, 30(9), 04018211. doi:10.1061/(ASCE)MT.1943-5533.0002304

- Yazıcı, H., Yardımcı, M. Y., Yiğiter, H., Aydın, S., & Türkel, S. (2010). Mechanical properties of reactive powder concrete containing high volumes of ground granulated blast furnace slag. *Cement and Concrete Composites*, 32(8), 639-648. doi:10.1016/j.cemconcomp.2010.07.005
- Zhang, D., Li, V. C., & Ellis, B. R. (2018). Optimal pre-hydration age for CO₂ sequestration through Portland cement carbonation. *ACS Sustainable Chemistry & Engineering*, 6(12), 15976-15981. doi:10.1021/acssuschemeng.8b03699
- Zhao, H., Sun, W., Wu, X., & Gao, B. (2015). The properties of the self-compacting concrete with fly ash and ground granulated blast furnace slag mineral admixtures. *Journal of Cleaner Production*, 95, 66-74. doi:10.1016/j.jclepro.2015.02.050

LIST OF FIGURE CAPTIONS

Figure 1. Sieving test results of fine aggregates: Particle Size Distribution (PSD)

Figure 2. Flowability test results of different mixes: effect of adding (a) GGBS, (b) FA, and (c) GP

Figure 3. Variation in the compressive strength of the mixes with time: effect of adding (a) GGBS, (b) FA, and (c) GP

Figure 4. Direct tensile strength of the different mixes at 28 days: effect of adding (a) GGBS, (b) FA, and (c) GP

Figure 5. SEM micrographs of the particle shapes of: (a) HESC, (b) GP, (c) FA, (d) GGBS, (e) NS, (f) GS and (g) FS

Figure 6. SEM micrographs of the fresh-cut surface of 20% HESC and 80% GGBS mixes: (a) NS, (b) GS and (c) FS group following the compression tests

Figure 7. SEM micrographs of the fresh-cut surface of NS mixes with: (a) 100% HESC, (b) 20% HESC and 80% GGBS, (c) 10% HESC and 90% GGBS, and (d) 100% GGBS following the compression tests

Figure 8. SEM micrographs of the fresh-cut surface of NS mixes with: (a) 20% HESC, 60% GGBS, and 20% FA and (b) 10% HESC, 70% GGBS, and 20% FA following the compression tests

Figure 9. SEM micrographs of the fresh-cut surface of NS mixes with: (a) 85% HESC and 15% GP, (b) 20% HESC, 70% GGBS, and 10% GP, and (c) 10% HESC, 75% GGBS, and 15% GP following the compression tests

LIST OF TABLE CAPTIONS

Table 1. Properties of fine aggregates

Table 2. Chemical composition of cementitious materials

Table 3. Mix proportions of mixtures

Table 4. EDX composition analysis of mixes

Table 1. Properties of fine aggregates

Aggregate type	Maximum size (mm)	Specific gravity (SSD)	Water absorption (%)	Fineness modulus
Natural sand	2.13	2.63	0.4	2.56
Foundry sand	1.90	2.41	0.9	2.46
Glass sand	1.91	2.49	0.2	2.48

SSD: Saturated surface dry

Table 2. Chemical composition of cementitious materials

Composition	HESC (%)	Fly ash (%)	GGBS (%)	GP (%)
SiO ₂	19.95	55.38	33.10	72.50
Al ₂ O ₃	4.79	28.14	13.33	0.16
Fe ₂ O ₃	3.14	3.31	0.69	0.20
CaO	63.28	3.45	42.83	9.18
MgO	2.03	1.85	5.57	3.35
Na ₂ O	0.29	2.30	0.27	13.20
K ₂ O	0.40	1.39	0.31	0.12
SO ₃	2.69	0.32	1.81	0.39
P ₂ O ₅	0.04	0.78	0.01	–
LOI	3.39	3.08	2.08	0.90
Specific surface area (m ² /kg)	390	396	450	217

HESC: High early strength cement

GGBS: ground granulated blast furnace slag

GP: Glass powder

Table 3. Mix proportions of mixtures

Mix	HESC (kg/m ³)	FA (kg/m ³)	GGBS (kg/m ³)	GP (kg/m ³)	NS (kg/m ³)	GS (kg/m ³)	FS (kg/m ³)	Water (kg/m ³)	w_{eff}/b
H100N	500	–	–	–	1500	–	–	325	0.65
H85P15N	425	–	–	75	1500	–	–	325	0.65
H20G80N	100	–	400	–	1500	–	–	325	0.65
H20G70F10N	100	50	350	–	1500	–	–	325	0.65
H20G60F20N	100	100	300	–	1500	–	–	325	0.65
H20G70P10N	100	–	350	50	1500	–	–	325	0.65
H10G90N	50	–	450	–	1500	–	–	325	0.65
H10G70F20N	50	100	350	–	1500	–	–	325	0.65
H10G75P15N	50	–	375	75	1500	–	–	325	0.65
G100N	–	–	500	–	1500	–	–	325	0.65
H100G	500	–	–	–	–	1420	–	325	0.65
H85P15G	425	–	–	75	–	1420	–	325	0.65
H20G80G	100	–	400	–	–	1420	–	325	0.65
H20G60F20G	100	100	300	–	–	1420	–	325	0.65
H20G70P10G	100	–	350	50	–	1420	–	325	0.65
H10G90G	50	–	450	–	–	1420	–	325	0.65
H10G70F20G	50	100	350	–	–	1420	–	325	0.65
H10G75P15G	50	–	375	75	–	1420	–	325	0.65
G100G	–	–	500	–	–	1420	–	325	0.65
H100F	500	–	–	–	–	–	1374	325	0.65
H20G80F	100	–	400	–	–	–	1374	325	0.65
H20G70F10F	100	50	350	–	–	–	1374	325	0.65
H20G60F20F	100	100	300	–	–	–	1374	325	0.65
H20G70P10F	100	–	350	50	–	–	1374	325	0.65
H10G90F	50	–	450	–	–	–	1374	325	0.65
H10G70F20F	50	100	350	–	–	–	1374	325	0.65

Table 4. EDX composition analysis of the mixes

Mix	O* (wt%)	Si (wt%)	Al (wt%)	Ca (wt%)	Na (wt%)	Others (wt%)
H100N	27.5	19.4	7.56	41.1	3.50	0.93
H20G80N	27.7	20.2	9.42	38.0	2.65	2.09
H20G80G	27.8	19.5	9.95	37.7	3.75	1.30
H20G80F	26.8	21.0	8.61	36.8	2.84	3.95
H10G90N	28.3	21.4	10.4	33.5	2.53	3.75
G100N	30.8	22.1	11.2	30.2	2.55	3.07
H20G60F20N	27.1	23.1	16.5	26.1	2.71	4.44
H85P15N	27.8	22.6	6.12	34.0	6.77	2.77

* Hydrogen constituent of the specimens was considered in the oxygen constituent.

SUCO_202000096_aliakbar.jpg

SUCO_202000096_Figure 1.jpg

SUCO_202000096_Figure 2a.jpg

SUCO_202000096_Figure 2b.jpg

SUCO_202000096_Figure 2c.jpg

SUCO_202000096_Figure 3a(bottom).jpg

SUCO_202000096_Figure 3a(top left).jpg

SUCO_202000096_Figure 3a(top right).jpg

SUCO_202000096_Figure 3b(bottom).jpg

SUCO_202000096_Figure 3b(top left).jpg

SUCO_202000096_Figure 3b(top right).jpg

SUCO_202000096_Figure 3c(bottom).jpg

SUCO_202000096_Figure 3c(top left).jpg

SUCO_202000096_Figure 3c(top right).jpg

SUCO_202000096_Figure 4a.jpg

SUCO_202000096_Figure 4b.jpg

SUCO_202000096_Figure 4c.jpg

SUCO_202000096_Figure 5a.jpg

Article

SUCO_202000096_Figure 5b.jpg

SUCO_202000096_Figure 5c.jpg

SUCO_202000096_Figure 5d.jpg

SUCO_202000096_Figure 5e.jpg

SUCO_202000096_Figure 5f.jpg

SUCO_202000096_Figure 5g.jpg

Accepted Article

SUCO_202000096_Figure 6a.jpg

SUCO_202000096_Figure 6b.jpg

SUCO_202000096_Figure 6c.jpg

SUCO_202000096_Figure 7a.jpg

SUCO_202000096_Figure 7b.jpg

SUCO_202000096_Figure 7c.jpg

SUCO_202000096_Figure 7d.jpg

SUCO_202000096_Figure 8a.jpg

SUCO_202000096_Figure 8b.jpg

SUCO_202000096_Figure 9a.jpg

SUCO_202000096_Figure 9b.jpg

Accepted Article

SUCO_202000096_Figure 9c.jpg

SUCO_202000096_Togay_Ozbakkaloglu.jpg

SUCO_202000096_Tuan_Ngo2.jpg

Minerva Access is the Institutional Repository of The University of Melbourne

Author/s:

Gholampour, A;Ozbakkaloglu, T;Ngo, TD

Title:

Development of a waste-based eco-friendly structural mortar without Portland cement and natural sand

Date:

2020-05-28

Citation:

Gholampour, A., Ozbakkaloglu, T. & Ngo, T. D. (2020). Development of a waste-based eco-friendly structural mortar without Portland cement and natural sand. STRUCTURAL CONCRETE, 22 (S1), <https://doi.org/10.1002/suco.202000096>.

Persistent Link:

<http://hdl.handle.net/11343/275788>