Manuscript submitted on December 21, 2015**Achieving fine beta grain structure in a metastable beta titanium alloy through multiple forging-annealing cycles**

A. Zafari^{a,*}, Y. Ding^{a,b}, J. Cui^b and K. Xia^{a,*}

^a*Department of Mechanical Engineering, The University of Melbourne, Victoria 3010, Australia*

^b*Key Laboratory of Electromagnetic Processing of Materials, Northeastern University, Shenyang 110004, P. R. China*

Abstract

A coarse grained (order of 1 mm) Ti-5553 metastable beta alloy was subjected to multiple passes of low temperature forging and multiple forging plus annealing cycles, respectively. In the forging only processing, strain was concentrated in the shear bands formed and accumulated with each forging pass, resulting in a heterogeneous microstructure and eventual cracking along the shear bands. In contrast, the introduction of a short beta annealing after each forging step led to fine recrystallized grains (50-100 μm) formed in the shear bands, and a uniformly refined beta grain structure after four cycles. This is attributed to the strengthening effect of the fine grains, causing redistribution of most severe strains to the coarse grain region in the subsequent forging, consistent with the simulated results by finite element analysis. The analyses of the microstructures and simulated strain distributions revealed that the critical strain for recrystallization is between 0.2 and 0.5 and the strain to fracture to be $\sim 0.8-0.9$. The fine grained (50-100 μm) beta alloy, however, fractured at a much smaller strain of < 0.4 during the next forging step, owing to the formation of stress induced martensitic α'' which is more prevalent in fine grains than in coarse ones.

Keywords: Titanium alloys, multiple forging, shear bands, finite element analysis (FEA), grain refinement.

***Corresponding author:** azafari@student.unimelb.edu.au, k.xia@unimelb.edu.au

1. Introduction

Beta titanium alloys are dominated by the bcc-structured β phase which remains stable upon quenching from the β phase field without martensitic transformation [1]. These alloys have been introduced to enhance the performance of the α/β alloys thanks to improved heat treatability, strength and deep hardenability [2]. Better ductility of the β phase also enables the β alloys to be formed more easily compared to the hcp dominated α and α/β alloys.

As in the processing of more conventional Ti alloys, β Ti alloys are typically subjected to hot working in the β phase field to breakdown the casting structure, followed by secondary processing such as forging or rolling above or below the β transus temperature (T_β), depending on the type of alloys [2, 3]. It has been shown that the activation energy of 137–193 kJ mol⁻¹ [4-7] for the deformation of β alloys is comparable to that of 153 kJ mol⁻¹ [8, 9] for Ti self-diffusion in the β phase, causing dynamic recrystallization and grain growth when deformed at $> T_\beta$. Consequently, it is difficult to control microstructures since a variety of parameters including strain, strain rate, temperature and impurities needs to be considered. Deforming β alloys in the $\alpha + \beta$ field (i.e. at $< T_\beta$) is even more complicated since additional phenomena such as the $\beta \rightarrow \alpha$ transformation, which changes the volume fraction of α [10], and α globularization [11-13] would further interfere. To control microstructure, the correlation between the kinetics of deformation, dynamic recrystallization, phase transformation and globularization must be understood [10].

In the case of forging β Ti alloys, a particular problem is related to local concentrations of strain and stress in the so-called deformation bands including slip and shear bands [14, 15]. At low temperatures, the non-uniform deformation would result in premature fracture and low ductility. At high temperatures, it has been shown that the number of nucleation sites for recrystallization in the deformation bands is high, leading to the formation of much finer grains inside the bands than those

outside [16, 17]. Although a uniform grain structure can be achieved by properly selecting the deformation strain, strain rate and temperature, as demonstrated in several β alloys [5, 6, 15, 18], the interactions between these processing parameters are complicated. In addition, these studies focused more on the deformation and recrystallization mechanisms than on the distribution of deformation bands and its role in the formation of a homogenous microstructure.

To avoid the complexity involving dynamic recrystallization when deformed at high temperatures and to take advantage of the much finer grain structures inside the deformation bands from recrystallization, the deformation in the present investigation is conducted at low temperatures, but annealing is introduced after each deformation step to cause static recrystallization in the deformed zones. In particular, a Ti-5553 metastable β alloy was subjected to cycles of cold forging and short-time annealing at $> T_{\beta}$, and the resulting microstructures were analysed by extensive microscopy and correlated with computer simulations. A uniform distribution of fine β grains in such an alloy was achieved after four forging-annealing cycles.

Moreover, a stress induced martensitic phase known as α'' may form during deformation of many metastable β alloys, affecting mechanical properties [19-21] and microstructural characteristics [22-25]. It has been shown that grain size is an important factor which affects the β to α'' martensitic transformation [24, 26] and consequently the formability. Although α'' is not stable thermodynamically at high temperatures [27] and thus not considered in the previous studies, it may be an important factor in the present low temperature forging. Indeed, the formability was found to decrease with a reduction in the β grain size from ~ 1 mm to ~ 50 - 100 μm , contrary to expectation.

2. Methods

2.1. Experimental material and procedures

A commercial cast Ti-5553 metastable β alloy with the nominal composition of Ti-5Al-5V-5Mo-3Cr (wt.%) was used. Square bars of 9×9 mm in cross section and 18 mm in height were cut from the ingot and solution treated (ST) at 1273 K (1000 °C) for 2 hours followed by water quenching, producing β grains of ~ 1 mm. Two types of processes, forging only and forging plus annealing, were conducted on the ST bars. Figure 1 schematically illustrates the forging process. The die had a cavity of the same thickness as the specimen, giving rise to plane strain deformation upon forging. The specimen with graphite lubrication was placed at one side of the die (left, Fig. 1) so that the material was only allowed to flow to the right during forging. After finishing each forging pass the specimen was rotated counter clockwise by 90° (centre, Fig. 1) and placed at the same side of the die for the next pass (right, Fig. 1). The speed of the forging plunger was 1 mm min^{-1} and all the forging processes were carried out isothermally at 423 K (150 °C) to avoid the formation of the isothermal omega (ω_{iso}) at $\sim 523\text{--}723$ K (250–450 °C) and α precipitates at $\sim 673\text{--}973$ K (400–700 °C) which would cause embrittlement, and to take advantage of better ductility and lower strength than those at room temperature. Straining during each pass was controlled to a specific amount of reduction in height and the process was continued for multiple passes until the specimen was fractured. For the forging only process, the numbers of passes achieved were 7 at 10% reduction each pass, 2 at 30% each and 1 at 40%, respectively. The forging plus annealing processing involved a 30% reduction in each forging step followed by annealing at 1173 K (900 °C) for 5 minutes and subsequent water quenching. This forging-annealing cycle was repeated for 4 times before the specimen fractured during the fifth forging step.

To study recrystallization and grain growth during annealing a sample after one forging-annealing cycle plus a second 30% forging was annealed at 1173 K (900 °C) for different times between 1 and 60 minutes, followed by water quenching. The average grain sizes ($D_{\text{avg.}}$) of the annealed samples were measured using the mean linear intercept method. A number of test lines

with a total length of L were randomly placed on a microstructure image and the total number of times the lines were intercepted by grain boundaries (P) were counted, leading to

$$D_{avg.} = \frac{L}{P} \quad (1)$$

Materials characterisation was carried out by optical microscopy (OM, Olympus BH2-UMA), scanning electron microscopy (SEM, FEI Quanta FEG 200 ESEM), and transmission electron microscopy (TEM, FEI Tecnai F20). TEM samples were prepared using a scanning electron microscope equipped with focused ion beam (SEM/FIB, FEI Nova 200 Nanolab DualBeam).

2.2. Computational simulations

Since the deformation during forging is plane strain, a 2D model was developed using the finite element analysis (FEA) package *MSC.MARC* to simulate the forging process. The sample was meshed with 4-noded quadrilateral elements. To reduce the analysis time, the plunger and walls of the forging die were treated as rigid bodies transferring heat from the sample. An elastic-plastic material model was employed to simulate the responses of the sample to the forging deformation in terms of equivalent stress and strain (von Mises). Mechanical properties needed for constructing the constitutive equations and describing the flow behavior of the Ti-5553 alloy were provided by conducting a set of compressive tests at strain rates of 10^{-4} to 1 s^{-1} at 423 K (150 °C), the isothermal forging temperature. An updated Lagrangian method was employed as a formulation technique and the simulated time-step was set as 0.001 s to raise the accuracy of computing.

As explained in details later (sections 3.1.2 and 3.2.2), incorporating an annealing step after a forging pass led to the formation of a finer grain zone in the sample, resulting in a material with two different ranges of grain sizes. Comparing the simulation results after one 30% reduction forging pass and the microstructure of a sample after one forging-annealing cycle revealed that much finer grains were formed where the local strain was > 0.5 . Instead of assigning a single

strength value for the first forging pass, the fine-grained areas that experienced strains of > 0.5 during a previous forging pass were assigned a new strength value following the Hall-Petch relationship [28, 29] for the simulation of the next forging pass. The constants in the Hall-Petch equation are taken as follows: the friction stress $\sigma_0 = 360.93 \text{ MPa}$ and the unpinning constant $k = 191.73 \frac{\text{MPa}}{\sqrt{\text{mm}}}$, obtained for a Ti-10V-2Fe-3Al (wt.%) metastable β alloy [30] with $M_{o_{eq.}} = 8.7 \text{ wt.}\%$ and mechanical properties similar to those of the Ti-5553 alloy used in the present study. As examples, Fig. 2a shows the mesh generated for the initial sample (before any forging) with a uniform grain structure and Fig. 2b the one for the sample following one forging-annealing cycle with two zones of different grain sizes (zone 1 of coarser grains and a lower strength and zone 2 of finer grains and a higher strength).

3. Results

3.1. Experimental results

3.1.1. Microstructures after forging only processing

Table 1 shows the cumulative equivalent strain ($\varepsilon_{eq.}$) for different forging conditions calculated using [31]

$$\varepsilon_{eq.} = \frac{2N}{\sqrt{3}} \left| \ln \frac{h}{h_0} \right| \quad (2)$$

where N is the number of forging passes, h_0 initial and h final heights of the specimen in a particular pass. It is apparent that when the cumulative equivalent strain reached a critical value of $\sim 0.6\text{--}0.85$, fracture would occur. The optical microstructures of the sample deformed for two 30% passes are shown in Fig. 3a illustrating the formation of a crack along shear bands, and Fig. 3b

displaying kinks formed at the intersection of shear bands. The SEM close-up in Fig. 3c of area *C* in Fig. 3b shows a large number of dislocation pits at the kinks, indicating a high density of dislocations generated by severe plastic deformation. Similar observations are made in the other two samples listed in Table 1.

Figures 4a and 4b show the dark field TEM image for β and associated selected area diffraction pattern (SADP) from an area adjacent to the crack in Fig. 3a, respectively, revealing nanoscale β grains. Weak diffractions of the α'' and ω phases are also detected in the SADP although neither is visible by dark field and bright field TEM imaging.

In contrast, there is no presence of shear bands far away from the crack, with only slip bands formed inside very large β grains (Fig. 5). The microstructure is thus extremely non-uniform.

3.1.2. Microstructures after forging-annealing cycles

Figure 6 shows the microstructural evolution during the first forging-annealing cycle. After the 30% reduction in the first forging step, shear bands formed (Fig. 6a) in isolated areas such as *A*, *B* and *C* marked in the illustration. Annealing at 1173 K (900 °C) for 5 minutes transformed the shear bands into β grains of 50-100 μm in sizes (Figs. 6b) while the grain sizes outside of these shear bands (e.g. in area *D*) remained the same as the ones before forging (Fig. 6c). After the second forging step, as shown in Fig. 7, a higher density of slip bands formed in the large grains while much fewer slip bands were present in the fine grains. The following annealing step resulted in the formation of fine β grains of 50-100 μm in a continuous region (shaded in the illustration in Fig. 8) much bigger than the isolated areas in Fig. 6, as exhibited in Figs. 8a, 8b and 8c corresponding to areas *A*, *B* and *C*, respectively. Outside this region the grains remained much coarser at ~1–2 mm (Fig. 8d corresponding to area *D*). This bimodal grain structure was eventually removed after 4 forging-annealing cycles, leading to a uniform distribution of β grains of 50-100 μm (Fig. 9).

However, it is somewhat surprising that this sample with uniform fine β grains was broken after a further ~30% forging (i.e. $\epsilon_{eq} < 0.4$ since annealing had eliminated most of the previous strain, evidenced by the disappearance of slip bands after 5 minutes of annealing as shown in Figs. 6 and 8), exhibiting lower formability than the sample with β grain sizes of 1–2 mm (2 passes with equivalent strain of 0.82 before fracture as in Table 1). The TEM results from an area in the vicinity of a crack formed during the fifth forging step are shown in Fig. 10. Some needle-shaped phase (Fig. 10a) was found, nucleated at grain boundaries (Fig. 10b). Based on the SADP shown in Fig. 10c, the needle-shaped phase is identified as the stress induced α'' . The presence of α'' is confirmed in the dark field TEM images for β (Fig. 10d) and for α'' (Fig. 10e). Further, the diffraction spots for the β phase in Fig. 10c are spread but do not form rings, suggesting a large number of β subgrains.

3.1.3. Recrystallization and grain growth

A sample subjected to one forging-annealing cycle plus a second 30% forging was annealed for different durations from 1 to 60 minutes at 1173 K (900 °C), with corresponding microstructures shown in Fig. 11. Figure 11a shows the initial stage of recrystallization after 1 minute of annealing, revealing recrystallization nuclei of ~2–4 μm in radii. Annealing for one more minute led to the formation of grains with an average size of $60 \pm 7 \mu\text{m}$ (Fig. 11b). The average grain size increased slowly with annealing time to $90 \pm 8 \mu\text{m}$ after 15 minutes, as shown in Figs. 11c to 11f. However, further annealing resulted in a rapid increase in the average grain size to $240 \pm 15 \mu\text{m}$ after 20 minutes (Fig. 11g), followed by continued grain growth to 245 ± 10 , 290 ± 20 and $400 \pm 17 \mu\text{m}$ after 30, 40 and 60 minutes, respectively (Figs. 11h-11j).

3.2. Computational results

3.2.1. Forging only

The stress and strain distributions in the sample forged by 30% for one and two passes and by 40% for one pass are shown in Figs. 12a-f, respectively. For all forging conditions the maximum strains occur where the maximum stresses are applied, as expected. It is noted in Figs. 12d and 12f that the maximum accumulated strain of ~ 1.5 – 2 is the highest possible before fracture occurs. Figures 13a-c show the temperature distributions corresponding to the three conditions. The maximum temperature rise due to deformation is ~ 2 K (2 °C) and thus negligible.

3.2.2. Forging-annealing

Taking the bimodal grain size distributions shown in Fig. 6 into consideration and applying the Hall-Petch relationship to obtain different strengths for them, the stress and strain distributions in the second forging step after the first forging-annealing cycle are shown in Figs. 14a and 14d, respectively. Comparing them to Figs. 12c and 12d, it is clear that although the presence of two different grain sizes has not changed the stress distribution, the strain distribution is significantly different. In particular, the greatest strains are accommodated in the coarse grain region (i.e. outside the region with smaller grains delineated by the dashed lines in Fig. 14), not where stresses are the largest as in Fig. 12d. Similar observations can be made in the third and fourth forging steps, as shown in Figs. 14b and 14e and Figs. 14c and 14f, respectively. It is also noted that the area of the region with smaller grains expands with increasing number of cycles. As for the forging only process, the maximum temperature rise is ~ 3 K (3 °C) (Fig. 15) and thus not significant.

4. Discussion

Although dynamic recrystallization in the shear bands during hot deformation of β Ti alloys may cause a heterogeneous grain structure [16, 32], it is shown that a uniform microstructure can be obtained when processing variables such as temperature, strain, and strain rate are properly

combined [2, 3, 5, 6, 15, 18]. However, it is unclear how a homogenous microstructure is achievable while the stress and strain distributions in a commonly used process like forging are heterogeneous [14]. By separating the deformation and recrystallization processes, the present study shows that the formation of fine β grains of 50–100 μm in the shear bands during the first annealing step (Fig. 6) has prevented the concentration of deformation in the same area in the following forging step thanks to the increased strength of the refined grains. This eventually leads to the formation of a uniform 50–100 μm grain structure after four forging-annealing cycles, as will be discussed in sections 4.1 and 4.2.

The effects of stress induced martensitic transformations in metastable β alloys on mechanical properties are important but only a limited number of studies [19–21] have been carried out. It has been suggested that the stress induced twinning and martensitic transformations are responsible for the increased strain hardening rates and consequently improved ductility [20]. The present results, however, indicate that the stress induced α'' appears to be detrimental to the formability, and this is the subject of discussion in section 4.3.

4.1. Role of annealing in the formation of a uniform grain structure

The introduction of an annealing step between forging passes has changed a heterogeneous microstructure of shear bands and coarse β grains to a uniform 50–100 μm β grain structure. As shown in Fig. 12, both stress and strain concentrated in the stripes running at $\sim 45^\circ$ with respect to the forging direction, contributing to the formation of shear bands as reported earlier [14]. In the following forging passes, the strain keeps accumulating in the same shear bands, resulting in fracture when a critical cumulative strain is reached. This critical strain is estimated to be ~ 0.6 – 0.85 based on calculations using Eq. 2 (Table 1) but ~ 1.5 – 2 from the simulation results (Fig. 12). This apparent discrepancy is attributed to the fact that Eq. 2 assumes a uniform strain distribution and thus calculates the average value whereas the simulation reveals the maximum local values. Using

the area under the stress-strain curve from compressive tests at 0.001 s^{-1} and 423 K (150 °C, similar to the forging conditions), the amount of energy absorbed (E) by the Ti-5553 alloy before fracture was estimated to be $\sim 497 \frac{\text{MJ}}{\text{m}^3}$. If the energy from straining at a point inside a shear band reaches this value, fracture is expected. The straining energy (E) can be calculated using

$$E = E_{el} + E_p = \int_0^{\varepsilon_y} \sigma_{el} \cdot d\varepsilon + \int_{\varepsilon_y}^{\varepsilon_f} \sigma_F \cdot d\varepsilon \quad (3)$$

where E_{el} is the elastic energy, E_p plastic energy, ε_y elastic strain limit, ε_f fracture strain, σ_{el} elastic stress, and σ_F flow stress. The tensile and compressive tests on the Ti-5553 alloy revealed that ε_y and E_{el} were ~ 0.003 and $\sim 0.9 \frac{\text{MJ}}{\text{m}^3}$, respectively. Using FEA the relationship between the flow stress (σ_F) and strain (ε) for an element inside a shear band is found to be

$$\sigma_F = 719 \varepsilon^{0.2} \quad (4)$$

If it is assumed that the fracture energy of $497 \frac{\text{MJ}}{\text{m}^3}$ is reached in the element, ε_f can be calculated to be ~ 0.86 using Eqs. 3 and 4. From the simulation results in Figs. 12d and 12f, it is apparent that a significant area along the $\sim 45^\circ$ line has experienced strains greater than this critical value, leading to fracture observed in Fig. 3. In contrast, the areas with exceeding strains are limited and isolated in Fig. 12b, and no macroscopic fracture occurs. Thus, this calculated critical strain for fracture matches the simulated and experimental results well (the equivalent strain values in Table 1 are lower since they are the average ones.)

When annealing is added, the recrystallized finer grains formed only in the areas strained by $\varepsilon_{eq.} > 0.5$ (Figs. 6, 8 and 14), while the areas with $\varepsilon_{eq.} < 0.2$ did not show any recrystallization even after longer durations of annealing (> 5 minutes), indicating that the critical strain for recrystallization may lie between 0.2 and 0.5. The observed bimodal grain-size structure (Fig. 6) is

schematically represented in Fig. 16a. The fine grained region becomes stronger than the coarse grained one. As a result, more significant deformation is moved to the coarse grained region (Figs. 7 and 14), leading to recrystallization and resulting fine grains there, i.e. the spreading of the fine grained region in the second cycle, as observed in Fig. 8 and illustrated in Fig. 16b. The redistribution of strain (Fig. 14) and relocation of recrystallization sites would continue in the third forging-annealing cycle (Fig. 16c) until a uniform distribution of grains of 50-100 μm is achieved in the entire specimen after the fourth cycle (Fig. 16d and Fig. 9).

The strain path in a multi-step plastic deformation process (e.g. the multi-step forging used here) may have significant effects on the microstructural evolution [33-36], especially when the accumulative strain is high and strains in different directions are interacting with each other, as observed in severe plastic deformation processes [34, 37, 38] or in multi-axial forging [33, 36]. However, any deformation structures produced in the forging step of a particular forging-annealing cycle have been replaced by the recrystallised grains formed during annealing (Fig. 11). Although different strain paths might lead to various strain and grain distributions, they should not affect the described process of grain refinement which relies on the strengthening of finer grains, wherever they are located, to reach a uniform grain size distribution.

4.2. Grain size achieved during recrystallization and grain growth

It deserves further investigation that all the β grains achieved after four cycles of forging-annealing are of very similar sizes of 50–100 μm . The question is why the newly crystallised grains have this range of sizes and the ones formed in the previous cycles do not grow considerably. Although the newly recrystallized grains after annealing at 1173 K (900 °C) for 1 minute are only 2–4 μm in radii, the centre-to-centre distances between them are ~30–50 μm (Fig. 11a). The existing nuclei grow by consuming the surrounding high energy areas with numerous slip bands until they are in touch with each other and reach an average grain size of ~60 μm after 2 minutes

(Fig. 11b). The nucleation of new β grains, however, is not limited to these prior β grain boundaries as recrystallisation might take place at the interfaces between the newly formed β and the deformed regions as well as on subgrain boundaries in the deformed β grains, leading to the formation of a large number of recrystallised β grains in a large area after a short period (2 minutes) of annealing, as seen in Fig. 11b. The average size ($D_{avg.}$) of the recrystallized grains revealed in Fig. 11 is plotted against the annealing time (t_A) in Fig. 17. It can be divided into three distinct regions. Region I marks the early stage with newly recrystallized grains bulging out of grain boundaries (Fig. 11a). In stage II, these nuclei grew rapidly to become in touch with each other, reaching an average size of $\sim 60\text{--}75\text{ }\mu\text{m}$ approximately equalling the distance between the nuclei, and the recrystallization is nearing completion. During stage III recrystallization continues to completion at a much slower rate with decreasing driving force [39], while the already formed grains grow at a slow rate. Since the annealing was only for 5 minutes, most of the newly recrystallized grains grow to $\sim 50\text{--}100\text{ }\mu\text{m}$, as observed.

On the other hand, the $50\text{--}100\text{ }\mu\text{m}$ grains formed in the previous cycle experienced strains of < 0.5 as shown in Figs. 14d, 14e, and 14f, less than the critical value for recrystallization. Instead, a much smaller number of slip bands were formed in them, as shown in Fig. 7, leading to recovery only. Since the total annealing times were less than 15 minutes (5 minutes at each cycle), these grains are still less than $100\text{ }\mu\text{m}$ at the fourth forging step.

Following the completion of recrystallization, the grain size sharply increased from $90\text{ }\mu\text{m}$ at 15 minutes of annealing (Fig. 11f) to $240\text{ }\mu\text{m}$ at 20 minutes (Fig. 11g), indicating a transition from recovery and recrystallization to grain growth. The driving force for grain growth can be expressed as [40]

$$F = \frac{2\gamma}{r} \quad (5)$$

where γ is the grain boundary energy and r the radius of the growing grain. Further, based on theoretical analysis the grain growth rate can be related to the driving force by [41, 42]

$$\frac{dD_{avg.}}{dt} = 2M \cdot F \quad (6)$$

where t is the time for grain growth, $D_{avg.}$ the average grain size and M the mobility of grain boundaries. Combining Eqs. 5 and 6, it leads to the familiar equation

$$D_{avg.}^2 - D_0^2 = 16\gamma Mt = Kt \quad (7)$$

where K is a temperature dependent constant ($= 16\gamma M$), known as the grain growth rate constant, and D_0 the average initial grain size. This equation can also be written in a general form as [43]

$$D_{avg.}^n - D_0^n = Kt \quad (8)$$

where n is the grain growth exponent. Taking the grain size at 15 minutes as the initial grain size (i.e. $D_0 = 90 \mu\text{m}$), $D_{avg.}^n - D_0^n$ versus t ($= 0$ at $t_A = 15$ minutes) is plotted for various values of n in Fig. 18. The correlation coefficients (R^2) for the fitted lines in Figs. 18a ($n = 2$) and 18b ($n = 3$) are similar and close to 1 while R^2 is much lower for $n = 4$ (Fig. 18c), indicating that n is between 2 and 3. It has been reported that the value of n for alloys may be greater than 2 for pure metals thanks to solute drag [44, 45]. Among very few experiments on β grain growth, Semiatin *et al.* [46, 47] observed $n = 2$ in two α/β Ti alloys annealed at $> T_\beta$ with rapid heating rates. Since the value of n is expected to vary with temperature (to decrease with increasing temperature) and composition, it is not possible to know the exact value for Ti-5553 with no extensive experimental results available.

If n is taken as 2 (reasonable based on the present results), the value of K is estimated to be $49 \frac{\mu\text{m}^2}{\text{s}}$ from the slop of the fitted line in Fig. 18a. This is much smaller than $\sim 248\text{--}360 \frac{\mu\text{m}^2}{\text{s}}$ calculated from the data for the growth of β grains in Ti-6.4Al-3.3MO-1.6Zr-0.28 Si [46] and Ti-

6Al-4V [47] alloys. As K is proportional to γ and M , both dependent on temperature as well as chemical composition and crystallographic characteristics of grain boundaries [43, 48], it is difficult to compare its values for different alloys and annealing temperatures.

4.3. Effect of the martensitic α'' phase on formability

It is apparent from the experimental results that the uniformly fine grained alloy with grain sizes of 50-100 μm is less formable (fractured at an equivalent strain of < 0.4) than the coarse grained one with initial grain sizes of the order of 1 mm (fractured at equivalent strains of ~ 0.6 – 0.85 as shown in Table 1). This seems to be against expectation since classic theories suggest that grain refinement should lead to an increase in ductility [49-51]. Although formation of any micro-pores during forging could have caused a reduction in ductility, no pores/cracks of any size have been found. However, several phase transformations are possible during the deformation which could have negative effects on ductility. One is the formation of the isothermal ω (ω_{iso}) from local temperature rise due to plastic deformation. ω_{iso} tends to cause drastic embrittlement in β -Ti alloys because it precipitates as uniformly distributed particles of ~ 10 – 20 nm in sizes, hindering dislocation movement and decreasing ductility [52, 53]. In addition, martensitic transformations are likely to be triggered by stress since Ti-5553 is metastable with a low molybdenum equivalency (Mo_{eq}) of 8.1 [24]. Indeed, the stress induced martensitic phase α'' has been detected in the present alloy (Figs. 4 and 10).

The isothermal ω phase precipitates as particles of 10-20 nm in diameter with specific diffraction patterns and morphologies [54-56], making it easy to be recognized using SADPs and dark field TEM images. However, none of the SADPs and dark field images in Figs. 4 and 10 showed any evidence of ω_{iso} . This is expected since ω_{iso} forms in the temperature range of 523–723 K (250–450 $^{\circ}\text{C}$) [57], much higher than the maximum temperature of ~ 426 K (153 $^{\circ}\text{C}$) reached based on simulations (Figs. 13 and 15). Instead, the weak rings associated with the ω phase

in Fig. 4b are likely to be those for the athermal ω (ω_{ath}) phase formed upon quenching [58] which does not have any significant impact on the ductility of β alloys [1]. Therefore, the effect of ω_{iso} on formability is dismissed.

Although the SADP in a shear band formed in the large grains of ~ 1 mm (Fig. 4b) reveals some traces, the α'' phase is not observed in any of the bright and dark field images, suggesting that the amount of α'' is very small. On the other hand, there appear to be significantly more stress induced martensitic α'' plates inside the shear bands in the fine grains of 50–100 μm (Fig. 10). This could be attributed to the higher density of grain boundaries in the fine grains which act as nucleation sites for α'' (Figs. 10b and 10e). This observation can be supported by estimating the volume fraction of α'' using the model shown in Fig. 19 in which a grain is treated as a cube of a in size containing a number of α'' plates with a width of w that are embedded and bounded by the cube surfaces, i.e. grain boundaries. The volume fraction of α'' can be found by

$$f = V_{\alpha''}/V_t = (Nwa^2)/a^3 = Nw/a$$

where $V_{\alpha''}$ is the total volume of the α'' plates, V_t the volume of the cubic grain and N the number of the α'' plates contained. It has been suggested that a reduction in grain size increases N as less elastic energy, and thus less triggering stress, is required for the formation of α'' [26] whereas it is reasonable to assume that the width of the α'' plates does not change with the grain size. It is then obvious that the volume fraction of α'' will increase with decreasing grain size. Although it is shown that the required mechanical energy for the formation of α'' in the Ti-5553 alloy increased as grain size decreased and the martensitic transformation would be suppressed in β grains of < 300 nm [24], this does not apply in the present case as the fine grains are still much coarser at 50–100 μm . Indeed, the easy observation of α'' in the grains of 50–100 μm (Figs. 10a, b and e) and stronger

α'' diffraction rings shown in Fig. 10c compared to Fig. 4b suggest a greater amount of α'' in the finer grains.

Now that it is established that the uniformly fine grained alloy contains significantly more α'' , it is reasonable to think this is responsible for the brittle behavior exhibited. In one study [19, 20], the stress induced twinning and martensitic transformations are credited for the enhanced ductility in some newly designed metastable β alloys, and it is attributed to the increased strain hardening rates caused by the interaction between dislocations and twins and martensitic plates. On the other hand, an investigation on a metastable Ti-10V-2Fe-3Al alloy [21] showed that the formation of α'' had little effect on ductility although it improved fatigue resistance. In contrast, the results obtained in the present study appear to indicate that α'' is detrimental to formability. Tensile testing of the Ti-5553 alloy used here shows no strain hardening and few twins or α'' plates have been observed in the tensile tested samples. Therefore, the positive effect of α'' on ductility is absent. Although properly oriented α'' plates might be sheared [24], its orthorhombic structure renders the α'' phase much harder to deform than the matrix. It is more likely that the pileup of dislocations at the α''/β interfaces may result in the formation of the so-called Zener-Stroh-Koehler cracks according to the Zener [59], Koehler [60] and Stroh [61] theory, leading to brittle fracture.

There is, however, one exception. It has been shown [23, 24] that the formation of α'' facilitates the creation of a nanocrystalline β alloy by high pressure torsion (HPT) which imparts a far higher strain than forging in the present case. This could be attributed to the much less specimen confinement in forging than that in HPT. Indeed, the confinement and high pressure applied in HPT cause high hydrostatic pressure which enables very large plastic strains even in nominally brittle alloys [62]. The crucial role played by hydrostatic pressure is further verified when a back pressure is applied in ECAP of brittle magnesium alloys to enable successful deformation at low temperatures [63].

5. Conclusions

- (1) A solution-treated Ti-5553 alloy with β grains of ~ 1 mm was subjected to processes of multiple passes of plane-strain forging at 423 K (150 °C) and multiple forging (423 K (150 °C))-annealing (1173 K (900 °C)) cycles, respectively. The former resulted in heterogeneous deformation and fracture owing to strain localisation and accumulation in each forging step, and the latter led to uniformly refined β grains of ~ 50 – 100 μm following four cycles thanks to strengthening of the fine recrystallized grains formed in the previously deformed areas during annealing.
- (2) The stress and strain distributions during the two processes were obtained by simulation, taking the strengthening effect of refined grains into consideration.
- (3) The simulated results correlate well with the grain structures observed, revealing that recrystallization takes place where $\varepsilon_{eq.} > 0.5$ whereas no recrystallization occurs where $\varepsilon_{eq.} < 0.2$ even after prolonged annealing. The critical strain for recrystallization is thus between 0.2 and 0.5.
- (4) The recrystallization was largely completed following 5–15 minutes of annealing at 1173 K (900 °C) after forging, reaching a recrystallized grain size of ~ 50 – 100 μm determined by the number of nuclei bulge-formed at the prior grain boundaries. Normal β grain growth followed with the estimated grain growth exponent (n) of ~ 2 and rate constant (K) of $49 \frac{\mu\text{m}^2}{\text{s}}$, respectively.
- (5) Analysis based on tensile testing results shows that when the accumulated equivalent strain reaches ~ 0.8 – 0.9 , fracture occurs along the shear bands formed during forging, and this is corroborated by the simulated results.
- (6) Contrary to expectation, the alloy containing uniformly sized β grains of ~ 50 – 100 μm exhibited lower formability than the initial alloy with much coarser grains of ~ 1 mm. This is attributed to

the role of the stress induced martensitic α'' phase in the creation of the so-called Zener-Stroh-Koehler cracks.

Acknowledgement

This investigation is partially supported by the *ARC Centre of Excellence for Design in Light Metals* and the *Australia-China Research Centre for Light Metals*. AZ acknowledges the receipt of a University of Melbourne postgraduate scholarship and YD the financial support from the Chinese Scholarship Council. AZ is grateful for useful discussions with Dr. Wei Xu.

References

- [1] T. W. Duerig and J. C. Williams: in *Beta Titanium Alloys in the 80s*, R. Boyer and H. W. Rosenberg, eds., Metallurgical Society of AIME, Atlanta, GA, United States, 1984, pp.19-67.
- [2] F. H. Froes and H. B. Bomberger: *JOM*, 1985, vol. 37 (7), pp. 28-37.
- [3] I. Weiss and S. L. Semiatin: *Mater. Sci. Eng. A*, 1998, vol. 243, pp. 46-65.
- [4] H. Oikawa, K. Nishimura, and M.X. Cui: *Scr. Metall.*, 1985, vol. 19, pp. 825-28.
- [5] B. Ru-qiang, X. Huang, and C. Chun-xiao Cao: *Trans. Nonferrous Met. Soc. China*, 2006, vol. 16, pp. 274-80.
- [6] V. V. Balasubrahmanyam and Y.V.R.K. Prasad: *Mater. Sci. Eng. A*, 2002, vol. 336, pp. 150-58.
- [7] Y. Liu and T.N. Baker: *Mater. Sci. Eng. A*, 1995, vol. 197, pp. 125-31.
- [8] N. E. W. De Reza and C. M. Libanati: *Acta Metall.*, 1968, vol. 16, pp. 1297-305.
- [9] F. Dymant and C. M. Libanati: *J. Mater. Sci.*, 1968, vol. 3, pp. 349-59.
- [10] G. A. Salishchev, R. M. Galeev, O. R. Valiakhmetov, M F. X. Gigliotti, B. P. Bewlay, and C. U. Hardwicke: *J. Mater. Eng. Perform.*, 2005, vol. 14, pp. 709-16.
- [11] I. Weiss, F. H. Froes, D. Eylon, and G. E. Welsch: *Metall. Trans. A*, 1986, vol. 17A, pp. 1935-47.
- [12] G. A. Salishchev, O. R. Valiakhmetov, and R. M. Galeev: *J. Mater. Sci.*, 1993, vol. 28, pp. 2898-902.
- [13] C. H. Park, K. T. Park, D. H. Shin, and C. S. Lee: *Mater. Trans.*, 2008, vol. 49, pp. 2196-200.

- [14] R. Berghammer, H. Weiping, A. Hasani, and G. Gottstein: *Adv. Eng. Mater.*, 2011, vol. 13, pp. 232-36.
- [15] V. V. Balasubrahmanyam and Y.V.R.K. Prasad: *Mater. Sci. Tech.*, 2001, vol. 17, pp. 1222-28.
- [16] T. H. Schofield and A. E. Bacon: *Acta Metall.*, 1961, vol. 9, pp. 653-69.
- [17] T. Sakai, A. Belyakov, R. Kaibyshev, H. Miura, and J. J. Jonas: *Prog. Mater. Sci.*, 2014, vol. 60, pp.130-207.
- [18] H. Matsumoto, M. Kitamura, Y. Li, Y. Koizumi, and A. Chiba: *Mater. Sci. Eng. A*, 2014, vol. 611, pp. 337-44.
- [19] F. Sun, T. Gloriant, P. Vermaut, P. Jacques, and F. Prima: *Solid State Phenom.*, 2011, vol. 172-174, pp. 129-34.
- [20] M. Marteleur, F. Sun, T. Gloriant, P. Vermaut, P. J. Jacquesa, and F. Primab: *Scr. Mater.*, 2012, vol. 66, pp. 749-52.
- [21] Q. Y. Sun, J. Song, R. H. Zhu, and H. C. Gu: *J. Mater. Sci.*, 2002, vol. 37, pp. 2543-47.
- [22] W. Xu, K. B. Kim, J. Das, M. Calin, B. Rellinghaus, and J. Eckert: *Appl. Phys. Lett.*, 2006, vol. 89, pp. 031906-1-3.
- [23] W. Xu, X. Wu, R. B. Figueiredo, M. Stoica, M. Calin, J. Eckert, T. G. Langdon, and K. Xia: *Int. J. Mater. Res.*, 2009, vol. 100, pp. 1662-67.
- [24] A. Zafari, X. S. Wei, W. Xu, and K. Xia: *Acta Mater.*, 2015, vol. 97, pp. 146-55.
- [25] W. Xu, X. Wu, M. Calin, M. Stoica, J. Eckert, K. Xia: *Scr. Mater.*, 2009, vol. 60, pp. 1012-15.
- [26] A. Bhattacharjee, S. Bhargava, V. K. Varma, S. V. Kamat, and A. K. Gogia: *Scr. Mater.*, 2005, vol. 53, pp. 195-200.
- [27] T. W. Duerig, J. Albrecht, D. Richter, and P. Fischer: *Acta Metall.*, 1982, vol. 30, pp. 2161-72.

- [28] E.O. Hall: *Proc. Phys. Soc. B*, 1951, vol. 64, pp. 747-53.
- [29] N. J. Petch: *J. Iron Steel Inst.*, 1953, vol. 174, pp. 25-28.
- [30] A. Bhattacharjee, V. K. Varama, S. V. Kamat, A. K. Gogia, and S. Bhargava: *Metall. Mater. Trans. A*, 2006, vol. 37A, pp. 1423-33.
- [31] H. P. Stüwe: *Adv. Eng. Mater.*, 2003, vol. 5, pp. 291-95.
- [32] Y. B. Chun, S. L. Semiatin, and S. K. Hwang: *Acta Mater.*, 2006, vol. 54, pp. 3673-89.
- [33] B. Han and Z. Xu: *Mater. Sci. Eng. A*, 2007, vol. 447, pp. 119-24.
- [34] V. M. Segal: *Mater. Sci. Eng. A*, 1995, vol. 197, pp. 157-64.
- [35] A. Gholinia, F. J. Humphreys, and P. B. Prangnell: *Acta Mater.*, 2002, vol. 50, pp. 4461-76.
- [36] J. Huang and Z. Xu: *Mater. Lett.*, 2006, vol. 60, pp. 1854-58.
- [37] B. Bay, N. Hansen, and D. Kuhlmann-Wilsdorf: *Mater. Sci. Eng. A*, 1989, vol. 113, pp. 385-97.
- [38] N. Hansen and D. A. Hughes: *Phys. Stat. Sol.*, 1995, vol. 149, pp. 155-72.
- [39] R. A. Vandermeer and P. Gordon: in *Recovery and Recrystallization of Metals*, L. Himmel, ed., Interscience Publisher, New York, 1963, pp. 211-38.
- [40] J. E. Burke and D. Turnbull: *Prog. Met. Phys.*, 1952, vol. 3, pp. 220-92.
- [41] M. Hillert: *Acta Metall.*, 1965, vol. 13, pp. 227-38.
- [42] R. Sandström: *Acta Metall.*, 1977, vol. 25, pp. 905-11.
- [43] H. V. Atkinson: *Acta Metall.*, 1988, vol. 36, pp. 469-91.
- [44] K. Lücke and K. Detert: *Acta Metall.*, 1957, vol. 5, pp. 628-37.
- [45] J. W. Cahn: *Acta Metall.*, 1962, vol. 10, pp. 789-98.
- [46] S. L. Semiatin, J. C. Soper, and I. M. Sukonnik: *Scr. Metall. et Mater.*, 1994, vol. 30, pp. 951-55.
- [47] S. L. Semiatin, J. C. Soper, and I. M. Sukonnik: *Acta Mater.*, 1996, vol. 44, pp. 1979-86.

- [48] S. L. Semiatin, P. N. Fagin, M. G. Glavicic, I. M. Sukonnik, and O. M. Ivasishin: *Mater. Sci. Eng. A*, 2001, vol. 299, pp. 225-34.
- [49] R. W. Armstrong: *Metall. Mater. Trans. B*, 1970, vol. 1, pp. 1169-76.
- [50] K. S. Chan: *Scr. Metall. Mater.*, 1990, vol. 24, pp. 1725-30.
- [51] A. Lasalmonie and J. L. Strudel: *J. Mater. Sci.*, 1986, vol. 21, pp. 1837-52.
- [52] A. W. Bowen: *Scr. Metall.*, 1971, vol. 5, pp. 709-15.
- [53] J. C. Williams, B. S. Hickman, and H. L. Marcus: *Metall. Mater. Trans. B*, 1971, vol. 2B, pp. 1913-19.
- [54] S. Nag, R. Banerjee, R. Srinivasan, J. Y. Hwanga, M. Harper, and H. L. Fraser: *Acta Mater.*, 2009, vol. 57, pp. 2136-47.
- [55] F. Prima, P. Vermaut, G. Texier, D. Ansel, and T. Gloriant: *Scr. Mater.*, 2006, vol. 54, pp. 645-48.
- [56] B. S. Hickman: *J. Mater. Sci.*, 1969, vol. 4, pp. 554-63.
- [57] M. Petrzlik: *JPCS*, 2013, vol. 438, pp. 012020-1–5.
- [58] W. Xu, D. P. Edwards, X. Wu, M. Stoica, M. Calin, U. Kühn, J. Eckert, and K. Xia: *Scr. Mater.*, 2013, vol. 68, pp. 67-70.
- [59] C. Zener: in *Fracturing of Metals*, G. Sachs and C. Zener, eds., ASM, Chicago, 1948, pp. 3-31.
- [60] J. K. Koehler: *Phys. Rev.*, 1952, vol. 85, pp. 480-1.
- [61] A. N. Stroh: *Adv. Phys.*, 1957, vol. 6, pp. 418-65.
- [62] R. Z. Valiev, R. K. Islamgaliev, and I. V. Alexandrov: *Prog. Mater. Sci.*, 2000, vol.45, pp. 103-89.
- [63] K. Xia, J. T. Wang, X. Wu, G. Chen, and M. Gurvan: *Mater. Sci. Eng. A*, 2005, vol. 410, pp. 324-27.

Table 1 Cumulative equivalent strain for different forging conditions.

Reduction% in each pass	Number of forging passes (N) before fracture	Cumulative equivalent strain ($\epsilon_{eq.}$)
10	7	0.85
30	2	0.82
40	1	0.59

Figure Captions

- Fig. 1 Schematic of the plane-strain forging process showing the samples before pressing (solid) and after pressing (dashed) in the first pass (left), and the same sample after rotating counter-clockwise by 90° (centre) and replacing before deformation in the second pass (right).
- Fig. 2 (a) The mesh generated for the initial sample with a uniform grain structure, and (b) that for the sample following one forging-annealing cycle with two zones of different grain sizes: Zone 1 for coarse grains ($\varepsilon_{eq.} < 0.5$ after forging) and Zone 2 for fine grains ($\varepsilon_{eq.} > 0.5$ after forging), divided by the dashed lines.
- Fig. 3 (a) and (b) OM microstructures showing shear bands, a crack formed along the shear bands and kinks at intersections of shear bands after 2 forging passes at 30% reduction each. (c) SEM microstructure of the area marked C in (b) showing dislocation pits near a kink.
- Fig. 4 (a) Dark field TEM image for β and (b) SADP in the vicinity of a crack formed in the Ti-5553 alloy with initial grains of ~ 1 mm after forging for 2 passes at 30% reduction each, revealing nanoscale β grains and presence of ω and α'' .
- Fig. 5 OM microstructure away from the shear bands in the coarse grains (of the order of 1 mm) after forging for 2 passes at 30% reduction each, showing the formation of slip bands.
- Fig. 6 OM microstructures showing (a) shear bands formed after one forging pass at 30% reduction, (b) recrystallized fine grains of 50–100 μm created after 5 minutes of annealing at 1173 K (900 $^\circ\text{C}$) in the shear zones marked A, B and C in the illustration, and (c) coarse grains of $> \sim 1$ mm in the area labelled D outside the shear zones.
- Fig. 7 SEM microstructure after one forging-annealing cycle plus a second 30% forging, showing a higher density of slip bands in the coarse grains (e.g. the top grain in the upper inset and the bottom grain in the lower inset) and much fewer slip bands in the fine grains (e.g. the bottom grain in the upper inset and the top grain in the lower inset).
- Fig. 8 OM microstructures after two forging-annealing cycles, showing (a), (b) and (c) the fine grains of 50–100 μm in areas A, B and C (in the shaded region in the illustration), respectively, and (d) coarse grains of $> \sim 1$ mm in area D (white).

- Fig. 9 SEM microstructure after four forging-annealing cycles, showing a uniform distribution of fine β grains of 50–100 μm throughout the entire sample.
- Fig. 10 TEM in the vicinity of a crack formed during the fifth forging step ($\varepsilon_{eq.} < 0.4$) in the Ti-5553 alloy after 4 forging-annealing cycles (i.e. with grains of 50–100 μm), showing (a) and (b) bright field images revealing needle shaped plates identified as α'' based on (c) the corresponding SADP, (d) dark field image for β and (e) dark field image for α'' .
- Fig. 11 OM microstructures after one forging-annealing cycle plus a second 30% forging followed by annealing at 1173 K (900 °C) for up to 60 minutes, showing the average grain size ($D_{avg.}$) at each time.
- Fig. 12 FE simulation of the forging only processing, showing the distributions of equivalent stress and strain after (a) and (b) one 30% forging pass, (c) and (d) two forging passes at 30% reduction each, and (e) and (f) one 40% forging pass.
- Fig. 13 The simulated temperature distributions after (a) one 30% forging pass, (b) two forging passes at 30% reduction each, and (c) one 40% forging pass, showing increases in temperature of less than 2–3 K (2–3 °C) in each case.
- Fig. 14 FE simulation of the forging-annealing processing, showing the distributions of equivalent stress and strain after (a) and (d) one forging-annealing cycle plus a second 30% forging, (b) and (e) two forging-annealing cycles plus a third 30% forging, and (c) and (f) three forging-annealing cycles plus a fourth 30% forging. The dashed lines delineate the fine grained ($\sim 50\text{--}100\ \mu\text{m}$) region with $\varepsilon_{eq.} > 0.5$ at the end of the previous forging step, which is formed after annealing and stronger in the current forging step. F and A stand for forging and annealing, respectively.
- Fig. 15 The simulated temperature distributions after (a) one forging-annealing cycle plus a second 30% forging, (b) two forging-annealing cycles plus a third 30% forging and (c) three forging-annealing cycles plus a fourth 30% forging, showing increases in temperature of less than 2–3 K (2–3 °C) in each case. F and A stand for forging and annealing, respectively.
- Fig. 16 Schematic of the evolution of the grain structures after (a) one forging-annealing cycle showing the formation of fine grains in the shear zones, (b) two cycles and (c) three cycles showing an increase in the amount of fine grains, and (d) four cycles showing the creation of a uniform fine-grained structure.
- Fig. 17 Grain growth (the average size of the recrystallized grains, $D_{avg.}$) during the first 15 minutes of annealing at 1173 K (900 °C) following one forging-annealing cycle plus a second 30% forging, reaching the recrystallized grain size of $\sim 90\ \mu\text{m}$.

Fig. 18 $D_{avg.}^n - D_0^n$ versus t , plotted for $n = 2, 3$ and 4 . R^2 and K represent the correlation coefficient of the fitted line and the grain growth rate constant, respectively.

Fig. 19 Schematic of α'' plates with a width of w formed inside a cubic grain of size a .

Fig. 1 Schematic of the plane-strain forging process showing the samples before pressing (solid) and after pressing (dashed) in the first pass (left), and the same sample after rotating counter-clockwise by 90° (centre) and replacing before deformation in the second pass (right).

Fig. 2 (a) The mesh generated for the initial sample with a uniform grain structure, and (b) that for the sample following one forging-annealing cycle with two zones of different grain sizes: Zone 1 for coarse grains ($\epsilon_{eq.} < 0.5$ after forging) and Zone 2 for fine grains ($\epsilon_{eq.} > 0.5$ after forging), divided by the dashed lines.

Fig. 3 (a) and (b) OM microstructures showing shear bands, a crack formed along the shear bands and kinks at intersections of shear bands after 2 forging passes at 30% reduction each. (c) SEM microstructure of the area marked C in (b) showing dislocation pits near a kink.

Fig. 4 (a) Dark field TEM image for β phase and (b) SADP in the vicinity of a crack formed in the Ti-5553 alloy with initial grains of ~ 1 mm after forging for 2 passes at 30% reduction each, revealing nanoscale β grains and presence of ω and α'' .

Fig. 5 OM microstructure away from the shear bands in the coarse grains (of the order of 1 mm) after forging for 2 passes at 30% reduction each, showing the formation of slip bands.

Fig. 6 OM microstructures showing (a) shear bands formed after one forging pass at 30% reduction, (b) recrystallized fine grains of 50-100 μm created after 5 minutes of annealing at 1173 K (900 $^{\circ}\text{C}$) in the shear zones marked *A*, *B* and *C* in the illustration, and (c) coarse grains of $> \sim 1$ mm in the area labelled *D* outside the shear zones.

Fig. 7 SEM microstructure after one forging-annealing cycle plus a second 30% forging, showing a higher density of slip bands in the coarse grains (e.g. the top grain in the upper inset and the bottom grain in the lower inset) and much fewer slip bands in the fine grains (e.g. the bottom grain in the upper inset and the top grain in the lower inset).

Fig. 8 OM microstructures after two forging-annealing cycles, showing (a), (b) and (c) the fine grains of 50-100 μm in areas *A*, *B* and *C* (in the shaded region in the illustration), respectively, and (d) coarse grains of $> \sim 1$ mm in area *D* (white).

Fig. 9 SEM microstructure after four forging-annealing cycles, showing a uniform distribution of fine β grains of 50-100 μm throughout the entire sample.

Fig. 10 TEM in the vicinity of a crack formed during the fifth forging step ($\epsilon_{eq} < 0.4$) in the Ti-5553 alloy after 4 forging-annealing cycles (i.e. with grains of 50-100 μm), showing (a) and (b) bright field images revealing needle shaped plates identified as α'' based on (c) the corresponding SADP, (d) dark field image for β and (e) dark field image for α'' .

Fig. 11 OM microstructures after one forging-annealing cycle plus a second 30% forging followed by annealing at 1173 K (900 °C) for up to 60 minutes, showing the average grain size (D_{avg}) at each time.

Fig. 12 FE simulation of the forging only processing, showing the distributions of equivalent stress and strain after (a) and (b) one 30% forging pass, (c) and (d) two forging passes at 30% reduction each, and (e) and (f) one 40% forging pass.

Fig. 13 The simulated temperature distributions after (a) one 30% forging pass, (b) two forging passes at 30% reduction each, and (c) one 40% forging pass, showing increases in temperature of less than 2-3 K (2-3 °C) in each case.

Fig. 14 FE simulation of the forging-annealing processing, showing the distributions of equivalent stress and strain after (a) and (d) one forging-annealing cycle plus a second 30% forging, (b) and (e) two forging-annealing cycles plus a third 30% forging, and (c) and (f) three forging-annealing cycles plus a fourth 30% forging. The dashed lines delineate the fine grained ($\sim 50\text{-}100\ \mu\text{m}$) region with $\varepsilon_{eq.} > 0.5$ at the end of the previous forging step, which is formed after annealing and stronger in the current forging step. F and A stand for forging and annealing, respectively.

Fig. 15 The simulated temperature distributions after (a) one forging-annealing cycle plus a second 30% forging, (b) two forging-annealing cycles plus a third 30% forging and (c) three forging-annealing cycles plus a fourth 30% forging, showing increases in temperature of less than 2-3 K (2-3 °C) in each case. F and A stand for forging and annealing, respectively.

Fig. 16 Schematic of the evolution of the grain structures after (a) one forging-annealing cycle showing the formation of fine grains in the shear zones, (b) two cycles and (c) three cycles showing an increase in the amount of fine grains, and (d) four cycles showing the creation of a uniform fine-grained structure.

Fig. 17 Grain growth (the average size of the recrystallized grains, D_{avg}) during the first 15 minutes of annealing at 1173 K (900 °C) following one forging-annealing cycle plus a second 30% forging, reaching the recrystallized grain size of $\sim 90 \mu\text{m}$.

Fig. 18 $D_{avg}^n - D_0^n$ versus t , plotted for $n = 2, 3$ and 4 . R^2 and K represent the correlation coefficient of the fitted line and the grain growth rate constant, respectively.

Fig. 19 Schematic of α'' plates with a width of w formed inside a cubic grain of size a .

Minerva Access is the Institutional Repository of The University of Melbourne

Author/s:

Zafari, A;Ding, Y;Cui, J;Xia, K

Title:

Achieving Fine Beta Grain Structure in a Metastable Beta Titanium Alloy Through Multiple Forging-Annealing Cycles

Date:

2016-07-01

Citation:

Zafari, A., Ding, Y., Cui, J. & Xia, K. (2016). Achieving Fine Beta Grain Structure in a Metastable Beta Titanium Alloy Through Multiple Forging-Annealing Cycles. METALLURGICAL AND MATERIALS TRANSACTIONS A-PHYSICAL METALLURGY AND MATERIALS SCIENCE, 47A (7), pp.3633-3648. <https://doi.org/10.1007/s11661-016-3496-5>.

Persistent Link:

<http://hdl.handle.net/11343/283277>