DOI: 10.1002/((please add manuscript number))

Article type: Communication

Ultrastable Supramolecular Self-encapsulated Wide-bandgap Conjugated Polymers for Large-area and Flexible Electroluminescent Devices

Jinyi Lin, Bin Liu, Mengna Yu, Xuhua Wang, Zongqiong Lin, Xinwen Zhang, Chen Sun, Juan Cabanillas-Gonzalez, Linghai Xie, Feng Liu, Changjin Ou, Lubing Bai, Yamin Han, Man Xu, Wensai Zhu, Trevor A. Smith, Paul N. Stavrinou, Donal D. C. Bradley* and Wei Huang**

((Optional Dedication))

Professor Dr Wei Huang, Professor Dr Feng Liu, Dr Jinyi Lin, Dr Changjin Ou, Mr Lubing Bai, Miss Yamin Han, Miss Man Xu, Mr Wensai Zhu

Key Laboratory of Flexible Electronics (KLOFE) & Institute of Advanced Materials (IAM), Jiangsu National Synergetic Innovation Center for Advanced Materials (SICAM), Nanjing Tech University (NanjingTech), 30 South Puzhu Road, Nanjing 211816, China.
E-mail: wei-huang@njtech.edu.cn

Professor Dr Donal D.C. Bradley, Dr Jinyi Lin

Departments of Engineering Science and Physics and Division of Mathematical, Physical and Life Sciences, University of Oxford, 9 Parks Road, Oxford OX1 3PD, UK.

Email: donal.bradley@mpls.ox.ac.uk

Professor Dr Donal D.C. Bradley, Professr Dr Paul N. Stavrinou, Dr Xuhua Wang, Dr Jinyi Lin

Department of Physics and Centre for Plastic Electronics, The Blackett Laboratory, Imperial College London, Prince Consort Road, London SW7 2AZ, UK.

This is the author manuscript accepted for publication and has undergone full peer review but has not been through the copyediting, typesetting, pagination and proofreading process, which may lead to differences between this version and the [Version of Record](#). Please cite this article as [doi: 10.1002/adma.201804811](#).

This article is protected by copyright. All rights reserved.

Professor Dr Wei Huang, Professor Dr Linghai Xie, Professor Dr Xinwen Zhang, Dr Bin Liu, Miss Mengna Yu

Center for Molecular Systems and Organic Devices (CMSOD), Key Laboratory for Organic Electronics and Information Displays & Institute of Advanced Materials (IAM), Jiangsu National Synergetic Innovation Center for Advanced Materials (SICAM), Nanjing University of Posts & Telecommunications, 9 Wenyuan Road, Nanjing 210023, China.

E-mail: iam@xjtu.edu.cn

Professor Dr Juan Cabanillas-Gonzalez, Miss Chen Sun

Madrid Institute for Advanced Studies (IMDEA Nanociencia), Ciudad Universitaria de Cantoblanco, Calle Faraday 9, Madrid 28049, Spain.

Professor Dr Trevor A. Smith, Miss Mengna Yu,

ARC Centre of Excellence in Exciton Science, School of Chemistry, The University of Melbourne, Parkville VIC 3010, Australia.

Professor Dr Paul N. Stavrinou

Department of Engineering Science, University of Oxford, Parks Road, Oxford OX1 3PD, UK.

Professor Dr Wei Huang, Professor Dr Zongqiong Lin, Dr Jinyi Lin,

Shaanxi Institute of Flexible Electronics (SIFE), Northwestern Polytechnical University (NPU), 127 West Youyi Road, Xi'an 710072, Shaanxi, China.

Keywords: Ultrastable, Self-encapsulated strategy, Deep blue, Polyfluorene, Flexible electroluminescent devices

Controlling chain behaviour through smart molecular design provides the potential to develop ultrastable and efficient deep-blue light-emitting conjugated polymers (LCPs). Herein, we proposed a novel supramolecular self-encapsulation strategy to construct a robust ultra-stable conjugated polydiarylfuorene (PHDPF-Cz) via precisely preventing excitons from inter-chain cross-transfer/coupling and contamination from external trace H_2O/O_2 . PHDPF-Cz consists of a mainchain backbone where the diphenyl groups localize at the 9-position as steric bulk moieties, and carbazole (Cz) units localize at the 4-position as supramolecular π -stacked synthon with dual functionality of self-assembly capability and hole-transport facility. Synergistic effect of the steric bulk groups and π -stacked carbazoles affords PHDPF-Cz an ultrastable property, including spectral, morphological stability and storage stability. In addition, PHDPF-Cz spin-coated gelation films also show thickness-insensitive deep-blue emission with respect to the reference polymers, which are suitable to construct

solution-processed large-scale optoelectronic devices with higher reproducibility. High-quality and uniform deep-blue emission is observed in large-area solution-processed films. Electroluminescence shows high-quality deep-blue intra-chain emission with a CIE (0.16, 0.12) and very narrow FWHM of 32 nm. Finally, large-area and flexible PLEDs devices with a single-molecular excitonic behavior are also fabricated. Our supramolecular self-encapsulation design provided an effective strategy to construct ultrastable LCPs for optoelectronic applications.

Flexible polymer light-emitting devices (PLEDs) are attracted more attentions in industrial and fundamental research for their potential application in wearable equipment, electronic skin and bio-smart devices.^[1,2] Beyond the device performance, the improvement of light-emitting conjugated polymers (LCPs) stability has been a long-standing challenge in plastic electronics, which is the main key factor to severely limit the commercialization of solid-state lighting and information displays.^[3-7] Compared to narrow band gap (green and red) luminescent molecular materials, the photophysical behavior in wide-bandgap blue LCPs are relatively complicated, involving energy transfer, a large Stokes shift and aggregation-induced excimer emission due to the high-energy absorption and active exciton behavior, which results in poor color purity, low luminescence efficiency and low spectral stability.^[8-11] In the last decades, polyfluorenes positioned as an important class of deep-blue LCPs that show pure blue color emission, high luminescence quantum efficiency, and easy processability.^[12-14] However, their emission behavior show undesirable features, such as an unstable green emission or strong film thickness-dependent emission, which degrades the color purity and decreases the device efficiency, reproducibility and stability.^[2,15-17] To enhance the spectral stability, all types of defects, including chemical and physical defects, should be avoided in polyfluorene solutions and films.^[18] Chemical defects are mainly associated to the reactive sites in the aromatic structure, which can facilitate the formation of keto defects following photo or thermal oxidation.^[6,17,19] Physical defects include chain aggregates, diverse conformation and

superstructures.^[6,20-22] All of these defects involve interchain excited states, aggregation-induced energy/charge transfer, non-emissive interchain polaron-pairs, and exciton-exciton annihilation, leading to a stronger lower-band emission or lower emission efficiency due to π -electron delocalization, hybridization and coupling.^[7,9,23,24] Technologically, these problems can be partially solved by isolating fluorophores in the solid state through a suitable molecular design.^[6] One effective method is to incorporate carbon-bridged fluorenes with steric bulks^[25,26] or dendron groups^[27,28] into ladder-type polymers to suppress π - π interactions.^[29,30] Another promising strategy is the design of polymers with non-covalent interactions or covalent linkages for the realization of insulated molecular wires (IMWs) by means of molecular encapsulation.^[31-37] However, such synthetic procedures are laborious, defects formed by post cyclization of polymer chains lead to steric congestion, and sophisticated threading limits wide application of ultrastable blue LCPs.^[33,37] In addition, insulated cyclical encapsulation or large steric frameworks tend to be randomly distributed among the chains in bulky states that significantly affect the interchain charge transport properties,^[31,38] which is unfavorable for their application to efficient electroluminescent devices and electrically-pumped lasers.^[32,39] A substantial PLEDs performance improving requires LCPs with high photoluminescence quantum yield as well as outstanding charge mobility. It is a challenge for all researchers to realize a careful balance between these conflicting design principles. Herein, we originally propose a supramolecular self-encapsulation strategy, that tethered bulky conjugated polymers with the π -stacked self-assembled units at side chain, is a versatile molecular design tool to achieve such completeness (*Scheme 1A*). π -Stacking of aromatic groups located at the side chain assemble into a sheath which surrounds the chain backbone, in analogy with electric power cords,

thus serving as "intermediate centers" to enable interchain charge transport and simultaneously to hinder interchain π - π interaction in solid states (*Scheme 1C*).^[40,41]

Inspired by the supramolecular steric hindrance (SSH) effect of bulk units on molecular conformation and packing, we proposed a novel strategy based on the molecular integration of steric bulk groups and supramolecular synthons into one functional molecule or chain (*Scheme 1A*).^[42,43] For all the effort put into the design of polyfluorenes over the last few decades,^[12] the utilization of the fluorene 4,5 position has been completely ignored. Recently, the second planar (θ) conformational stable polydiarylfuorenes was designed with a balance between the steric interaction of bulky diphenyl (9-position) and the entangled attraction of octyl side chain at 4-position (van der Waals force, vDW).^[22,43-46] Herein, we demonstrate a supramolecular approach in plastic electronic (Also called Supramolecular Plastic Electronic, SPE) to subtly avoid various pathways for defect generation based on ketone and aggregate formation to construct supramolecular self-encapsulated polyfluorenes. The state-of-the-art model is shortened to PHDPF-Cz, with the incorporation of diphenyl groups as steric repulsors and π -stacked Cz as the attractor at the 4-position (*Scheme 1B*). From theoretical analysis, the diaryl methanene bridge not only suppresses aggregate formation due to the tetrahedral sp^3 carbon configuration but also exhibits the functionality of an antioxidant over the alkyl side chain due to the high bonding strength.^[12,16] As expected, the pendent π -stacked Cz group self-assembles into an "encapsulated layer" surrounding the backbone,^[47] which hinders the interchain π - π interaction (analogous to the arrangement of electric power cords) and also serves as an "intermediate centre" to allow for interchain two-dimensional (2D) charge transporting (*Scheme 1C*). Therefore, uniform and ultrastable luminescence properties with the single-chain excitonic

behavior are observed for large-scale PHDPF-Cz films, which is encouraging for the fabrication of large-area and flexible devices.

π -Stacked aromatic groups based on sp^3 nitrogen are known to show excellent self-assembling and charge transporting behaviour.^[40,47-51] In this work, we introduced a π -stacked carbazole (Cz) group into polyfluorene as a pendent steric synthon to fabricate a novel supramolecular bulky wide-bandgap LCPs, PHDPF-Cz (*Scheme 1B* and *Figure S1*).^[12] PHDPF-Cz together with the controlled polymers PHDPF, PODPF, PNDPF and PFO were synthesized following our previous works (*Scheme S1*).^[23,45,46] GPC measurements revealed the number-average molecular weight (M_n) of 4.96×10^4 with a polydispersity index (PDI) of 1.65 for PHDPF-Cz, 4.37×10^4 (PDI = 1.68) for PHDPF, 4.74×10^4 (PDI = 1.56) for PNDPF and 5.80×10^4 (PDI = 1.42) for PFO (*Figure S2*). PHDPF-Cz showed a high decomposition temperature (T_d) of up to 415 °C and glass transition temperature (T_g) of ~168 °C (*Figures S3* and *S4*). The highest occupied molecular orbital (HOMO) and lowest unoccupied molecular orbital (LUMO) energy levels of PHDPF-Cz were estimated to be -2.48 and -5.42 eV via cyclic voltammetry (CV) analysis (*Figure S5*).

Firstly, to demonstrate the strong π -stacking interaction of Cz units in the supramolecular self-encapsulated polymer, X-ray diffraction, as well as GIXD of the polymer or monomer were used to visualise the behaviour of the polymer chains. Crystallographic analysis of DBrHDPF-Cz (PHDPF-Cz monomer) gives clear evidence for a π -stacked structural arrangement in which the fluorene monomer is isolated by a Cz "insulated" layer while leaving the terminal bromide groups intact for further modification and polymerization (*Figure S6*). In addition, as shown in *Figure S7*, DBrHDPF-Cz in diluted solution showed purple-coloured photoluminescence with a predominant narrow peak in the emission spectrum at a wavelength of 365 nm, which is attributed to light emission from a single

Cz unit. Two emission peaks were observed in the PL spectra of a DBrHDPF-Cz single crystal at 390 and 410 nm, which are attributed to partial and full face-to-face intermolecular overlap of Cz groups, suggested strong π - π stacked interaction for the Cz units (Figure S7).^[48] This strong π -stacking interaction of Cz units in the monomer crystal implies the possibility for the pendent Cz stacking interaction in PHDPF-Cz in the solid state.

Compared to the non-encapsulated polyfluorenes, PCzODPF has excellent gelation capability in toluene, with a significantly lower critical gel concentration (CGC) of 2.5 mg/ml (0.28% wt, aged 24 hours) at room temperature (Figure S8), indicates that the π - π stacking interaction of pendent Cz moieties is the most likely driving force for PHDPF-Cz/toluene gelation, consistent with the crystallographic analysis of DBrHDPF-Cz discussed above (Figure S6). Besides, circular dichroism (CD) studies were used to demonstrate a positive CD signal for PHDPF-Cz toluene solution or gelation films compared to no CD signal observed in non-gelatin solvent (CHCl_3) solution where PHDPF-Cz is molecularly dissolved (Figure S9). Films coated from CHCl_3 , as well as all controlled PNDPF films, also showed no CD effects, and confirmed that the self-assembled gelation structure of PHDPF-Cz has a helical property. In practice, this molecular gelation structure in “precursor” hydrocarbon solutions may propagate into the mesoscale morphology of a spun film, particularly when only chain swelling occurs in the absence of non-covalent interactions between chain and solvent molecules.^[12,20,22,45,52]

As shown by the AFM images in Figures S10-S15, in contrast to the smooth surfaces found in the controlled polymer films, the “likely” oriented nanostructure can be obtained in PHDPF-Cz films spin-coated from toluene solution. Grazing incidence X-ray diffraction (GIXD) is also applied here to characterize the interchain π - π interaction and chain behaviour of PHDPF-Cz, PODPF, PNDPF and PHDPF spin-coated films. In general, the GIXD images clearly show a continuous diffraction ring and

no obvious patterned spots, which indicated that all materials are in completely amorphous states.

The corresponding diffusive ring with a broad peak at $Q_{xy} = 1.325 \sim 1.378 \text{ \AA}^{-1}$ ($d = 4.557 \sim 4.740 \text{ \AA}$, from $d = 2\pi/q$) and $Q_z = 1.423 \sim 1.433 \text{ \AA}^{-1}$ ($d = 4.413 \sim 4.382 \text{ \AA}$) may be ascribed to the interchain π - π interaction (chain aggregation in all controlled films) (Figures S10-S15). However, for the PHDPF-Cz film spin-coated from toluene solution, no obvious diffraction ring was observed for the Q_{xy} (from $1.300 \sim 1.400 \text{ \AA}^{-1}$) direction in the GIXD pattern image, indicating extremely weak or even no interchain π - π interaction ($d > 4.740 \text{ \AA}$, Figure S12). The fairly intense peak at $Q_z = 1.382 \text{ \AA}^{-1}$ is ascribed to the distance between the steric carbazole moieties ($d_{Cz} = 4.544 \text{ \AA}$, Scheme 1c and Figure S12), similar to previous work.^[47] Intuitively, the results shown above further confirmed weak interchain π - π interaction in the PHDPF-Cz films spin-coated from toluene, which leads to the realization of remarkable intrachain photophysical properties in the absence of interchain excited states in the solid state.

Ideally, our supramolecular self-encapsulation approach enable PHDPF-Cz to show excellent intrachain photo-physical properties in the solid state.^[25,31,32] One can expect reduced energy transfer and quenching aggregation processes to result in a very small red-shift of the PL spectrum in films compared to that in solution.^[36,53] The PL spectrum of PHDPF-Cz in toluene solution (10^{-3} mg/ml) consisted of three emission peaks at 434, 458 and 491 nm, attributed to the 0-0, 0-1 and 0-2 vibronic transitions of a single polyfluorene chain (Figure 1). Interestingly, the PL spectral shape of a PHDPF-Cz spin-coated film was very similar to the PL measured in solution (Figure 1A), with a slight red-shift of approximately ~ 4 nm (438, 461 and 495 nm) observed. These small peak shifts, which we could not assign to any particular feature of conventional "IMWs", are probably due to solvent effects, where restriction of the conformational motion and/or dielectric constant leads to changes

in the solid films. Importantly, PHDPF-Cz gelation samples showed similar emission peaks but with a slightly larger 0-1/ 0-0 peak ratio compared to solution and the spin-coated film. This can be reasonably explained by the stronger self-absorption shown by thicker samples. Conversely, PFO, PODPF, and PPEOH gels show different PL spectral shapes when processed in any of the mentioned forms, which is mainly assigned to stronger aggregation and interchain π - π interaction.^[20,21,45] In addition, the intrachain emission properties of PHDPF-Cz solution and gels were further investigated by time-resolved PL measurements (Table S1). Typical PHDPF-Cz gels showed a PL decay lifetime of 466 ps at 440 nm, 486 ps at 468 nm and 491 ps at 499 nm, which are nearly the same as in diluted solution for the emission peak of 433 (472 ps), 460 (486 ps) and 480 nm (480 ps), with only one component (Figure S16), which are all significantly different from those obtained for PFO.^[38] These data strongly supported that there is weaker π - π interaction of backbone chain and the absence of interchain excited states in the gelation structure. Moreover, the fluorescence quantum yields (PLQY, Φ) of PHDPF-Cz in solution and pristine film are ~80% (± 5) and ~55% (± 5), respectively, which are slightly higher than that found for the controlled polymers, retaining 71% of the value in solution ($\Phi_{\text{film}}/\Phi_{\text{solution}}$). Similar $\Phi_{\text{film}}/\Phi_{\text{solution}}$ ratios are found in conventional IMW films that have been highlighted as solid-state emissive materials in the literature.^[35]

More interestingly, the PL spectral shape of PHDPF-Cz pristine gelation films is independent of film thickness from 60 to 155 nm (Figures 1B and S17) due to the screening effect of the “insulation”. This thickness-insensitive PL property is very important for industrial applications and can be used to enhance the reproducibility of device performance and fabrication via large-scale print processing. Conversely, the intensity ratio for the 0-1/0-0 band emission for a PHDPF-Cz film spin-coated from CHCl_3 solution is slightly enhanced with increasing film thickness, which may be attributed to weaker

intrachain and interchain *JH*-aggregation behaviour in the solid state.^[3,53] Note that we cannot completely avoid the self-absorption effect in the thick film samples (Similar absorbance intensity of PHDPF-Cz and PHDPF with the same film thickness as shown in Figure S18). For the controlled polymers, the emission spectra of PHDPF and PNDPF pristine thin films (thickness of 90~100 nm) showed three peaks at 443, 463 and 493 nm, but the intensity of the emission peak at 463 nm (0-1 band) was stronger than that at 443 nm (0-0 band).^[54] Moreover, PL spectra of PHDPF, PODPF and PNDPF pristine films were strongly influenced by the film thickness from 60 to 150 nm (Figures S17), which also confirmed strong interchain aggregation, consistent with the GIXD and NMR results.^[3] Due to the screening effect of the insulation, the optical properties of PHDPF-Cz films are only slightly sensitive to the solution processing conditions, film morphology and thickness. Therefore, a large-scale high-quality PHDPF-Cz film (30 cm × 10 cm) deposited onto a flexible PET substrate using a scraping method showed PL similar to that found for the spin-coated film, with a uniform deep-blue emission under 365 nm UV light excitation (inset shown in Figure 1B).

Subsequently, we also demonstrated a systematic visualization for this single-chain excitonic behaviour in PHDPF-Cz and PHDPF films via ultrafast time-resolved spectroscopy (Figures 1C-1F). Novel time-resolved scanning confocal fluorescence imaging (FLIM) measurements are explored here to investigate excitonic behaviour in solid states. As discussed above, a uniform and smooth PHDPF film was obtained by spin-coating from toluene solution. As shown in Figure 1C, a relatively homogeneous morphology was observed in FLIM images collected from typical regions in this film for the completely amorphous states. The major lifetime of the PHDPF exciton in this film was approximately 308~450 ps, with an average value of 380 ps, consistent with the values reported for polyfluorene solutions and spin-coated films. However, for the PHDPF-Cz film obtained from toluene

solution, increased roughness was observed, which is attributed to the formation of oriented nanostructures. The morphology of the films, in particular the presence of relatively inhomogeneities in the fluorescence decay behaviour on the submicro- or nanometer scales (Figure 1C), is clearly similar to the results of AFM analysis. Meanwhile, the exciton lifetime was measured to be much shorter (150~300 ps, average value is about 190 ps). According to the Franck-Condon principle, these striking differences in band shape, suggested the slightly different geometry between the excited state and the ground state observed for the case of the Cz-threaded layer.^[36] Weakly emissive π - π stacked strands can suppress ultrafast exciton transferred into non-emissive inter-chain polaron-pairs, which can decrease the exciton decay time. In fact, chain separation induced by the self-encapsulation in PHDPF-Cz also suppresses exciton-exciton annihilation, which is usually happened in densely packed condensed structure. Figures 1D and 1E show the pump-probe transient absorption spectra of PHDPF and PHDPF-Cz spin-coated films which contain spectral signatures of stimulated emission (SE) and photoinduced absorption (PA). Below 2.4 eV (517 nm), PHDPF and PHDPF-Cz films exhibit strong SE bands confirming their emissive and light amplification capabilities, being promising candidates as optical gain media in lasers. In line with PFO, the PA signal in PHDPH and PHDPF-Cz is expected to have two different components: a PA band in the 520-540 nm spectral region arising from polaron pairs and a singlet exciton PA band extending towards the red-NIR, both having different kinetics. Figure 1F depicts a comparison between SE and PA dynamics at 603 and 611 nm (the wavelength where polarons supposedly have the larger spectral contribution) in both polymers. Starting with PHDPF-Cz, SE and PA dynamics follow parallel trends suggesting the dominant interplay of intra-chain singlet excitons and the lack of polaron states at long time delays. Conversely, in PHDPF film, SE at 2.7 eV (462 nm) clearly exhibits a much shorter-

lived component absent in PA at 2.06 eV (602 nm). These discrepancies seem to confirm that the polaron pair yield is much higher in PHDPF than in PHDPF-Cz upon same photoexcitation conditions.^[55,56] Recently, Sun et al. reported on a suppression of polaron features in the transient absorption spectra of thiophene-based IMWs films, which they assign to hindrance of inter-chain hole / electron transfer required to stabilize polaron pairs.^[57] Accordingly, chain isolation promoted by Cz stacked layers in PHDPF-Cz could contribute to effectively encapsulate excitons and reduce the exciton dissociation probability. Our molecular design enables the suppression of induced absorption associated with long-lived excited states by inhibiting inter-chain aggregation, while further enhancing the emission properties of LCPs.

Compared to the conventional thermal stability and working stability of LCPs, the storage stability of LCPs films has been rarely addressed in the last several decades, which is the most important factor determining practical optoelectronic application in the future. Molecular encapsulation of the conjugated backbone can also significantly improve the chemical stability.^[31,58-60] In previous studies, the stability of LCPs was analysed by thermal annealing and DSC recycling.^[12,18] Note that it is not enough to only evaluate the chemical, morphological, or spectral stability, especially to check the storage and working stability of materials and devices. Similar to other reported highly stable polydiarylfluorenes, PHDPF-Cz, PHDPF, PODPF and PNDPF films showed excellent spectral stability after thermal annealing at 180 °C under ambient conditions for 10 min (Figures 2A, and S19).^[45] Increased thermal annealing temperature or ageing time led to the observation of weaker green-band emission in common polydiarylfluorenes without Cz units. The corresponding $I_{\text{green}}/I_{\text{blue}}$ (ratio of light emission intensity at 555 nm and 440 nm) is approximately 0.35 (2 h) (initial value is about 0.07). Interestingly, our novel self-encapsulated PHDPF-Cz showed excellent thermal spectral

stability, with an $I_{\text{green}}/I_{\text{blue}}$ value of 0.08 after annealing for 8 h (initial value was approximately 0.05). Besides, the 3D AFM image of the PHDPF-Cz pristine film also showed some nanostructure. In addition, instead of larger aggregates or domains, we found a slightly smoother morphology in all annealed films, which indicates excellent thermal morphological stability (Figure 2A). However, the thermally annealed PHDPF films showed some obvious aggregate formation and crystalline superstructure, consistent with our previous work.^[22] However, evaluating the stability via thermal annealing is extremely not enough. Therefore, we also aged the pristine films in air for about 21 days, and, in some cases, even longer (room temperature, R.H.: 70%, daylight and even under UV irradiation, Figure S20) and observed that all PL spectra of the PHDPF and PNDPF films changed conspicuously with the appearance of an additional shoulder of green (g)-band emission at 555 nm (Figure 2B). The corresponding light emission colour of PHDPF and PNDPF films changed from deep-blue to green-yellow. Remarkably, PHDPF-Cz films spin-coated from toluene solution showed excellent stability, with no obvious g-band emission observed under the same ageing conditions and even greater stability than films spin-coated from CHCl_3 solution that showed a weaker g-band emission at 555 nm and a stronger 0-1 band emission. The green indices $I_{\text{green}}/I_{\text{blue}}$ are approximately 0.75 and 0.45, 0.60 and 0.62, and 0.10 and 0.05 for PNDPF, PHDPF and PHDPF-Cz aged films spin-coated from CHCl_3 and toluene solutions, respectively. As expected, all β conformation and amorphous PFO films showed stronger g-band emission after ageing for 3 days under the same conditions (Figure S21), with the corresponding $I_{\text{green}}/I_{\text{blue}}$ ratio being approximately 0.48 (DCE), 1.55 (Toluene) and 1.85 (CHCl_3). These results indicated that PHDPF-Cz shows an advantage over PNDPF, PODPF, PHDPF and PFO in terms of improved film spectral stability. However, the Φ of all our films decreased with prolonged aging time, as shown in the inset of Figure 2C. Pristine films processed

under the same conditions but stored in a N₂ atmosphere glove box showed no g-band emission, which suggested a synergistic effect of H₂O and O₂ on g-band emission (Figure S22). Besides, we also observed that there is no obvious change in the absorbance spectra of all polymers spin-coated films in this work after thermal annealing aging in the air several days (Data not shown here). The mechanism for the instability (also called photobleaching) has not yet been elucidated, but whatever process is involved, the control PFO, PHDPF and PNDPF films show lower photostability under mixed H₂O/O₂ and light. The discovery that the supramolecular self-encapsulation can significantly improve the fluorescence and photostability of PHDPF-Cz indicates that this may be a valuable method for enhancing the stability and brightness of LCPs.

Conventional architectures for IMWs with the encapsulated framework served as so-called insulated "dopants" with steric hindrance, tended to be randomly distributed within the conjugated chain, and showed extremely lower transport properties that were strongly affected by the resulting structural and electronic disorder^[31,36] (such as the incorporation of cyclic side chains, which decreased the carrier mobility from 4.8×10^{-5} to $4.7 \times 10^{-11} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$,^[39] for example). In this regard, such "IMWs" bulky film may not be suitable for efficient electroluminescent devices and electrically pumped lasers. In sharp contrast with the insulated encapsulated layer used in these reported IMWs, use of π -stacked Cz groups as a threaded "encapsulated layer" in our system probably not only suppresses interchain energy transfer and facilitates single-molecular excitonic behavior but also enables two-dimensional (2D) coherent charge transport (both π -conjugated and π -stacked channel^[48,61]) with comparable charge mobility (Scheme 1C). Firstly, we fabricated hole-dominated devices (ITO/PEDOT:PSS/polymers/MoO₃/Au) to investigate the transport capability of PHDPF-Cz. As shown in Figure 3A, the hole mobility of PHDPF-Cz films spin-coated from CHCl₃ solution is slightly

dependent on the film thickness and is approximately $10^{-5} \sim 10^{-4} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ for a root square of the electrical field $E^{1/2}$ in the range of $400 \sim 600 \text{ (V/cm)}^{1/2}$, similar to PFO and PODPF films.^[13,44,62] In addition, the hole mobility of PHDPF-Cz MWs films clearly shows a thickness dependence, with values of approximately $10^{-6} \sim 10^{-4} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ under the same conditions, which is comparable to the hole mobility reported for conjugated polymers with stronger π - π interaction.^[39,63] Although the rough surface morphology of PHDPF-Cz film may lead to slightly lower mobility values than those found for films spin-coated from CHCl_3 solution, this mobility is several orders of magnitude higher than that previously reported for spin-coated IMW films.^[38] For our novel PHDPF-Cz film, Cz units incorporated into the side-chain do not only disturb the π -stacking of the polymer backbones but also act as an "intermediate centre", which enables hole charges to delocalize across different chains sufficiently to exhibit the signatures of 2D coherent transport, as discussed above (*Scheme 1C*). As a consequence, given the importance of charge carrier balance, the hole mobilities observed are likely to be beneficial for realizing high values for the electroluminescence quantum efficiency. PLEDs with a sandwich structure composed of ITO/PEDOT: PSS/polymer films with varying film thickness/TPBi (30 nm)/LiF (0.5 nm)/Al (100 nm) were fabricated (Figures 3 and S23-30). As shown in Figure 3B, the EL spectra of PHDPF-Cz devices consisted of three emission peaks at 440, 461 and 495 nm, with a full-width at half-maximum (FWHM) of 32 nm, which is strikingly similar to the corresponding PL spectrum. As the applied voltage was increased from 4 (0.072 mA cm^{-2}) to 9 V (218.3 mA cm^{-2}), devices showed stable deep blue emission, with CIE coordinates of (0.16, 0.12). Moreover, owing to the absence of interchain energy transfer, the EL spectra of PHDPF-Cz-based PLEDs are independent of emissive film thickness (Figures S23-25). Conversely, the EL spectra of PHDPF pristine films (92 nm) showed a maximum peak at 470 nm, together with emission peaks at 443 and 495 nm, with a

full-width at half-maximum (FWHM) of 72 nm and a CIE of (0.20, 0.21) (Figure S28). However, the 0-1 band emission peak decreased in the EL spectra measured for PHDPF pristine films with decreasing thickness from 92 to 58 nm (Figure S29). These thicknesses (morphology)-dependent EL spectra are undesirable for improving device reproducibility and stability. Devices based on PHDPF-Cz films spin-coated from toluene solution showed a lower turn-on voltage of 3.95 V and a maximum brightness of 3523 cd m⁻², with a luminous efficiency of 2.56 cd A⁻¹ (Figure 3C). In addition, devices based on PHDPF-Cz films spin-coated from toluene outperformed devices based on films processed from CHCl₃ as well as devices based on PHDPF, which demonstrates the improved emission stability.

Excellent deep-blue spectral and morphological stability with a relatively narrow FWHM of 32 nm for the light output can enable fabrication of larger-scale flexible PLEDs. Therefore, flexible large-scale PLEDs were also fabricated based on a flexible substrate configuration of (PET) (75 μm)/PEDOT:PSS electrode layer (30 nm)/ PEDOT:PSS (80 nm)/PHDPF-Cz layer (110 nm)/Ca (30 nm)/Al (120 nm). The total area for the flexible devices is approximately 8 × 8 cm, with two different cell sizes of approximately 30 mm × 2 mm and 10 mm × 2 mm. The transparent electrode is also based on a commercially available PEDOT:PSS formulation. The PHDPF-Cz film thickness is approximately 105~125 nm. Finally, an Al electrode is used to form the back contact. The flexible PLEDs show a luminance of 1000 cd m⁻² at 8.2 V, with the highest luminance obtained of 1780 cd m⁻² and a power efficiency of 1.73 cd A⁻¹. The devices are fully functional PLEDs, with reasonable operating conditions of <5 V turn on voltage (4.55 V). Finally, PL and EL spectra of PHDPF-Cz solution, gel and films with varying thicknesses (pristine, annealed, and aged in air) are remarkably similar (Figure 3D), strongly supporting the validity and effectiveness of the supramolecular self-encapsulation strategy.

Therefore, our self-encapsulated polymer demonstrates excellent electroluminescent properties, which can be exploited for plastic-based flexible displays.

To summarize, we have implemented a supramolecular self-encapsulation strategy for controlling interchain interactions of LCPs in the solid state via tethering the backbone chain with supramolecular π -stacked layers. An excellent gelation property of PHDPF-Cz in toluene solution indicated a strong π - π stacking interaction of Cz groups. Therefore, pendent Cz groups can self-assemble into a protective sheath, not only to inhibit interchain interaction and afford intrachain emission behaviour but also to improve spectral and morphological stability and interchain charge transport. Finally, stable deep-blue PHDPF-Cz-based PLEDs with EL featuring the intrachain excited state, can be fabricated with a high current efficiency of 2.56 cd/A and low turn-on voltage of 3.95 V. The fabrication of larger-scale and efficient flexible PLEDs further confirmed the effectiveness of our supramolecular self-encapsulation strategy.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

We thank primary financial supports by the National Natural Science Foundation of China (61874053, 21504041, 21502091), the National Key Basic Research Program of China (973) (2015CB932200). Natural Science Funds of the Education Committee of Jiangsu Province (18KJA430009), “High-Level Talents in Six Industries” of Jiangsu Province (XYDXX-019), J.C-G acknowledges financial support from the Spanish Ministry of Economy and Competitiveness through projects MAT2014-57652-C2-1/2-R (LAPSEN) and PCIN-2015-169-C02-01/02 (MOFSENS) and through the Severo Ochoa Programme for Centers of Excellence (SEV-2016-0686) and the Campus of International Excellence (CEI) UAM+CSIC. J. C-G. and C. S. are also grateful to the China Scholarship Council (201608390023) for a PhD sponsorship.

Received: ((will be filled in by the editorial staff))

Revised: ((will be filled in by the editorial staff))

Published online: ((will be filled in by the editorial staff))

References

- [1] Lipomi, D. J.; Bao, Z. *Mrs Bull.* **2017**, *42*, 93.
- [2] Heo, S. W.; Lee, E. J.; Han, Y. W.; Lee, Y. S.; Lee, W. J.; Choa, S.-H.; Kim, Y. S.; Moon, D. K. *J. Ind. Eng. Chem.* **2017**, *53*, 68.
- [3] Spano, F. C.; Silva, C. In *Annual Rev. Phys. Chem., Vol 65*; Johnson, M. A., Martinez, T. J., Eds. 2014; Vol. 65, p 477.
- [4] Grimsdale, A. C.; Chan, K. L.; Martin, R. E.; Jokisz, P. G.; Holmes, A. B. *Chem. Rev.* **2009**, *109*, 897.
- [5] Honmou, Y.; Hirata, S.; Komiyama, H.; Hiyoshi, J.; Kawauchi, S.; Iyoda, T.; Vacha, M. *Nature Commun.* **2014**, *5*, 4666
- [6] Friend, R. H.; Gymer, R. W.; Holmes, A. B.; Burroughes, J. H.; Marks, R. N.; Taliani, C.; Bradley, D. D. C.; Santos, D. A. D.; Brédas, J. L.; Lögdlund, M.; Salaneck, W. R. *Nature* **1999**, *397*, 121.
- [7] Heeger, A. J. *Chem. Soc. Rev.* **2010**, *39*, 2354.
- [8] So, F.; Kondakov, D. *Adv. Mater.* **2010**, *22*, 3762.
- [9] Lakowicz, J. R.; Masters, B. R. *Naturwissenschaften* **1991**, *78*, 456.
- [10] Shin, S. H.; Park, J. S.; Park, J. W.; Kim, H. K. *Synth. Met.* **1999**, *102*, 1060.
- [11] Farinola, G. M.; Ragni, R. *Chem. Soc. Rev.* **2011**, *42*, 3467.
- [12] Xie, L. H.; Yin, C. R.; Lai, W. Y.; Fan, Q. L.; Huang, W. *Prog. Polym. Sci.* **2012**, *37*, 1192.
- [13] Yap, B. K.; Xia, R.; Campoyquiles, M.; Stavrinou, P. N.; Bradley, D. D. *Nature Mater.* **2008**, *7*, 376.

- [14] Perevedentsev, A.; Sonnefraud, Y.; Belton, C. R.; Sharma, S.; Cass, A. E.; Maier, S. A.; Kim, J. S.; Stavrinou, P. N.; Bradley, D. D. *Nature Commun.* **2015**, *6*, 5977.
- [15] And, Q. P.; Yang, Y. *J. Am. Chem. Soc.* **1996**, *118*, L1673.
- [16] Scherf, U.; List, E. J. W. *Adv. Mater.* **2002**, *14*, 477.
- [17] And, V. N. B.; Carter, S. A.; Scott, J. C.; Klärner, G.; And, R. D. M.; Miller, D. C. *Macromolecules* **2011**, *32*, 361.
- [18] Liang, J.; Qian, Y.; Xie, L. H.; Shi, N. E.; Chen, S. F.; Deng, X. Y.; Huang, W. *Acta Phys. Chim. Sin.* **2010**, *26*, 946.
- [19] Sims, M.; Bradley, D. D. C.; Ariu, M.; Koeberg, M.; Asimakis, A.; Grell, M.; Lidzey, D. G. *Adv. Funct. Mater.* **2010**, *14*, 1037.
- [20] Knaapila, M.; Monkman, A. P. *Adv. Mater.* **2013**, *25*, 1090.
- [21] Lin, Z. Q.; Shi, N. E.; Li, Y. B.; Qiu, D.; Zhang, L.; Lin, J. Y.; Zhao, J. F.; Wang, C.; Xie, L. H.; Huang, W. *J. Phys. Chem. C* **2011**, *115*, 4418.
- [22] Liu, B.; Lin, J.; Yu, M.; Li, B.; Xie, L.; Ou, C.; Liu, F.; Li, T.; Lu, D.; Huang, W. *J. Phys. Chem. C* **2017**, *121*.
- [23] Lin, J.; Yu, Z.; Zhu, W.; Xing, G.; Lin, Z.; Yang, S.; Xie, L.; Niu, C.; Huang, W. *Polym. Chem.* **2013**, *4*, 477.
- [24] Shaw, P. E.; Ruseckas, A.; Peet, J.; Bazan, G. C.; Samuel, I. D. W. *Adv. Funct. Mater.* **2010**, *20*, 155.
- [25] Pan, C.; Sugiyasu, K.; Aimi, J.; Sato, A.; Takeuchi, M. *Angew. Chem.* **2014**, *53*, 8870.
- [26] Swager, T. M. *Acc. Chem. Res.* **2008**, *41*, 1181.
- [27] Pogantsch, A.; Wenzl, F. P.; List, E. J. W.; Leising, G.; Grimsdale, A. C.; Müllen, K. *Adv. Mater.* **2002**, *14*, 1061.

- [28] Marsitzky, D.; Vestberg, R.; Blainey, P.; Tang, B. T.; Hawker, C. J.; Carter, K. R. *J. Am. Chem. Soc.* **2001**, *123*, 6965.
- [29] Wu, Y.; Zhang, J.; Fei, Z.; Bo, Z. *J. Am. Chem. Soc.* **2008**, *130*, 7192.
- [30] Scherf, U.; Müllen, K. *Die Macromol. Rapid Commun.* **1991**, *12*, 489.
- [31] Swager, T. *Nature Mater.* **2002**, *1*, 151.
- [32] Cacialli, F.; Wilson, J. S.; Michels, J. J.; Daniel, C.; Silva, C.; Friend, R. H.; Severin, N.; Samori, P.; Rabe, J. P.; O'Connell, M. J. *Nature Mater.* **2002**, *1*, 160.
- [33] Michael, J. F.; Harry, L. A. *Angew. Chem. Int. Ed.* **2007**, *46*, 1028.
- [34] Cardin, D. J. *Adv. Mater.* **2002**, *14*, 553.
- [35] Pan, C.; Sugiyasu, K.; Wakayama, Y.; Sato, A.; Takeuchi, M. *Angew. Chem.* **2013**, *125*, 10975.
- [36] Brovelli, S.; Cacialli, F. *Small* **2010**, *6*, 2796.
- [37] Pan, C.; Zhao, C.; Takeuchi, M.; Sugiyasu, K. *Chem. An Asian J.* **2015**, *10*, 1820.
- [38] Brovelli, S.; Latini, G.; Frampton, M. J.; McDonnell, S. O.; Oddy, F. E.; Fenwick, O.; Anderson, H. L.; Cacialli, F. *Nano Lett.* **2008**, *8*, 4546.
- [39] Méhes, G.; Pan, C.; Bencheikh, F.; Zhao, L.; Sugiyasu, K.; Takeuchi, M.; Ribierre, J. C.; Adachi, C. *Acs Macro Lett.* **2016**, *2016*, 781.
- [40] Sasaki, T.; Mawatari, Y.; Tabata, M. *Polym. Chem.* **2015**, *6*, 8012.
- [41] Wang, S.; Feng, X.; Zhang, J.; Yu, P.; Guo, Z.; Li, Z.; Wan, X. *Macromolecules* **2017**, *50*.
- [42] Hoebe, F. J. M.; Jonkheijm, P.; Meijer, E. W.; Schenning, A. P. H. J. *Chem. Rev.* **2005**, *105*, 1491.
- [43] Li, Y. X.; Wang, S. S.; Yu, Y.; Zhang, H.; Wang, W. Y.; Yang, R. Q.; Xie, L. H.; Liu, F.; Lin, Z. Q.; Shi, N. E. *Small* **2017**, *14*, 1703151.
- [44] Liu, B.; Lin, J. Y.; Liu, F.; Yu, M. N.; Zhang, X. W.; Xia, R.; Yang, T.; Fang, Y. T.; Xie, L.; Huang, W. *Acs Appl Mater Interfaces* **2016**, *8*, 21648.

- [45] Lin, J. Y.; Zhu, W. S.; Liu, F.; Xie, L. H.; Zhang, L.; Xia, R.; Xing, G. C.; Huang, W. *Macromolecules* **2015**, *47*, 1001.
- [46] Bai, L. B.; Liu, B.; Han, Y. M.; Yu, M. N.; Wang, J.; Zhang, X. W.; Ou, C. J.; Lin, J. Y.; Zhu, W. S.; Xie, L. *Acs Appl Mater Interfaces* **2017**.
- [47] Sasaki, T.; Yoshida, Y.; Mawatari, Y.; Tabata, M. *Macromolecules* **2015**, *48*, 889-897.
- [48] Xie, L. H.; Ling, Q. D.; Hou, X. Y.; Huang, W. *J. Am. Chem. Soc.* **2008**, *130*, 2120.
- [49] Moulin, E.; Niess, F.; Maaloum, M.; Buhler, E.; Nyrkova, I.; Giuseppone, N. *Angew. Chem.* **2010**, *49*, 6974.
- [50] Faramarzi, V.; Niess, F.; Moulin, E.; Maaloum, M.; Dayen, J. F.; Beaufrand, J. B.; Zanettini, S.; Doudin, B.; Giuseppone, N. *Nature Chem.* **2012**, *4*, 485.
- [51] Uemura, T.; Uchida, N.; Asano, A.; Saeki, A.; Shu, S.; Tsujimoto, M.; Isoda, S.; Kitagawa, S. *J. Am. Chem. Soc.* **2012**, *134*, 8360.
- [52] Zheng, Y.-Q.; Yao, Z.-F.; Lei, T.; Dou, J.-H.; Yang, C.-Y.; Zou, L.; Meng, X.; Ma, W.; Wang, J.-Y.; Pei, J. *Adv. Mater.* **2017**, *29*.
- [53] J. Cornil; D. A. dos Santos; X. Crispin; R. Silbey, a.; J. L. Brédas, *J. Am. Chem. Soc.* **1998**, *120*, 1289.
- [54] Michels, J. J.; O'Connell, M. J.; Taylor, P. N.; Wilson, J. S.; Cacialli, F.; Anderson, H. L. *Chem. Eur.-J.* **2003**, *9*, 6167.
- [55] Zhang, Q.; Liu, J.; Wei, Q.; Guo, X.; Xu, Y.; Xia, R.; Xie, L.; Qian, Y.; Sun, C.; Lüer, L.; Cabanillas-Gonzalez, J.; Bradley, D. D. C.; Huang, W., *Adv. Funct. Mater.* **2018**, *28* (17), 1705824.
- [56] Mróz, M. M.; Sforazzini, G.; Zhong, Y.; Wong, K. S.; Anderson, H. L.; Lanzani, G.; Cabanillas-Gonzalez, J. *Adv. Mater.* **2013**, *25*, 4347.

- [57] Sun, C.; Mróz, M. M.; Castro Smirnov, J. R.; Lüer, L.; Hermida-Merino, D.; Zhao, C.; Takeuchi, M.; Sugiyasu, K.; Cabanillas-González, J., *J. Mater. Chem. C* **2018**, 6 (24), 6591.
- [58] Stone, M. T.; Anderson, H. L. *Chem. Commun.* **2007**, 23, 2387.
- [59] Yau, C. M.; Pascu, S. I.; Odom, S. A.; Warren, J. E.; Klotz, E. J.; Frampton, M. J.; Williams, C. C.; Coropceanu, V.; Kuimova, M. K.; Phillips, D. *Chem. Commun.* **2008**, 25, 2897.
- [60] Frampton, M. J.; Claridge, T. D.; Latini, G.; Brovelli, S.; Cacialli, F.; Anderson, H. L. *Chem. Commun.* **2008**, 24, 2797.
- [61] Shao, S.; Hu, J.; Wang, X.; Wang, L.; Jing, X.; Wang, F. *J. Am. Chem. Soc.* **2017**, 139, 17739.
- [62] Redecker, M.; Bradley, D. D. C.; Inbasekaran, M.; Woo, E. P. *Appl. Phys. Lett.* **1998**, 73, 1565.
- [63] Sirringhaus, H.; Brown, P. J.; Friend, R. H.; Nielsen, M. M.; Bechgaard, K.; Langeveld-Voss, B. M. W.; Spiering, A. J. H.; Janssen, R. A. J.; Meijer, E. W.; Herwig; Amp, P. *Nature* 1999, 401, 685.

Scheme 1. Schematic representation of the supramolecular self-encapsulation strategy for wide bandgap LCPs. (A) Typical molecular model of our supramolecular self-encapsulated LCPs. (B) Chemical structure of the model polymer, PHDPF-Cz, together with the controlled polyfluorenes. (C) Computer-generated model of PHDPF-Cz: i) axial and ii) lateral views. Schematic diagram illustrating the ideal molecular packing model for a PHDPF-Cz self-assembled superstructure, where the pendent Cz groups self-assemble into a sheath and act as an encapsulated layer to isolate the chain and inhibit the interchain interaction between π - π backbones, similar to previous studies.^[47, 52, 53] Blue rings signify the backbone chain. Red loops indicate the Cz-threaded layers. The yellow arrow represents the 2D charge transport channel. The orange-yellow arrow denotes the penetration path for various gases, which is disrupted by the Cz-threaded layer.

Figure 1. Optical properties of PHDPF-Cz in various states. (A) Absorbance and PL spectra of PHDPF-Cz in toluene solution (10^{-3} mg/ml), pristine film spin-coated from toluene solution (10 mg/ml, 95 nm) and gels (6 mg/ml). Inset shows photographs of the PHDPF-Cz film, concentrated solution and gel taken under a UV lamp (365 nm). The colour of the light emission from the PHDPF-Cz/toluene gel is similar to the pristine concentrated solution and corresponding spin-coated film. (B) PL spectra of PHDPF-Cz pristine films with varying thicknesses spin-coated from toluene and CHCl_3 solutions, together with PL spectrum of transparent film drop-coated from toluene (Drop-cast film: 2 mg/ml). Inset shows a photograph of a PHDPF-Cz film on a large-scale flexible PET substrate prepared using a scraping method from toluene solution (0.5 mg/ml; under 365 nm UV light; scale: 30 cm $\times$ 20 cm). (C) Fluorescence lifetime distribution histograms of PHDPF-Cz and PHDPF films spin-coated from toluene.

toluene solution (90-100 nm). Inset shows the corresponding FLIM images. Top: PHDPF-Cz. Bottom: PHDPF. Contour plots of transient absorption spectra of (D) PHDPF and (E) PHDPF-Cz pristine spin-coated films from toluene solution. (F) $\Delta T/T$ kinetics of PHDPF and PHDPF-Cz in pristine spin-coated films upon pumping with $6.8 \times 10^{-3} \text{ mJ/cm}^2$.

Figure 2. Ultrastable emission spectra of polyfluorene films. (A) PL spectra of the PHDPF-Cz, PHDPF and PFO spin-coated film after thermal annealing at 220 °C for varying times in ambient atmosphere. 3D AFM images of the corresponding films taken after thermal annealing for different times: (i~vi) PHDPF-Cz pristine film annealed for approximately 1 h, 2 h, 4 h, 6 h and 8 h; (vii) PHDPF film annealed for approximately 2 h. Scale bar dimensions are $6 \mu\text{m} \times 6 \mu\text{m}$. PL spectra of PHDPF-Cz, PHDPF and PNDPF pristine (B) and aged (C) films spin-coated from toluene (all films have a thickness of approximately 90~100 nm) and CHCl₃ (film thickness of 95~105 nm). Aged films were obtained by storing the pristine films in ambient atmosphere for 21 days (Humidity: 50%, Temperature: 301 K, Daylight). Insets show photographs and the PLQY of films stored under air for 0 and 21 days. PLQY of all films decreased with prolonged aging times.

Figure 3. Electrical properties of PHDPF-Cz. (A) Hole mobility of PHDPF-Cz films with varying thicknesses. The structure for the hole-dominated device is ITO/PEDOT:PSS/PHDPF-Cz film/MoO₃/Al. The MoO₃ layer can effectively block electron injection and avoid charge (electron/hole) recombination at high current density. (B) EL spectra of PHDPF-Cz films spin-coated from toluene solution at varying voltages (film thickness is approximately 110 nm.). (C) Luminous efficiency-luminance characteristics of conventional and flexible PLEDs based on PHDPF-Cz films (110 nm). Photographs show ultrathin PHDPF-Cz solid (ITO is used as the electrode) and flexible (PEDOT:PSS blended material is used as the electrode) PLEDs driven at 25 mA cm⁻². Scale bar corresponds to approximately 30 mm. (D) Ultrastable PL and EL CIE for PHDPF-Cz in various solid states.

The table of contents entry should be 50–60 words long, and the first phrase should be bold. The entry should be written in the present tense and impersonal style.

Ultrastable wide-bandgap conjugated polymers are obtained via effective isolating and encapsulating chain based on supramolecular self-encapsulation mechanism, which preserves the fundamental opto-electronic property of conjugated backbone core and also improves the spectral and morphological stability. Thickness-insensitive emission behavior enable it excellent film-

processing ability with a higher reproducibility. Larger-scale flexible deep-blue electroluminescent devices with a single-chain excitonic behavior are also fabricated.

Keyword: Ultrastable, Self-encapsulated strategy, Deep blue, Polyfluorene, Flexible electroluminescent devices

Jinyi Lin, Bin Liu, Mengna Yu, Xuhua Wang, Zongqiong Lin, Xinwen Zhang, Chen Sun, Juan Cabanillas-Gonzalez, Linghai Xie*, Feng Liu, Changjin Ou, Lubing Bai, Yamin Han, Man Xu, Wensai Zhu, Trevor A. Smith, Paul N. Stavrinou, Donal D. C. Bradley* and Wei Huang*

Ultrastable Supramolecular Self-encapsulated Wide-bandgap Conjugated Polymers for Large-area and Flexible Electroluminescent Devices

ToC figure ((Please choose one size: 55 mm broad × 50 mm high **or** 110 mm broad × 20 mm high. Please do not use any other dimensions))

Minerva Access is the Institutional Repository of The University of Melbourne

Author/s:

Lin, J;Liu, B;Yu, M;Wang, X;Lin, Z;Zhang, X;Sun, C;Cabanillas-Gonzalez, J;Xie, L;Liu, F;Ou, C;Bai, L;Han, Y;Xu, M;Zhu, W;Smith, TA;Stavrinou, PN;Bradley, DDC;Huang, W

Title:

Ultrastable Supramolecular Self-Encapsulated Wide-Bandgap Conjugated Polymers for Large-Area and Flexible Electroluminescent Devices

Date:

2019-01-04

Citation:

Lin, J., Liu, B., Yu, M., Wang, X., Lin, Z., Zhang, X., Sun, C., Cabanillas-Gonzalez, J., Xie, L., Liu, F., Ou, C., Bai, L., Han, Y., Xu, M., Zhu, W., Smith, T. A., Stavrinou, P. N., Bradley, D. D. C. & Huang, W. (2019). Ultrastable Supramolecular Self-Encapsulated Wide-Bandgap Conjugated Polymers for Large-Area and Flexible Electroluminescent Devices. *ADVANCED MATERIALS*, 31 (1), <https://doi.org/10.1002/adma.201804811>.

Persistent Link:

<http://hdl.handle.net/11343/284739>