Detection of Iodomethane using Luminescent Lead Halide Perovskite Nanocrystals

Wenping Yin^{†,1,2}, Hanchen Li^{†,1,2}, Anthony S. R. Chesman^{1,3,4}, Ben Tadgell^{1,5}, Andrew D. Scully^{1,3},
Mingchao Wang², Wenchao Huang², Christopher R. McNeill², Wallace W. H. Wong^{1,5}, Nikhil V.
Medhekar², Paul Mulvaney^{1,5}, Jacek J. Jasieniak^{*,1,2}

¹Australian Research Council Centre of Excellence in Exciton Science, Australia

²Department of Materials Science and Engineering, Monash University, VIC, 3168 Clayton, Australia

³CSIRO Manufacturing, Clayton, VIC, 3168 Clayton, Australia

⁴Melbourne Centre for Nanofabrication, VIC, 3168 Clayton, Australia

⁵School of Chemistry, The University of Melbourne, VIC, 3010 Parkville, Australia

*E-mail: Jacek.Jasieniak@monash.edu

[†]Both authors contributed equally to this work

Abstract

The extensive use of iodomethane (CH_3I) as a pesticide has drawn serious concern due to its potential biological and atmospheric impact, yet there is currently no effective on-site monitoring method for determining iodomethane concentration. Here, we introduce a highly sensitive and selective photoluminescence (PL)-based CH_3I sensor, that relies on changes in the optical properties of cesium lead bromide (CsPbBr_3) inorganic perovskite nanocrystals arising from halide exchange. CH_3I alone does not react efficiently with CsPbBr_3 . However, after the pre-exposure of CH_3I to oleylamine a rapid alkylation reaction occurs, forming alkyl ammonium iodide species that undergo facile halide exchange with the perovskite nanocrystals. The extent of the halide exchange is directly dependent on the CH_3I concentration, with the PL emission of the CsPbBr_3 nanocrystals exhibiting a concomitant linear redshift of more than 150 nm upon the addition of 100 ppbv to 10,000 ppbv of CH_3I , and with a fast response time of ca. 5 s. This is the most sensitive approach to the detection of CH_3I using a low-cost and portable approach reported to date, with the limit of detection (LOD) being 30 ± 10 ppbv, and according to simulations, could be improved even further. These PL changes are found to be independent of the intermediate morphology of the nanocrystals and operate effectively over a practical temperature range of 15–35 °C. The selectivity of the reaction mechanism is governed by the dramatic difference in the rate of the alkylation between CH_3I and oleylamine compared with other organoiodine analogues. Furthermore, the facile transduction mechanism provides scope for the development of a portable and low-cost sensor system suitable for both visual and instrumental readout.

1 Introduction

2 The high reactivity of iodomethane (methyl iodide, CH_3I) confers both its potential
3 utility and hazard in human applications. Since its approval for use as a pesticide by the United
4 States Environmental Protection Agency in 2007 it has gained popularity as a fumigant for
5 insect and fungus control^{1,2}. However, there has also been strong academic scrutiny and public
6 concern regarding its latent toxicity^{3,4} due to the possible mutagenic and carcinogenic effects
7 arising from its high reactivity with biological nucleophiles after prolonged exposure⁵.
8 Furthermore, CH_3I can release its constituent iodine atoms via photodecomposition, which can
9 subsequently react with atmospheric ozone to produce the monoxide radical, IO , leading to
10 ozone-depletion in the troposphere and stratosphere^{6,7}. Because of the high reactivity of CH_3I
11 and the difficulties of detection due to its odourless and colourless nature, a rapid, on-site
12 method for monitoring CH_3I has remained elusive.

13 Traditionally, CH_3I detection relies on sophisticated instrumentation, such as gas
14 chromatography coupled with mass spectroscopy (GC-MS) or flame ionization detector based
15 methods (GC-FID)⁷⁻¹⁰. However, these techniques are restricted to the laboratory environment
16 and require complex sample preparation. An alternative approach involves the use of more
17 affordable and portable spectroscopic methods. For example, a limit of detection (LOD) for
18 CH_3I of 5.3 ppt (10^{-15}) was achieved using resonance fluorescence detection of atomic iodine
19 (170–190 nm)⁶, although the utility of this system was greatly reduced by its low selectivity.
20 To enhance selectivity, the strong methylating ability of CH_3I (iodide as a leaving group)
21 compared with other iodine containing species has also been exploited. Organic and
22 organometallic luminescent probes, such as cyclometallated iridium (III) complexes¹¹ and
23 pyridine-based pi-conjugated oligomers/polymers^{2,5,12,13}, change their optical properties in
24 response to iodomethane. However, the reactions proceed over minutes to hours, leading to

1 lower sensitivity (>100 ppb) and long measurement times. It is, therefore, critical to develop a
2 reliable method for more rapid, selective, and sensitive detection of CH_3I .

3 The luminescence characteristics of cuboid lead halide perovskite nanocrystals (PNCs)
4 are known to be highly dependent on the nature of the halide anion in the crystal lattice¹⁴.
5 Consequently, perovskites are potential spectroscopic probes for the iodide component of CH_3I .
6 Cuboid PNCs have the chemical formula ABX_3 , where A is a monovalent inorganic or organic
7 cation such as cesium (Cs^+), methylammonium (MA^+) or formamidinium (FA^+), B is a divalent
8 metal ion (usually Pb^{2+} or Sn^{2+}), and X is a halide anion, typically chloride (Cl^-), bromide (Br^-),
9 or iodide (I^-). The optoelectronic properties of PNCs are comparable, or even superior, to
10 conventional group II-VI or III-V semiconductor quantum dots. In addition, they are cheaper
11 and easier to synthesize and do not require a shell layer to passivate their surfaces owing to
12 their remarkable defect tolerance¹⁵. In a landmark study in 2014, Schmidt et al. reported the
13 synthesis of MAPbBr_3 PNCs demonstrating a PL quantum efficiency (PLQE) of approximately
14 20%¹⁶. Subsequently, synthetic improvements and an expansion of the compositional range to
15 include various combinations of Cs^+ , FA^+ and modified X^- , yielded PNCs with vastly improved
16 PLQEs approaching 100%¹⁷. An exciting property of PNCs is that their highly ionic nature
17 allows their optoelectronic properties to be readily engineered post-synthesis through facile
18 and rapid ion-exchange¹⁸. Through such exchange processes, tunable emission wavelengths
19 throughout the entire visible spectrum (390–780 nm) with near-unity PLQE can be achieved¹⁷.
20 While this tunability is typically exploited for optoelectronic applications, here we utilise the
21 ability of such PNCs to undergo rapid halide exchange as a signal transduction method to detect
22 CH_3I .

23 For this purpose, we focus on using highly photoluminescent inorganic cesium lead
24 bromide (CsPbBr_3) PNC dispersions that are designed to efficiently interact with CH_3I . This is
25 facilitated through the PNCs' native surface ligand, oleylamine (OLA), which acts as a

sacrificial nucleophile in a reaction with CH₃I that releases the iodide. Subsequent halide exchange of the bromide in the PNCs with iodide results in a rapid change in the optical properties. This mechanism allows for the detection of CH₃I across a broad concentration range (30 ± 10 ppbv to 20,000 ppbv), with a response time of ca. 5 s. Moreover, the large differences in the rate of nucleophilic substitution reaction between various organoiodines and OLA provides for a high degree of selectivity of the PNC-based indicator for CH₃I. First principles density functional theory (DFT) calculations further confirm that stronger chemical interactions of the resulting oleylammonium iodide compared to CH₃I with the PNC surface, also facilitates the high sensitivity of the indicator from a thermodynamic viewpoint.

Results and Discussion

The underlying premise of utilising CsPbBr₃ PNCs for the detection of CH₃I is based on the ability of PNCs to undergo halide exchange, which dramatically alters their spectroscopic characteristics¹⁴. However, the direct exposure of CsPbBr₃ PNCs in toluene to CH₃I solutions did not cause any discernible change in PL properties over modest timescales (Error! Reference source not found.a, Fig. S1a). This demonstrates that efficient halide exchange in perovskites only occurs between ionic halide species and not with covalently-bound iodine species¹⁹. To activate the sensor, we exploited the well-known methylation reaction between organoiodines (R₃C:I) and appropriate nucleophiles (Nu:) to generate [R₃C:Nu]⁺ and free iodide (I:⁻)²⁰. In this work, OLA was a convenient choice as the nucleophile given its use in the synthesis of the CsPbBr₃ PNCs:

1 An S_N2 reaction between CH_3I and an excess of OLA initially yields N-methyl oleylammonium
2 iodide (**eq.1**), while further reaction with additional OLA yields N-methyl oleylamine and an
3 oleylammonium iodide salt, as illustrated in Error! Reference source not found.**b**^{20, 21}. A
4 subsequent methylation reaction with CH_3I is also possible, resulting in the formation of N,N-
5 dimethyl oleylamine and additional oleylammonium iodide. Evidence supporting this reaction
6 mechanism was obtained for a model OLA analogue, dodecylamine, using NMR and GC-MS
7 measurements (**Fig. S2, S3**, see Supporting Information for additional details).

8 The use of OLA in the synthesis of PNCs in the present work results in the concomitant
9 formation of its quarternized ammonium form when an acid is also present in the reaction
10 medium, such as oleic acid²². The OLA and/or oleylammonium salts subsequently passivate
11 the surface of the nanocrystals²³. The addition of excess OLA into the PNC dispersions did not
12 cause any changes in their PL emission wavelength (Error! Reference source not found.**a, S1b**).
13 In contrast, when a toluene solution of CH_3I and OLA ($CH_3I : OLA = 1 : 3$ molar ratio) was
14 added to a dispersion of the PNCs, significant changes in the optical properties of the PNCs
15 were observed (**Fig. 1b-d**Error! Reference source not found.). The red-shift in the UV-visible
16 absorption and PL emission spectra upon CH_3I addition is the result of a decrease in the optical
17 bandgap of the cuboid nanocrystals, which is direct evidence for the exchange of bromide with
18 iodide in the lattice of the $CsPbBr_3$ PNCs²⁴. Notably, the dramatic redshift in PL is linearly
19 correlated with the CH_3I concentration in the range 100 ppbv to 10,000 ppbv (**Fig. 1**Error!
20 Reference source not found.**d**), and is sufficiently large to provide a practical visual response
21 according to the CIE chart shown in **Fig. 1**Error! Reference source not found.**e**. Further
22 inspection of the absorption spectra for samples with CH_3I concentrations above 3,000 ppbv
23 show an increased absorption at shorter wavelengths, which suggests the possible concurrent
24 formation of 2D Ruddlesden-Popper perovskite (2DRP) nanosheets²⁵. The generalized
25 chemical formula for 2DRP nanosheets is given by $L_2[ABX_3]_{n-1}BX_4$, where L represents a

monovalent organic cation that is usually larger than A^+ and the value of n is the number of metal halide layers. The UV-visible absorption energy profile (Fig. 1c) and other results discussed below are consistent with the 2DRP nanosheets with $n = 1$ and $n = 2^{26}$.

Fig. 1 | Reaction mechanisms and spectroscopic response of CsPbBr₃ perovskite nanocrystals (PNCs) to CH₃I. **a**, Oleylamine (OLA, 0.96 mM) or CH₃I (20,000 ppbv solution) were introduced separately into PNC dispersions in toluene. The emission images under 365 nm UV light were recorded after 100 mins, showing no change in emission. **b**, OLA pre-treated CH₃I solutions (CH₃I concentration: 20,000 ppbv) was added to a PNC dispersion in toluene, with the emission colour under 365 nm UV light before and 20 s after addition. The hypothesised reaction mechanism, where CH₃I induces the methylation of OLA by an S_N2 mechanism and stops at dimethyl analogue formation. **c**, UV-visible

absorption spectra of PNCs exposed to varying amounts of CH₃I. **d**, Emission spectra of CsPbBr₃ PNCs as a function of the amount of added CH₃I. (Insert: redshift of PNCs PL emission as a function of CH₃I concentration. Linear fitting of results from 100 ppbv to 10,000 ppbv shown as a red line with R² = 0.997). **e**, CIE chart converted from the PL spectra of PNCs exposed to varying amounts of CH₃I. (Note: Spectra in **c**, **d**, were recorded 20 s after CH₃I addition at room temperature to ensure the reaction was complete).

To correlate these spectroscopic changes with the underlying structural transformations in the PNCs, transmission electron microscopy (TEM) and X-ray scattering measurements were conducted. TEM images of the as-synthesized PNCs reveal a well-defined cuboid morphology, with an average size of 11 nm (**Fig. 2a**, **S4**). For CH₃I concentrations up to 3,000 ppbv, high-resolution TEM (HRTEM) diffraction patterns indicate the progressive expansion of the (100) lattice spacing in the cuboid CsPbBr₃ PNCs from 5.9 Å to 6.4 Å due to iodide substitution (**Fig. 2a-c**). While the cuboid geometry is retained at low CH₃I concentrations, clear evidence for the dissolution of the cuboid phase of the PNCs and the concurrent formation of 2DRP nanosheets is seen at higher CH₃I concentrations. Laterally-stacked 2DRP assemblies are observed upon addition of 3,000 ppbv CH₃I (**Fig. 2c**), with the interlayer spacing of 10.0 Å correlating well with that of nanosheets²⁶. X-ray diffraction (XRD) measurements confirm that nanocuboids exist in the perovskite phase (**Fig. 2e**), although discrimination between the cubic and orthorhombic structures requires a more detailed structural analysis²⁷. A progressive shift of the nanocuboid XRD peaks toward lower 2θ values occurs with increasing concentrations of CH₃I, in accordance with the expected lattice expansion within the iodide-rich PNCs. Moreover, consistent with HRTEM, the XRD results also indicate the formation of 2DRP at CH₃I concentrations of 3,000 ppbv and higher^{28, 29}. The partial transformation from 3D perovskites into 2DRP nanosheets is further supported by comparing the 2D grazing incidence

1 wide-angle X-ray scattering (GIWAXS) measurements of the samples containing 1,000 and
 2 6,000 ppbv CH₃I (Fig. 2f, g)^{30,31}.

Fig. 2 | Changes to morphology and crystal structure of CsPbBr₃ PNCs exposed to varying amounts of CH₃I. **a**, TEM images of pristine PNCs, showing a cuboid shape. **b**, **c**, TEM images of PNCs after reaction with 1,000 ppbv and 3,000 ppbv solutions of CH₃I. **d**, TEM images of PNCs on addition of 6,000 ppbv CH₃I showing almost complete loss of the cuboid PNCs, with the remaining phase comprising 2DRP nanosheets. **e**, XRD patterns of PNCs exposed to various CH₃I amounts, which showed standard CsPbBr₃ cuboid signal at both 15.2° (100) and 30.6° (200) for the pristine sample. **f**, GIWAXS images for PNCs corresponding to 1,000 ppbv and 6,000 ppbv CH₃I, respectively. **g**, 1D GIWAXS profile extracted from 2D scattering patterns.

The structural transformation of the CsPbBr₃ PNCs involves a complex halide exchange process. It has been suggested that this occurs through a reaction-limited exchange

1 at the surface of the PNCs, with subsequent fast ionic diffusion occurring within the nanocrystal
2 lattice³². The spectroscopic properties of the PNCs reflect this complexity. The changes in the
3 PL emission colour occur gradually and over multiple stages of halide exchange as a function
4 of CH₃I concentration (**Fig. 3, S5**). These stages can be categorised first according to their
5 relative PL intensity changes (**Fig. 3a**), with a slight enhancement of the emission (**stage A**)
6 followed by a rapid decrease (**stage B**) and then a gradual transition towards nearly complete
7 quenching (**stage C**) being observed. Further inspection of the temporal changes in the UV-
8 visible absorption and PL emission within these stages reveals vastly different dynamics. UV-
9 visible absorption properties are retained in **stage A** (**Fig. S5a, b**), whereas the PL emission
10 exhibits a slight redshift and enhanced intensity (ca.10%) after an induction period of a few
11 seconds (**Fig. 3b**). This behaviour is indicative of a surface-trap filling effect^{33,34}. During **stage**
12 **B** the UV-visible absorption spectrum of the PNCs remains unchanged (**Fig. S5c, d**), while the
13 PL emission initially vanishes and then partly recovers at a red-shifted wavelength (**Fig. 3c**).
14 Finally in **stage C** the cuboid PNCs undergo rapid dissolution and re-nucleation as 2DRP
15 nanosheets (**Fig. S5e, f**), thus resulting in a largely suppressed PL emission (**Fig. 3d**). For
16 completeness, to understand the role of excess OLA across these stages, control experiments
17 were conducted using equivalent OLA additions but without any CH₃I (**Fig. 3a**); only a slight
18 PL emission intensity enhancement, with no change in the peak position (see **Fig. S1**), was
19 observed at the higher OLA concentrations. This demonstrates that the spectroscopic changes
20 across the three identified stages are directly related to the alkyl ammonium iodide species
21 generated in solution and not to the residual OLA. A schematic depiction of the structural
22 transformation across these stages is presented in **Fig. 3b-d**.

Fig. 3 | Integrated steady-state photoluminescence and millisecond time-dependent emission spectra. **a**, Integrated steady-state PL intensity difference displayed as a function of CH_3I concentration, which explored three different stages, *stage A* ($\text{CH}_3\text{I} \leq 100$ ppbv), *stage B* ($100 \text{ ppbv} < \text{CH}_3\text{I} \leq 3000$ ppbv) and *stage C* ($\text{CH}_3\text{I} > 3000$ ppbv). **b**, **c**, **d**, Time-dependent emission spectra of CsPbBr_3 PNCs at CH_3I concentration of 100 ppbv, 1,000 ppbv, and 6,000 ppbv, respectively. The PNC emission images under 365 nm UV light at 5 and 20 sec, and the schemes of structural transformation are shown in the lower panels of **b**, **c**, **d**. It is found that the OLA-reacted CH_3I in *Stage A* ($\text{CH}_3\text{I} \leq 100$ ppbv) acts as a

trap passivant, while at higher CH₃I concentrations it causes the PNCs to undergo i) surface disruption/PNCs decomposition, ii) iodide migration and iii) surface passivation processes in *Stage B* and *C*. (Note: PL emission signals stabilized after 20 s.)

To further correlate the ensuing structural and spectroscopic properties, the radiative relaxation dynamics of the PNCs were studied using time-resolved photoluminescence (TRPL) measurements. The PL excitation spectra in **Fig. S6a** suggest that, in both *stage B* and *stage C*, energy transfer occurs from small n-value 2DRP nanosheets to nanocubes, consistent with previous reports^{35, 36}. The absence of PL from the 2DRP phases suggests that this energy transfer results in efficient quenching of PL from the 2DRP phases, and for this reason the PL from the nanocubes only is considered here. Analysis of the TRPL decay curves using an empirical bi-exponential function yields average PL lifetimes that show a gradual increase with increasing CH₃I concentrations (Error! Reference source not found.). This is consistent with the fact that iodide- based cuboid PNCs exhibit longer radiative lifetimes than their bromide analogues (Error! Reference source not found.a)^{37, 38}. An accelerated slow decay in *stage A* suggests a reduction in the number of shallow states due to trap filling^{39, 40}. Meanwhile, the progressive increase in the lifetime of this component and its overall magnitude across *stages B* and *C* are indicative of more defective cuboid PNCs being generated (Error! Reference source not found.b, c). This confirms that the structural transformation across these stages yielding lower quality cuboid PNCs.

The chemical and structural transformations across these three stages are evidently dependent on the interaction between the oleylammonium iodide species in solution and the PNC nanocrystals. To explore this dependence, the changes in the PL redshift as a function of the PNC concentration are plotted in Error! Reference source not found.d. The results can be readily described by a semi-empirical formalism that considers the concentration of PNCs (denoted as [PNC]) as a fitting parameter (**see SI-Discussion**). Collectively, the results show

1 that tuning the [PNC] provides a facile way to modulate the sensitivity window for CH₃I
2 detection, with lower concentrations yielding higher sensitivity factors. Given that the practical
3 range for [PNC] is ~1 nM to ~1 mM, the achievable linear sensitivity window for detection of
4 CH₃I, through [PNC] modifications alone, is ~10 ppbv to ~10,000 ppmv.

5 To gauge the practical limit of the thermal response window for this sensor system, the
6 PL emission characteristics were measured between 5 °C and 45 °C for 1,000 and 6,000 ppbv
7 CH₃I concentrations as representative samples (Error! Reference source not found.e-g, S8). It
8 was found that the response time is slightly longer at lower temperatures for the lower CH₃I
9 concentration sample, whereas temperature had little effect on response time at the higher CH₃I
10 concentration. Apart from slight differences in initial reaction dynamics, after a 20 seconds
11 stabilization period the PL redshifts are consistent to within $\pm 3.4\%$ at temperatures between
12 15 °C and 35 °C (Error! Reference source not found.g). This provides a practical temperature
13 range for the reliable operation of a sensor platform based on this approach.

Fig. 4 | Radiative relaxation dynamics as measured by time-resolved photoluminescence (TRPL)

measurements, and reliability studies under different CsPbBr₃ concentrations or temperatures.

a, Quantitative values of slow, fast, and average PL decay as calculated from the bi-exponential fitting

of the time-resolved PL decays of CsPbBr₃ PNCs before and after addition of various concentrations of

CH₃I, and corresponding PL redshifts. **b,** The radiative dynamic processes in ideal PNCs without

vacancies, where the photon is absorbed and quickly converted to prompt PL (“fast decay”). **c,** The

radiative dynamic processes in PNCs with vacancy defects, which generate shallow states inside the

conduction and valance bands. The delayed PL signal is generated due to part of the excited electrons traveling between shallow states, namely trapping/de-trapping, appears as a “slow decay” component. **d**, The simulated PL redshifts (lines) of PNCs as a function of CH₃I concentration, with the coloured symbols corresponding to experimental data. **e, f**, Time-dependent PL emission spectra of the sensor system at 15, 25, and 35 °C at a CH₃I concentration of 1,000 ppbv and 6,000 ppbv, respectively. **g**, Relative PL redshift at 15, 25, and 35 °C after adding CH₃I at a concentration of 1,000 or 6,000 ppbv, with average fluctuations $\leq 3.5\%$ and $\leq 3.4\%$, respectively, after 20 s at 15, 25, and 35 °C.

The selectivity of the PNC-oleylamine for CH₃I system was measured using a range of organoiodine compounds including iodomethane, iodoethane, iodopentane, iodoheptane, iodotoluene, methyammonium iodide (MAI), formamidinium iodide (FAI), n-butylammonium iodide (n-BAI) and tetrabutylammonium iodide (TBAI) after pre-treating with OLA (see Error! Reference source not found. **a, b**). Negligible changes to the PL emission peak wavelength were observed for all tested organoiodines, apart from CH₃I. This demonstrates the high degree of selectivity of this indicator system for CH₃I, which can be understood by considering the dramatic differences in reaction rates of different organoiodines towards nucleophilic substitution. For a typical S_N2 reaction involving iodoalkanes, the reaction rate (**R**), given by $R = k[\text{Nu:}][\text{R}_3\text{C:I}]$, is dependent on the rate constant (**k**), the concentrations of the nucleophile (i.e. OLA in our case) and the specific organoiodine compound. Among the organoiodine derivatives studied here, CH₃I has a **k** value that is more than 30 times larger than the others (**Fig. S10**)^{20, 21}. This facilitates much faster overall dynamics, which leads to inherent selectivity for CH₃I in the CsPbBr₃ PNC system (**Fig. S11**). Furthermore, this finding validates the need to generate halide salts to induce the rapid transformation of the PNCs into anion exchange analogues.

Importantly, the chemical nature of the alkyl ammonium halide salt also impacts the extent of the exchange process. This is evident from the substantially smaller spectral changes

(Error! Reference source not found.**a-b**, **S12a**) and the slower exchange dynamics (**Fig. S12b**) observed for the various ammonium iodide salts compared to those for an equivalent concentration of CH₃I reacted with OLA. When the PL peak changes are compared to the ratio of total iodide added vs the parent bromide concentration (as determined from the [PNC]), a universal curve is found for the individual iodide species. This confirms that (i) the transformation mechanism in these systems is primarily dependent on the ratio of added iodide/parent bromide; (ii) the different iodide sources have varied PL change characteristics; and (iii) the OLA-activated CH₃I provides the greatest sensitivity across the tested iodine sources evaluated in the present work.

To provide further thermodynamic insights into these transformation trends, we explored the interactions energies between CH₃I, OLAI and MAI with the PNC surface using first-principles density functional theory (DFT) calculations (**Table S2 &** Error! Reference source not found.**c, d**). The predicted positive surface interaction energy (ΔE_{SI}) between CH₃I and PNCs reveals a thermodynamically unfavourable chemical interaction. On the other hand, taking MAI and OLAI as representatives, the large negative surface interaction energies demonstrate that these alkyl ammonium salts favourably interact with the PNC surface. We have further investigated these potential chemical reaction pathways (**Table S2 & Fig. S13**). The reaction enthalpy of pure I/Br exchange (ΔE_{re3}) is much lower than that of just Cs substitution by alkyl ammonium (ΔE_{re1}) for both MAI and OLAI, indicating that halide exchange could happen spontaneously prior to other processes on the native surface of CsPbBr₃. Nonetheless, this advantage diminishes when 25% pre-existing surface passivation with OLA is taken into account. It can be seen that OLA⁺ substitution becomes the rate limiting step for halide migration in passivated PNCs (**Fig. S13**), which is also consistent with the previous optical discussion in **Fig. 3**. On the whole, the larger negative reaction energies of OLA⁺ compared to the shorter alkyl ammoniums, such as MA⁺ (ΔE_{re1} and ΔE_{re2} , see **Table S2**),

- 1 contribute to more efficient surface disruption, in turn enabling more extensive halide
- 2 migration within the PNCs.

Fig. 5 | Selectivity and sensitivity studies of the CsPbBr₃ nanocrystals indicator. **a**, Change in the photoluminescence peak energy of the PNCs as a function of the total introduced halide species (CH₃I or another other exchange halide species) relative to the starting bromide concentration within the PNC sensor solution. The energy variation response to treated CH₃I is independent on the original concentration of PNCs ([PNC]=3, 6, 9.32, 15, 21, 27 nM). However, the response is distinctly different to that of other iodide containing analogues (*e.g.* iodopentane, iodoethane, iodoheptane, iodotoluene, methyammonium iodide (MAI), formamidinium iodide (FAI), *n*-butylammonium iodide (*n*-BAI) and tetrabutylammonium iodide (TBAI)). The dotted grey trendline is derived from literature values of the energy difference at various ratios of CsPbI₃ : CsPbBr₃²⁴. **b**, PL redshifts of PNCs with OLA-treated equimolar organoiodine

analytes in IPA at various concentrations. Iodoethane, iodopentane, iodohexane, and iodotoluene impart no change to the emission colour of CsPbBr₃ PNCs due to the lack of iodide formation. Meanwhile, other alkyl ammonium iodide salts, reacted less efficiently than OLAI-treated CH₃I. **c, d**, Schematic representation and histogram of the surface interaction energies of OLAI, MAI or CH₃I onto the native CsPbBr₃ surface. The atomistic representations are obtained after a complete relaxation of the slab models with CsBr-terminated surface using first principles density functional theory (DFT) methods.

Conclusion

Metal halide perovskite nanocrystals have previously been used as optical sensors due to their attractive selectivity towards metal ions, such as copper and mercury^{41, 42}. In this work we have extended their versatility to the detection of widely used organohalides by developing a spectroscopic sensor suitable for the highly sensitive and selective detection of CH₃I based on distinct changes in the PL of CsPbBr₃ PNCs. The transduction mechanism involves an initial methylation reaction between the CH₃I and an aliphatic amine, yielding an iodide-containing ammonium salt. The liberated iodide anion undergoes lattice exchange with bromide anion, which in turn leads to structural reconfiguration of the PNCs. The ensuing changes in the PL properties provide a linear spectroscopic response and enable quantitative detection of CH₃I between 100 ppbv to 10,000 ppbv, with a limit of detection of 30 ± 10 ppbv and a response time of 5 s at room temperature. Furthermore, the significant differences in the methylation rate of aliphatic amines by CH₃I compared with other organoiodine enables excellent selectivity to be achieved. This study highlights the potential applications of metal halide perovskites in other fields beyond conventional optoelectronics. In particular the nanoscale chemistry of the lead halide based perovskites opens up a unique pathway towards their application as rapid, selective and sensitive chemical detectors.

Acknowledgements

This research was supported financially by the Australia Research Council funded Centre of Excellence in Exciton Science (Grant No. CE170100026). The authors acknowledge the technical contributions of Australian Defence Science and Technology Group (DSTG), particularly the assistance and advice of Dr. Genevieve H. Dennison. W. H. acknowledges an ACAP fellowship supported by the Australian Government through the Australian Renewable Energy Agency (ARENA). The authors acknowledge use of the facilities and the assistance of Dr. Jisheng Ma and Mr. James Griffith at the Monash X-ray Platform. M. W. and N. M. gratefully acknowledge the support from the Australian Research Council (DP166103661) and thank Monash Computing Cluster, National Computing Infrastructure and Pawsey Supercomputing Facility for the use of computational facilities. Authors also acknowledge use of the facilities at Monash Centre for Electron Microscopy (MCEM). In addition, this work was performed in part at the SAXS/WAXS beamline at the Australian Synchrotron, part of ANSTO.

Author contributions

W. Y. and J. J. J. conceived and designed the experiments, under the technical support from P. M., and W. W. H. W.. W. Y., H. L. and B. T. performed the experiments. W. Y., H. L., and J. J. analysed and constructed the results. W. H. and C. R. M. performed the GIWAXS measurement. A. D. S. performed the time-resolved photoluminescence experiments. A. S. R. C. helped with the GC-MS and NMR measurements and analysis. M. W. and N. M. performed first principles DFT calculations. W. Y., A. S. R. C., and J. J. J. mainly worked on the manuscript, with all the authors contributing to the drafting and correction.

Competing Interests

1 The authors declare no competing interests.

2 **Additional information**

3 Supplementary information available for this paper includes the synthesis of CsPbI₃; GC-MS;
4 ¹H-NMR; TRPL fitting table; time-dependent absorption spectra, size distribution and
5 temperature-dependent PL/UV-visible absorption of CsPbBr₃ under various CH₃I
6 concentrations; selectivity/efficiency optical analysis; and the additional detection of various
7 bromide sources by CsPbI₃ PNCs.

8

9 **Methods:**

10 **Materials and chemicals.** Lead(II) bromide (PbBr₂, 99.999% trace metals basis), cesium
11 carbonate (Cs₂CO₃, 99.995% trace metals basis), oleylamine (OLA, technical grade, 70%),
12 diisooctylphosphinic acid (DPA, technical grade, 90%), 1-octadecene (ODE, technical grade,
13 90%), iodomethane (CH₃I, 99.5%, copper as stabilizer), iodoethane (CH₃CH₂I, 99%, copper as
14 stabilizer), iodopentane (CH₃(CH₂)₃CH₂I, 98%, copper as stabilizer), 1-iodohexane (98+%), 2-
15 iodotoluene (98%), n-butylammonium iodide (n-BAI, 98%), and tetrabutylammonium iodide
16 (TBAI, ≥99.0%) were from Sigma-Aldrich. Toluene (99.5%) and isopropanol (IPA, 99.5%)
17 were from Merck. Methylammonium iodide (MAI, 99%), and formamidinium iodide (FAI,
18 99%) were from Dyenamo. All chemicals were used without further purification.

19 **Preparation of Cs-DPA.** Cs₂CO₃ (100 mg, 0.31 mmol) was added to a 25 ml 2-neck flask
20 containing ODE (5 ml) and DPA (0.5 ml), and heated at 120 °C under vacuum (ca. 2 mbar) for
21 30 min to remove residual water. The temperature was then raised to 150 °C under N₂, with the
22 temperature maintained until the complete dissolution of Cs₂CO₃. The solution was stored
23 under N₂ at room temperature, and heated to 120 °C prior to injection in subsequent reactions.

24 **Synthesis of CsPbBr₃ PNCs.** PbBr₂ (69 mg, 0.188 mmol) was added to ODE (5 ml) in a 50
25 ml 3-neck flask, with OLA (0.5 ml) and DPA (0.5 ml) then added to the suspension. The

1 solution was then heated to 120 °C under vacuum (ca. 2 mbar) with stirring for 30 min in order
2 to remove residual water and dissolve the PbBr₂. Upon complete dissolution of the PbBr₂, the
3 solution was placed under an N₂ atmosphere and the temperature was raised to 160 °C. The
4 pre-heated Cs-DPA solution (0.4 ml) was then injected into the reaction solution, and after 5s
5 the solution was cooled in an ice bath.

6 **Isolation and Purification of CsPbBr₃ PNCs.** The crude reaction solution was mixed with
7 IPA (crude solution:IPA = 1:3 v/v), resulting in the precipitation of most of the PNCs. After
8 centrifugation at 10,000 rpm for 5 min, the supernatant was discarded and the precipitated
9 PNCs were redispersed in toluene to give a solution that was colloidally stable over an extended
10 period.

11 **Preparation of PNC Sensor and Analyte Solutions.** The perovskite NC sensor solution was
12 prepared by diluting the washed perovskite dispersion with toluene to 3 ml. The concentration
13 of PNCs was adjusted and maintained at about 9.32±0.15 nM, which was calculated by the
14 absorption and the relative molar extinction coefficient as determined in the study of Maes et
15 al⁴³. A stock solution of CH₃I was prepared by adding CH₃I (10 µL, ~ 30.9 µM) toluene or IPA
16 (1 ml), followed by the addition of OLA (ca. 90 µM). This solution was then diluted 120-fold
17 and a portion was added to the sensor solution to add a known concentration of CH₃I. Other
18 analyte solutions were prepared using a similar method.

19 **Characterization.** Samples for powder X-ray diffraction (XRD) were prepared by drop-
20 casting a PNC dispersion onto a glass substrate, which was then dried without heating in an
21 ambient environment. XRD patterns were collected by a Bruker D8 Advance diffractometer
22 equipped with a Cu-Kα radiation source operated at 40 kV and 40 mA, and equipped with a
23 high-speed line-position sensitive Lynxeye XE detector. Transmission electron microscopy
24 (TEM) images of each sample on ultra-thin carbon grids were collected using a Tecnai G² T20
25 TWIN (FEI Company) microscope equipped with a LaB₆ electron emitter. The steady-state

absorption and emission spectra were recorded with a commercial spectrometer (StellarNet) equipped with a CCD camera (Silver-Nova-TEC-X2), using a halogen lamp (SL1) or 390 nm excitation source (SL1-LED), respectively. The relative time-course experiment spectra were collected using the same system. Time-resolved photoluminescence (TRPL) spectra were measured using an FLS 980 spectrometer (Edinburgh Instruments) with a 405 nm pulsed diode laser for excitation with a 500 kHz frequency (average power up to 6.25 μ W) and the maximal emission wavelength of each sample used for detection. The 2-Dimensional grazing incidence wide-angle X-ray scattering (GIWAXS) was measured at the SAXS/WAXS beamline at Australian Synchrotron^{44, 45}. The energy of the incident X-ray beam was fixed at 15 keV. The 2D scattering patterns were acquired using a Dectris Pilatus 1M detector with an exposure time of 1 s and an incident angle of 0.2°. GC-mass spectra were obtained with a Thermo Scientific TSQ 8000 TRACE 1310 GC mass spectrometer using electron ionization in the positive ion mode with ionization energy of 70 eV. Gas chromatography was performed on a SGE SOLGEL-1MS column (30 m $\times$ 0.25 mm ID, 0.25 μ m film thickness), with a temperature program of 50 °C for 2 min, then heating at 25 °C/min to 300 °C where the temperature was held for 8 minutes with a split injection, split ratio of 10, an injector temperature of 300 °C and the transfer line was set to 300 °C. High-purity helium was used as carrier gas with a flow rate of 1 ml/min. ¹H-NMR measurements were performed on a Bruker Bio Spin Av400H with a 9.4 T magnet and a 5 mm inverse 1H-X BBI autotuning broadband probe at a ¹H frequency of 400.13 MHz in toluene-*d*₈.

Computational Methods. First principles, density functional theory (DFT) calculations were carried out using the Vienna Ab Initio Simulation Package (VASP)⁴⁶. The projector augmented wave (PAW)⁴⁷ pseudopotentials were utilized to describe core and valence electrons, and the generalized gradient approximation based on the Perdew-Burke-Ernzerhof (GGA-PBE)⁴⁸ form was selected to describe electron exchange and correlation. Grimme's energy correction

method was employed to correctly account for the dispersion interactions⁴⁹. Various chemical reactions at the CsBr-terminated neutral surface of CsPbBr₃ nanocrystals were investigated using a slab model consisting of a 2×2 surface unit cell and 8 layers of the CsPbBr₃ crystal. For calculating the reaction enthalpies, all models were fully relaxed to account for the lattice expansion due to Cs substitution and I/Br exchange. In all cases, plane wave kinetic energy cut-off was set to 450 eV.

References

1. Ashworth, D. J., Yates, S. R., Luo, L. & Xuan, R. Phase partitioning, retention kinetics, and leaching of fumigant methyl iodide in agricultural soils. *Sci. Total Environ.* **432**, 122-127 (2012).
2. Tang, P. X., Nguyen, N. T. H., Lo, J. G. & Sun, G. Colorimetric Detection of Carcinogenic Alkylating Fumigants on a Nylon 6 Nanofibrous Membrane. Part II: Self-Catalysis of 2-Diethylaminoethyl-Modified Sensor Matrix for Improvement of Sensitivity. *Acs Applied Materials & Interfaces* **11**(14), 13632-13641 (2019).
3. Guthman, J. & Brown, S. I will never eat another strawberry again: the biopolitics of consumer-citizenship in the fight against methyl iodide in California. *Agr. Human Values* **33**(3), 575-585 (2016).
4. Guthman, J. & Brown, S. Midas' Not-So-Golden Touch: On the Demise of Methyl Iodide as a Soil Fumigant in California. *Journal of Environmental Policy & Planning* **18**(3), 324-341 (2016).
5. Tang, P. X., Leung, H. T. & Sun, G. Colorimetric Detection of Carcinogenic Alkylating Fumigants on Nylon-6 Nanofibrous Membrane. Part I: Investigation of 4-(p-Nitrobenzyl)pyridine as a "New" Sensing Agent with Ultrahigh Sensitivity. *Anal. Chem.* **90**(24), 14593-14601 (2018).
6. Bale, C. S. E., *et al.* Novel measurements of atmospheric iodine species by resonance fluorescence. *JAtC* **60**(1), 51-70 (2008).

7. Mekic, M., Temime-Roussel, B., Monod, A. & Strekowski, R. S. Quantification of gas phase methyl iodide using H_3O^+ as the reagent ion in the PTR-MS technique. *Int. J. Mass spectrom.* **424**, 10-15 (2018).
8. Das, S., Sharma, P., Badani, P. M. & Vatsa, R. K. Ionisation of methyl iodide clusters using nanosecond laser pulses: detection of multiply charged positive ions, negative ions and energetic electrons. *Rsc Advances* **5**(12), 8887-8894 (2015).
9. R'Mili, B., *et al.* Quantification of the gas phase methyl iodide using O_2^+ as the reagent ion in the PTR-ToF-MS technique. *Int. J. Mass spectrom.* **431**, 43-49 (2018).
10. Kim, T., *et al.* Concentration Determination of Volatile Molecular Iodine and Methyl Iodide. *Bull. Korean Chem. Soc.* **39**(6), 824-828 (2018).
11. Wu, C., *et al.* Chemoselective detection of alkyl halides via an iridium(III) luminescent probe. *Dyes and Pigments* **159**, 479-482 (2018).
12. Chen, W., *et al.* A pyridinium cation- π interaction sensor for the fluorescent detection of alkyl halides. *Chemical Communications* **47**(1), 253-255 (2011).
13. Hertzog-Ronen, C., *et al.* Detection and Identification of Alkylating Agents by Using a Bioinspired "Chemical Nose". *Chemistry – A European Journal* **15**(40), 10380-10386 (2009).
14. Kovalenko, M. V., Protesescu, L. & Bodnarchuk, M. I. Properties and potential optoelectronic applications of lead halide perovskite nanocrystals. *Science* **358**(6364), 745 (2017).
15. Huang, H., *et al.* Lead Halide Perovskite Nanocrystals in the Research Spotlight: Stability and Defect Tolerance. *ACS Energy Letters* **2**(9), 2071-2083 (2017).
16. Schmidt, L. C., *et al.* Nontemplate Synthesis of $\text{CH}_3\text{NH}_3\text{PbBr}_3$ Perovskite Nanoparticles. *J. Am. Chem. Soc.* **136**(3), 850-853 (2014).
17. Shamsi, J., *et al.* Metal Halide Perovskite Nanocrystals: Synthesis, Post-Synthesis Modifications, and Their Optical Properties. *Chem. Rev.* **119**(5), 3296-3348 (2019).
18. Doane, T. L., *et al.* Using Perovskite Nanoparticles as Halide Reservoirs in Catalysis and as Spectrochemical Probes of Ions in Solution. *ACS Nano* **10**(6), 5864-5872 (2016).
19. Jang, D. M., *et al.* Reversible Halide Exchange Reaction of Organometal Trihalide Perovskite Colloidal Nanocrystals for Full-Range Band Gap Tuning. *Nano Lett.* **15**(8), 5191-5199 (2015).

20. Robert C. Neuman, J. Reactions of Haloalkanes, Alcohols, and Amines : Nucleophilic Substitution. *Organic Chemistry*, chapter 7, 1-51 (2013).
21. Robert C. Neuman, J. Haloalkanes, Alcohols, Ethers, and Amines. *Organic Chemistry*, chapter 3, 1-59 (2013).
22. Pan, A., *et al.* Insight into the Ligand-Mediated Synthesis of Colloidal CsPbBr₃ Perovskite Nanocrystals: The Role of Organic Acid, Base, and Cesium Precursors. *ACS Nano* **10**(8), 7943-7954 (2016).
23. De Roo, J., *et al.* Highly Dynamic Ligand Binding and Light Absorption Coefficient of Cesium Lead Bromide Perovskite Nanocrystals. *ACS Nano* **10**(2), 2071-2081 (2016).
24. Akkerman, Q. A., *et al.* Tuning the Optical Properties of Cesium Lead Halide Perovskite Nanocrystals by Anion Exchange Reactions. *J. Am. Chem. Soc.* **137**(32), 10276-10281 (2015).
25. Shi, E., *et al.* Two-dimensional halide perovskite nanomaterials and heterostructures. *Chem. Soc. Rev.* **47**(16), 6046-6072 (2018).
26. Weidman, M. C., Goodman, A. J. & Tisdale, W. A. Colloidal Halide Perovskite Nanoplatelets: An Exciting New Class of Semiconductor Nanomaterials. *Chem. Mater.* **29**(12), 5019-5030 (2017).
27. Brennan, M. C., Kuno, M. & Rouvimov, S. Crystal Structure of Individual CsPbBr₃ Perovskite Nanocubes. *Inorg. Chem.* **58**(2), 1555-1560 (2019).
28. Blancon, J. C., *et al.* Extremely efficient internal exciton dissociation through edge states in layered 2D perovskites. *Science* **355**(6331), 1288 (2017).
29. Yang, X., *et al.* Efficient green light-emitting diodes based on quasi-two-dimensional composition and phase engineered perovskite with surface passivation. *Nature Communications* **9**(1), 570 (2018).
30. Chen, Z. M., *et al.* Stable Sn/Pb-Based Perovskite Solar Cells with a Coherent 2D/3D Interface. *Science* **9**, 337-346 (2018).
31. Wang, Z., *et al.* Efficient ambient-air-stable solar cells with 2D–3D heterostructured butylammonium-caesium-formamidinium lead halide perovskites. *Nature Energy* **2**, 17135 (2017).

32. Koscher, B. A., *et al.* Surface- vs Diffusion-Limited Mechanisms of Anion Exchange in CsPbBr₃ Nanocrystal Cubes Revealed through Kinetic Studies. *J. Am. Chem. Soc.* **138**(37), 12065-12068 (2016).
33. Xu, W., *et al.* Iodomethane-Mediated Organometal Halide Perovskite with Record Photoluminescence Lifetime. *ACS Applied Materials & Interfaces* **8**(35), 23181-23189 (2016).
34. Stoeckel, M.-A., *et al.* Halide Perovskites: Reversible, Fast, and Wide-Range Oxygen Sensor Based on Nanostructured Organometal Halide Perovskite *Adv. Mater.* **29**(38), 1702469 (2017).
35. Li, M., *et al.* Amplified Spontaneous Emission Based on 2D Ruddlesden–Popper Perovskites. *Adv. Funct. Mater.* **28**(17), 1707006 (2018).
36. Protesescu, L., *et al.* Nanocrystals of Cesium Lead Halide Perovskites (CsPbX₃, X = Cl, Br, and I): Novel Optoelectronic Materials Showing Bright Emission with Wide Color Gamut. *Nano Lett.* **15**(6), 3692-3696 (2015).
37. Zhang, Y., *et al.* Quantitative imaging of anion exchange kinetics in halide perovskites. *Proceedings of the National Academy of Sciences* **116**(26), 12648 (2019).
38. Zhang, D., *et al.* Synthesis of Composition Tunable and Highly Luminescent Cesium Lead Halide Nanowires through Anion-Exchange Reactions. *J. Am. Chem. Soc.* **138**(23), 7236-7239 (2016).
39. Chirvony, V. S., *et al.* Delayed Luminescence in Lead Halide Perovskite Nanocrystals. *The Journal of Physical Chemistry C* **121**(24), 13381-13390 (2017).
40. Brandt, R. E., *et al.* Searching for “Defect-Tolerant” Photovoltaic Materials: Combined Theoretical and Experimental Screening. *Chem. Mater.* **29**(11), 4667-4674 (2017).
41. Liu, Y., *et al.* All-inorganic CsPbBr₃ perovskite quantum dots as a photoluminescent probe for ultrasensitive Cu²⁺ detection. *Journal of Materials Chemistry C* **6**(17), 4793-4799 (2018).
42. Lu, L. Q., *et al.* Visual and sensitive fluorescent sensing for ultratrace mercury ions by perovskite quantum dots. *Anal. Chim. Acta* **986**, 109-114 (2017).
43. Maes, J., *et al.* Light Absorption Coefficient of CsPbBr₃ Perovskite Nanocrystals. *The Journal of Physical Chemistry Letters* **9**(11), 3093-3097 (2018).
44. Huang, W., *et al.* Probing Molecular and Crystalline Orientation in Solution-Processed Perovskite Solar Cells. *Adv. Funct. Mater.* **25**(34), 5529-5536 (2015).

- 1 45. Kirby, N. M., *et al.* A low-background-intensity focusing small-angle X-ray scattering undulator
2 beamline. *J. Appl. Crystallogr.* **46**(6), 1670-1680 (2013).
- 3 46. Kresse, G. & Furthmüller, J. Efficiency of ab-initio total energy calculations for metals and
4 semiconductors using a plane-wave basis set. *Computational Materials Science* **6**(1), 15-50 (1996).
- 5 47. Kresse, G. & Joubert, D. From ultrasoft pseudopotentials to the projector augmented-wave method.
6 *Physical Review B* **59**(3), 1758-1775 (1999).
- 7 48. Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized Gradient Approximation Made Simple.
8 *Physical Review Letters* **77**(18), 3865-3868 (1996).
- 9 49. Grimme, S., Antony, J., Ehrlich, S. & Krieg, H. A consistent and accurate ab initio parametrization
10 of density functional dispersion correction (DFT-D) for the 94 elements H-Pu. *The Journal of*
11 *Chemical Physics* **132**(15), 154104 (2010).

Minerva Access is the Institutional Repository of The University of Melbourne

Author/s:

Yin, W;Li, H;Chesman, ASR;Tadgell, B;Scully, AD;Wang, M;Huang, W;McNeill, CR;Wong, WWH;Medhekar, N;Mulvaney, P;Jasieniak, JJ

Title:

Detection of Halomethanes Using Cesium Lead Halide Perovskite Nanocrystals

Date:

2021-01-13

Citation:

Yin, W., Li, H., Chesman, A. S. R., Tadgell, B., Scully, A. D., Wang, M., Huang, W., McNeill, C. R., Wong, W. W. H., Medhekar, N., Mulvaney, P. & Jasieniak, J. J. (2021). Detection of Halomethanes Using Cesium Lead Halide Perovskite Nanocrystals. ACS NANO, 15 (1), pp.1454-1464. <https://doi.org/10.1021/acsnano.0c08794>.

Persistent Link:

<http://hdl.handle.net/11343/285512>