PLEASE READ ALL 'COMMENT' TEXT BEFORE PREPARING YOUR ARTICLE. If you do not see the Comments, select View > Print Layout. Please delete them before submitting (Review > Delete All Comments in Document) so that peer reviewers see a clean copy of the manuscript.

Remember that you are writing for an interdisciplinary audience. Please be sure to discuss interdisciplinary themes, issues, debates, etc. where appropriate. Note that the WIREs are forums for review articles, rather than primary literature describing the results of original research.

If you have any questions, [contact your editorial office](#).

Article Title: Nanoescapology: Progress Towards Understanding the Endosomal Escape of Polymeric Nanoparticles

Article Type:

- ☐ OPINION
- ☐ PRIMER
- ☐ OVERVIEW
- ☐ ADVANCED REVIEW
- ☐ FOCUS ARTICLE
- ☐ SOFTWARE FOCUS

Authors:

Full name and affiliation; email address if corresponding author; any conflicts of interest

Laura I. Selby
Drug Delivery, Disposition and Dynamics, Monash Institute of Pharmaceutical Sciences, Monash University, Parkville, Victoria, Australia
Christina M. Cortez-Jugo
Drug Delivery, Disposition and Dynamics, Monash Institute of Pharmaceutical Sciences, Monash University, Parkville, Victoria, Australia ARC Centre of Excellence in Convergent Bio-Nano Science and Technology, Monash University, Parkville, Victoria, Australia Department of Chemical and Biomolecular Engineering, The University of Melbourne, Parkville, Victoria, Australia
Georgina K. Such*
Department of Chemistry, The University of Melbourne, Parkville, Victoria, Australia gsuch@unimelb.edu.au

This is the author manuscript accepted for publication and has undergone full peer review but has not been through the copyediting, typesetting, pagination and proofreading process, which may lead to differences between this version and the [Version of Record](#). Please cite this article as doi: [10.1002/wnan.1452](https://doi.org/10.1002/wnan.1452)

Angus P.R. Johnston*

Drug Delivery, Disposition and Dynamics, Monash Institute of Pharmaceutical Sciences,
Monash University, Parkville, Victoria, Australia
ARC Centre of Excellence in Convergent Bio-Nano Science and Technology, Monash
University, Parkville, Victoria, Australia
angus.johnston@monash.edu

Abstract

Using nanoparticles to deliver drugs to cells has the potential to revolutionize the treatment of many diseases, including HIV, cancer and diabetes. One of the major challenges facing this field is controlling where the drug is trafficked once the nanoparticle is taken up into the cell. In particular, if drugs remain localized in an endosomal or lysosomal compartment, the therapeutic can be rendered completely ineffective. To ensure the design of more effective delivery systems we must first develop a better understanding of how nanoparticles and their cargo are trafficked inside cells. This needs to be combined with an understanding of what characteristics are required for nanoparticles to achieve endosomal escape, along with methods to detect endosomal escape effectively. This review is focused into three sections; firstly, an introduction to the mechanisms governing internalization and trafficking in cells, secondly a discussion of methods to detect endosomal escape and finally, recent advances in controlling endosomal escape from polymer and lipid based nanoparticles, with a focus on engineering materials to promote endosomal escape.

Graphical/Visual Abstract and Caption

Nanoparticles have the potential to drastically improve the delivery of therapeutics, but their use is limited by their ability to escape endosomes after being internalized into cells. As new materials are engineered it is essential we understand how they behave in cells to overcome this substantial barrier.

1. INTRODUCTION

The treatment of a wide range of diseases and the development of improved vaccines both stand to benefit from more efficient therapeutic delivery.^{1,2} Nanoparticles have the capacity to transform conventional drug delivery, with the potential to reduce side effects through targeting, improve solubility of hard to deliver drugs, and provide sustained and controlled release of therapeutics.³ Nanoparticles also have the potential to offer protection to promising but delicate therapeutics such as nucleic acids and proteins through encapsulation.^{4,5} However, while encapsulation can protect a therapeutic from degradation before it reaches the target cell, it is also critical that it is trafficked to the site inside the cell where the drug is therapeutically active. The optimal nanoparticle size depends on the delivery application. For most applications where the nanoparticles enter the systemic circulation system, the optimal size is above 10 nm, to prevent clearance by the kidneys, and below 200 nm to enable passage through microcapillaries.⁶

Nanoparticles are typically taken up into cells via endocytosis into endosomes, and are then subsequently trafficked into acidic lysosomal compartments.⁷ The environment of the lysosome can result in significant degradation of the therapeutic cargo. Nanoparticle systems are of particular interest for the delivery of short interfering RNA (siRNA) for RNA interference (RNAi),⁸ DNA for gene therapy,⁹ antigens for vaccines¹⁰ and proteins for anti-cancer treatment or enzyme delivery.^{11,12} The aforementioned therapies exert their effect in either the cytosol or nucleus and hence must escape endocytic vesicles in a fundamental step known as endosomal escape. This critical event is widely considered to be the rate-limiting step or “bottleneck” of intracellular delivery of therapeutics using nanoparticle-based systems.^{13–15}

A variety of both natural and synthetic materials have been investigated for their potential to induce endosomal escape. Naturally occurring fusogenic or endosomolytic peptides derived from viruses^{16,17} and bacterial toxins¹⁸ have been explored as both bear the innate ability to escape the trafficking pathway as is required for their pathogenicity.^{19,20} This has created a drive for the design of synthetic peptides with similar chemical properties.^{21,22} Carbon-based materials such as fullerenes²³ and nanotubes²⁴ have been developed, along with functionalized inorganic nanoparticles including quantum dots²⁵ and nanoparticles with gold, mesoporous silica and calcium phosphate cores.^{26,27} A significant body of work has focused on soft materials, such as liposomes and polymeric particles,²⁸²⁹ and these materials will be the focus of this review.

A major roadblock in the development of endosomal escape materials is the lack of methods to quantify escape efficiency and subsequently the ability to determine the mechanisms behind it. Engineering nanoparticles for endosomal escape requires a fundamental understanding of how they interact with cells but our knowledge in this area is still lacking. Herein, we outline the current understanding of the cellular processing of polymeric and lipid nanoparticles and the methods for probing endosomal escape. The final section of this review focuses on the recent progress in engineering soft materials (polymers and lipids) that have demonstrated endosomal escape.

2. UPTAKE AND INTRACELLULAR TRAFFICKING

2.1 Internalization Mechanisms

Knowledge of nanoparticle uptake mechanisms and the subsequent trafficking within the cell is imperative if we are to design nanoparticles capable of delivering therapeutic cargo to its active site. Endocytosis is the dominant mechanism of uptake for nanoparticles into cells (Figure 1),^{7,30,31} as opposed to direct diffusion across the cellular membrane. However, fusion of nanoparticles with the plasma membrane has also been demonstrated.³² Endocytosis is a broad term for many specific endocytic pathways with individual mechanisms.³³ While much research has focused on clathrin and caveolae-dependent mechanisms, growing evidence suggests additional clathrin and caveolin-independent pathways may play a substantial role in endocytosis.³⁴ Nanoparticles decorated with targeting moieties such as antibodies^{35,36} or specific ligands such as for the transferrin³⁷ or folate^{38,39} receptors aim to induce uptake, but non-targeted particles can still enter through receptor-mediated endocytosis via scavenger or G-protein coupled receptors.⁴⁰ The uptake mechanism and subsequent trafficking is nanoparticle and cell line dependant, and entry into multiple pathways can occur simultaneously.⁴¹

Our understanding of these pathways is currently quite limited, which is partly due to a lack of acceptable markers and specific inhibitors for these processes.^{7,42} Following endocytosis at the cell membrane, Rab5 (a signalling protein) binds to the cytoplasmic side of the endocytic vesicle. Rab5 then interacts with EEA1 on early endosomes, which tethers to the surface of the vesicle and draws it in to fuse with the early endosome.⁴³ The endocytic vesicles rapidly acidify via V-type H⁺ ATPases,⁴⁴ reducing the pH from an extracellular pH of 7.4 down to ~6.3.⁴⁵ The initial fate of clathrin and caveolin dependent or independent vesicles is similar in most cell lines, with fusion to early endosomes occurring within minutes of internalization.⁴⁶ Endosomes are then either recycled back to the cell surface or continue to acidify to pH 5.5 in late endosomes and multivesicular bodies before fusion with lysosomes (pH 4.7).⁴⁵ As the major function of lysosomes is to break down incoming material, they contain a range of acid hydrolases, including proteases, nucleases, esterases and lipases.⁴⁷ Nanoparticles that are trafficked to the lysosome are subjected to these enzymes, degrading the cargo.⁴⁸ Nanoparticles can also be engineered to degrade in the presence of enzymes such as proteases⁴⁹ and nucleases⁵⁰ to control the release of the cargo. Rupture of lysosomes is associated with cell death (apoptosis) through release of cathepsins and calcium ions, so timing of escape and limiting the release of pro-apoptotic molecules is critical.^{51,52} Therefore, the window of time between internalization into the initial vesicles and fusion with lysosomes has been targeted as optimal period for pH responsive nanomaterials to be engineered to induce endosomal escape.^{53,54}

The principal method for determining the mechanism of nanoparticle internalisation is treating cells with drugs that inhibit endocytic pathways. These drugs work via a variety of mechanisms, such as by affecting the formation of clathrin-coated vesicles or by blocking enzymes involved in the budding of the vesicles from the cell surface.⁵⁵ Caution is required when interpreting data from inhibitor

studies, as most inhibitors show off target effects. For example, methyl- β -cyclodextrin causes cholesterol depletion and filipin disturbs cholesterol function to inhibit caveolae-mediated endocytosis, but both drugs may also alter clathrin-mediated uptake and other clathrin-independent mechanisms for which cholesterol is required.⁴²

Alternatively, the colocalization of the fluorescence from particles with that from markers of particular internalization pathways such as caveolin-1 has been used to assign mechanisms. However, caveolin has also been identified to localize in late endosomes and lysosomes after it has been tagged for degradation. This can lead to incorrect assumptions over the role caveolin plays in nanoparticle internalization. The existence of 'caveosomes' as distinct organelles involved in a unique caveolae mediated trafficking pathway has previously been hypothesized, however this is now regarded as unlikely.⁵⁶ Helenius and co-workers, the originators of the caveosome hypothesis, demonstrated in more recent work that the presence of caveolin inside endosomal compartments corresponds to ubiquitinated caveolin marked for degradation, rather than corresponding to a distinct endosomal compartment.⁵⁷ Despite these findings, there are still a number of reports in the literature relating to caveosomes playing a role in nanoparticle trafficking.

The uptake mechanism of nanoparticles has been extensively studied and shown to be highly dependent on the physical properties of the material^{58,59} as well as cell type.^{60,61} The protein corona that forms from the adsorption of proteins and other biomolecules onto the surface of nanoparticles from *in vivo* circulation⁶² also plays a role in cellular processing. Which proteins are adsorbed has been shown to be dependent on both the size and surface chemistry of particles.⁶³ In addition, the surface chemistry can disrupt proteins in the corona and change the mechanism of uptake.⁶⁴ The targeting ability to specific receptors can also be compromised from the corona shielding access to targeting moieties.⁶⁵ Experiments testing nanoparticles are typically carried out in media supplemented with serum to simulate *in vivo* conditions and induce corona formation. However, chemical differences in the media and *in vivo* conditions can cause differences in corona formation which in turn effects cellular processing.⁶⁶

Furthermore, it has been suggested that the specific mechanism of internalization can be associated with the fate of the particles. This is exemplified by studies into polyethylenimine (PEI) mediated gene delivery. Gabrielson and Pack suggest PEI-mediated transfection is only highly efficient when taken up through the caveolae-dependent pathway, and when taken up by the clathrin-dependent pathway, particles were trafficked quickly to the lysosomes for degradation.⁶⁷ Rejman et al. reached a similar conclusion by demonstrating that clathrin-dependent internalized particles were trafficked to lysosomes using the inhibitors chlorpromazine and K⁺ depletion for clathrin-dependent or filipin and genistein for caveolae-dependent endocytosis.⁶⁸ They also found that inhibition of the caveolae-dependent pathway stopped transfection via PEI polyplexes completely, while inhibition of the clathrin-dependent pathway had no effect.

Quantifying nanoparticle internalisation is also critical, as the kinetics and level of internalisation may influence endosomal escape. This requires the ability to differentiate between nanoparticles that have been internalized and those remaining bound to the cell surface. Fluorescence microscopy is commonly used to qualitatively determine internalisation, however it is inherently low throughput. Recently, confocal microscopy combined with flow cytometry has been used to increase the throughput of analysis.⁶⁹ Internalisation can also be quantified using flow cytometry by acid washing⁷⁰ or surface etching the cells,⁷¹ where acidic pH or particular chemicals remove particles remaining bound to the surface. Trypan blue has been used to non-discriminately quench cell-surface fluorescence.⁷² Both these techniques are limited by removal of all surface markers, limiting the ability to phenotype different populations of cells. Alternatively, a fluorescent sensor can be incorporated into the nanoparticles that remains switched on only when the particle is internalized into the cell (SHIP method).⁷³ The SHIP method has been used to demonstrate distinct differences in uptake in separate cell lines and when used in conjunction with inhibitors, can explore the mechanisms of internalization.⁷⁴ Flow cytometry assays can also be enhanced by deconvolving flow cytometry histograms to enhance the detection of interactions that would otherwise be lost in the background noise of cell autofluorescence.⁷⁵

While there is some evidence to suggest internalization pathways play a role in the subsequent fate of the cargo, it is unclear the mechanism by which this happens. As the fate of most endocytic vesicles that bud from the plasma membrane is trafficking to an early endosome, it has not been established how the subsequent trafficking pathways are differentiated. It is possible that differences in intracellular trafficking and endosomal escape relate to interactions that occur within the endosomal compartment rather than the initial mechanism of entry. Notwithstanding, the link between the mechanism of nanoparticle uptake and successive efficacy clearly warrants further investigation, as successful targeting to a particular pathway may be the key to an improvement in delivery efficiency.

2.2 Mechanisms of Endosomal Escape

The mechanism by which endosomal escape occurs is still highly contentious. There is little consensus in the literature around the mechanism of trafficking across the endosomal membrane, and there are a number of diverse mechanisms that can be employed to induce endosomal escape (Figure 2). We have focused on three proposed strategies for inducing endosomal escape, however it is highly likely that more than one of the mechanisms are required for efficient cytoplasmic delivery of therapeutics.

2.2.1 Proton Sponge Effect and Osmotic Lysis

A common strategy for inducing endosomal escape is via the proton sponge effect, which is based on the buffering effect of polymers with a pKa in a physiologically relevant range. This mechanism is often assigned to polycationic materials such as PEI⁷⁶ and poly(amidoamine) (PAMAM) dendrimers⁷⁷

but is still heavily debated.^{78–80} As the polymer becomes protonated, protons are continuously pumped into the endosomes/lysosomes, necessitating the transport of chloride counter ions to maintain a charge balance. This results in a high osmotic pressure that eventually causes the endosome/lysosome to rupture (Figure 2a). While in theory this is quite an elegant hypothesis, it does not provide a full explanation for endosomal escape. Not all polymers that buffer within the pH 5–7 range are capable of inducing endosomal escape, and efforts to engineer polymers with an enhanced buffering capacity within a physiologically relevant range has not resulted in an increased escape capacity.⁸¹ It has also been shown that when PEI is added to HeLa cells, the pH of the lysosomes remains at pH 4.5 over 24 hours.⁸⁰ It is clear that changes in pH play an important role in endosomal escape. However, it is difficult to decouple the role that pH buffering plays from other factors such as membrane interactions and conformational changes that are induced by a drop in the pH.

A related mechanism proposed by Battaglia and co-workers describes the role of osmotic pressure upon the disassembly of nanoparticles in the endosome.⁸² In this mechanism, rather than the buffering capacity of the polymer inducing the osmotic pressure and subsequent lysis, it is proposed that the disassembly of a particle into many polymer subunits causes an osmotic shock that ruptures the endosome.⁸³

2.2.2 Membrane Fusion

In nature, enveloped viruses can induce endosomal escape by fusion of the viral envelop with the endosomal membrane, allowing the viral capsid to enter the cytoplasm.⁸⁴ Similarly, for particles assembled from lipids or amphiphilic materials, it is proposed that the phospholipid bilayer of a liposome can fuse with the endosomal membrane (Figure 2b), inverting the structure of the liposome and delivering the therapeutic core to the cytoplasm.⁸⁵ Safinya and co-workers used synchrotron small-angle X-ray scattering (SAXS) to relate the structure of DOTAP-DOPE to its transfection efficiency.⁸⁶ DOPE was found to induce the transition from a multilamellar structure to an inverted hexagonal liquid crystalline phase in DNA lipoplexes. The inverted hexagonal structure interacts more favourably with model anionic membranes, resulting in membrane fusion and DNA release.

2.2.3 Membrane Disruption and Pore Formation

Destabilizing the endosomal membrane can allow therapeutic cargo to diffuse out of the endosomal compartment through holes or pores. Endosomal disruption can occur through the direct interaction of polymers⁸⁷ or peptides⁸⁸ with the endosomal membrane, or via peptides that self-assemble across the membrane to create defined pores (Figure 2c).^{89,90} Typically, the dimensions of transmembrane pores are ~1 nm,⁹¹ which generally limits their usefulness to induce efficient release of therapeutic cargo. However, the engineered peptide GALA is capable of inducing release of molecules up to 5,000 Da (see section 4.7).⁸⁹

In addition, a large body of evidence suggests that polymer based systems induce escape by interacting with cellular membranes (Figure 2d). Coarse-grain molecular simulations with asymmetric lipid membranes demonstrated that dendrimers insert into membranes and interfere with asymmetry.⁹² Supported-lipid bilayer studies with atomic force microscopy visually demonstrate dendrimers and PEI induce thinning or hole formation.^{93,94} It is likely simulations and artificial membranes are not able to fully represent the complexities of cell membranes but *in vitro* experiments have shown similar results. Whole-cell patch clamp conductance measurements show that polycations cause membrane defects and that these can heal overtime.⁹⁵ In addition, electron microscopy shows direct interaction and disruption of lysosomal membranes by PEI.⁹⁶ The escape mechanism for polyanionic polymers is attributed to an increase in hydrophobicity due to protonated carboxylate groups which results in membrane insertion and subsequent membrane disruption.⁸⁷

It is important to understand the mechanism by which endosomal escape can occur when designing a delivery system. Endosomal lysis and membrane fusion have the potential to deliver cargo to the cytoplasm regardless of the cargo size, while membrane disruption and pore formation will inherently have limits to the molecular weight than can diffuse across the destabilized membrane. Additionally, how the cargo is encapsulated or attached to the delivery vehicle can affect the therapeutic outcome. For example, conjugation of therapeutics to the components of the particle responsible for membrane fusion can be counterproductive and even lead to increased localization in endosomes and lysosomes.⁹⁷ It is also important to consider the potentially toxic side effects of endosomal escape. Lysosomes play an important role in regulating apoptosis, and the uncontrolled release of cathepsin as well as calcium ions can significantly affect the viability of cells.⁹⁸

3. DETECTION OF ENDOSOMAL ESCAPE

The difficulty in engineering materials for endosomal escape is due in part to a lack of understanding how nanoparticles behave in cells. Thus, more robust and reliable methods to detect escape and probe the mechanisms by which it occurs are needed. The complex nature of cellular trafficking means that a number of techniques must be used in combination to probe the mechanisms. It is also important to understand what information each assay can provide, and what it cannot. This review summarizes some of the most commonly used approaches to detect endosomal escape. A comprehensive review of the methods has recently been published.⁹⁹

3.1 Fluorescent Labelling

Fluorescent labelling is one of the simplest methods to identify endosomal escape. The polymers or lipids used to assemble the nanoparticles,^{52,81} or the therapeutic cargo within the nanoparticle,^{100,101} can be conjugated with small fluorescent dyes. This allows for the intracellular distribution of the fluorescence to be imaged. Labelled material trapped in endocytic vesicles has a punctate appearance (Figure 3a) while a diffuse appearance (Figure 3b) suggests material has left the vesicles

and moved into the cytosol. Difficulties arise when the degree of escape is low, causing the fluorescence from escaped material to be indiscernible from the background of the image.

By labelling organelles involved in cellular trafficking, colocalization studies can be performed to gain a better understanding of where nanoparticles are transported. Trafficking vesicles can be labelled in live cells with acidotropic dyes such as acridine orange^{87,102} and LysoTracker,^{103,104} which accumulate non-specifically in acidic organelles.^{105,106} While these stains can be useful to gain a basic level of understanding of cellular trafficking, they have a number of limitations. Dyes such as LysoTracker often exhibit high levels of background, which leads to low signal to noise ratios. There is also potential for nanoparticles to interfere with the fluorescence of these sensors. Nanoparticles that buffer endosomal pH typically suppress LysoTracker signal, as LysoTracker relies on a decrease in pH to sense the lysosomal compartments.¹⁰⁶

For precise labelling, specific organelle markers such as lysosomal-associated membrane protein-1 (LAMP-1) can be immunostained¹⁰⁷ or expressed fused with a fluorescent protein via transfection.¹⁰⁸ Immunofluorescence labelling can be performed in almost any cell type after fixing and permeabilizing the cells.¹⁰⁹ Fixation relies on crosslinking amines, amides and hydroxyl groups into a formaldehyde/glutaraldehyde network to preserve the structure of the cell.¹¹⁰ If the nanoparticles are not cross-linked to the network of proteins during fixation, they will diffuse out of the cell during permeabilization. This is particularly problematic for nanoparticles that are engineered to have stealth characteristics. Imaging localization in live cells can be achieved by transfection with markers for specific cellular compartments, such as LAMP, EEA1 or Rab, fused to fluorescent proteins. This enables colocalization imaging of particles in situ.¹¹¹ The limitation with this technique is that it can only be performed in cell lines that can be readily transfected, making it difficult to study primary cells. Also, the effect of the transfection process and over expression of trafficking proteins on the behaviour of cells has to be considered.¹¹²

While organelle labelling is much more specific than using pH sensitive or lysosomal accumulating dyes, quantitative assessment of colocalization can be challenging. The endosomal/lysosomal markers are associated with the vesicular membrane and as a result may not overlap with the enclosed particle (Figure 4). This can give rise to low degrees of colocalization from statistical calculations even though the particle is enclosed in the vesicle. Furthermore, the lack of colocalization of particles with an endosomal/lysosomal marker can be confused with endosomal escape. Punctate fluorescence in the cell is an indicator of nanoparticles or therapeutic cargo encapsulated within vesicular membranes that is not accessible to the cytoplasm.

Fluorescent labelling is a versatile tool for investigating both the trafficking and endosomal escape capacity of nanoparticles. However, imaging gives limited insight into the mechanism of endosomal escape and therefore should be considered as a starting point. Complementary assays to probe the mechanism of escape are required. Furthermore, the use of high intensity light in fluorescence imaging has been observed to induce the redistribution of fluorescently labelled peptides from the

endosome to the cytoplasm. This phenomenon can easily be limited by ensuring low levels of light during imaging with short exposure times, but must be considered as a factor during live cell imaging assays with extended durations.¹¹³

3.2 Leakage assays

These assays examine the ability of a given material to induce leakage in cell and vesicle membranes. The behaviour of the material can be examined under either *ex vivo* or *in vitro* conditions.

3.2.1 Ex Vivo Leakage Assays

Preliminary evaluation of the endosome escape capacity of a material can be performed using liposomes as a model membrane. The liposomes are composed of combinations of phospholipids representative of those found in cells and contain an encapsulated fluorescent dye. The local concentration of the dye is high and this quenches the fluorescence, allowing for a large increase in fluorescence intensity if leakage occurs. An example of this is 6-carboxyfluorescein which increases in fluorescence 30-fold on release.¹¹⁴ This method has been used for a variety of membrane destabilizing materials including cell-penetrating peptides⁹⁷ and cationic polymers^{115,116} and has been used to show differences in the behaviour of liposome nanoparticles functionalized with octaarginine or octalysine.¹¹⁷

Red blood cells have also been used as a more biologically relevant model to study membrane disruption. By observing the lysis of red blood cells and release of hemoglobin at varying pH values, the pH dependent membrane disruption of nanoparticles can be determined. Red blood cells in solutions buffered at pH values mimicking those corresponding to the extracellular, endosomal and lysosomal environments are co-incubated with the material of interest. pH-induced changes in the material that cause membrane disruption results in hemoglobin release into the surrounding media, which is then measured via spectrophotometry.^{118,119} This information can be used to assess when the material is likely to activate its disruptive properties along the intracellular trafficking pathway. For example, cationic lipid nanoparticles formed from (1-aminoethyl)iminobis[N-(oleicysteinyl-1-amino-ethyl)- propionamide] showed ~50% hemolytic activity at the pH of early endosomes and ~90% at the pH of lysosomes but minimal disruption at the pH of the extracellular space.¹²⁰ The increase in lysis corresponded with an increase in protonation of the lipid head groups as assessed by the zeta potential.

These *ex vivo* assays give insight into the mechanism of escape as they rely on membrane disruption or pore formation to release dye or hemoglobin from within the membrane. Materials that induce escape solely via osmotic lysis are unlikely to induce escape in these assays. It is important to note that in addition to any proton sponge effect that PEI may have, PEI also induces red blood cell lysis,¹²¹ further indicating the role membrane interactions play in inducing endosomal escape.

3.2.2 In Vitro Leakage Assays

Calcein, 6-carboxyfluorescein and fluorescently labelled dextran have been used *in vitro* to investigate escape from trafficking vesicles.^{87,117,122,123} Cells macropinocytose the dye and a combination of low pH and self-quenching leads to a weak, punctate fluorescence in the endosomes (Figure 5d). If the nanoparticles can induce escape, a high fluorescent signal distributed through the cytoplasm is observed (Figure 5e).⁸⁷ This method is limited by low throughput, as cells with diffuse fluorescence are identified and counted manually. Attempts have been made to improve throughput by incorporating an algorithm to recognise cells with diffuse fluorescence. The escape efficiency of a polyamidoamine-PEG polyplex system was investigated by acquiring multiple fields of view and using the intensity of the calcein fluorescence in the nuclear region to count cells with endosomal escape.¹²⁴ Alternatively, the calcein assay can be used with flow cytometry. pH sensitive poly-(β -amino ester)-core phospholipid-shell particles showed a drastic increase in the percentage of cells positive for a calcein signal while the signal from samples incubated with pH-insensitive poly-(lactide-co-glycolide) particles remained similar to the value for cells incubated with only calcein.¹²⁵ A combination of flow cytometry and microscopy is normally required when assessing escape, as calcein can associate with nanoparticles. This causes an increase in calcein signal due to increased calcein uptake rather than endosomal escape.

Although small molecule leakage assays have the ability to show that membranes have been compromised, they cannot determine if the disruption is sufficient to allow the escape of particles or cargo unless these are labelled separately. The molecular weight threshold of escape can be investigated using dextran with a range of molecular weights (3,000 – 2,000,000 Da).^{126,127} The release of small, but not large dextran suggests leakage, while escape of all sizes implies complete disruption. While dextran is a useful model, it should be noted that dextran is a highly flexible molecule, enabling it to diffuse through pores that would inhibit the diffusion of globular proteins of a similar molecular weight. Leakage assays can be complimented by studies that inhibit the acidification of lysosomes through the use of drugs such as bafilomycin A1. Inhibiting lysosomal acidification typically inhibits endosomal escape.¹²⁸

3.3 Transfection Assays

In addition to small molecule therapeutics, endosomal escape is important for the delivery of nucleic acids for gene silencing or expression. siRNA must reach the cytosol to access the RNA-induced silencing complex (RISC)¹²⁹ and DNA needs to enter the nucleus before it can be transcribed into RNA for protein expression.^{130,131} These criteria allow transfection assays to indirectly determine if escape has occurred by measuring knockdown or expression of the protein of interest. The most commonly used assays include delivery of genes for the enzymes luciferase^{132,133} and β -galactosidase.^{81,134,135} When successfully delivered and transcribed, an enzyme is produced that converts a specific substrate into a luminescent or coloured compound. The luminescence or absorbance of cell lysates in the presence of the substrate can then be compared to non-transfected cells to give an indirect measure of the relative level of escape. Transfection with plasmids coding for inherently fluorescent molecules such as green fluorescent protein (GFP)^{136,137} have also been used in a similar way using

flow cytometry or microscopy. Since transportation of DNA to the nucleus can be a significant barrier, RNA interference can be used to evaluate cytoplasmic release through delivery of siRNAs to silence reporter genes.^{138,139} RNA interference occurs in the cytosol, and hence is a more direct method of assessing endosomal escape.

Transfection assays are able to provide confirmation of escape with a reasonable amount of certainty by detection of, or reduction in expression of a reporter gene. Yet, these assays are an indirect indicator of escape and cannot elucidate the mechanism. It is also imperative that the cytotoxicity of the materials is considered to ensure that any signal measured is not simply due to necrotic/apoptotic cells. This is highlighted with PEI, which is widely considered to be one of the most efficient non-viral transfection agents but also highly cytotoxic.⁶¹ Bieber et al. introduced fluorescently labelled PEI/DNA complexes to human embryonic kidney (HEK) cells and found after an 18-hour incubation, the majority of cells displayed fluorescence in a punctate distribution in the perinuclear region.⁹⁶ Although a small proportion of cells had a cytoplasmic distribution of fluorescence, they were also necrotic in appearance. The cells had become non-adherent and the morphology did not reoccur following subsequent media change, which suggested the cells were irreversibly damaged. As these cells were not part of the collective that express the reporter gene, they cannot be used to show escape regardless of the presence of labelled PEI-DNA complexes in the cytoplasm. Godbey et al. also demonstrated an inverse relationship between transfection efficiency and cell viability, using free and complexed PEI on the EA.hy 926 endothelial cell line.¹⁴⁰ As transfection with toxic materials is futile for the application of gene therapy, this research highlights the need to carefully consider the viability of cells alongside the ability to induce endosomal escape.

There is a significant need for new quantitative assays to assess endosomal escape. End point assays such as transfection do not quantify the efficiency of escape, but instead give a yes/no answer if escape has occurred in the remaining healthy cells. Endosomal escape efficiency is rarely quoted, partly because it is a difficult parameter to quantify. No individual method is able to provide a conclusive answer on the mechanism and extent of escape. Therefore, it is important for multiple complementary techniques to be employed before drawing conclusions about the mode and extent of endosomal escape.

4. STRATEGIES TO ENGINEER ENDOSOMAL ESCAPE

Over the past decade, numerous nanoparticle systems have been developed to enhance the cytoplasmic delivery of therapeutics. These nanoparticles rely on a diverse array of mechanisms to promote escape and in a number of instances, the mechanism by which endosomal escape occurs is not entirely clear. It is important we gain better insight into the parameters that control endosomal escape, to enable nanoparticles to be engineered so their cellular fate can be controlled and thus have improved efficacy.

4.1 Lipid Mediated Membrane Fusion

Liposomal formulations have demonstrated potential for cytoplasmic delivery, particularly through the use of cationic lipids (DOTAP, DOTMA, DODAC) for use in gene therapy.¹⁴¹ Cationic liposomes are usually prepared with the neutral or helper lipids DOPE or DOPC in the mixture to provide stabilization of the lipid bilayer. Cationic liposomes prepared with DOPE have been shown to facilitate escape due to structural transitions when exposed to the low pH of endocytic vesicles.^{142,143} DOPC is a structural analogue of DOPE and promotes stable lamellar structures, but does not improve endosomal escape and hence transfection. Electron microscopy of DOPE containing cationic liposomes showed an endosomal destabilizing effect, whereas DOPC formulations did not have an effect.^{143,144}

Modification of liposomes with PEG is used extensively to improve *in vivo* circulation time, as demonstrated by the clinical liposomal formulation of doxorubicin, Doxil. However, the presence of PEG in liposomes has been observed to reduce endosomal escape. This has also been observed with other polymer-based nanoparticles, including PEI- and β -cyclodextrin-based polyplexes.¹⁰¹ In contrast to PEGylated polyplexes,¹⁴⁵ PEGylation in this lipid system had minimal effect on cellular uptake¹⁴⁶ and delivery was instead limited by effective escape.^{147,148} The steric barrier provided by PEG is thought to interfere with membrane fusion events that occur between fusogenic lipids and the endosomal membrane.¹⁴⁷ In a study by Song et al, DODAC:DOPE liposomes at a 1:1 mole ratio with 5% PEG-lipid showed inefficient transfection in HepG2 cells.¹⁴⁷ By reducing the molecular weight of the PEG from 3400 Da to 220 Da and the amide chain length of the lipid anchor, transfection efficiency was improved. This suggests that PEG molecular weight and the size of the hydrophobic anchor are important. With confocal microscopy, they demonstrated a difference in the intracellular fate of PEGylated and naked liposomes. Lipids from liposomes without PEG localized in the perinuclear space while the oligonucleotide cargo escaped from endosomes and accumulated in the nucleus. In PEGylated liposomes, both the cargo and lipid remained perinuclear.

A number of groups have overcome the adverse effect of PEGylation on endosomal escape by designing pH-sensitive PEG analogues¹⁴⁹ or PEG that can be cleaved in reducing conditions.^{150,151} Bio-functionalization with targeting moieties has also been shown to address the effects of PEGylation. Meyer et al. showed that conjugation of anti-HER2 F(ab') fragments on the PEG chains improved uptake, albeit non-specifically, by a factor of ~2.5 compared with PEGylated liposomes alone.¹⁵² Importantly, there was a significant improvement in the release and nuclear localization of encapsulated cargo with targeted PEGylated liposomes. It was suggested that targeted liposomes are trafficked by receptor mediated endocytosis into early endosomes that are more permissible to cargo release than those in early endosomes from non-specific pinocytosis, however the mechanism by which this happens is not clear.¹⁵²

Hybrid systems can also be of significant interest as they can combine the advantages of different materials (e.g. proteins with polymers). An interesting example was reported by Rotello and co-workers, where an oil template stabilised by a mixture of protein and gold nanoparticles

functionalised with a HKRK peptide motif was prepared.³² The proteins GFP and Caspase-3 were incorporated and the resulting particle sizes were 130 ± 40 nm and 140 ± 20 nm respectively. This study demonstrated GFP could be delivered effectively into HeLa cells, showing diffuse fluorescence throughout the cell, including the nucleus (Figure 6). The authors postulate the mechanism for this process is through plasma membrane fusion, delivering the protein directly into the cytoplasm and not through endosomal escape from an acidic compartment.

4.2 Polymers Capable of Endosomal Buffering

A number of studies demonstrate that polymers with cationic amino substituents can buffer the endosomal/lysosomal compartments to induce endosomal escape. PEI is a well-known example of such a polymer and is commonly used to complex DNA and siRNA to form polyion complexes. It has generally been observed that higher molecular weight PEI achieves better transfection than lower molecular weight but is also significantly more toxic. Recent studies have looked at using different PEI hybrids to improve transfection efficiency of low molecular weight variants.¹⁵³ Polypeptides poly(L-histidine) (PHis)¹⁵⁴ and poly(arginine) (PArg)¹⁵⁵ have also been shown to assist with endosomal buffering and thus have been incorporated into different polymer carriers.¹⁵⁶ While pH plays an important role in the endosomal escape of these materials, it is likely that other escape mechanisms are also involved.

4.3 Expandable pH-Responsive Nanoparticles

Mechanical stress has also been used to induce endosomal disruption by designing nanoparticles that change size upon a change in pH. One strategy is the synthesis of cross-linked polymer nanoparticles that are assembled from pH responsive polymers. Such materials swell significantly when they become ionized due to repulsion between the polymer chains.¹⁵⁷

Irvine and co-workers have performed a number of elegant studies on emulsion particles with a diethylamino ethyl methacrylate (DEAEMA) core cross-linked with poly(ethylene glycol) dimethacrylate (PEGDMA) and a 2-aminoethyl methacrylate (AEMA) shell.¹²³ The particles underwent a 2.8-fold change in diameter (by dynamic light scattering (DLS)) on changing the pH from extracellular pH (7.4) to an endolysosomal pH of 5. A pH insensitive control particle was also synthesized based on cross-linked methyl methacrylate (MMA). These particles had minimal toxicity at concentrations below 25 $\mu\text{g/mL}$. The capability of these particles to disrupt the endosome was investigated using calcein in the model dendritic cell line, DC2.4. Microscopy showed cells loaded with control particles (pH insensitive) demonstrated only punctate fluorescence of the calcein while PDEAEMA particles showed diffuse fluorescence throughout the cell, indicating release from the endosomal compartments. Approximately 90% of cells incubated with PDEAEMA had diffuse cytosol fluorescence compared to fewer than 5 % of cells incubated with calcein or calcein with control particles. Functional escape was also confirmed by loading particles with the model antigen ovalbumin (OVA) and measuring interferon- γ (IFN- γ) secretion by primary T cells in response to

antigen presentation by DCs.¹²² The responsive nanoparticles showed a 9 - 10 fold increase in IFN- γ production compared to non-responsive particles or soluble OVA. In addition, the level of response was related to the concentration of OVA, with higher levels of protein showing an increased response.

The authors hypothesise that the endosomal escape mechanism of these particles is based on a combination of osmotically driven uptake of water into the endosome caused by counterion build-up and mechanical pressure from particle swelling. Interestingly, it was found that particles had to be delivered at the same time as the fluid phase marker (e.g. calcein) for endosomal escape to occur, suggesting the fluid phase marker needed to be colocalized in the same endosome. The nanoparticles were also used to load fluorescently labelled siRNA. While 40% of cells had diffuse siRNA fluorescence when incubated for 1 hour, knockdown of this system was lower compared to a commercially available lipid reagent at 23 +/- 14% and 6 +/- 1.2 % respectively. This was thought to be due to an electrostatic interaction between the cargo and the carrier when in the cytosol.

A similar nanoparticle was reported by Nagasaki and co-workers based on the emulsion polymerization of DEAEMA in the presence of heterobifunctional poly(ethylene glycol) ($\text{CH}_2=\text{CH}-\text{Ph}-\text{PEG}-\text{COOH}$) and using ethylene glycol dimethacrylate (EGDMA) as a crosslinker.¹⁵⁸ The nanoparticles were shown to increase in size between 5.1 - 6.8 fold when the PDEAEMA was protonated, depending on the size of the heterofunctional PEG used. A nanoparticle based on this chemistry was then functionalized with a lactose group (p-aminophenyl- β -D-lactopyranoside) using the carboxylic acid functional group on the PEG. This particle was added in combination with a PEG-b-poly(L-Lysine)/pDNA polyplex to investigate the effect on transfection efficiency of HuH-7 cells. A significant increase was observed when the two nanoparticles were added together, while a control sample with asialofetuin (ASF) showed less binding. This suggested that the particles were being internalized through an asialoglycoprotein receptor (ASGP) mediated process as ASF acts as a competitive inhibitor of ASGP receptor-mediated endocytosis.

4.4 Rapid Disassembly of pH-Responsive Nanoparticles

Another endosomal escape mechanism postulated in the literature involves the disassembly of a cationic polymer particle into component unimers to create an increase in osmotic pressure and rupture of the endosomal membrane. One of the initial studies using this approach involved the synthesis of a responsive polymersome that could disassemble within the endosomal pH range. The polymersomes were synthesised from poly(2-methacryloyloxy)ethylphosphorylchlorine)-co-poly(2-(diisopropylamino)ethyl methacrylate) (PMPC-PDPAEMA). Stable vesicles were formed at physiological pH but disassembled below pH 6 due to a change in hydrophobicity of the PDPAEMA component. To test transfection efficiency, the plasmid encoding luciferase was encapsulated within the polymersome and delivered into primary human dermal fibroblast (HDF) cells. Transfection efficiency was significantly enhanced by plasmid-loaded polymersomes compared to plasmid alone.⁸³

Irvine and co-workers have also reported a rapidly degradable, pH-dependent nanoparticle based on 10 kDa molecular weight poly(β -amino ester) (poly-1). Poly-1 is a weak polyelectrolyte that is water insoluble at elevated pH but dissolves in aqueous solutions below pH 7.¹²⁵ This polymer is stabilized by a lipid bilayer and a PEG-lipid and forms particles by nanoprecipitation. The particles formed were approximately 200 nm in diameter and were found to rapidly degrade *ex vivo* with a decrease in pH (within 5 mins). Endosomal escape capacity was investigated by incubating the particles for 1 hour with DC2.4 cells in the presence of calcein. Particles with a non-responsive poly lactic-co-glycolic acid (PLGA) core were used as a control. Both flow cytometry and microscopy showed an increase in calcein fluorescence when added in the presence of poly-1 particles, compared to calcein or PLGA particles added in isolation. In a separate experiment, particles with electrostatically associated mRNA encoding for GFP were incubated with cells and the subsequent expression was assessed by flow cytometry. Approximately 30% of the cells were successfully transfected thus indicating evidence of endosomal escape. The authors proposed two mechanisms for the endosomal escape capacity of their particles: (i) a strong osmotic pressure gradient generated across the endosomal membrane as the solid particles dissolve into individual polymer chains and (ii) the proton sponge effect (section 2.2.1).

Recently, our group has demonstrated the synthesis of a new pHlexi nanoparticle based on a combination of PDEAEMA homopolymer and a block poly(ethylene glycol)-*b*-PDEAEMA copolymer using nanoprecipitation. The particles were found to disassemble rapidly *ex vivo* when the pH was decreased below 6.8 and found to induce endosomal escape as determined via the calcein leakage assay. Endosomal escape was observed in approximately 40% of the cells, and there was strong colocalization of the polymer building blocks with the lysosomal compartments of the cells¹⁵⁹. This suggests release was more likely due a membrane disrupting or pore-forming mechanism than complete vesicle rupture. Later work showed the endosomal escape of these pHlexi particles could be tuned by the molecular weight of the polymer building blocks.¹⁶⁰ This indicates small variations in nanoparticle properties can also play an important role in cellular behaviour.

4.5 Nanoparticles Capable of Interacting with the Endosomal Membrane

An additional avenue to enhance endosomal escape is engineering the polymer to interact with membranes. Some useful polymers to achieve such interactions are poly(propylacrylic acid) (PPAA) and poly(butyl acrylate) (PBA). Recently, a new micelle carrier was synthesized based on a cationic poly(N,N'-dimethylamino) ethylmethacrylate (DMEAMA) and a second pH-responsive membrane disruption block containing DMEAMA, poly(acrylic acid) and BA.¹⁰⁰ This polymer formed micelles in the size range of 45 nm in physiological conditions. The particles were stable in PBS (pH 7.4) but disassembled readily in the lower pH conditions (pH 5.8) that would be present in an endosomal compartment. Further confirmation of their action within a biologically relevant range was obtained by a red blood cell hemolysis assay which demonstrated the particles increased lysis at a pH range of 6.6 - 5.8. The micelles were also loaded with siRNA targeting mRNA for the housekeeping gene GAPDH by interacting the negatively charged cargo with the DMEAEMA shell. Significant knockdown

was observed for all concentrations above the critical micelle concentration. Fluorescence microscopy was also conducted using fluorescein-labelled siRNA in both loaded carriers and Lipofectamine complexes. Lipofectamine transfection resulted in punctate fluorescence while the micelle system showed diffuse siRNA release (Figure 7).

Polymersomes assembled from a triblock copolymer of consisting PEG and poly(glycerol methacrylate) (poly-GMA) ends, and a central weakly basic block, polyimidazole-hexyl methacrylate (poly-ImHeMA), showed similar siRNA delivery efficiency.¹⁶¹ A PDEAEMA polymer micelle has also been used as a vaccine delivery system, by including pyridyl disulfide methacrylate in the PDEAEMA block to load OVA.¹¹⁹ The polymer was then complexed with an adjuvant containing an unmethylated cytosine-phosphate-guanine (CpG) sequence. The efficacy of these particles was tested *in vivo* by injecting C57BL/6 mice subcutaneously with polymer-protein conjugate/CpG, polymer-protein conjugate or free OVA alone. The CD8+ response was determined by *ex vivo* stimulation of isolated splenocytes with the ova epitope SIINFEKL to determine IFN- γ production. Cytokine production was enhanced significantly when CpG and the polymer conjugate were present, inducing a 7-fold increase in production compared to conjugate alone and an 18-fold increase over free antigen.

In another recent study Zhan et al. used a tripolymer based on 2-propyl acrylic acid (PPAA), butyl methacrylate (BMA) and 2-(dimethylamino)ethyl methacrylate (DMAEMA) in combination with PLGA to make blend particles. To investigate endosomal escape, fluorescent molecules with varying molecular weights (calcein, FITC-dextran with the MW of 4, 40, 150 and 2000 kDa) were co-delivered with particles into DC2.4 cells. A control of no particles or polystyrene (PS) was used for comparison of the cellular distribution¹²⁶. For both controls, the fluorescence remained punctate indicating little diffusion outside the endosomal membrane. In the case of the blend particles, diffuse fluorescence was seen for the lower molecular weight fluorescent species but remained punctate in the case of 150 and 2000 kDa dextran. This study gave interesting insight into the size of the pores that were formed in the membrane.

Poly(*N*-(2-aminoethyl)-2-aminoethyl- α , β -aspartamide) PAsp(DET) has also shown evidence of endosomal escape due to membrane interactions. Kataoka and co-workers used particles with either a disulfide or non-degradable linker between the PEG and AspDET components and compared their transfection efficiency.¹⁶² Knockdown of luciferase expression was enhanced in the carrier containing PEG-SS-PAsp(DET) relative to the control sample that contained no disulfide moieties. Such polymers are thought to also have capability to fuse with membranes due to their hydrophobic components but only below a certain pH range.

4.6 Drug-Induced Endosomal Escape

While a number of particle systems undergo endosomal escape as a result of rapid pH-induced disassembly to unimers, other similar systems that undergo rapid particle disassembly do not show

clear evidence of escape.^{163,164} A recent example is a micelleplex based on PDMEAEMA-b-PDEAEMA, which allows for siRNA complexation and pH-induced disassembly below pH 6.3.¹⁶³ In this system, pH responsive cationic components cause an increase in endosomal osmotic pressure due to disassembly of the particles into individual polymers. However, fluorescence from labelled siRNA remained punctate after 12 hours incubation *in vitro*. To improve endolysosomal escape, particles were loaded with amphotericin B (AmB), a hydrophobic antifungal drug known to increase membrane permeability by forming transmembrane pores. The cellular distribution of siRNA loaded into the particles and a fluid marker (tetramethylrhodamine (TMR)-dextran) was investigated using confocal microscopy. Diffuse fluorescence was clearly observed with increasing concentration of AmB, especially in the case of the fluid phase marker (TMR-dextran). This was confirmed by the enhanced knockdown of luciferase in the presence of AmB.

4.7 Peptide-induced Endosomal Escape

Beyond using the intrinsic properties of the polymers or lipids, nanoparticles can be modified with endosomal escape agents to further enhance trafficking to the cytoplasm. A number of polypeptides derived from viral or bacterial proteins have been demonstrated to facilitate endosomal escape. A common motif present in many cell penetrating peptides (CPP) that have been observed to escape the endosome is the presence of arginine residues.¹⁶⁵ Arginine has a guanidinium functional group, which readily forms a complex with phosphate groups on phospholipids through a combination of hydrogen bonding and electrostatic interactions.¹⁶⁶ A number of materials that contain the guanidinium group, such as polymers and lipids, also show enhanced membrane permeation.^{32,166} The role of guanidinium has been demonstrated in studies comparing octaarginine-functionalized liposomes to octalysine-functionalized liposomes. Liposomes functionalized with a high density of octaarginine showed significantly increased transfection efficiency compared to liposomes functionalized with octalysine.¹¹⁷

One of the most ubiquitous arginine-rich peptide sequences used for inducing endosomal escape is the TAT peptide, which is derived from the Trans-Activator of Transcription protein in HIV. The primary role of TAT protein is in the replication of the viral genome and does not play an active role in HIV infection.¹⁶⁷ However, the high content of arginine residues within the 11-amino acid sequence allows the protein to readily translocate across cell membranes.¹⁶⁷ This protein transduction domain of TAT can be fused to proteins and polymers to induce endosomal escape. TAT induced escape is generally quite inefficient, requires high concentrations of TAT, and can be highly variable depending on the cargo to escape and the cells being targeted.¹⁷ In particular, direct fusion of TAT to materials to induce trafficking from the endosome has had limited success.¹⁷ This suggests that either free TAT is required for membrane disruption, or that TAT remains in the endosomal membrane as part of the destabilization process. In recent work, a disulfide linked TAT dimer has shown significantly enhanced endosomal escape at concentrations more than an order of magnitude less than that of monomeric TAT.¹⁷ The mechanism by which TAT and dimeric TAT induce endosomal escape is not understood.

Both TAT and Arg8 peptides are initially trafficked to Rab5 positive early endosomes then to Rab7+ late endosomes before they can escape from the endosomal compartments.¹⁶⁵ Schepartz and co-workers have developed peptide sequences with controlled arginine topology, whereby 5 arginine residues are presented on the same face of an alpha helical peptide. This peptide (5.3) induces endosomal escape that is more efficient than TAT or Arg8, and interestingly enables endosomal escape from the Rab5+ early endosomes without the need for maturation into Rab7+ late endosomes.¹⁶⁵

The second class of endosomal escape peptides lack arginine residues and are thought to disrupt the endosomal membrane via insertion into the lipid bilayer. A number of useful peptides have been derived from the hemagglutinin HA2 subunit of the influenza virus. The flu virus escapes from the endosomal compartment by pH induced conformational changes in the HA2 subunit that enables the virus to fuse with the endosomal membrane. The 23 N-terminal amino acid sequence of HA2 fuses and disrupts cell membranes, and has been shown to induce membrane fusion, leakage and lysis.¹⁶⁸ While the HA2 peptide and its variants can effectively induce membrane fusion and leakage, direct attachment of the HA2 peptide to a protein cargo increased association to endosomal compartments. However, when free HA2 was co-delivered with the protein, escape was induced but the HA2 fusion protein remained in the endosome.⁹⁷ This is likely due to HA2 remaining inserted in the endosomal membrane, preventing the conjugated protein cargo from escaping. Although HA2 and related peptides have potential, their application must be carefully considered so they cause release of the particle or cargo without remaining attached.

A peptide with a related mechanism of action is GALA, a purely synthetic sequence designed to adopt an alpha helical confirmation at low pH that can span the lipid bilayer of the endosome. GALA is negatively charged at pH 7 and comprises a repeated EALA (glu-ala-leu-ala) motif, which forms an alpha helix when the glutamic acid residues become protonated. The sequence induces pH dependent fusion of lipid membranes and can also self-assemble to form transmembrane pores capable of transporting molecules up to 5000 Da.⁸⁹ Cationic variants of GALA have been engineered by substituting the glutamic acid for lysine (KALA). Despite the KALA sequence undergoing the opposite conformational change to GALA (alpha helix to random coil, rather than random coil to alpha helix), KALA is still able to induce endosomal escape. DNA complexed with KALA has shown significantly increased transfection efficiency compared to polylysine-condensed DNA. Modification of liposomes with a shortened GALA (shGALA) has also been shown to enhance endosomal escape. shGALA-modified and PEGylated lipid-based particles called multi-functional nano devices (PEG-MEND) demonstrated 82% knockdown of the target gene through RNA silencing.¹⁶⁹ Reduced gene silencing efficiency was seen in cells incubated with NH₄Cl, which suppresses endosome acidification. This pH-dependence suggests the peptide requires an acid environment to exert its fusogenic properties.¹⁶⁹

Using a screen of antimicrobial peptides from the antimicrobial peptide database, Liu and co-workers have identified the aurein 1.2 peptide sequence to have endosomolytic properties. This

sequence has been demonstrated to induce endosomal escape both *in vitro* and *in vivo*. In another study Liang et al. demonstrated enhanced cytoplasmic localization of a therapeutic loaded nanoparticle when it contained a R4H4 peptide consisting of four arginine units and four histidine units.¹⁷⁰

5. CONCLUSIONS

Significant progress has been made over the last 10 years in developing nanoparticles to address the challenges of cytoplasmic delivery. However, as we rapidly generate new materials, our knowledge of how nanoparticles induce endosomal escape lags behind. Furthermore, significant promise seen *in vitro* is not matched with efficient delivery *in vivo*. A fundamental understanding of how nanoparticles are transported within the cell is key to engineering materials to improve escape and overcome this significant bottleneck.

Our ability to understand the mechanisms of escape is limited by the current techniques used to detect it. We need to move beyond assays that simply report the percent of cells that show escape, and develop techniques that can also quantify efficiency. New assays and sensors will help us address some of the fundamental questions behind endosomal escape. These include: Does the mechanism of nanoparticle internalization affect the subsequent trafficking and escape of the particle? What physical and chemical properties such as size, shape or charge must a particle possess in order to be successful at escaping the endosome and are they interdependent? What role does targeting play in endosomal escape, and does targeting to a specific pathway dominate trafficking over the native pathways untargeted nanoparticles take?

The answers to these questions will not be straight forward. Mammalian cells are innately complex and highly regulated, coordinating a multitude of biochemical processes. This is compounded by interactions between the nanoparticle and endogenous biomolecules in the extracellular space. This complexity highlights the need for studies where the properties of nanoparticles are understood and controlled in order to link their attributes to how they behave in cells.

Although the interactions between cell and particle are complicated, it is imperative that we make the nanoparticle solution simple. Nanoparticles must be engineered keeping their eventual application in mind and as such must have characteristics suitable for a drug delivery system if they are going to have a significant impact in the way we treat diseases. Next generation treatment of diseases with gene therapy, vaccination and drugs active in the cytosol all rely on the development of delivery systems that effectively deliver cargo from the endosome into the cytoplasm. We must overcome the barrier of endosomal escape to fulfil the promise these therapies offer. This begins with a greater understanding of how materials interact with cells.

Figures and Captions

Figure 1 Nanoparticles can enter cells through multiple mechanisms. Particles are taken up into vesicles coated with clathrin, caveolin or by using a clathrin/caveolin-independent mechanism. EEA1 tethers to RAB5 on internalized vesicles and draws them into RAB5-positive early endosomes. The pH drops to ~ 6.3 and cargo is recycled to the surface or trafficked to RAB7-positive late endosomes (pH ~ 5.5). Contents are trafficked to the lysosome (pH ~ 4.7) where they are degraded by acid hydrolases. Alternative modes of entry include membrane fusion or direct translocation across the membrane, bypassing the trafficking pathway.^{171–173}

a. Proton Sponge Effect

b. Membrane Fusion

c. Peptide Pore Formation

d. Polymer-induced Disruption Membrane Disruption

Figure 2 Mechanisms of endosomal escape. a. Proton sponge effect – Polymers capable of buffering become protonated as protons are pumped into endosomes as part of the regular trafficking process by ATPases. Chloride ions are also transported in to maintain the charge balance within the endosome. The increase in ion concentration causes osmotic swelling and ruptures the membrane.⁷⁶ b. Membrane fusion - Anionic lipids on the cytoplasmic side of the endosomes rearrange to form a

neutral ion-pair with cationic lipids of the carrier, destabilizing the membrane. The membranes fuse and allow the cargo to move into the cytoplasm.⁸⁵ c. Pore formation – certain peptides self-assemble in the lipid membrane to form pores that enable low molecular therapeutics to escape. d. Membrane disruption – Polymers or peptides interact directly with the endosomal membrane causing disruption, allowing cargo to escape.

Figure 3 Fluorescence microscopy image contrasting a. zero to low levels of endosomal escape with b. high levels of escape. Fluorescently labelled cargo sequestered in endo/lysosomes appears punctate while a cytosolic localization causes a diffuse appearance.¹⁷ Reprinted with permission from Ref 17. Copyright Nature Publishing Group 2014.

Figure 4 Cargo enclosed in lysosomes appears as a ring of the labelled lysosome marker around the labelled particle and results in low overlap coefficients. Scale bar = 5 μ m.

Author Manuscript

Figure 5 pH-responsive nanoparticles induce endosomal escape of calcein in a dendritic cell line. (A-I) Confocal microscopy images. (A-C) bright-field images. (D-I) Fluorescence overlays (red, nanoparticles; green, calcein). (A,D,G) Cells were treated with calcein alone. (B,E,H) Cells were co-incubated with calcein and PDEAEMA-core/PAEMA-shell nanoparticles. (C,F,I) Cells were co-incubated with calcein and PMMA-core/PAEMA-shell nanoparticles. Scale bars: (A-F) 20 μm ; (G-I) 10 μm . (J) Average percentage of cells observed by confocal microscopy exhibiting endosomal vs cytosolic/nuclear calcein distributions after 1 h from three independent experiments: calcein alone (gray bar), calcein with PDEAEMA core-shell particles (white bar), or calcein with PMMA core-shell particles (black bar). Reprinted with permission from Ref 119. Copyright American Chemical Society 2007.

Figure 6. Delivery of GFP into HeLa cells. (a) Confocal image showing GFP delivery into HeLa cells by nanoparticles (NPSCs). (b) Confocal images showing the co-localization of delivered GFP with expressed mCherry in HeLa cell. (c) Flow cytometry results of HeLa cells treated with GFP-NPSCs (red) or GFP alone (blue) for 2 h, using untreated HeLa cells as the control (black). Scale bars: 20 μm . Reprinted with permission from Ref 32. Copyright American Chemical Society 2013.

Figure 7. Polymer enhanced intracellular delivery of FAM-labeled siRNA. Representative images illustrating (a) punctate staining (green) in the samples treated with lipofectamine/siRNA complexes alone and (b) dispersed fluorescence within the cytosol following delivery of diblock copolymer/siRNA complexes. Samples were treated for 15 min with 25 nM FAM-siRNA and prepared for microscopic examination following DAPI nuclear staining (blue). Reprinted with permission from Ref 100. Copyright American Chemical Society 2010.

References

1. Johnston, A. P. R. R., Such, G. K., Ng, S. L. & Caruso, F. Challenges facing colloidal delivery systems : From synthesis to the clinic. *Curr. Opin. Colloid ...* **16**, 171–181 (2011).
2. Van Dongen, S. F. M. *et al.* Biohybrid polymer capsules. *Chem. Rev.* **109**, 6212–6274 (2009).
3. Zhang, L. *et al.* Nanoparticles in Medicine: Therapeutic Applications and Developments. *Clin. Pharmacol. Ther.* **83**, 761–769 (2008).
4. De Geest, B. G. *et al.* Polymeric multilayer capsule-mediated vaccination induces protective immunity against cancer and viral infection. *ACS Nano* **6**, 2136–2149 (2012).
5. Davis, M. E. *et al.* Evidence of RNAi in humans from systemically administered siRNA via targeted nanoparticles. *Nature* **464**, 1067–1070 (2010).
6. Singh, R., Lillard, J. W. & W., L. J. Nanoparticle-based targeted drug delivery. *Exp. Mol. Pathol.* **86**, 215–23 (2009).
7. Canton, I. & Battaglia, G. Endocytosis at the nanoscale. *Chem. Soc. Rev.* **41**, 2718–2739 (2012).
8. Kanasty, R., Dorkin, J. R., Vegas, A. & Anderson, D. Delivery materials for siRNA therapeutics. *Nat. Mater.* **12**, 967–77 (2013).
9. Pack, D. W., Hoffman, A. S., Pun, S. & Stayton, P. S. Design and development of polymers for gene delivery. *Nat. Rev. Drug Discov.* **4**, 581–93 (2005).
10. Zhao, L. *et al.* Nanoparticle vaccines. *Vaccine* **32**, 327–37 (2014).
11. Torchilin, V. Intracellular delivery of protein and peptide therapeutics. *Drug Discov. Today. Technol.* **5**, e95–e103 (2008).
12. Leader, B., Baca, Q. J. & Golan, D. E. Protein therapeutics: a summary and pharmacological classification. *Nat. Rev. Drug Discov.* **7**, 21–39 (2008).
13. Shete, H. K., Prabhu, R. H. & Patravale, V. B. Endosomal escape: a bottleneck in intracellular delivery. *Journal of nanoscience and nanotechnology* **14**, 460–74 (2014).
14. Varkouhi, A. K., Scholte, M., Storm, G. & Haisma, H. J. Endosomal escape pathways for delivery of biologicals. *J. Control. Release* **151**, 220–8 (2011).
15. Heath, F., Hara, P. & Alexander, C. Varying polymer architecture to deliver drugs. *AAPS J.* **9**, E235–40 (2007).
16. Wagner, E., Plank, C., Zatloukal, K., Cotten, M. & Birnstiel, M. L. Influenza virus hemagglutinin HA-2 N-terminal fusogenic peptides augment gene transfer by transferrin-polylysine-DNA complexes: toward a synthetic virus-like gene-transfer vehicle. *Proc. Natl. Acad. Sci. U. S. A.* **89**, 7934–7938 (1992).

17. Erazo-Oliveras, A. *et al.* Protein delivery into live cells by incubation with an endosomolytic agent. *Nat. Methods* **11**, 861–867 (2014).
18. Kakimoto, S. *et al.* The conjugation of diphtheria toxin T domain to poly(ethylenimine) based vectors for enhanced endosomal escape during gene transfection. *Biomaterials* **30**, 402–408 (2009).
19. Cross, K. J., Burleigh, L. M. & Steinhauer, D. a. Mechanisms of cell entry by influenza virus. *Expert Rev. Mol. Med.* **3**, 1–18 (2001).
20. Collier, R. J. Understanding the mode of action of diphtheria toxin: A perspective on progress during the 20th century. *Toxicon* **39**, 1793–1803 (2001).
21. Wyman, T., Nicol, F., Zelphati, O. & Scaria, P. Design, Synthesis, and Characterization of a Cationic Peptide That Binds to Nucleic Acids and Permeabilizes Bilayers. *Biochemistry* **2960**, 3008–3017 (1997).
22. Subbarao, N. K., Parente, R. A., Szoka, F. C., Nadasdi, L. & Pongracz, K. The pH-dependent bilayer destabilization by an amphipathic peptide. *Biochemistry* **26**, 2964–2972 (1987).
23. Raoof, M., Mackeyev, Y., Cheney, M. A., Wilson, L. J. & Curley, S. A. Internalization of C60 fullerenes into cancer cells with accumulation in the nucleus via the nuclear pore complex. *Biomaterials* **33**, 2952–2960 (2012).
24. Cheung, W., Pontoriero, F., Taratula, O., Chen, A. M. & He, H. DNA and carbon nanotubes as medicine. *Adv. Drug Deliv. Rev.* **62**, 633–649 (2010).
25. Probst, C. E., Zrazhevskiy, P., Bagalkot, V. & Gao, X. Quantum dots as a platform for nanoparticle drug delivery vehicle design. *Adv. Drug Deliv. Rev.* **65**, 703–718 (2013).
26. Bogart, L. K. *et al.* Nanoparticles for imaging, sensing, and therapeutic intervention. *ACS Nano* **8**, 3107–3122 (2014).
27. Jiang, Y., Huo, S., Hardie, J., Liang, X. & Rotello, V. M. Progress and perspective of inorganic nanoparticle-based siRNA delivery systems. *Expert Opin. Drug Deliv.* **13**, 547–559 (2016).
28. Cho, Y. W., Kim, J.-D. & Park, K. Polycation gene delivery systems: escape from endosomes to cytosol. *J. Pharm. Pharmacol.* **55**, 721–734 (2003).
29. Yessine, M.-A. & Leroux, J.-C. Membrane-destabilizing polyanions: interaction with lipid bilayers and endosomal escape of biomacromolecules. *Adv. Drug Deliv. Rev.* **56**, 999–1021 (2004).
30. Nazareus, M. *et al.* In vitro interaction of colloidal nanoparticles with mammalian cells: What have we learned thus far? *Beilstein J. Nanotechnol.* **5**, 1477–90 (2014).
31. Sahay, G., Alakhova, D. Y. & Kabanov, A. V. Endocytosis of nanomedicines. *J. Control. Release* **145**, 182–95 (2010).

32. Tang, R. *et al.* Direct delivery of functional proteins and enzymes to the cytosol using nanoparticle-stabilized nanocapsules. *ACS Nano* **7**, 6667–6673 (2013).
33. Doherty, G. J. & McMahon, H. T. Mechanisms of endocytosis. *Annu. Rev. Biochem.* **78**, 857–902 (2009).
34. Kirkham, M. & Parton, R. G. Clathrin-independent endocytosis: New insights into caveolae and non-caveolar lipid raft carriers. *Biochim. Biophys. Acta - Mol. Cell Res.* **1746**, 350–363 (2005).
35. Bhattacharyya, S. *et al.* Switching the targeting pathways of a therapeutic antibody by nanodesign. *Angew. Chemie - Int. Ed.* **51**, 1563–1567 (2012).
36. Mintern, J. D. *et al.* Targeting Dendritic Cells: The Role of Specific Receptors in the Internalization of Polymer Capsules. *Adv. Healthc. Mater.* **2**, 940–944 (2013).
37. Lin, G. G. & Scott, J. G. Transferrin Receptor-Targeted Lipid Nanoparticles for Delivery of an Antisense Oligodeoxyribonucleotide against Bcl-2. *Mol. Pharm.* **6**, 221–230 (2009).
38. Van Steenis, J. H. *et al.* Preparation and characterization of folate-targeted pEG-coated pDMAEMA-based polyplexes. *J. Control. Release* **87**, 167–176 (2003).
39. Pereira, P. *et al.* siRNA Inhibition of Endocytic Pathways to Characterize the Cellular Uptake Mechanisms of Folate-Functionalized Glycol Chitosan Nanogels. *Mol. Pharm.* **12**, 1970–9 (2015).
40. Zhang, L. W. & Monteiro-Riviere, N. A. Mechanisms of quantum dot nanoparticle cellular uptake. *Toxicol. Sci.* **110**, 138–155 (2009).
41. Lin, G. G. & Scott, J. G. Endocytosis of Nanomedicines. *J. Control. Release* **145**, 182–195 (2010).
42. Iversen, T.-G., Skotland, T. & Sandvig, K. Endocytosis and intracellular transport of nanoparticles: Present knowledge and need for future studies. *Nano Today* **6**, 176–185 (2011).
43. Christoforidis, S., McBride, H. M., Burgoyne, R. D. & Zerial, M. The Rab5 effector EEA1 is a core component of endosome docking. *Nature* **397**, 621–625 (1999).
44. Beyenbach, K. W. & Wieczorek, H. The V-type H⁺ ATPase: molecular structure and function, physiological roles and regulation. *J. Exp. Biol.* **209**, 577–89 (2006).
45. Casey, J. R., Grinstein, S. & Orlowski, J. Sensors and regulators of intracellular pH. *Nat. Rev. Mol. Cell Biol.* **11**, 50–61 (2010).
46. Sheff, D. R., Daro, E. a, Hull, M. & Mellman, I. The Receptor Recycling Pathway Contains Two Distinct Populations of Early Endosomes with Different Sorting Functions. *J. Cell Biol.* **145**, 123–139 (2013).

47. Lübke, T., Lobel, P. & Sleat, D. E. Proteomics of the lysosome. *Biochim. Biophys. Acta - Mol. Cell Res.* **1793**, 625–635 (2009).
48. Pinto-González Howell, D., Krieser, R. J., Eastman, A. & Barry, M. A. Deoxyribonuclease II is a lysosomal barriers to transfection. *Mol. Ther.* **8**, 957–963 (2003).
49. Laurent, N. *et al.* Uptake by rat liver and intracellular fate of plasmid DNA complexed with poly-L-lysine or poly-D-lysine. *FEBS, Lett.* **443**, 61–65 (1999).
50. Johnston, A. P. R., Lee, L., Wang, Y. & Caruso, F. Controlled degradation of dna capsules with engineered restriction-enzyme cut sites. *Small* **5**, 1418–1421 (2009).
51. Roberg, K., Kågedal, K. & Ollinger, K. Microinjection of cathepsin d induces caspase-dependent apoptosis in fibroblasts. *Am. J. Pathol.* **161**, 89–96 (2002).
52. Thomas, T. P. *et al.* Cationic poly(amidoamine) dendrimer induces lysosomal apoptotic pathway at therapeutically relevant concentrations. *Biomacromolecules* **10**, 3207–14 (2009).
53. Schmaljohann, D. Thermo- and pH-responsive polymers in drug delivery. *Adv. Drug Deliv. Rev.* **58**, 1655–70 (2006).
54. Gao, W., Chan, J. & Farokhzad, O. pH-responsive nanoparticles for drug delivery. *Mol. Pharm.* **7**, 1913–1920 (2010).
55. Dutta, D. & Donaldson, J. G. Search for inhibitors of endocytosis. *Cell. Logist.* **2**, 203–208 (2012).
56. Parton, R. G. & Howes, M. T. Revisiting caveolin trafficking : the end of the caveosome. **191**, 439–441 (2010).
57. Hayer, A. *et al.* Caveolin-1 is ubiquitinated and targeted to intraluminal vesicles in endolysosomes for degradation. *J. Cell Biol.* **191**, 615–629 (2010).
58. Albanese, A., Tang, P. S. & Chan, W. C. W. The effect of nanoparticle size, shape, and surface chemistry on biological systems. *Annu. Rev. Biomed. Eng.* **14**, 1–16 (2012).
59. Zhao, F. *et al.* Cellular uptake, intracellular trafficking, and cytotoxicity of nanomaterials. *Small* **7**, 1322–37 (2011).
60. Sohaebuddin, S. K., Thevenot, P. T., Baker, D., Eaton, J. W. & Tang, L. Nanomaterial cytotoxicity is composition, size, and cell type dependent. *Part. Fibre Toxicol.* **7**, 1–17 (2010).
61. Parhamifar, L., Larsen, A. K., Hunter, a. C., Andresen, T. L. & Moghimi, S. M. Polycation cytotoxicity: a delicate matter for nucleic acid therapy—focus on polyethylenimine. *Soft Matter* **6**, 4001 (2010).
62. Nel, A. E. *et al.* Understanding biophysicochemical interactions at the nano-bio interface. *Nat. Mater.* **8**, 543–557 (2009).

63. Lundqvist, M. *et al.* Nanoparticle size and surface properties determine the protein corona with possible implications for biological impacts. *Proc. Natl. Acad. Sci. U. S. A.* **105**, 14265–70 (2008).
64. Fleischer, C. C. & Payne, C. K. Nanoparticle-cell interactions: Molecular structure of the protein corona and cellular outcomes. *Acc. Chem. Res.* **47**, 2651–2659 (2014).
65. Salvati, A. *et al.* Transferrin-functionalized nanoparticles lose their targeting capabilities when a biomolecule corona adsorbs on the surface. *Nat. Nanotechnol.* **8**, 137–43 (2013).
66. Maiorano, G. *et al.* Effects of cell culture media on the dynamic formation of protein-nanoparticle complexes and influence on the cellular response. *ACS Nano* **4**, 7481–7491 (2010).
67. Gabrielson, N. P. & Pack, D. W. Efficient polyethylenimine-mediated gene delivery proceeds via a caveolar pathway in HeLa cells. *J. Control. Release* **136**, 54–61 (2009).
68. Rejman, J., Bragonzi, A. & Conese, M. Role of clathrin- and caveolae-mediated endocytosis in gene transfer mediated by lipo- and polyplexes. *Mol. Ther.* **12**, 468–74 (2005).
69. Rezgui, R., Blumer, K., Yeoh-Tan, G., Trexler, A. J. & Magzoub, M. Precise quantification of cellular uptake of cell-penetrating peptides using fluorescence-activated cell sorting and fluorescence correlation spectroscopy. *Biochim. Biophys. Acta - Biomembr.* (2016). doi:10.1016/j.bbamem.2016.03.023
70. Fraser, L. & Hamm-alvarez, S. F. Intracellular Uptake and Trafficking of Difluoroboron Dibenzoylmethane-Poly(lactic acid) Nanoparticles in HeLa Cells. *ACS Nano* **4**, 2735–2747 (2011).
71. Braun, G. B. *et al.* Etchable plasmonic nanoparticle probes to image and quantify cellular internalization. *Nat. Mater.* **13**, 1–19 (2014).
72. Rosenholm, J. M. *et al.* Targeting of porous hybrid silica nanoparticles to cancer cells. *ACS Nano* **3**, 197–206 (2009).
73. Liu, H. & Johnston, A. P. R. A programmable sensor to probe the internalization of proteins and nanoparticles in live cells. *Angew. Chemie - Int. Ed.* **52**, 5744–5748 (2013).
74. Mann, S. K. *et al.* Quantifying nanoparticle internalization using a high throughput internalization assay. *Pharm. Res.* **33**, 2421–2432 (2016).
75. Selby, L. I., Kongkatigumjorn, N., Such, G. K. & Johnston, A. P. R. HD Flow Cytometry : An Improved Way to Quantify Cellular Interactions with Nanoparticles. *5*, 2333–2338 (2016). doi:10.1002/adhm.201600445
76. Behr, J. The proton sponge: a trick to enter cells the viruses did not exploit. *Chim. Int. J. Chem.* **2**, 34–36 (1997).
77. Patil, M. L. *et al.* Internally cationic polyamidoamine PAMAM-OH dendrimers for siRNA

- delivery: Effect of the degree of Quaternization and cancer targeting. *Biomacromolecules* **10**, 258–266 (2009).
78. Boussif, O. *et al.* A versatile vector for gene and oligonucleotide transfer into cells in culture and in vivo: polyethylenimine. *Proc. Natl. Acad. Sci. U. S. A.* **92**, 7297–301 (1995).
 79. Won, Y.-Y., Sharma, R. & Konieczny, S. F. Missing pieces in understanding the intracellular trafficking of polycation/DNA complexes. *J. Control. Release* **139**, 88–93 (2009).
 80. Benjaminsen, R. V., Matthebjerg, M. a, Henriksen, J. R., Moghimi, S. M. & Andresen, T. L. The possible 'proton sponge' effect of polyethylenimine (PEI) does not include change in lysosomal pH. *Mol. Ther.* **21**, 149–57 (2013).
 81. Funhoff, A. M. *et al.* Endosomal escape of polymeric gene delivery complexes is not always enhanced by polymers buffering at low pH. *Biomacromolecules* **5**, 32–39 (2004).
 82. Massignani, M. *et al.* Controlling cellular uptake by surface chemistry, size, and surface topology at the nanoscale. *Small* **5**, 2424–2432 (2009).
 83. Lomas, H. *et al.* Non-cytotoxic polymer vesicles for rapid and efficient intracellular delivery. *Faraday Discuss.* **139**, 143–159 (2008).
 84. White, J. M. & Whittaker, G. R. Fusion of Enveloped Viruses in Endosomes. *Traffic* **17**, 593–614 (2016).
 85. Zelphati, O. & Szoka, F. Mechanism of oligonucleotide release from cationic liposomes. *Proc. Natl. Acad. Sci. U. S. A.* **93**, 11493–11498 (1996).
 86. Koltover, I. *et al.* An inverted hexagonal phase of cationic liposome-DNA complexes related to DNA release and delivery. *Science* **281**, 78–81 (1998).
 87. Jones, R. a *et al.* Poly(2-alkylacrylic acid) polymers deliver molecules to the cytosol by pH-sensitive disruption of endosomal vesicles. *Biochem. J.* **372**, 65–75 (2003).
 88. Nakase, I., Kobayashi, S. & Futaki, S. Endosome-disruptive peptides for improving cytosolic delivery of bioactive macromolecules. *Biopolymers* **94**, 763–770 (2010).
 89. Li, W., Nicol, F. & Szoka, F. C. GALA: a designed synthetic pH-responsive amphipathic peptide with applications in drug and gene delivery. *Adv. Drug Deliv. Rev.* **56**, 967–985 (2004).
 90. Danial, M., Perrier, S. & Jolliffe, K. a. Effect of the amino acid composition of cyclic peptides on their self-assembly in lipid bilayers. *Org. Biomol. Chem.* **13**, 2464–2473 (2015).
 91. Prchla, E., Plank, C., Wagner, E., Blaas, D. & Fuchs, R. Virus-mediated release of endosomal content in vitro: Different behavior of adenovirus and rhinovirus serotype 2. *J. Cell Biol.* **131**, 111–123 (1995).
 92. Tian, W. & Ma, Y. Insights into the endosomal escape mechanism via investigation of dendrimer–membrane interactions. *Soft Matter* **8**, 6378 (2012).

93. Leroueil, P. R. *et al.* Wide varieties of cationic nanoparticles induce defects in supported lipid bilayers. *Nano Lett.* **8**, 420–4 (2008).
94. Hong, S. *et al.* Interaction of polycationic polymers with supported lipid bilayers and cells: nanoscale hole formation and enhanced membrane permeability. *Bioconjug. Chem.* **17**, 728–34 (2006).
95. Chen, J. *et al.* Cationic nanoparticles induce nanoscale disruption in living cell plasma membranes. *J. Phys. Chem. B* **113**, 11179–11185 (2009).
96. Bieber, T., Meissner, W., Kostin, S., Niemann, A. & Elsasser, H.-P. Intracellular route and transcriptional competence of polyethylenimine-DNA complexes. *J. Control. Release* **82**, 441–54 (2002).
97. Lee, Y., Johnson, G., Peltier, G. C. & Pellois, J. A HA2-Fusion tag limits the endosomal release of its protein cargo despite causing endosomal lysis. *BBA - Gen. Subj.* **1810**, 752–758 (2011).
98. Turk, B. & Turk, V. Lysosomes as ‘suicide bags’ in cell death: Myth or reality? *J. Biol. Chem.* **284**, 21783–21787 (2009).
99. Martens, T. F., Remaut, K., Demeester, J., De Smedt, S. C. & Braeckmans, K. Intracellular delivery of nanomaterials: How to catch endosomal escape in the act. *Nano Today* (2014). doi:10.1016/j.nantod.2014.04.011
100. Convertine, A. J. *et al.* pH-Responsive Polymeric Micelle Carriers for siRNA Drugs. *Biomacromolecules* **11**, 2904–2911 (2010).
101. Mishra, S., Webster, P. & Davis, M. E. PEGylation significantly affects cellular uptake and intracellular trafficking of non-viral gene delivery particles. *Eur. J. Cell Biol.* **83**, 97–111 (2004).
102. Lu, J., Liong, M., Zink, J. I. & Tamanoi, F. Mesoporous silica nanoparticles as a delivery system for hydrophobic anticancer drugs. *Small* **3**, 1341–1346 (2007).
103. Panyam, J., Zhou, W.-Z., Prabha, S., Sahoo, S. K. & Labhasetwar, V. Rapid endo-lysosomal escape of poly(DL-lactide-co-glycolide) nanoparticles: implications for drug and gene delivery. *FASEB J.* **16**, 1217–26 (2002).
104. Liu, P. *et al.* Intracellular trafficking and cellular uptake mechanism of mPEG-PLGA-PLL and mPEG-PLGA-PLL-Gal nanoparticles for targeted delivery to hepatomas. *Biomaterials* **35**, 760–770 (2014).
105. Via, L. E. *et al.* Effects of cytokines on mycobacterial phagosome maturation. *J. Cell Sci.* **905**, 897–905 (1998).
106. Chikte, S., Panchal, N. & Warnes, G. Use of LysoTracker dyes: A flow cytometric study of autophagy. *Cytom. Part A* **85**, 169–178 (2014).
107. Chen, J. W., Pan, W., D’Souza, M. P. & August, J. T. Lysosome-associated membrane proteins: characterization of LAMP-1 of macrophage P388 and mouse embryo 3T3 cultured cells. *Arch.*

- Biochem. Biophys.* **239**, 574–586 (1985).
108. Ames, R. S., Kost, T. A. & Condreay, J. P. BacMam technology and its application to drug discovery. *Expert Opin. Drug Discov.* **2**, 1669–1681 (2007).
 109. Bivas-Benita, M., Romeijn, S., Junginger, H. E. & Borchard, G. PLGA-PEI nanoparticles for gene delivery to pulmonary epithelium. *Eur. J. Pharm. Biopharm.* **58**, 1–6 (2004).
 110. Thavarajah, R., Mudimbaimannar, V. K., Elisabeth, J., Rao, U. K. & Ranganathan, K. Chemical and physical basics of routine formaldehyde fixation. *Journa Oral Maxillofacial Pathol.* **16**, 400–405 (2012).
 111. Wiedenmann, J., Oswald, F. & Nienhaus, G. U. Fluorescent proteins for live cell imaging: Opportunities, limitations, and challenges. *IUBMB Life* **61**, 1029–1042 (2009).
 112. Lisenbee, C. S., Karnik, S. K. & Trelease, R. N. Overexpression and mislocalization of a tail-anchored GFP redefines the identity of peroxisomal ER. *Traffic* **4**, 491–501 (2003).
 113. Maiolo III, J. R., Ottinger, E. A. & Ferrer, M. Specific redistribution of cell-penetrating peptides from endosomes to the cytoplasm and nucleus upon laser illumination. *J. Am. Chem. Soc.* **126**, 15376–15377 (2004).
 114. Weinstein, J. N., Yoshikami, S., Henkart, P., Blumenthal, R. & Hagins, W. a. Liposome-cell interaction: transfer and intracellular release of a trapped fluorescent marker. *Science* **195**, 489–492 (1977).
 115. Funhoff, A. M. *et al.* Cationic polymethacrylates with covalently linked membrane destabilizing peptides as gene delivery vectors. *J. Control. Release* **101**, 233–46 (2005).
 116. Madani, F., Perálvarez-Marín, A. & Gräslund, A. Liposome Model Systems to Study the Endosomal Escape of Cell-Penetrating Peptides: Transport across Phospholipid Membranes Induced by a Proton Gradient. *J. Drug Deliv.* **2011**, 897592 (2011).
 117. El-Sayed, A., Khalil, I. a, Kogure, K., Futaki, S. & Harashima, H. Octaarginine- and octalysine-modified nanoparticles have different modes of endosomal escape. *J. Biol. Chem.* **283**, 23450–61 (2008).
 118. Evans, B. C. *et al.* Ex vivo red blood cell hemolysis assay for the evaluation of pH-responsive endosomolytic agents for cytosolic delivery of biomacromolecular drugs. *J. Vis. Exp.* e50166 (2013). doi:10.3791/50166
 119. Wilson, J. T. *et al.* pH-Responsive Nanoparticle Vaccines for Dual-Delivery of Antigens and Immunostimulatory Oligonucleotides. *ACS Nano* **7**, 3912–3925 (2013).
 120. Gujrati, M. *et al.* Multifunctional cationic lipid-based nanoparticles facilitate endosomal escape and reduction-triggered cytosolic siRNA release. *Mol. Pharm.* **11**, 2734–2744 (2014).
 121. Tomlinson, R. *et al.* Pendent Chain Functionalized Polyacetals That Display pH-Dependent Degradation : A Platform for the Development of Novel Polymer Therapeutics.

- Macromolecules* **35**, 473–480 (2002).
122. Hu, Y. *et al.* Cytosolic delivery mediated via electrostatic surface binding of protein, virus, or siRNA cargos to pH-responsive core-shell gel particles. *Biomacromolecules* **10**, 756–65 (2009).
 123. Hu, Y. *et al.* Cytosolic delivery of membrane impermeable molecules in dendritic cells using pH responsive core-shell nanoparticles. *Nano Lett.* (2007).
 124. Bonner, D. *et al.* Intracellular Trafficking of Polyamidoamine - Polyethylene Glycol Block Copolymers in DNA Delivery. *Bioconjugate ...* **22**, 1519–1525 (2011).
 125. Su, X., Fricke, J., Kavanagh, D., Irvine, D. J. & Chase, C. In Vitro and in Vivo mRNA Delivery Using Lipid-Enveloped pH-Responsive Polymer Nanoparticles. *Mol. Pharm.* **8**, 774–787 (2011).
 126. Zhan, X., Tran, K. K., Wang, L. & Shen, H. Controlled endolysosomal release of agents by pH-responsive polymer blend particles. *Pharm. Res.* **32**, 2280–2291 (2016).
 127. Su, X., Yang, N., Wittrup, K. D. & Irvine, D. J. Synergistic antitumor activity from two-stage delivery of targeted toxins and endosome-disrupting nanoparticles. *Biomacromolecules* **14**, 1093–1102 (2013).
 128. Wang, K. *et al.* Structure-Invertible Nanoparticles for Triggered Co-Delivery of Nucleic Acids and Hydrophobic Drugs for Combination Cancer Therapy. *Adv. Funct. Mater.* **25**, 3380–3392 (2015).
 129. Zeng, Y. & Cullen, B. R. RNA interference in human cells is restricted to the cytoplasm. *RNA* **8**, 855–860 (2002).
 130. Zelphati, O., Liang, X., Hobart, P. & Felgner, P. L. Gene chemistry: functionally and conformationally intact fluorescent plasmid DNA. *Hum. Gene Ther.* **10**, 15–24 (1999).
 131. Glover, D. J., Leyton, D. L., Moseley, G. W. & Jans, D. A. The efficiency of nuclear plasmid DNA delivery is a critical determinant of transgene expression at the single cell level. *J. Gene Med.* **12**, 77–85 (2010).
 132. Abdallah, B. *et al.* A Powerful Nonviral Vector for In Vivo Gene Transfer into the Adult Mammalian Brain: Polyethylenimine. *Hum. Gene Ther.* **7**, 1947–1954 (1996).
 133. Hatakeyama, H. *et al.* A pH-sensitive fusogenic peptide facilitates endosomal escape and greatly enhances the gene silencing of siRNA-containing nanoparticles in vitro and in vivo. *J. Control. Release* **139**, 127–32 (2009).
 134. Pack, D. W., Putnam, D. & Langer, R. Design of imidazole-containing endosomolytic biopolymers for gene delivery. *Biotechnol. Bioeng.* **67**, 217 (2000).
 135. Haensler, J. & Jr, F. S. Polyamidoamine cascade polymers mediate efficient transfection of cells in culture. *Bioconjug. Chem.* 372–379 (1993). at <http://pubs.acs.org/doi/abs/10.1021/bc00023a012>

136. Song, Y. K., Liu, F., Chu, S. & Liu, D. Characterization of Cationic Liposome-Mediated Transfer In Vivo by Intravenous Gene Administration. *Hum. Gene Ther.* **8**, 1585–1594 (1997).
137. Wang, Y., Gao, S., Ye, W.-H., Yoon, H. S. & Yang, Y.-Y. Co-delivery of drugs and DNA from cationic core-shell nanoparticles self-assembled from a biodegradable copolymer. *Nat. Mater.* **5**, 791–796 (2006).
138. Spagnou, S., Miller, A. D. & Keller, M. Lipidic carriers of siRNA: differences in the formulation, cellular uptake, and delivery with plasmid DNA. *Biochemistry* **43**, 13348–13356 (2004).
139. Lee, H. *et al.* Molecularly self-assembled nucleic acid nanoparticles for targeted in vivo siRNA delivery. *Nat. Nanotechnol.* **7**, 389–393 (2012).
140. Godbey, W. T., Wu, K. K. & Mikos, A. G. Poly(ethylenimine)-mediated gene delivery affects endothelial cell function and viability. *Biomaterials* **22**, 471–480 (2001).
141. Balazs, D. A., Godbey, W., Balazs, D. A. & Godbey, W. Liposomes for Use in Gene Delivery. *J. Drug Deliv.* **2011**, 1–12 (2011).
142. Cullis, P. R., Hope, M. J. & Tilcock, C. P. S. Lipid Polymorphism and the Roles of Lipids in Membranes. *Chem. Phys. Lipids* **40**, 127–144 (1986).
143. Farhood, H., Serbina, N. & Huang, L. The role of dioleoyl phosphatidylethanolamine in cationic liposome mediated gene transfer. *Biochim. Biophys. Acta* **1235**, 289–295 (1995).
144. Zhou, X. & Huang, L. DNA transfection mediated by cationic liposomes containing lipopolylysine: characterization and mechanism of action. *Biochim. Biophys. Acta* **1189**, 195–203 (1994).
145. Deshpande, M. C. *et al.* The effect of poly(ethylene glycol) molecular architecture on cellular interaction and uptake of DNA complexes. *J. Control. Release* **97**, 143–156 (2004).
146. Harvie, P., Wong, F. M. P. & Bally, M. B. Use of Poly (ethylene glycol)–Lipid Conjugates to Regulate the Surface Attributes and Transfection Activity of Lipid–DNA Particles. *J. Pharm. Sci.* **89**, 652–663 (2000).
147. Song, L. Y. *et al.* Characterization of the inhibitory effect of PEG-lipid conjugates on the intracellular delivery of plasmid and antisense DNA mediated by cationic lipid liposomes. *Biochim. Biophys. Acta* **1558**, 1–13 (2002).
148. Remaut, K., Lucas, B., Braeckmans, K., Demeester, J. & Smedt, S. C. De. Pegylation of liposomes favours the endosomal degradation of the delivered phosphodiester oligonucleotides. *J. Control. Release* **117**, 256–266 (2007).
149. Choi, J. S., Mackay, J. A. & Szoka, F. C. Low-pH-Sensitive PEG-Stabilized Plasmid-Lipid Nanoparticles: Preparation and Characterization. *Bioconjug. Chem.* **14**, 420–429 (2003).
150. Kirpotin, D., Hong, K., Mullah, N., Papahadjopoulos, D. & Zalipsky, S. Liposomes with detachable polymer coating: destabilization and fusion of dioleoylphosphatidylethanolamine

- vesicles triggered by cleavage of surface-grafted poly (ethylene glycol). *FEBS Lett.* **388**, 115–118 (1996).
151. Kuai, R. *et al.* Efficient Delivery of Payload into Tumor Cells in a Controlled Manner by TAT and Thiolytic Cleavable PEG. *Mol. Pharm.* **7**, 1816–1826 (2010).
 152. Meyer, O. *et al.* Cationic Liposomes Coated with Polyethylene Glycol As Carriers for Oligonucleotides. *J. Biol. Chem.* **273**, 15621–15627 (1998).
 153. Zhong, Z. *et al.* Poly(ethylene oxide) grafted with short polyethylenimine gives DNA polyplexes with superior colloidal stability, low cytotoxicity, and potent in vitro gene transfection under serum conditions. *Biomacromolecules* **13**, 881–888 (2012).
 154. Wu, H., Zhu, L. & Torchilin, V. P. pH-sensitive poly(histidine)-PEG/DSPE-PEG co-polymer micelles for cytosolic drug delivery. *Biomaterials* **34**, 1213–1222 (2013).
 155. Zhao, Z. X. *et al.* Self-assembly nanomicelles based on cationic mPEG-PLA-b-Polyarginine(R15) triblock copolymer for siRNA delivery. *Biomaterials* **33**, 6793–6807 (2012).
 156. Kodama, Y. *et al.* Quaternary Complexes Modified from pDNA and Poly-L-Lysine Complexes to Enhance pH-Buffering Effect and Suppress Cytotoxicity. *J. Pharm. Sci.* **104**, 1470–1477 (2015).
 157. Mura, S., Nicolas, J. & Couvreur, P. Stimuli-responsive nanocarriers for drug delivery. *Nat. Mater.* **12**, 991–1003 (2013).
 158. Oishi, M. & Nagasaki, Y. Synthesis, characterization, and biomedical applications of core–shell-type stimuli-responsive nanogels – Nanogel composed of poly[2-(N,N-diethylamino)ethyl methacrylate] core and PEG tethered chains. *React. Funct. Polym.* **67**, 1311–1329 (2007).
 159. Wong, A. S. M., Mann, S. K., Czuba, E., Sahut, A. & Liu, H. Self-assembling dual component nanoparticles with endosomal escape capability. 1–3 (2013). doi:10.1039/x0xx00000x
 160. Kongkatigumjorn, N. *et al.* Probing Endosomal Escape Using pHlexi Nanoparticles. *Macromol. Biosci.* (2016). doi:10.1002/mabi.201600248
 161. Gallon, E. *et al.* Triblock Copolymer Nanovesicles for pH-Responsive Targeted Delivery and Controlled Release of siRNA to Cancer Cells. *Biomacromolecules* **16**, 1924–1937 (2015).
 162. Suma, T. *et al.* Smart Multilayered Assembly for Biocompatible siRNA Delivery Featuring Dissolvable Silica, Endosome-Disrupting Polycation, and Detachable PEG. *ACS Nano* **6**, 6693–6705 (2012).
 163. Dual, A. B. *et al.* Overcoming Endosomal Barrier by Amphotericin B-Loaded Dual pH-Responsive PDMA-b-PDPA Micelleplexes for siRNA Delivery. *ACS Nano* **5**, 9246–9255 (2011).
 164. Zhou, K., Wang, Y., Huang, X., Luby-philps, K. & Sumer, B. D. Tunable, Ultrasensitive pH-Responsive Nanoparticles Targeting Specific Endocytic Organelles in Living Cells. *Angew. Chemie - Int. Ed.* **50**, 6109–6114 (2011).

165. Appelbaum, J. S. *et al.* Arginine topology controls escape of minimally cationic proteins from early endosomes to the cytoplasm. *Chem. Biol.* **19**, 819–830 (2012).
166. Pantos, A., Tsogas, I. & Paleos, C. M. Guanidinium group : A versatile moiety inducing transport and multicompartimentalization in complementary membranes. *Biochim. Biophys. Acta* **1778**, 811–823 (2008).
167. Romani, B., Engelbrecht, S. & Glashoff, R. H. Functions of Tat: the versatile protein of human immunodeficiency virus type 1. *J. Gen. Virol.* **91**, 1–12 (2010).
168. Erazo-Oliveras, A., Muthukrishnan, N., Baker, R., Wang, T.-Y. & Pellois, J.-P. Improving the Endosomal Escape of Cell-Penetrating Peptides and Their Cargos: Strategies and Challenges. *Pharmaceuticals* **5**, 1177–1209 (2012).
169. Sakurai, Y. *et al.* Endosomal escape and the knockdown efficiency of liposomal-siRNA by the fusogenic peptide shGALA. *Biomaterials* **32**, 5733–5742 (2011).
170. Liang, K., Richardson, J. J., Ejima, H., Such, G. K. & Cui, J. Peptide-Tunable Drug Cytotoxicity via One-Step Assembled Polymer Nanoparticles. *Adv. Mater.* **26**, 2398–2402 (2014).
171. Parton, R. G. & Simons, K. The multiple faces of caveolae. **8**, 185–194 (2007).
172. Kinchen, J. M. & Ravichandran, K. S. Phagosome maturation : going through the acid test. **9**, (2008).
173. Stenmark, H. Rab GTPases as coordinators of vesicle traffic. *Nat. Publ. Gr.* **10**, 513–525 (2009).

figure 1.tif

figure 3.tif

figure 4.tif

figure 7.tif

Figure 5.tif

Figure 6.tif

Mechanisms_V2.tif

ToC.tif